

PAN AMERICAN SILVER CORP

Form 6-K

July 25, 2007

**UNITED STATES
SECURITIES AND EXCHANGE COMMISSION
Washington, D.C. 20549
FORM 6-K
REPORT OF FOREIGN PRIVATE ISSUER TO RULE 13A or 15D-16
UNDER THE SECURITIES EXCHANGE ACT OF 1934**

For the Month of: July, 2007

File No.: 000-13727

PAN AMERICAN SILVER CORP.
(Translation of Registrant's Name into English)
Suite 1500, 625 Howe Street Vancouver British Columbia, Canada V6C 2T6
(Address of Principal Executive Office)

Indicate by check mark whether the registrant files or will file annual reports under cover of Form 20-F or Form 40-F:

Form 20-F

Form 40-F

Indicate by check mark if the registrant is submitting the Form 6-K in paper as permitted by Regulation S-T Rule 101(b)(1).

Yes

No

Indicate by check mark if the registrant is submitting the Form 6-K in paper as permitted by Regulation S-T Rule 101(b)(7).

Yes

No

Indicate by check mark whether the registrant by furnishing the information contained in this Form is also thereby furnishing the information to the Commission pursuant to Rule 12g3-2(b) under the Securities Exchange Act of 1934.

Yes

No

If "Yes" is marked, indicate below the file number assigned to the registrant in connection with Rule 12g3-2(b): 82

_____.

Submitted herewith:

- 1. Form 43-101 Technical Report for the San Vicente Mine Expansion Project**
- 2. Press Release dated July 20, 2007**

SIGNATURES

Pursuant to the requirements of the Securities Exchange Act of 1934, the registrant has duly caused this report to be signed on its behalf by the undersigned, thereunto duly authorized.

PAN AMERICAN SILVER CORP.

Date: July 24, 2007

Robert Pirooz
General Counsel

**TECHNICAL REPORT
FOR THE
SAN VICENTE MINE EXPANSION PROJECT
POTOSÍ BOLIVIA
Effective: June 6, 2007
PREPARED BY:
Martin Wafforn, P. Eng
Michael Steinmann, P. Geo
Douglas K. Maxwell, P.E.**

TABLE OF CONTENTS

<u>1.0 TITLE PAGE</u>	5
<u>2.0 TABLE OF CONTENTS</u>	5
<u>3.0 SUMMARY</u>	5
3.1. <u>Background</u>	5
3.2. <u>Property Ownership, Location and Description</u>	5
3.3. <u>Geology and Mineralization</u>	6
3.4. <u>Exploration and Development</u>	6
3.5. <u>Mineral Resource and Reserve Estimates as at December 31, 2006</u>	7
3.6. <u>Mining Operations</u>	9
3.7. <u>Authors Conclusions</u>	9
3.8. <u>Authors Recommendations</u>	10
<u>4.0 INTRODUCTION</u>	10
<u>5.0 RELIANCE ON OTHER EXPERTS</u>	12
<u>6.0 PROPERTY DESCRIPTION AND LOCATION</u>	12
6.1. <u>Mineral Tenure</u>	12
6.2. <u>Permits and Agreements</u>	13
6.3. <u>Environmental</u>	14
<u>7.0 ACCESSIBILITY, CLIMATE, LOCAL RESOURCES, INFRASTRUCTURE AND PHYSIOGRAPHY</u>	15
<u>8.0 HISTORY</u>	16
<u>9.0 GEOLOGICAL SETTING</u>	18
<u>10.0 DEPOSIT TYPES</u>	18
<u>11.0 MINERALIZATION</u>	21
<u>12.0 EXPLORATION</u>	24
<u>13.0 DRILLING</u>	25
13.1. <u>Surface Diamond Drilling</u>	26
13.2. <u>Underground Diamond Drilling</u>	29
<u>14.0 SAMPLING METHOD AND APPROACH</u>	31

<u>15.0 SAMPLE PREPARATION, ANALYSES, AND SECURITY</u>	32
<u>16.0 DATA VERIFICATION</u>	34
<u>17.0 ADJACENT PROPERTIES</u>	34
<u>18.0 MINERAL PROCESSING AND METALLURGICAL TESTING</u>	34

<u>19.0 MINERAL RESOURCE AND MINERAL RESERVE ESTIMATES</u>	37
<u>19.1. Mineral Reserves</u>	40
<u>19.2. Mineral Resources</u>	41
<u>20.0 OTHER RELEVANT DATA AND INFORMATION</u>	42
<u>21.0 INTERPRETATION AND CONCLUSIONS</u>	42
<u>22.0 RECOMMENDATIONS</u>	43
<u>23.0 REFERENCES</u>	44
<u>24.0 DATE</u>	44
<u>25.0 ADDITIONAL REQUIREMENTS FOR TECHNICAL REPORTS ON DEVELOPMENT PROPERTIES AND PRODUCTION PROPERTIES</u>	44
<u>25.1. Underground Mine Operations</u>	44
<u>25.2. Recoverability</u>	48
<u>25.3. Markets</u>	51
<u>25.4. Revenues</u>	51
<u>25.5. Environmental Considerations</u>	51
<u>25.6. Exploration Expenditures</u>	53
<u>25.7. Taxes</u>	53
<u>25.8. Capital and Operating Costs</u>	55
<u>25.9. Economic Analysis</u>	60
<u>25.10. Mine Life</u>	64

LIST OF FIGURES

Figure 1-1	Location of the San Vicente mine in Bolivia	65
Figure 1-2	San Vicente Mine Location Map in Potosi	66
Figure 1-3	San Vicente Mine General Site Layout	67
Figure 1-4	San Vicente Mine Mine Site General Layout	68
Figure 1-4a	San Vicente Mine, Mining Concessions	69
Figure 1-4b	San Vicente Mine, Geology Map	70
Figure 1-5	Longitinal Section of a Typical Shrinkage Stope	71
Figure 1-6	Longitudinal Section Showing the Modified Avoca Longhole Mining Method	72
Figure 1-7	San Vicente Mine Deposit Areas	73
Figure 1-8	Geology Map	74
Figure 1-9	San Vicente Process Plant Flow Diagram	75
Figure 1-10	Process Plant General Arrangement	76
Figure 1-11	Section of 6 de Agosto Vein	77
Figure 1-12	Section of Litoral Vein	78

LIST OF APPENDICES

Appendix A Certificates and Consents

Appendix B Diamond Drill Hole Intercepts

Appendix C Channel Sampling Results

Qualified Persons

- Ø Certificate of Qualified Persons and Consent of Authors

Responsibility	Qualified Person	Registration
Mineral Resource Modelling	Michael Steinmann, PAS	P. Geo.
Mineral Reserves	Martin Wafforn, PAS	P.Eng.
Geology	Michael Steinmann, PAS	P.Geo.
Mine Planning	Martin Wafforn, PAS	P.Eng.
Metallurgy	Douglas K. Maxwell, Lyntek	P.E.
Process Plant Design	Douglas K. Maxwell, Lyntek	P.E.

LIST OF TABLES

Table 1 San Vicente Mineral Reserves	8
Table 2 San Vicente Mineral Resources	8
Table 3 References	11
Table 4 Mining Concessions	13
Table 5 Water Sources	15
Table 6 Occurrence of Veins in San Vicente Mine. (Modified from JICA, 1979)	20
Table 7 Mineralogy of San Vicente Veins Recognized Under Microscope	23
Table 8a Summary Data San Vicente Surface Diamond Drill Holes	27
Table 8b Summary Data San Vicente Underground Diamond Drill Holes	30
Table 8c Diamond Drilling Check Assays	33
Table 9 Lyntek Recommended Metal Recoveries	36
Table 10 Anticipated Plant Metal Recoveries	37
Table 11 Specific Gravity by Vein	38
Table 12 Dilution Calculation	39
Table 13 Resource Metal Prices and Factors	39
Table 14 San Vicente Mineral Reserves	40
Table 15 San Vicente Measured and Indicated Mineral Resources	41
Table 16 San Vicente Inferred Mineral Resources	42
Table 17 Mining Method Cost per tonne	46
Table 18 Mechanized Equipment	46
Table 19 Life of Mine Plan	47
Table 20 San Vicente Closure Cost Estimate	53
Table 21 Capital Cost Estimate Summary	56
Table 22 Life-of-Mine Unit Operating Costs	59
Table 23 Economic Model	61
Table 24 Metal Price Sensitivity	62
Table 25 Metal Grade Sensitivity	62
Table 26 Capital Cost Sensitivity	63
Table 27 Operating Cost Sensitivity	63
Table 28 Copper Grade Samples	63
Table 29 Copper Revenue Sensitivity	64

1.0 TITLE PAGE

This Technical Report has been prepared in accordance with the *National Instrument 43-101 Standards of Disclosure for Mineral Projects* (N.I. 43-101) and the contents herein are organized and in compliance with *Form 43-101F1 Contents of the Technical Report* (Form 43-101 F1). The first two items are the Title Page and the Table of Contents presented previously in this report. They are mentioned here simply to maintain the specific report outline numbering required in Form 43-101F1.

2.0 TABLE OF CONTENTS

See discussion in Section 1.

3.0 SUMMARY

3.1. Background

This Technical Report has been compiled from studies completed by an international team of professionals and consultants for the San Vicente Mine Expansion Project. Mr. Martin Wafforn, P. Eng. Vice President of Mine Engineering of Pan American Silver Corp. (PAS), Dr. Michael Steinmann, P. Geo. Senior Vice President of Exploration and Geology of PAS, and Mr. Douglas K. Maxwell, P.E. of Lyntek Inc. are the co-authors of this report. Each of Mr. Wafforn, Dr. Steinmann and Mr. Maxwell is a Qualified Person as that term is defined in N.I. 43-101. The goal of the San Vicente Mine Expansion Project described in this Technical Report is to expand the current mine capacity from approximately 250 tonnes per day (TPD), to 750 TPD. The San Vicente Mine Expansion Project includes the construction of a new process plant and tailings storage facility at the mine site.

3.2. Property Ownership, Location and Description

PAS has a 94.999% interest in Pan American Silver Bolivia (PASB), a Bolivian company that holds a 50% joint venture interest in, and is the operator of the San Vicente property. The remaining interest in the joint venture is held by Corporación Minera de Bolivia (COMIBOL), the Bolivian state mining company. Trafigura Beheer B.V. (Trafigura), a commercial trading company domiciled in Holland holds a 5% interest in PASB with the remaining 0.001% being held by Pan American Silver Peru S.A.

Pursuant to the joint venture agreement entered into with COMIBOL in 1999, with respect to the development of the San Vicente property, PASB is obligated to pay COMIBOL a participation fee of 37.5% of the operations cash flow. Once the commercial production phase of the San Vicente Mine Expansion Project begins, the COMIBOL participation fee will be reduced by 75% until PASB recovers its investment in the property. Thereafter the COMIBOL participation fee will revert back to 100% of the participation fee described above.

In May 2007, PAS purchased the 40% interest in PASB that was held by Empresa Minera Unificada S.A. (EMUSA), a Bolivian company. EMUSA has retained 80% of a 2.0% net smelter return royalty interest in the property that is payable only, after recovery of the costs to complete the San Vicente Mine Expansion Project from January 1, 2007 up to the point of commercial production; after recovery of the cost of the purchase of EMUSA 's 40% interest in PASB; and is only payable in a calendar quarter where the average price of silver is \$9.00 per ounce or greater.

The San Vicente silver-zinc mine is located at latitude 21°-16' south and longitude 66°-19' west in the southern end of Bolivia in the Province of Sud-Chichas, Department of Potosí. The mine is 460 kilometres south of the city of Oruro and 300 kilometres west of Tarija. Access is by dirt road 100 km west of the town of Tupiza and 150 km south of Uyuni. The property is in the Andean High Plateau (Altiplano), at approximately 4,400 metres above sea level, with semi-arid climatic conditions. The land is sterile and rugged.

The project consists of 13 mining concessions totalling 7,075 hectares that are part of COMIBOL's contribution to the joint venture. Of the concessions, five, totalling 662 hectares, start with the name *Aguas* which is Spanish for water. However, all of the concessions include the rights for mining, water and surface usage. PASB has continually complied with the joint venture agreement (and various addendums thereto), and as a result the project and the concessions are in good standing. All mining property concessions of the San Vicente property are in the name of COMIBOL, and contractually PASB is responsible for paying the annual mining tenure tax. These payments are currently up to date.

3.3. Geology and Mineralization

The regional sedimentary sequence consists of a basement of a thin sequence of Palaeozoic marine siliciclastic sediments overlying non-continuous cretaceous continental sediments, and a package of thick continental clastics of Tertiary age of the Potoco and San Vicente Formations. Various thin intrusive volcanic flows with an intermediate composition are also included in the Tertiary sequence. The Palaeozoic sediments were folded before the deposition of the Cretaceous sediments. Sedimentation in the tertiary basin was controlled during the Upper Oligocene and Lower Miocene periods by thrust faults to the east and west.

The lithology of the Project area is relatively simple. Included are the fanglomerate facies of the San Vicente formation, which are in contact with Ordovician shales along the San Vicente fault. The fanglomerate consists of poorly sorted conglomerate with clastic sub angular fragments of Palaeozoic sediments cross cut by quartz veins. The matrix is red in colour and consists of iron bearing sandstone.

The structural environment of the mine area consists of a series of pre-mineral faults dipping 50-80 degrees and striking west-northwest. They are part of the first and second tension shearing pattern of structures with an environment of tension running east-west caused by a thrust of the San Vicente fault.

Mineralization in the district is known to cover an area of 3 by 4 kilometres to a depth of 300 metres. It consists of vein mineralization in pre-existing faults, dissemination in brecciated conglomerates in the San Vicente fault and mineralization in dacitic dykes.

3.4. Exploration and Development

There has been sporadic mining activity in the San Vicente area since colonial times. Initial exploitation was the mining of oxidized silver from exposed veins. The first written records of mining activity were in 1820, when the area was named the Guernica Mine. Several different owners operated the mine from 1911 through 1950. From 1950 until 1952, the Aramayo Mining Company operated the mine. In 1952, the Bolivian government nationalized the mine and placed it under control of COMIBOL. Following the discovery of new silver and zinc veins in the late sixties, COMIBOL constructed the Vetillas concentrating plant in 1972 with a capacity of 400 tonnes per day. The mine was operated by COMIBOL until 1993, at which time mining was suspended pending the privatization of mining in Bolivia. In 1995, the San Vicente property was offered for a joint-venture contract by COMIBOL. On June 21, 1999, PASB signed a joint-venture agreement (Contrato de Riesgo Compartido) with COMIBOL. In late 2001, PASB and COMIBOL, the Bolivian state mining company that optioned the San Vicente property to PASB, entered into a two-year toll milling agreement with EMUSA, to process up to 250 tonnes of San Vicente's ore per day at EMUSA's nearby Chilcobija mill. In late 2005, PASB and COMIBOL entered into an additional 7-month toll milling agreement with EMUSA to process up to 250 tonnes of San Vicente's ore per day at EMUSA's nearby Chilcobija mill. This toll milling agreement was renewed for an additional 150,000 tonne program that is currently in progress. The economic analysis assumes that COMIBOL will approve an additional program for mining in 2008 and that the toll milling agreement will be extended.

The PASB exploration program began in 1999 following the execution of the joint venture agreement with COMIBOL. The work started with mapping and sampling the surface and was followed by the construction of drill access roads and platforms. Contracts were established with Leduc Drilling and Exploration Core Drilling S.R.L., and a total of 21 holes (3,831 m) were drilled from surface using HQ core and a further 8 holes (405 m) from underground using NQ core. These holes targeted the old stoping areas, continuations of the principal veins along strike and at depth, and other veins to the northeast and south of the mine. Since the start of the exploration program, a total of 109 diamond core holes have been drilled, with 2,575 vein intercepts sampled with varying lengths from 0.2 metres to 7.14 metres.

In addition to the diamond drilling, a sampling program was started in the mine. An initial 41 channel samples were taken in four of the principal structures (6 de Agosto, Adela, Litoral and Unión). The results of the surface drilling showed wider intersections than had previously been mined underground and so the channel samples were unable to explore the full width of each vein. After this realization, mining work was undertaken to develop small cross section cross cuts (1.5 m by 2.0 m) at a maximum of 75 metres apart along strike in the four veins on levels 0, -30, -70 and -110 in order to explore the full economic width of each vein. Some 5,807 channel samples were taken by COMIBOL and a further 2,449 channel samples taken by PAS. Some of the PAS channel samples replace the COMIBOL channel samples where the vein width is actually greater than was initially thought by COMIBOL.

Exploration activities continued in 2004 with the concept of drilling 13,919 metres of surface and underground diamond drilling, 2983 metres of underground development and resampling of historical reserve blocks for purposes of resource definition and exploration. Mine development and production to supply the Chilcobija mill continued in 2005, 2006 and 2007 and provided additional channel sample data for the resource database. A requirement of the interim mining programs agreed between PASB and COMIBOL was that sufficient additional development work be undertaken so that the total quantity of ore developed and ready for mining is maintained. This development provided additional channel samples in the principal and other structures.

3.5. Mineral Resource and Reserve Estimates as at December 31, 2006

The proven and probable mineral reserves at the San Vicente mine as at December 31, 2006 are estimated to be as shown in Table 1. This mineral reserve estimate was calculated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc, and was prepared under the supervision of and reviewed by Martin Wafforn, P. Eng. Vice President of Mine Engineering of PAS and Dr. Michael Steinmann, P. Geo. Senior Vice President of Exploration and Geology of PAS. Each of Mr. Wafforn and Dr. Steinmann is a Qualified Person as that term is defined in N.I. 43-101.

Table 1 San Vicente Mineral Reserves

Reserve Category	Tonnes	Grams of Silver per tonne	Zn (%)
Proven	1,988,538	304	3.85
Probable	1,069,647	430	2.66
TOTAL	3,058,185	348	3.43

Notes:

1. Total grades of silver and zinc before mill recoveries of 85.0% for both metals are applied.
2. PAS's share is 94.999% of the total mineral reserves,
3. San Vicente's mineral reserves have been estimated at a minimum mineralized width of 0.8 metres and at a cut off value per tonne of \$34 for shrinkage stoping and \$30 for longhole stoping.
4. The geological model employed for San Vicente involves geological interpretations on sections and

plans derived
from core drill
hole
information and
channel
sampling,

5. Mineral reserves have been estimated using the O Hara dilution formula, which typically adds 20% to 50% dilution at zero grade depending on dip angle and vein width.
6. Mineral reserves have been estimated using a mining recovery of 90% with a further 5% subtracted for other mining losses.
7. Mineral reserves were estimated based on the use of longhole stoping in the Litoral Ramal 2 vein and shrinkage stoping in all other veins. The mining and processing rate is assumed to be 750 tonnes per day on completion of the new plant.

8. Mineral reserves for the principal structures are estimated with a 3 dimensional block model using datamine software. Mineral reserves for minor structures are estimated using polygonal methods on longitudinal sections.
9. Mineral reserves were estimated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc.
10. Environmental, permitting, legal, title, taxation, socio economic, political, marketing or other issues are not expected to materially effect the above estimate of mineral reserves.

The measured, indicated and inferred mineral resources at the San Vicente mine as at December 31, 2006 are estimated to be as shown in Table 2. This mineral resource estimate was calculated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc, and was prepared under the supervision of and reviewed by Martin Wafforn, P. Eng. Vice President of Mine Engineering of PAS and Dr. Michael Steinmann, P. Geo. Senior Vice President of Exploration and Geology of PAS. Each of Mr. Wafforn and Dr. Steinmann is a Qualified Person as that term is defined in N.I. 43-101. The mineral resources shown in Table 2 are in addition to the mineral reserves shown in Table 1.

Table 2 San Vicente Mineral Resources

Class Reserve Category	Tonnes	Grams of Silver per tonne	Zn (%)
Measured	224,953	74	1.15
Indicated	445,244	294	3.67
Inferred	531,223	243	2.34

Notes:

1. PAS reports mineral resources and mineral reserves separately. Reported mineral resources do not include amounts identified as mineral reserves.
2. PAS's share is 94.999% of the total mineral resources.
3. Inferred mineral resources have a great amount of uncertainty as to their existence and as to whether, they can be mined legally or economically. It cannot be assumed that all or any part of the inferred mineral resources will ever be upgraded to a higher category.

4. The geological model employed for San Vicente involves geological interpretations on sections and plans derived from core drill hole information and channel sampling,
5. Mineral resources have been estimated using the O Hara dilution formula, which typically adds 20% to 50% dilution at zero grade depending on dip angle and vein width.
6. Mineral resources have been estimated using a mining recovery of 90%.
7. Mineral resources were estimated based on the use of longhole stoping in the Litoral Ramal 2 vein and shrinkage stoping in all other veins. The mining and processing rate is assumed to be 750 tonnes

per day on completion of the new plant.

8. Mineral resources for the principal structures are estimated with a 3 dimensional block model using datamine software. Mineral resources for minor structures are estimated using polygonal methods on longitudinal sections.
9. Mineral resources were estimated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc.
10. Environmental, permitting, legal, title, taxation, socio economic, political, marketing or other issues are not expected to materially effect the above estimate of mineral resources.
11. Mineral resources that are not mineral reserves do not

have
demonstrated
economic
viability.

12. A cut off value
per tonne of
\$17.00 was
used for
inclusion in the
mineral
resources.

The resource estimate involved statistical and geostatistical interpolation. Composites and 3-dimensional models were constructed utilizing Data Mine[®], commercial mine modeling software. Variables interpolations were done for silver and zinc grades and the true thickness of economic mineralization. Ordinary kriging was applied in two phases, first to Pan American silver sampling data only (channels and drill holes) and later to remnant blocks containing data collected by COMIBOL. Variogram models were obtained for each variable and for each vein which were divided in blocks of 40 metres x 20 metres (strike and dip). The blocks have been classified as measured, indicated or inferred based on the relative confidence of the supporting data for each evaluated block.

3.6. Mining Operations

The existing mine was designed and built to extract from steeply dipping narrow veins using conventional shrinkage stoping. Levels have been developed at 30 to 40 metre intervals and include the +70, +35, 0, -30, -70, and -110 levels. For reference, the 0 level is at an elevation of 4,440 metres above sea level. The main accesses to the mine are via the San Jose adit at the 0 level and the San Juan adit on the -30 level. The vertical Pelayo shaft extends from the surface above the 0 level down to the -110 level, which is currently the deepest level in the mine. The inclined Rampa shaft also extends down to the -110 level. Existing track drift dimensions are small at 2.4 by 2.3 metres and therefore mine cars and locomotives are restricted to 40 cubic feet and 6 tonnes respectively.

The San Vicente Mine Expansion Project includes the construction of a new 750 tonnes-per-day flotation process plant at the mine site. The implementation of the project will require an increase in the mine's production capacity to match the production rate of the new mill. The mine produced 300 tonnes per day from shrinkage stoping in 2003. The mine intends to continue using shrinkage stoping in the narrow vein stopes and increase the conventional mining capacity by improving the Pelayo shaft and the haulage equipment. The remainder of the production will be by longhole mining using mechanized equipment and will require the development of a new decline from surface for equipment access and for ore haulage using mine trucks. The discovery by diamond drilling of the Litoral Ramal Dos vein has provided a wide and high-grade addition to the mine resource base. This vein is amenable to longhole mining which may allow a reduction in mine operating costs and will allow a higher mining recovery of the wider ore zones than could be achieved through shrinkage mining. PASB has determined that these advantages warrant the introduction of longhole mining methods.

3.7. Authors Conclusions

The results of the study for the San Vicente Mine Expansion Project indicate that the project is technically feasible and economically viable using PAS ore reserve silver and zinc prices. These prices are considerably lower than the current spot market prices. The economics take into account an increase in the mining taxation rate that has been discussed by the Bolivian government but not yet implemented. The project will provide jobs and economic stimulus to an area that is economically depressed, and can be constructed in and operated in an environmentally sound manner. The project enjoys strong support from the union that represents the current employees at the mine and current indications are that the Bolivian national mining company COMIBOL and joint venture partner in the project will provide support as well. There have been some threats of nationalization of mining projects in Bolivia, however this has not occurred to date and the risk is balanced by the high projected IRR of the project and the relatively small cash outlay that is required when considering the cash benefits that will be received from on-going operations during the construction period.

The results of the metallurgical testwork as well as the previous processing of San Vicente ore at the Vetillas plant and the current processing of San Vicente ore at the Chilcobija plant give the authors a high degree of confidence that the projected metallurgical recoveries of 85% for silver and 85% for zinc will be realized.

The economic analysis calculates an Internal Rate of Return of 22% and capital payback in 2.9 years. The Net Present Value is \$23.6 million at a 10% discount rate and is \$14.4 million at a 15% discount rate. The undiscounted after tax cash flow is \$53.8 million. PAS's 95% share of the undiscounted after tax cash flow

is estimated to be \$50.9 million. Capital cost is estimated to total \$40.5 million in 2007 and 2008. The San Vicente Mine Expansion Project is not sensitive to capital fluctuations of up to 25% which is the expected accuracy of the engineering estimate. When in full production, the San Vicente mine unit operating costs are expected to total \$48.16 per tonne.

The life of mine plan presented in this study is based solely on proven and probable mineral reserves. The life of mine plan extends until 2019. Any conversion of the mineral resources to proven and probable mineral reserves and any new exploration discoveries will add to the mine life.

The environmental license for the San Vicente mine is now in the process of being updated to reflect the proposed expansion of the mine, construction of a new processing plant, new tailings facility and associated infrastructure. PAS is committed to developing the San Vicente Mine Expansion Project by minimizing and mitigating environmental impacts in accordance with Bolivian regulations, industry best management practices and its own Environmental Policy.

3.8. Authors Recommendations

It is the recommendation of the co-authors of this Technical Report that the San Vicente Mine Expansion Project be implemented. The agreement with COMIBOL stipulates that this construction must be completed within 18 months of approval by COMIBOL of an engineering report that was presented to them (the permission was received in July 2007).

The co-authors recommend that the San Vicente Mine Expansion Project should proceed according to the designs and schedules contained in this Technical Report. PAS currently has sufficient cash to develop this project and does not need to arrange for project financing. The next key step will be the award of an EPCM contract for the construction of the new process plant and upgraded infrastructure. The co-authors recommend that the mineral reserve and resource statements presented herein be adopted.

4.0 INTRODUCTION

This Technical Report has been prepared in accordance with NI 43-101 and the format and contents of this report are intended to conform to Form 43-101 F1. This Technical Report has been prepared for PAS for the purposes of: Reporting and summarizing the results of the studies shown in Table 3 into the feasibility of the San Vicente Mine Expansion Project, and presenting the technical basis for the reserve and resource estimate for the San Vicente Mine property.

Mr. Martin Wafforn, P.Eng., PAS's Vice President of Mine Engineering serves as the Qualified Person with respect to the mineral reserve statements described herein and sections 1, 2, 3, 4, 5, 6, 7, 8, 19, 20, 21, 22, 23, 24 and 25 of this Technical Report and the figures 1-4, 1-4a, 1-5 and 1-6, contained in this Technical Report. Mr. Wafforn last visited the San Vicente mine site from January 21st to January 23rd, 2007.

Dr. Michael Steinmann, P.Geo., PAS's Senior Vice President of Exploration and Geology serves as the Qualified Person with respect to the mineral resource statements described herein and sections 1, 2, 3, 4, 9, 10, 11, 12, 13, 14, 15, 16, 17, 19, 20, 21, 22, 23 and 24 of this Technical Report and the figures 1-1, 1-2, 1-3, 1-4b, 1-7, 1-8, 1-11 and 1-12 contained in this Technical Report. Dr. Steinmann last visited the San Vicente mine site from January 21st to January 23rd, 2007.

Mr. Maxwell, P.E. of Lyntek Inc. serves as a qualified person with respect to the mineral processing and metallurgical testing, as well as process design, capital cost estimates for the plant and infrastructure, and operating cost estimates for the plant and for sections 18 and 25 and the figures 1-9 and 1-10 of this Technical Report. Mr. Maxwell has not visited the San Vicente mine site. Other members of the Lyntek team visited the San Vicente site from August 12, 2006 to August 18, 2006 and have reviewed site photos and discussed the project with Mr. Maxwell.

Elmer Idefonso a consulting mining engineer to PAS performed the geostatistical evaluation and resource modelling under the direct supervision of Dr. Steinmann.

Sources of information and data contained in this Technical Report or used in its preparation are shown in Table 3.

Table 3 References

Report	Section
Assessment of Borrow Sources for concrete Aggregates Worley, Parson , Komex April 4, 2007	25
San Vicente Mine Site D Tailings Facility Preliminary Design Worley, Parsons, Komex April 12, 2007	25
Interim Report Geotechnical Engineering Assessment of the Proposed Process Plant Worley, Parsons, Komex January 22, 2007 ²	25
Evaluation of Water Sources for the San Vicente Mine Worley, Parsons, Komex October 31, 2006	3, 6, 7, 25
PASB Internal Report Updating COMIBOL on Project power supply E. Robles January, 2007	25
Shaft and Hoist Review and Recommendations Dynatec Mining Corporation October 19, 2005	25
Metallurgical Study of the Metallic Minerals at the San Vicente Mine conducted at TECSUP lab, Lima, Peru- A. Vargas October, 2004 ⁴	18, 25
Metallurgical Study of the Metallic Minerals at the San Vicente Mine conducted at Quiruvilca Mine, Peru- G. Portales September, 2005	18, 25
Determination of Bond Work Index Universidad Nacional de Ingeniería, September, 2005	18, 25
Numerous correspondences and reports Estudios Mineros latest in May, 2007	25
Preliminary Design and Evaluation of Alternate Tailings Disposal Sites Komex October 28, 2005	18, 25
Electrical Project of San Vicente (Upgrading transmission lines and sub-stations) Alicon SRL August 29, 2005	25
Upgrading existing electrical facilities Empresa de Servicios Eléctricos	25
Feasibility Study Report San Vicente, Bolivia Lyntek Inc.October, 2006	18, 25
Basic Engineering Interim Report San Vicente, Bolivia Lyntek Inc.December, 2006	18, 25

Notes:

1. PAS retained Estudios Mineros, an Engineering company based in Lima, Peru, to assist with the preparation of the mine plan and schedule. The work performed included a determination of the required capacity of the Pelayo shaft, preliminary geotechnical report, recommendation of dilution

quantities to be applied, Litoral ramp design, and development layouts for each of the major levels, and short and long-term mine plans.

2. PAS retained Worley Parsons Komex (Komex) of Calgary, Alberta, Canada to provide engineering and reports on the design of the tailings storage facility, geotechnical assessment of the proposed plant location as well as on ground water hydrology and the location of the required water supply for the San Vicente Mine Expansion Project.
3. PAS retained Dynatec USA of Salt Lake City, Utah, USA to inspect the Pelayo shaft and hoisting system. Their scope includes replacing the mine hoist, the small headframe and making necessary repairs in the shaft.
- 4.

Alfredo Vargas
P.E. was retained
to supervise the
metallurgical
testwork and to
compile the data.

5. Lyntek
Incorporated of
Denver,
Colorado, USA
has been retained
to provide
detailed
engineering and
procurement for
the new flotation
process plant and
selected mine
infrastructure.
Lyntek prepared
a feasibility
study report in
October 2006
and a basic
engineering
interim report in
December 2006
concentrating on
the following
specific areas: 1)
Design of a new
concentrator, 2)
Milling, 3)
Complete
process circuit,
flotation circuit,
and metallurgy,
4) Electrical
requirements,
and 5) Plant
infrastructure.
Their work
included
providing capital
and operating
cost estimates for
the above areas
as well as
preparing a
project schedule.

6. Sistemas de Agua of Bolivia were retained for water well drilling.

The co-authors have reviewed the information contained in these documents and included in this Technical Report and determined in their professional judgement that such information is sound and confirm and approve of such information.

All tonnages stated in this Technical Report are dry metric tonnes (dmt) unless otherwise specified. Ounces pertaining to silver metal content are expressed in troy ounces. All dollar values stated in this report are U.S. dollars.

5.0 RELIANCE ON OTHER EXPERTS

Martin Wafforn, Michael Steinmann and Douglas Maxwell, as co-authors of this Technical Report, have relied upon the references, opinions and statements from the following Non-Qualified Persons contained within the references listed in Section 23 – References. These reports, documents, and statements were found to be generally well organized and presented, and where applicable, the conclusions reached are judged reasonable.

MINCO of Bolivia were retained to provide the environmental assessment as well as to conduct field sampling, data interpretation and permit application.

It is assumed that technically qualified and competent persons prepared these reports and documents. It is the authors opinion that the materials referenced above are prepared and presented according to mining and engineering industry standards. The co-authors conclude that the contents are reasonably organized and presented and the conclusions reached are prudent.

6.0 PROPERTY DESCRIPTION AND LOCATION

The San Vicente silver-zinc mine is located at latitude 21°-16´south and longitude 66°-19´west in the southern end of Bolivia in the Province of Sud-Chichas, Department of Potosí. The mine is 460 kilometres south of the city of Oruro and 300 kilometres west of Tarija. Access is by dirt road 100 km west of the town of Tupiza and 150 km south of Uyuni. The property is in the Andean High Plateau (Altiplano), at approximately 4,400 metres above sea level, with semi-arid climatic conditions. The land is sterile and rugged. The following figures show the location of the San Vicente Mine:

- § Figure 1-1 Location of the San Vicente Mine in Bolivia
- § Figure 1-2 San Vicente Mine Location Map in Potosi
- § Figure 1-3 San Vicente Mine General Site Layout
- § Figure 1-4 San Vicente Mine, Mine Site General Layout (view of the mine area)
- § Figure 1-4a San Vicente Mine, Mining Concessions
- § Figure 1-4b San Vicente Mine, Geology Map

Property boundaries are located by co-ordinates and are not marked physically in the field.

The locations of all know mineralized veins and structures containing the mineral reserves and mineral resources are shown in Figure 1-8. The plant site, tailings facility, mine workings and other infrastructure are shown in Figures 1-3 and 1-4.

6.1. Mineral Tenure

The Project consists of 13 concessions, with a combined area of 7,075 hectares as shown in Table 4. Of the concessions, five with an area of 662 hectares start with the name *Aguas* which is Spanish for Waters. All of these concessions were contributed to the joint venture by COMIBOL in exchange for its participation in the project. COMIBOL however retains ownership of the concessions. PASB has the same exclusive right on all of the concessions to explore, develop and exploit as well as the right to marketing of the products. The use of all other mining resources existing on the concessions are included, as well as water rights, surface rights, its easements, uses and customs, without any limitation or restriction. All of the concessions, with the exception of Cinturón I and Cinturón II, were granted under the old mining code that was superseded on March 17th, 1997 by Law No. 1777, the new mining code. The current mining code provides that the previously awarded mining rights for the properties are still valid as long as the

registration requirements have been met. All San Vicente mining concessions are in good standing, according to article 93 of the Bolivian Mining Code. PASB has complied with the joint venture agreement (and various addendums thereto) and as a result the project and the concessions are in good standing.

Table 4 Mining Concessions

Concession	Hectares
Aguas Confianza	125
Aguas Confianza 2	145
Aguas Jayajmayu	103
Aguas San Francisco	60
Aguas San Vicente 2	229
Sub Total	662
Apolo 2	3,467
Codiciada	229
Complemento	16
La Confianza	10
Sucre	28
Marcela	1,163
Cinturón	225
Cinturón 2	1,275
Sub Total	6,413
Total Mining Concessions	7,075

Since 1997, the granting of concessions in Bolivia has been legislated by the Political Constitution of the State, under Mining Code No. 1777. Code DS 23230-A authorizes COMIBOL to grant concessions and mining centers in Lease and Joint Venture agreements. Supreme Decrees and Laws regulate taxation, environmental regulations, and administrative matters for joint ventures and leases.

Mineral resources, whether surface or underground, are the domain of the State, and may be granted for Lease and Joint Venture agreements for their exploitation as stated by Article 136 of the Political Constitution of the State. Bolivian incorporated companies, foreign companies, or individuals may possess mining concessions (with the exception of: minors, government employees, members of the armed forces, police, and relatives of people employed in the aforementioned), in accordance with Chapter II, Part I of the Mining Code (Articles 16 to 23).

Foreigners are not permitted, according to article 25 of the Political Constitution of the State and article 17 of the Mining Code, to exploit concessions within 50 km of any international boundary but they are authorized to subscribe to agreements to form Joint Venture Companies in said areas. (San Vicente is 62 km from the Argentina border).

Once a mining concession has been granted, the concessionaire can explore and exploit ores inside the concession, including tailings and residual material. Mining concessions cannot be transferred, sold, or mortgaged.

6.2. Permits and Agreements

Pursuant to the Joint Venture Agreement between PASB and COMIBOL, PASB is required to pay to COMIBOL a participation fee of 37.5% of the operations cash flow after deducting management fees. Once the commercial production phase of San Vicente begins, the COMIBOL participation fee will be reduced by 75% until PASB recovers

its investment in the property. Thereafter the COMIBOL participation will revert to 100% of the participation fee described above.

In the latest amendment, PASB was authorized to execute a program of mining and toll milling at the Chilcobija plant of 150,000 tonnes of ore. This decree allows time for execution of the projects outlined in the feasibility study while permitting mining and milling operations, providing cash flow to COMIBOL and PASB and addressing the social issues relating to the San Vicente miners. During this program, COMIBOL participation is 50% of operating cash flow.

In May 2007, PAS purchased the 40% interest in PASB held by EMUSA. 80% of a 2% net smelter return royalty interest in the property has been retained by EMUSA. This royalty is payable only: (1) after PASB recovers the costs to develop the project from January 1, 2007 up to the point of commercial production; (2) recovery of the cost of the purchase of EMUSA's 40% interest in PASB, and (3) is only payable in a calendar quarter where the average price of silver is \$9.00 per ounce or higher.

6.3. Environmental

The environmental license for the San Vicente mine is now in the process of being updated to reflect the proposed expansion of the mine, construction of a new processing plant, new tailings facility and associated infrastructure. The existing license only contemplated the operation of the mine where the ore was processed off site by EMUSA at the Chilcobija plant under a toll milling contract. The existing environmental license also included the provision for all tailings produced from the processing of San Vicente ores at the Chilcobija plant to be permanently stored at a tailings facility near the plant. The responsibility for the design, operation and permitting of this tailings facility was part of the responsibilities of EMUSA under the terms of the toll milling contract.

PASB contracted the Bolivian consulting firm of Minco to carry out an environmental baseline study, ALBA, as they are known for the acronym in Spanish, in 2001. Between 2001 and the present, this baseline information has been complemented with semi-annual monitoring of air, soil and water quality parameters at various monitoring locations in the vicinity of the San Vicente Mine. This existing information will be further complemented by a further round of sampling to establish the baseline conditions for the proposed expansion of the San Vicente Mine.

Minco is currently in the stage of preparing the Environmental Impact Study, or EEIA, as it is known under Bolivian legislation, for submittal to Bolivian environmental authorities. The main incremental impacts resulting from the proposed expansion of the mine are related to:

- § Construction of a new tailings facility in a valley that is tributary to the San Vicente River, downstream of the mine;
- § Construction of a new processing plant on the south side of the San Vicente river valley between the proposed location of the tailings facility and mine;
- § Increased groundwater use in the new plant; and
- § Waste rock storage from mine development.

Pan American Silver is committed to developing the San Vicente Mine Expansion Project by minimizing and mitigating environmental impacts in accordance with Bolivian regulations, industry best management practices and its own Environmental Policy.

The Vetillas plant and old tailings will not be used for the San Vicente Mine Expansion Project, and any environmental liability related to the Vetillas tailings is COMIBOL's responsibility as specified in the Joint Venture Agreement.

There are no other known environmental liabilities.

7.0 ACCESSIBILITY, CLIMATE, LOCAL RESOURCES, INFRASTRUCTURE AND PHYSIOGRAPHY

Access to the San Vicente mine is by dirt road from the towns of Tupiza or Uyuni. Tupiza is approximately 100 kilometres east. There is a road from Tupiza to the border with Argentina, which is to the south. Tupiza is connected to the rail system, which serves Bolivia and connects with the ports of Arica and Antofagasta in Chile. Zinc concentrates produced at EMUSA's Chilcobija are loaded to rail cars in Tupiza and transported by rail to Antofagasta. Uyuni is another hub for the rail line and is 119 road kilometres to the north of San Vicente. Concentrates produced at the new San Vicente mill in San Vicente will be transported to Uyuni to be loaded onto rail cars. The roads from Uyuni and Tupiza are open year round; nevertheless, in the rainy season some sections suffer from landslides and flooding and may close from time to time. There are gravel airstrips near both Uyuni and Tupiza however; they do not have regularly scheduled plane service.

Plant equipment and heavy equipment for the San Vicente Mine Expansion Project will be transported via road to the plant site. The best route is via the town of Uyuni either from La Paz in the north or from Arica or Antofagasta to the West. The route from La Paz starts with a paved highway to the town of Challapata. After Challapata, the paved highway becomes a heavily traveled gravel road that is the major North/South route through the country. Depending upon the season of the year, this road is normally sufficiently graded to carry light vehicular traffic. There are several rivers that must be forded between Challapata and Uyuni. The road from Chile and the port of Antofagasta up to the Bolivian Border is in good condition. The road from the border to the town of Uyuni was upgraded recently. The road from Uyuni to San Vicente is 119 kilometres and the last 88 kilometres of this road will be upgraded to an all weather road in particular five areas where rivers or streams are crossed.

Climatic data from the weather station in Atocha (60 kilometres to the Northeast) reflects weather conditions in the Altiplano in the south of Bolivia. Daytime temperatures range from 4°C in June and July to 14°C in December and January. The winter months are May to September and night time temperatures are frequently below zero with extremes of minus 15°C. Average annual rainfall is 190mm, with no rain from May to September. Rainfall occurs mainly in the summer months, when up to 20mm of rain can fall in a day.

The continuous fresh water supply requirements for the new San Vicente concentrator are calculated to be 22 litres per second. A combination of the water wells drilled and the surface water sources within the area will be required to provide the required water supply. The four confirmed water sources within the immediate plant site vicinity are shown in Table 5:

Table 5 Water Sources

Source	Reported Flow Rate	pH
Rio San Vicente	2 to 3 L/Sec.	3.5
Mine Discharge	2 to 3 L/Sec.	3.5
Vetillas Mill	14 L/Sec.	3.5
Angosto Mica	18 to 20 L/Sec.	7.0 to 8.0

Angosto Mica is a proven water source that supplied water to the Vetillas Mill when it was in operation. It is located some 16 kilometres from the plant site and has an existing concrete dam that will be rehabilitated. As the new power line that will be constructed to supply the new plant will pass close by the Angosto Mica dam, a power line can be run down to the selected pump station area. Water from the dam will be pumped to a concrete storage sump that will be located near Vetillas. Water from the Vetillas River will also be pumped to this storage sump.

The Vetillas Mill is not on a mining concession owned by PASB, however, it is part of the assets that COMIBOL contributed to the joint venture. There are verbal agreements that San Vicente has the right to use part of the Vetillas Mill water source, however, for the purposes of

this report and for the purposes of the economic analysis it has been assumed that Angosto Mica and other water sources will supply the water to the project. As can be seen from Table 5 the surface water sources only just cover the projected requirements of the mine and some additional water well drilling is recommended by the authors to provide a more plentiful water supply.

At this time, only one domestic water source is being considered for use and is located 2.7 km from Vetillas. This well was drilled and cased by Komex and the initial pump tests from this well were reported to be 10L/sec of water flow at a pH = 7.0. Martin Wafforn, one of the authors of this Technical Report, has verified this number from the report

Evaluation of Water Sources from the San Vicente Mine by Worley, Parsons, Komex. Actual flow rates are yet to be confirmed by additional pump testing.

A pump will be installed in this well to pump water to a domestic water storage tank that is located at the man camp in Vetillas and a distribution pump at the storage tank will supply the water requirements for the man-camp. A second booster pump located at the Vetillas storage tank will pump water to a second domestic water storage tank that is located at the San Vicente concentrator. A distribution pump at this second water storage tank will provide the mine, mill and the mine offices with domestic water.

The power supply must be upgraded to meet the increased electrical demand from the new mill and the expanded facilities. The existing power supply is via a 27.7 kilometre long 15 Kv, 2MVA, line from a substation that is owned and operated by a cooperative in Telamayu. A new 34 Kv, 5MVA, electrical transmission line and associated sub stations and switch gear will be constructed parallel to the existing line so that the power supply is maintained to the town and the mine during the construction period. After the new electrical transmission line has been commissioned, the old one can be removed.

The area is poorly vegetated. With the exception of those employed at the mine there are very few other inhabitants in the area. The only use of the ground, other than for mining activities, is a wild pasture for llamas.

The property is in the Andean High Plateau (Altiplano) at an average elevation of about 4,400 metres above sea level. Elevations in the immediate area of the mine vary from 4,300 metres to 4,550 metres above sea level. The property is in an historical mining area with a sufficient supply of experienced mining personnel. The project holds sufficient mining claims and surface rights for all of the mining buildings, processing plant, tailings dam etc for all of the operations that are in the mine plan.

8.0 HISTORY

The area of San Vicente has been sporadically exploited since Colonial times. The first written records of mining activities are from 1820 when the mine was known as Guernica mine. It was operated under this name from 1820 to 1830. The area was originally exploited for Silver Oxide and some of the old mine workings are still visible today. The mine was closed from 1880 to 1910 and then operated by various owners between 1911 and 1950. A Chilean company operated the mine in the 1920 s. Between 1950 and 1952, Compañía Minera Aramayo operated the mine. In 1952, the Bolivian government nationalized the mine and placed it under control of COMIBOL who in 1972 constructed the Vetillas concentrating plant with a capacity of 400 tonnes per day. The mine was operated by COMIBOL from 1972 until 1993 at which time mining was suspended pending the privatization of the mine. During the last 5 years of operations under COMIBOL (1988 to 1993), the mine produced an average of 106,000 tonnes per year grading 402 grams/tonne silver and 3.58% zinc per tonne. The mill produced a simple concentrate with a grade of 41% Zinc and 7,800 grams of Silver per tonne. The mine was maintained by COMIBOL until 1999.

In 1995, the Bolivian government launched a tender to joint venture the San Vicente mine and the Vetillas mill. After two failed attempts, the tender was declared void. COMIBOL was then authorized and permitted to invite international companies to present offers. PASB submitted a proposal. The COMIBOL Board of Directors accepted PASB s proposal and a joint venture contract with respect to the development of the San Vicente property was subscribed with Resolution number 1751/99, on June 21, 1999.

The joint venture contract was protocolized by Notary of Public Faith, a requirement of Bolivian law, and later inscribed in the Mining Registry and the Registry of Trade. The joint venture contract for San Vicente

is registered in Testimony #132/99, dated July 28 1999, granted by Dra. Nelly Alfaro de Maldonado, Notary of Public Faith, registration #003.

There have been several amendments to the original joint venture contract as follows:

The first amendment to the joint venture contract was executed on May 18, 2001. The amendment, in accordance with Bolivian law, was protocolized by Notary and then inscribed in the Mining Registry and the Registry of Trade. The amendment is Testimony #101/2001 dated June 13, 2001 granted by Dra. Nelly Alfaro de Maldonado, Notary of Public Faith, registration #003. The amendment modifies the original schedule of the Committed Investment.

The second amendment was executed on July 20, 2001. The amendment was protocolized by Notary and inscribed in the Mining Registry and the Registry of Trade. The amendment is Testimony number 127/2001 dated August 7, 2001, granted by Dra. Nelly Alfaro de Maldonado, Notary of Public Faith, registration #003. The amendment specifies the addition of two new mining concessions to the Joint Venture Contract: the concessions Cinturón I and Cinturón II. The third amendment was executed on December 19, 2003. The amendment was protocolized by Notary and then inscribed in the Mining Registry and the Registry of Trade. The amendment is Testimony number 17/2004 dated February 12, 2004, granted by Dra. Nelly Alfaro de Maldonado, Notary of Public Faith, registration #003. In this amendment, PASB gave up the rights to the Montserrat concession.

The fourth amendment was executed on March 25 2004. The amendment was protocolized by Notary and then inscribed in the Registry Mining and the Registry of Trade. The amendment is Testimony Nr. 51/2005 dated April 21 of 2005, granted by Dra. Nelly Alfaro de Maldonado, Notary of Public Faith, registration #003. In this amendment, COMIBOL authorizes PASB to execute a program of the exploitation and tolling of 55,000 tonnes of ore.

The fifth amendment was executed on June 13 of 2005. The amendment was protocolized by Notary and later inscribed in the Mining Registry and the Registry of Trade. The amendment is Testimony Nr. 74/2005 dated June 20, 2005, granted by Dra. Nelly Alfaro de Maldonado, Notary of Public Faith, registration #003. In this amendment, COMIBOL authorizes PASB to execute a program of the exploitation and tolling of 35,000 tonnes of ore.

The sixth amendment was executed on August 01 of 2006. The amendment was protocolized by Notary and later inscribed in the Mining Registry and the Registry of Trade. The amendment is Testimony Nr. 411/2006 dated August 08, 2006, granted by Dra. Ruth Rosario Villarroel Quisbert, Notary of Public Faith, registration number 4450. In this amendment, it is recognized the participation COMIBOL is increased to 37.5% of operating cash flow.

The seventh amendment was executed on August 01 of 2006. The amendment was protocolized by Notary and later inscribed in the Mining Registry and the Registry of Trade. The amendment is Testimony Nr. 412/2006 dated August 08, 2006, granted by Dra. Ruth Rosario Villarroel Quisbert, Notary of Public Faith, registration number 4450. In this amendment, COMIBOL authorizes PASB to execute a program of the exploitation and tolling of 150,000 tonnes of ore. This decree allows time for execution of the projects outlined in the feasibility study while permitting mining and milling operations, providing cash flow to COMIBOL and PASB and addressing the social issues relating to the San Vicente miners. During this program, COMIBOL participation is 50% of operating cash flow.

On June 21, 1999, when the joint-venture contract (Contrato de Riesgo Compartido) was signed with COMIBOL, PASB was a 100% subsidiary of PAS. In the fourth quarter of 2003, PAS signed a joint-venture agreement with EMUSA, granting them an option to earn a 50% interest in PASB. To vest its interest, EMUSA agreed to spend \$2.5 million in project costs in 2004 including drilling, underground tunnelling and initiating small-scale production. EMUSA had some difficulties fulfilling the requirements of the option agreement and the ownership of PASB settled at 55% to PAS, 40% to EMUSA and 5% to Traftigura. PAS being the major shareholder became operator and appointed the president of PASB. In May 2007, EMUSA sold its 40% interest in PASB to PAS. PAS transferred one share to Pan American Silver Peru S.A. to fulfill the Bolivian corporate law requirements, leaving PAS with a 94.999% ownership in PASB and Pan American Silver Peru with a 0.001% ownership.

9.0 GEOLOGICAL SETTING

San Vicente is a Polymetallic Vein Deposit, located 2.5 kilometres west of a prominent thrust fault. This north-south striking San Vicente fault forms the eastern limit of the intermountain Bolivian Altiplano basin. Mineralization at the mine site is hosted by conglomerates of Late Oligocene age. The clastic sediments are overthrust by an Ordovician turbidite sequence, outcropping on the east side of the mine. Igneous activity at the site is represented by intermediate to acid volcanism related to a volcanic complex of mid-Miocene age.

The regional sedimentary sequence consists of a basement of Paleozoic marine siliciclastic sediments. This sequence was folded and later unconformably overlain by non continuous cretaceous continental sediments, and a thick sequence of Tertiary continental clastic sediments (Potoco and San Vicente Formations). Sedimentation in the Tertiary basin was controlled during the Upper Oligocene and Lower Miocene by thrust faults to the east and west and contains various thin volcanic flows with an intermediate composition. A sequence of felsic volcanics forms the top of the Tertiary basin in the southern part.

An important lithology in the project area is the conglomerates of the San Vicente Formation which are in contact with Ordovician shales along the strike of the San Vicente fault. The conglomerate consists of poorly sorted conglomerate with sub angular fragments of Palaeozoic sediments cross cut by younger quartz veins. The matrix is red in colour and consists of iron bearing sandstone.

Mineralisation is related to hydrothermal systems associated to repeated calc-alkaline intrusions and their extrusive products forming vein type and disseminated polymetallic deposits.

10.0 DEPOSIT TYPES

San Vicente is a polymetallic vein type deposit with a large amount of mineralised structures. The three different vein systems strike west-northwest, northwest and in a minor extent northeast and show dip angles of 50 to 80 degrees. The mine site area can be divided into four areas with variable degree of exploration information (see Figure 1-7).

The North San Vicente area includes veins D, E, F, Lipeña, Brunton, Miriam, Lucero, Gandy and San Vicente; with strikes varying from N100-N120. The veins dip mostly to the north with angles from 55 degrees to sub vertical. Other veins located in the same area are the N060 striking H vein and some minor east west striking structures all of them with a sub vertical dip. All these veins are located north of the San Vicente river on the Rosario Hill, NW of the town San Vicente. There is a large amount of underground workings and small pits in this area. The veins are narrow, showing widths from 0.30 m to about 1.0 m. Mineralization is polymetallic, alteration is typically comprised of manganese oxides, and silicification in variable degrees.

The central San Vicente area includes some of the economically most important structures like Adela-Guernica, Jesus Maria, Disputada, Cantera, 6 de Agosto, Litoral, Litoral Ramo 2, San Lorenzo, Deseada, and Arturo veins. At surface they are marked by open stopes and silicified fault zones of variable length; being the 6 de Agosto vein the longest one up to today with about 1.3km of outcropping strike length and vein widths from cm to several metres. The Litoral and Litoral Ramo 2 veins do not outcrop. However, they are recognized by underground workings and diamond drilling for over 800 m along strike. Litoral Ramo 2 is locally up to 20 metres wide and shows some areas with very high silver grades. Most of the outcropping veins have been worked for centuries having historical grades from 500 to more than 1000 g/mt Ag.

The South San Vicente Area includes San Francisco, Nueva, Rica, and Potoco. These veins are characterized by having a roughly E-W trend; with San Francisco vein mined to an unknown depth with historical values of more than 500 g/mt of Ag and minor tin content. The other veins show only small amounts of open stopes and are structures for future exploration programs.

Far South San Vicente includes the Chichas, Lucio, Crucera, and Bandy veins. These veins were only subject of minor surface sampling and have not been exploited in the past but will be included in future exploration programs.

The West of San Vicente area includes different veins with some underground workings of unknown length and depth. Values from surface samples returned more than 100 g/mt Ag. In the area there is evidence for hydrothermal brecciation with strong silicification.

A list of the mentioned veins at the San Vicente site is shown in Table 6. Their location and strike direction are shown in Figure 1-8. The economic model used for this report uses only proven and probable mineral reserves. Therefore no additional exploration is required in order to meet the projections in the economic model. In the future a program may be initiated to explore by diamond drilling for additional mineralized structures and or to convert mineral resources into proven and probable mineral reserves.

Table 6 Occurrence of Veins in San Vicente Mine. (Modified from JICA, 1979)

Vein	Level	Surface	Azimuth	Dip	Length (m)	Principal mineral	Secondary Mineral
Inca	0		N240°	60°S	300	Sp-Py-Gn	Td-Cpy
Guernica II	0		N50°	80°N	400	Sp-Gn-Td-Cp-Py	
Guernica I	0		N300°	80°N	150	Sp-Gn-Td-Cp-Py	
Adela		X	N305°	65°S	300	Sp-Gn-Td-Cp-Py	
Jesús Maria		X	N280°	85°N	440	Sp-Gn-Td-Cp-Py	Gn
Disputada		X	N280°	65°N	300	Sp-Gn-Td-Cp-Py	
San José		X	N310°	65°N	650	Sp-Td-Cp-Py	Gn-Mc
Ferelys	0		N50°	60°N	150	Sp-Td-Py	Cp-Gn
Cantera		X	N305°	60°N	520	Sp-Td-Py	Cp-Gn
Artola	0		N65°	70°S	200	Sp-Td-Py	Cp-Gn
Rmo 6 de Agosto	0		N65°	60°N	150	Sp-Td-Py	Cp-Gn
6 de Agosto		X	N280°	65°N	2000	Sp-Td-Py	Cp-Gn
Litoral			N65°	70°S	1160	Sp-Gn-Td-Cp-Py	
San Lorenzo		X	EW	70°S	600	Sp-Gn-Td-Cp-Py	
Peritas	0		N75°	70°S	250	Sp-Td-Cp-Py	Gn
Deseada	0		N285°	65°N	950	Sp-Td-Cp-Py	Gn-Mc
Esperanza	0		N290°	60°S	150	Sp-Py	Gn-Cp
Porvenir	0		N75°	70°S	250	Sp-Td-Py	Gn-Cp
Rmo. Arturo	0		N75°	80°N	150	Sp-Td-Py	Gn-Cp
Arturo		X	N300°	65°N	1350	Sp-Td-Py	Gn-Td.Cc-Cv-Mc
Unión			N68°	65°NW	450	Sp-Td-Py-Cp	
Sophia		X	N84°	80°NE	570	Sp-Td-Cp-Py	
Sophia I		X	N103°	80°SW	900	Sp-Td-Cp-Py	
San Francisco		X	N93°	82°N	250	Sp-Td-cc-Cv-Py-Cp	
Chichas		X	N95°	70°N	1250	Sp-Gn-Py	
Brunton		X	N122°	68°NE	110	Sp-Gn-Py	
Miriam		X	N122°	70°NE	400	Sp-Gn-Py	
Lucero		X	N97°	66°NE	450	Sp-Gn-Py	
Gandy		X	N105°	67°NE	650	Sp-Gn-Py	
San Vicente		X	N130°	68°NE	400	Sp-Gn-Py	
Nueva		X	N102°	61°NE	380	Sp-Gn-Py	
Rica		X	N97°	78°NE	500	Sp-Gn-Py	
Potoco		X	N112°	70°NE	500	Sp-Gn-Py	
Bandy		X	N85°	70°NW	570	Sp-Gn-Py	
Lucio		X	N100°	68°NE	550	Sp-Gn-Py	
Crucero		X	N102°	62°NE	500	Sp-Gn-Py	
Negro		X	N97°	60°SW	360	Sp-Gn-Py	
SECTOR		T	A J O S				
Colonial		X	N103°	65°NE	450	Gn-Td-Sulfs-Py	
Veta D		X	N130°	73°NE	1350	Gn-Td??-Sulfs-Py-Pr	
Veta G		X	N105°	77°SW	430	Gn-Td??-Sulfs-Py-Pr	

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Veta E	X	N115°	75°NE	850	Gn-Td??-Sulfs-Py-Pr
Veta H	X	N55°	82°SE	320	Gn-Td??-Sulfs-Py-Pr
Veta F	X	N105°	68°SW	630	Gn-Td??-Sulfs-Py-Pr
Lipeña	X	N110°	66°SW	360	Gn-Td??-Sulfs-Py-Pr

REFERENCES

Sp: Sphalerite	Py: Pyrite	Cp: Chalcopyrite	Mc: Marcasite	Cv: Covellite
Td: Tetrahedrite	Gn: Galena	Pr: Pyrolusite	Cc: Chalcocite	Sulfs.: Sulfosalts

11.0 MINERALIZATION

The polymetallic mineralization in the district is known to cover an area of 3 km by 4 km to a depth of 300 metres below surface. The mineralization consists of (1) veins filling pre-existing faults, (2) replacements in brecciated conglomerates along the San Vicente fault and (3) in a lesser extent in dacitic dykes (Photographs 1, 2 and 3).

The structural environment of the mine area consists of a series of pre-mineral faults dipping 50°- 80° to the south and striking west northwest. A second set of structures is striking northeast.

The west northwest striking structures contain veins that have longer horizontal extensions and a mineralized width of 2 m to 6 m. The northeast veins are developed in the more dilatational direction and are characterized by the best widths and grades but over a shorter strike length.

The minerals of economic importance are sphalerite, tetrahedrite (the variety of freibergite rich in silver), chalcopyrite and galena. Cassiterite, covellite and bornite are found in some veins. The primary gangue minerals are quartz, pyrite, marcasite and barite.

The paragenetic sequence consists of an early phase of quartz pyrite, followed by the main phase of mineralization of sphalerite, galena, freibergite, and chalcopyrite with subsequent phases of quartz pyrite, barite and marcasite. A lateral zonation of metals exists in a central zone of high zinc grades that superimposes an area of high silver grades. More distant zones have medium silver grades and significant lead grades. The only significant vertical zonation encountered is the increasing copper grades (in chalcopyrite) in the deeper parts of some veins.

Hydrothermal alteration in the district is restricted to a 20 m band along the mineralized structures. It is represented by a fine grained sericite pyrite assemblage that has bleached the original red matrix. A moderate amount of silicification is also present. Locally iron and manganese oxides are present at surface.

The geologic history can be generally summarized as follows:

- § Deposition of a continental fan conglomerate at the margin of a tectonically active basin resulting in the emplacement of the San Vicente conglomerate.
- § Formation of west northwest, northwest and northeast striking faults in the conglomerate.
- § Emplacement of a dacitic intrusive 2 km to the east of San Vicente with small dykes and bodies in the area of the mine.
- § Alteration and zinc silver mineralization in the breccia zones of the faults by hydrothermal fluids over a time span of about 13 million years.

The known mineralized veins and structures are shown in Figure 1-8.

Photograph 1.

Fault vein with open space filling mineralization

Photograph 2.

Replacement style of mineralization. Replaced breccia matrix and clasts by sulphides

Photograph 3.

Intermediate intrusion hosting sulfide veinlets.

Table 7 Mineralogy of San Vicente Veins Recognized Under Microscope

<i>Channel N°</i>	<i>Ag (g/t)</i>	<i>Zn (%)</i>	<i>Pb (%)</i>	<i>Cu (%)</i>	<i>Sulfi</i>										<i>Rock</i>			<i>Paragenesis</i>
					<i>Sph</i>	<i>Tet</i>	<i>Cp</i>	<i>Gal</i>	<i>Py</i>	<i>Mar</i>	<i>Pol</i>	<i>des</i>	<i>Cov</i>	<i>Born</i>	<i>Qz</i>	<i>Bar</i>	<i>Frag.</i>	
0-007	345	4.13	2.05	0.41	3	<1	<1	3	5	30					6	40		qz>sph-Ttet-gal>marc>barita
0-006	218	15.57		0.78	5	2	<1		5	2				<1	23	3	58	py>tet>barita
0-005	733	22.52		0.88	20	<1	1		5						30		43	py>tet-cp-sph>qz
0-008	49	2.11		0.24	3	2	2	<1	2		<1				40		49	Sulfuros>qz
0-013	47	2.72	0.50	0.10	25	<1	<1	<1	2	2							60	marc>sphal
0-009	74	1.80		0.20	5	<1	<1		5	15	<1				25		48	sulfs>marc
0-010	256	20.08	0.72	0.62	10	2	2	1	8	<1		<1	<1		35		38	qz>sulfs
0-011	252	29.97	0.23	0.35	6	<1	<1		15	3					20		36	
0-004	1291	28.79	0.16	0.48	30	<1	<1	<1	25	<1					35		8	
0-003	203	2.91		0.26	<1	<1	<1	<1	27	8					40		22	
0-002	295	1.49		0.24	5	<1	<1		24	20					40		10	sulfs>qz
0-001	476	0.66		0.90	<1		<1		30	<1					40		30	py>sphal>qz
0-012	74	9.43		0.10	30	<1			40	2					10		12	sphal-py>qz-py>sph vetillas
30-010	156	3.21	1.43	0.29	10	<1	<1	8	2						40	3	37	qz>bar
30-006	294	14.66	0.13	0.27	20	<1	<1		3						30		47	qz>sph-py-yet>qz-py
30-005	391	10.44	2.64	0.78	3	8	1	2	30					<1	30	3	22	qz>suls>qz>sph-cp-tet vetill
30-008	2267	17.24			30	<1	<1	<1	6	2							62	
30-004	2650	12.99	0.12	1.00	5	<1	<1		30						10		55	py>tet

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

30-004	470	12.72	0.57	0.27	30	2	<1		10		40	1	16	qz>sulfs>qz	
30-007	72	1.87	0.13	0.20	2	<1	<1	<1	3	1	5		88		
30-003	1073	7.41		2.20	15	2	40		10		33			cp>qz-py; sph-tet-cp>qz	
30-002	892	0.45		0.88	<1	<1	<1		20		80			sulfs>qz	
30-001	330	2.49	0.22	1.70	3	<1	2	<1	20	12	40	3	20	sulfs>qz>bar	
30-002	396	1.55		0.47	2	<1	3	<1	35		<1	40	10	8	qz>py-cp-sph-dig-bn>bar
30-001	446	0.37		0.60	<1	3	2		40	20	35			py>cp-tet vetillas	
30-011	1159	2.04	0.99	0.40	20	5	<1	<1	1	1	20		53		
70-001	58	5.84			40	<1		<1	2		30	10	18	qz-sulfs>bar	
70-002	640	10.53		0.57	20	<1	<1		2		8	20	50	sulfs>qz-bar	
70-003	122	7.34		0.17	40	<1	<1	<1	3		20	12	25	sulfs-qz>bar	
70-004	788	8.98	0.11	0.69	3	2	1	1	8		20		65	qz>py>sulfs>qz	
70-007	333	6.16		0.44	65	<1	<1	<1	2	<1	30		3	py>sph>	
70-009	101	4.34		0.37	10	<1	2		40		40		10	sph>cp vetillas>py>qz	
70-005	639	9.10		1.10	3	2	6		10		40		38	qz-py-sph-tet-cp>qz	
70-006	244	1.43		0.41	20	<1	<1	<1	5		60		15	py>cp>sph>gal>qz	
70-008	282	8.52	0.67	0.22	5			<1	10		45		40	sulfs>qz	
70-013	125	6.95		0.34	42	<1	25	<1	20			<1		py>tet-gal>bar	
70-012	605	0.32		0.27	<1	1	<1	<1	2		40	4	56	py>tet-sph>qz	
70-011	935	3.79	0.12	0.61	2	<1	<1		30		40		28	py>cp-tet-sph>qz	
70-010	30	4.90			15	<1	<1		5	<1	30	10	50		
110-002	123	4.64	0.17	0.10	20	<1	<1	<1	3	8	40	5	25	cp>sph>gal>py>tet>qz>bar	
	1615	0.15	0.92	0.67	<1	<1	5	3	6		40		45	py>gal-tet-cp>qz	
	1617	1.55	0.31	1.02	8	<1	2	3	3		40		34		

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

243	9.81	0.13	0.56	15	<1	<1	2	3	<1	40	35	sulfs>qz>bar
116	5.29	0.11	0.11	50	<1	<1		2		30	13	
950	5.48	2.51	0.21	5	<1	<1	8	<1	<1	70	17	sulfs>qz
1415	0.55	0.16		<1				8	2	30	60	
14049	0.80	0.11	0.68					5	2	20	65	
2906	0.97	0.38	0.15	5	2	<1	<1	2	1	20	60	10 barita>sulfs-qz???
1006	3.35	0.52	0.19	12	1	<1	10	3		30	15	30 sulfs>bar
4292	0.86	0.70	0.12	<1				5	1	20	75	
575				<1	<1			5		30	3	61
677					<1	<1		3		40	2	55

12.0 EXPLORATION

There has been sporadic mining activity in the San Vicente area since colonial times. Initial exploitation was the mining of oxidized silver from exposed veins. The first written records of mining activity were in 1820, when the area was named the Guernica Mine. Several different owners operated the mine from 1911 through 1950. From 1950 until 1952, the mine was operated by the Aramayo Mining Company. In 1952, the Bolivian government nationalized the mine and placed it under control of COMIBOL. Following the discovery of new silver and zinc veins in the late sixties, COMIBOL constructed the Vetillas concentrating plant in 1972 with a capacity of 400 tonnes per day. The mine was operated by COMIBOL until 1993, at which time mining was suspended pending the privatization of mining in Bolivia. In 1995, the San Vicente property was offered for a joint-venture contract by COMIBOL. On June 21, 1999, PAS signed a joint-venture agreement (Contrato de Riesgo Compartido) with COMIBOL. In late 2001, PASB and COMIBOL, the Bolivian state mining company entered into a two-year toll mining agreement with EMUSA, to process up to 250 tonnes of San Vicente s ore per day at EMUSA s nearby Chilcobija mill. In late 2005, PASB and COMIBOL entered into an additional 7 month toll mining agreement with EMUSA to process up to 250 tonnes of San Vicente s ore per day at EMUSA s nearby Chilcobija mill. This toll mining agreement was renewed on August 8, 2006 for an additional 150,000 tonne program that is currently in progress.

The PASB exploration program began in 1999 following the execution of the joint venture agreement with COMIBOL. The work started with mapping and sampling the surface and was followed by the construction of drill access roads and platforms. Contracts were established with Leduc Drilling and Exploration Core Drilling S.R.L., and a total of 21 holes (3,831 m) were drilled from surface using HQ core and a further 8 holes (405 m) from inside the mine using NQ core. These holes targeted the old stoping areas, continuations of the principal veins along strike and at depth, and other veins to the northeast and south of the mine. Since the start of the exploration program, a total of 109 diamond core holes have been drilled, with 2,575 vein intercepts sampled with varying lengths from 0.2 metres to 7.14 metres.

In addition to the diamond drilling, a sampling program was started in the mine. An initial 41 channel samples were taken in four of the principal structures (6 de Agosto, Adela, Litoral and Unión). The results of the surface drilling showed wider intersections than had previously been mined underground and so the channel samples were unable to explore the full width of each vein. After this realization, mining work was undertaken to develop small cross section cross cuts (1.5 m by 2.0 m) at a maximum of 75 metres apart along strike in the four veins on levels 0, -30, -70 and -110 in order to explore the full economic width of each vein. Some 5,807 channel samples were taken by COMIBOL and 4,371 of these channel samples taken by COMIBOL remain in the database. The remainder have been excluded due to uncertainties over their location or replaced by PASB samples. A further 2,223 channel samples taken by PASB are included in the database. Some of the PAS channel samples replace the COMIBOL channel samples where the vein width is actually greater than was initially thought by COMIBOL.

Exploration activities continued in 2004 with 13,919 metres of surface and underground diamond drilling, and 2983 metres of underground development and resampling of historical reserve blocks for purposes of resource definition and exploration. Mine development and production to supply the Chilcobija mill continued in 2005, 2006 and 2007 and provided additional channel sample data for the resource database. A requirement of the interim mining programs agreed between PASB and COMIBOL was that sufficient additional development work be undertaken so that the total quantity of ore developed and ready for mining is maintained. This development provided additional channel samples in the principal and other structures.

All diamond drilling (underground and surface) was executed by Leduc Drilling S.R.L., and by Exploration Core Drilling S.R.L. Both are Bolivian companies and both were contractors to PASB under the supervision of PASB geologists.

Channel sampling underground was originally partially done by COMIBOL and later done by PASB employees under the supervision of PASB geologists. The channel sampling conducted by COMIBOL has been resampled and replaced by PASB sampling in the major structures as explained in section 14.0.

Mineral resource blocks that rely entirely on the COMIBOL channel samples have not been converted to mineral reserves and remain in the mineral resource categories.

Soil sampling was conducted in 6 parallel lines with a 100 m line spacing and 50 m sample spacing along lines. These lines cut the extension of the Guernica vein, the Litoral area and the extension of San Francisco and San Lorenzo veins. Samples were analyzed by SGS del Peru S.A.C for Cu, Zn, Cd, Pb, Au, Ni, Pd, and Ag.

The principal structures explored by PASB are: 6 de Agosto; Litoral Ramal 2; Litoral; Deseada; Adela, and Union. These principal structures contain 2,504,619 tonnes or 82% of the 3,058,185 tonnes in the mineral reserves. The highest grades and widest widths were discovered to be in the Litoral Ramal 2 structure, which has been diamond drilled using a 70 metre by 30 metre pattern. This structure contains 801,895 tonnes or 26% of the mineral reserves. The San Vicente deposit is typical of the polymetallic vein deposits found in the Bolivian Andes. The system contains a large amount of mineralized structures and veins which in many cases remain open for exploration both at depth and laterally.

13.0 DRILLING

109 drill holes were completed by PASB from 1999 to 2006 totalling 18,155 metres, obtaining HQ (approximately 6 cm) diameter core. Downhole deviation surveys were executed using a Tropari (mechanical) compass.

The initial drilling program was focused on the North San Vicente Area, where veins are close together and abundant. Results were not completely satisfactory and drilling was re-focused on the central zone. Although the veins in the north show economic values they do not have exploitable widths. The north zone maintains its exploration potential as many structures show increasing thickness at depth and sigmoidal loops. Minor reconnaissance drilling was done outside of the central San Vicente area.

A listing of the San Vicente drill hole collar locations and the economically important down hole intersects are given in Tables 8a and 8b. More detailed information on the intercepts and the channel sampling is shown in Appendix B. Tables 8a and 8b show the surface and underground diamond drill results and includes the structures that were interpreted to be intercepted as well as the approximate level at which the intersection occurred.

The diamond drill hole spacing and covered areas are derived from a combination of underground and surface diamond drilling. The information for veins that received the most exploration diamond drilling focus are as follows:

6 de Agosto vein drill spacing is 70 metres horizontal by 30 metres vertical centers. Some holes were drilled at the extents of the vein with wider spacing in order to evaluate the continuation of the structure. The explored portion of this vein covers an area that extends 450 metres horizontally by 90 metres vertically.

Litoral Ramal 2 vein drill spacing is 70 metres horizontal by 30 metres vertical centers. Some holes were drilled at the extents of the vein with wider spacing in order to evaluate the continuation of the structure. The explored portion of this vein covers an area that extends 800 metres horizontally by 250 metres vertically.

Litoral vein drill spacing is 50 to 70 metres horizontal by 30 metres vertical centers. Some holes were drilled at the extents of the vein with wider spacing in order to evaluate the continuation of the structure. The explored portion of this vein covers an area that extends 200 metres horizontally by 50 metres vertically.

Union vein drill spacing is 35 to 90 metres horizontal by 30 to 50 metres vertical centers. Some holes were drilled at the extents of the vein with wider spacing in order to evaluate the continuation of the structure. The explored portion of this vein covers an area that extends 420 metres horizontally by 160 metres vertically.

Colonial vein although this is not a principal vein it was subject to a drilling program. Drill spacing is 90 metres horizontal by 40 metres vertical centers. Some holes were drilled at the extents of the vein with wider spacing in order to evaluate the continuation of the structure. The explored portion of this vein covers an area that extends 300 metres horizontally by 90 metres vertically.

Deseada vein drill spacing is 150 metres horizontal by 30 metres vertical centers. Due to disappointing results from drilling the depth extension of this vein, no further infill drilling was done. The mineral reserve on this vein is based on development channel samples.

13.1. Surface Diamond Drilling

Drilling from surface was carried out in two stages totalling 15,922 metres. The first stage included 13 drill holes mainly located in the North San Vicente area; the second one contains 63 diamond drill holes mostly in the central zone. Diamond drill holes are located and oriented by geologists in the field. Typical drill holes are oriented to cut across the vein zones at an orientation perpendicular to the local strike of the zones and inclined to intercept the vein at as high an angle as is practical. In these cases the true width is assumed to be the same as the sample length of the vein intercept. In other cases, drilling to greater depths caused veins to be intercepted at less than 90 degree core axial angles. In these cases true widths of the vein intersection was calculated using trigonometry and stated in table 8a together with drill hole numbers, level of intersection and geochemical results for the mineralized zones.

Table 8a Summary Data San Vicente Surface Diamond Drill Holes

<i>HOLE No.</i>	<i>STRUCTURE</i>	<i>Level</i>		<i>RESULTS</i>			
		<i>intersected</i>	<i>Width (True)</i>	<i>Ag (g/t)</i>	<i>Cu (%)</i>	<i>Pb (%)</i>	<i>Zn (%)</i>
DDH-99-001	Desconocida	-50	0.55	288	0.12	0.86	0.30
DDH-99-001	Clavo Inca	-95	3.36	150	0.09	0.09	0.11
DDH-99-002	Veta E			NO SIGNIFICANT INTERCEPTS			
DDH-99-003	Lipena	+25	0.23	282	0.05	0.90	0.71
DDH-99-004	Desconocida	+122	0.16	669	0.08	0.04	0.06
DDH-99-004	Desconocida	+50	1.80	158	0.03	0.07	0.01
DDH-99-005	Veta D			NO SIGNIFICANT INTERCEPTS			
DDH-99-006	Veta "G"	-65	0.25	35	0.02	0.21	2.45
DDH-99-007	Guernica	-113	0.71	279	0.48	0.14	0.24
DDH-99-007	Rmo-Guernica		0.25	167	0.34	0.12	0.22
DDH-99-008	Desconocida	+116	0.47	358	0.02	0.31	0.16
DDH-99-008	Veta "E"	+78	1.83	234	0.01	0.36	0.10
DDH-99-009	Desconocida	+120	0.90	1,425	0.03	0.18	0.35
DDH-99-009	Desconocida	+70	0.90	246	0.007	0.05	0.56
DDH-99-010	Brunton y Myriam			NO SIGNIFICANT INTERCEPTS			
DDH-99-011	Gandy	-52	1.31	65	0.04	0.12	2.70
DDH-99-011	San Vicente	-97	0.75	22	0.03	0.09	3.68
DDH-99-012	6Agosto	-40	5.20	275	0.13	0.12	3.57
DDH-99-014	Rmo Arturo		0.70	36	0.04	0.05	6.32
DDH-99-014	Arturo Footwall	-60	0.74	80	0.20	0.11	4.19
DDH-99-014	Arturo	-60	6.70	41	0.06	0.04	5.54
DDH-99-015	San Francisco	-110	1.66	93	0.15	0.02	2.00
DDH-99-016	Chichas			NO SIGNIFICANT INTERCEPTS			
DDH-99-017	Litoral	-95	7.14	1022	0.78	0.02	1.45
DDH-99-017	Litoral Ramo 2	-105	2.78	351	0.11	0.01	1.18
DDH-99-018	Veta "H"	+30	0.55	286	0.02	0.07	0.57
DDH-99-019	Veta E			NO SIGNIFICANT INTERCEPTS			
DDH-99-020	Stockwork			NO SIGNIFICANT INTERCEPTS			
DDH-99-021	6Agosto	+50	3.42	183	0.10	0.11	3.59
DDH-99-021	6Agosto	+50	1.25	208	0.20	0.07	5.24
DDH-52-3	Cantera	-55	0.86	153	0.10	0.43	6.00
DDH-52-3	6Agosto			NO SIGNIFICANT INTERCEPTS			
DDH-03-022	Litoral	-120	1.50	54	0.70	0.10	0.57
DDH-03-023	Litoral	-117	2.03	1,201	2.50	0.30	3.80
DDH-03-023	Litoral Ramo 2	-125 a -135	6.29	813	0.51	0.10	3.10
DDH-03-024	Arturo	-110	1.75	88	0.18	0.16	4.55
DDH-03-025	Litoral	-55	1.50	93	0.76	0.01	0.11
DDH-03-025	SLorenzo	-131	0.70	422	0.54	0.08	2.32
DDH-03-026	Litoral	-61	4.45	429	0.61	0.05	0.07
DDH-03-026	Litoral Ramo 2	-102 a -110	6.10	454	0.16	0.07	2.29
DDH-03-027	Litoral	-78 a -92	4.45	793	0.69	0.08	0.23

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-03-027	Litoral Ramo 2	-126 a -150	6.29	741	0.71	0.03	1.05
DDH-04-028	Litoral		1.97	38	0.21	0.05	1.19
DDH-04-028	SLorenzo		0.70	13	0.01	0.03	0.07

27

<i>HOLE No.</i>	<i>STRUCTURE</i>	<i>Level</i>		<i>RESULTS</i>			
		<i>intersected</i>	<i>Width (True)</i>	<i>Ag (g/t)</i>	<i>Cu (%)</i>	<i>Pb (%)</i>	<i>Zn (%)</i>
DDH-04-029	Litoral Ramo 2	-128	3.07	1,398	0.47	0.27	11.26
DDH-04-030	SLorenzo	-100	0.70	153	0.27	0.05	0.14
DDH-04-030	Litoral	-116	1.69	261	0.76	0.10	1.49
DDH-04-031	Litoral Ramo 2	-90	1.50	81	0.08	0.02	2.73
DDH-04-032	Litoral Ramo 2		1.50	8	0.01	0.01	0.02
DDH-04-033	Litoral		1.50	9	0.03	0.08	0.49
DDH-04-034	Litoral Ramo 2	-33	1.50	118	0.62	0.32	3.31
DDH-04-035	Guernica2	-155	0.85	119	0.16	0.09	0.86
DDH-04-036	Union	-98	0.70	25	0.05	0.01	0.02
DDH-04-037	Deseada	-84	0.70	206	0.42	0.07	1.64
DDH-04-038	Litoral Ramo 2	-117	1.50	74	0.05	0.02	0.06
DDH-04-038	Litoral	-130	1.50	200	0.23	0.02	0.66
DDH-04-039	Deseada	-105	1.06	171	0.09	0.05	7.51
DDH-04-040	Ramo Arturo	+35	1.02	58	0.06	0.30	6.63
DDH-04-040	Arturo	+31	1.17	101	0.22	0.42	5.28
DDH-04-040	Arturo	-27	0.83	114	0.26	0.35	3.00
DDH-04-41	Unión	-32	0.70	5	0.00	0.01	0.13
DDH-04-41	Ramo Unión	-54	0.42	109	0.09	0.48	14.10
DDH-04-042	Desconocida	-85	0.33	205	0.56	0.10	3.58
DDH-04-042	Litoral Ramo 2	-160	1.70	260	0.37	0.01	3.46
DDH-04-042	Litoral.	-196	0.70	202	0.33	0.01	0.10
DDH-04-043	Union	+4	0.70	3	0.00	0.02	0.05
DDH-04-044	Deseada	-88	0.70	5	0.01	0.01	0.96
DDH-04-045	Union	-60	0.70	3	0.00	0.01	0.06
DDH-04-046	Litoral	-134	1.50	1,171	0.37	0.10	0.40
DDH-04-046	Litoral Ramo 2		1.50	10	0.01	0.01	0.01
DDH-04-047	Sophia I	-91	0.77	204	0.08	0.57	0.16
DDH-04-048	Desconocida	0	1.25	279	0.06	0.07	0.47
DDH-04-048	Rmo. Colonial	-68	0.37	475	0.04	0.02	0.15
DDH-04-048	Colonial	-75	2.32	732	0.21	0.16	0.37
DDH-04-049	Rmo Adela ???	-40	0.37	300	0.03	0.05	1.27
DDH-04-049	Disputada.	-82	0.3	167	0.02	0.50	1.98
DDH-04-049	Rmo Unión	-140	0.5	374	1.62	0.48	2.40
DDH-04-049	Union	-148	0.70	9	0.00	0.01	0.05
DDH-04-050	Rmo Deseada	-62	1.13	154	0.02	0.05	5.43
DDH-04-050	Deseada	-91	0.70	6	0.00	0.02	0.28
DDH-04-051	6Agosto	-134	0.72	30	0.00	0.01	0.28
DDH-04-052	Desconocida	-32	0.79	165	0.02	0.07	0.13
DDH-04-052	Veta Colonial	-50	1.86	294	0.03	0.39	0.35
DDH-04-053	Sophia I	-99	1.27	607	0.01	0.16	0.02
DDH-04-054	Ramo Adela	-13	0.4	21	0.03	0.04	3.71
DDH-04-054	Unión	-97	1.94	179	0.26	0.14	1.74

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-054	Union	-133	0.70	82	0.07	0.03	0.21
DDH-04-055	Litoral Ramo 2	-163	5.35	306	0.71	0.01	0.41
DDH-04-056	Desconocida	-15	0.42	128	0.02	0.06	0.62
DDH-04-056	Colonial	-95	0.9	78	0.05	0.41	0.42

28

<i>HOLE No.</i>	<i>STRUCTURE</i>	<i>Level</i>	<i>Width</i>	<i>RESULTS</i>				
		<i>intersected</i>	<i>(True)</i>	<i>Ag (g/t)</i>	<i>Cu (%)</i>	<i>Pb (%)</i>	<i>Zn (%)</i>	
DDH-04-057	Desconocida	+17	0.29	1,015	0.01	0.04	0.01	
DDH-04-057	Desconocida A	+11	0.54	392	0.02	0.05	0.01	
DDH-04-057	Colonial	-76	0.63	167	0.14	0.60	0.97	
DDH-04-058	Desconocida A	-14	0.9	438	0.12	0.08	0.16	
DDH-04-058	Colonial	-115	NO SIGNIFICANT INTERCEPTS					
DDH-04-059	Desconocida	-14	0.92	378	0.26	0.15	0.49	
DDH-04-059	Colonial	-90	0.37	200	0.17	0.14	0.36	
DDH-04-060	Sophia I	-89	1.22	71	0.05	0.23	0.35	
DDH-04-061	Litoral Ramo 2	-78	3.79	757	0.31	0.11	3.06	
DDH-04-062	Litoral Ramo 2	-125	3.56	2,262	0.45	0.36	5.75	
DDH-04-063	Litoral Ramo 2	-68	1.50	79	0.23	0.09	0.51	
DDH-04-064	Litoral Ramo 2	-114	1.68	534	0.22	0.20	1.41	
DDH-04-065	Litoral Ramo 2	-160	5.42	1,967	0.56	0.12	0.37	
DDH-04-066	Litoral Ramo 2	-70	1.81	32	0.05	0.07	0.36	
DDH-04-067	Litoral Ramo 2	-113	1.60	321	0.10	0.31	5.45	
DDH-04-068	Litoral Ramo 2	-163	2.71	287	0.38	0.27	0.36	
DDH-04-069	Litoral Ramo 2	-132	1.58	231	0.02	0.36	4.83	
DDH-04-070	Litoral Ramo 2	-127	1.78	275	0.27	0.08	2.51	
DDH-04-071	Litoral Ramo 2	-127	1.50	53	0.01	0.36	0.63	
DDH-04-072	Litoral Ramo 2	-122	1.53	355	0.40	0.30	4.61	
DDH-04-073	Litoral Ramo 2	-156	1.50	44	0.02	0.01	0.03	
DDH-04-074	Litoral Ramo 2	-215	1.50	93	0.02	0.25	0.10	
DDH-04-075	Litoral Ramo 2	-269	1.50	43	0.01	0.08	0.63	
DDH-04-076	Litoral Ramo 2	-160	6.29	564	0.16	0.08	1.56	
DDH-04-077	Litoral Ramo 2	-231	1.50	22	0.01	0.02	0.42	
DDH-04-078	Litoral Ramo 2	-196	1.50	44	0.71	0.01	0.35	
DDH-04-079	Litoral Ramo 2	-42	1.94	302	0.71	0.18	0.74	
DDH-04-080	Litoral Ramo 2	-209	1.50	150	0.09	0.19	1.01	
DDH-04-081	Litoral Ramo 2	-180	1.54	263	0.09	0.36	1.98	
DDH-04-082	Litoral Ramo 2	-230	1.50	48	0.02	0.10	0.36	
DDH-04-083	Litoral Ramo 2	-185	1.84	814	0.71	0.36	0.71	
DDH-04-084	Litoral Ramo 2	-245	1.50	407	0.10	0.36	1.32	

13.2. Underground Diamond Drilling

Underground drilling was carried out in two stages, totalling 2,233 metres. The first campaign was directed to test down dip extensions of 6 de Agosto with 8 drill holes totalling 405.30 metres. NQ diameter core was obtained for further logging and sampling. The second campaign was targeting the down dip and extension of Litoral vein. Typical drill holes are oriented to cut across the vein zones at an orientation perpendicular to the local strike of the zones and inclined to intercept the vein at as high an angle as is practical. In these cases the true width is assumed to be the same as the sample length of the vein intercept. In other cases, drilling to greater depths caused veins to be intercepted at less than 90 degree core axial angles. In these cases true widths of the vein intersection was calculated using trigonometry and stated in Table 8b together with drill hole numbers, level of intersection and geochemical results for the mineralized zones.

Table 8b Summary Data San Vicente Underground Diamond Drill Holes

DRILL HOLE	STRUCTURE	HITS AT		RESULTS			
		LEVEL	Trure Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
DDH-99-70-001	Veta Unión	-105		NO SIGNIFICANT INTERCEPTS			
DDH-99-70-002	Veta Adela	-75		NO SIGNIFICANT INTERCEPTS			
DDH-99-70-003	Veta Adela	-73	2.68	304.0	0.33	0.05	1.89
DDH-99-70-003	Veta Ramo Union	-95	1.02	244.2	0.23	0.03	0.41
DDH-99-70-003	Veta Unión	-90	1.65	2125.4	1.03	0.37	4.99
DDH-99-70-004	Veta Litoral	-80	10.65	355.0	0.16	0.04	2.47
DDH-99-70-004	Veta Adela Ramo-2	-90	3.20	469.0	0.46	0.02	6.91
DDH-99-70-005	Veta 6 de Agosto	-85	0.86	433.3	0.56	0.11	0.37
DDH-99-70-006	Veta 6 de Agosto	-110	4.19	76.4	0.15	0.09	6.85
DDH-99-70-007	Veta Desconocida	-74	0.53	475.0	0.44	0.05	2.48
DDH-99-70-007	Veta Rmo. Adela	-88	0.72	150.5	0.21	0.05	0.94
DDH-99-70-008	Veta Desconocida	-74	0.41	198.0	0.15	0.04	0.58
	Veta Ramo San			NO SIGNIFICANT INTERCEPTS			
DDH-9101	José			NO SIGNIFICANT INTERCEPTS			
DDH-9101	Veta 6 de Agosto	-160		NO SIGNIFICANT INTERCEPTS			
	Veta Ramo San	-173	1.19	626.5	0.16	0.09	0.18
DDH-9102	José			NO SIGNIFICANT INTERCEPTS			
DDH-9101	Veta 6 de Agosto	-260		NO SIGNIFICANT INTERCEPTS			
DDH-03-70-009	6 de Agosto	-142	1.71	34.7	0.08	0.08	0.70
DDH-03-70-010	Deseada	-122	0.68	174.0	0.48	0.18	1.88
DDH-04-70-011	Adela			NO SIGNIFICANT INTERCEPTS			
	Ramo 6 de	-122	0.49	101.0	0.28	0.05	2.00
DDH-04-70-012	Agosto??			NO SIGNIFICANT INTERCEPTS			
DDH-04-70-012	6 de Agosto	-135	1.61	74.5	0.24	0.12	7.58
DDH-04-70-013	Adela Rmo -2	-80	1.02	369.8	0.11	1.63	13.41
DDH-04-70-013	Rmo-Ramo Adela	-84	0.31	60.0	0.07	0.04	7.20
DDH-04-70-013	Ramo Adela	-92	0.63	2231.0	0.64	0.02	7.20
DDH-04-70-013	Unión	-107	1.41	314.6	1.90	0.15	1.44
DDH-04-70-014	Unión	-114	2.04	1090.0	0.49	0.02	2.14
DDH-04-70-014	Ramo Unión	-124	0.35	65.6	0.08	0.04	9.13
DDH-04-70-015	Adela			NO SIGNIFICANT INTERCEPTS			
DDH-04-70-016	Unión			NO SIGNIFICANT INTERCEPTS			
DDH-03-70-017	6 de Agosto	-154	1.37	89.0	0.92	0.18	1.80
DDH-04-30-018	6 de Agosto	-112	0.92	290.0	0.68	0.02	2.41
DDH-04-30-019	6 de Agosto	-150		NO SIGNIFICANT INTERCEPTS			
DDH-04-30-020	Rmo San Lorenzo	-32	1.67	163.3	0.94	0.16	3.44
DDH-04-30-020	Vet. Desconocida	-52	1.65	19.6	0.03	0.34	3.30
DDH-04-30-020	Vet. Desconocida	-57	1.69	100.7	0.25	1.01	8.91
DDH-04-30-021	Vet. Desconocida	-36	0.69	324.0	0.24	0.01	1.30
DDH-04-30-021	Vet. Desconocida	-43	1.85	77.2	0.17	0.02	1.80
DDH-04-30-021	Veta Porvenir	-51	0.44	127.0	0.08	0.01	0.36
DDH-04-30-021	Rmo. Arturo	-53		NO SIGNIFICANT INTERCEPTS			

14.0 SAMPLING METHOD AND APPROACH

In addition to the diamond drilling, a sampling program was started in the mine. An initial 41 channel samples were taken in 4 of the principal structures (6 de Agosto, Adela, Litoral and Unión). The results of the surface drilling showed wider intersections than had previously been mined underground; hence the channel samples were unable to explore the full width of each vein. After this realization, mining work was undertaken to develop small cross section cross cuts (1.5 m by 2.0 m) at a maximum of 75 metres apart along strike in the four veins on levels 0, -30, -70 and -110 in order to explore the full economic width of each vein. Some 5,807 channel samples were taken by COMIBOL and a further 2,449 channel samples taken by PASB. Some of the PAS channel samples replace the COMIBOL channel samples where the vein width is actually greater than was initially thought by COMIBOL.

All underground channel sampling and re-sampling (COMIBOL and PASB) which includes two generation of samples are shown in detail in Appendix C. The first generation includes samples collected from similar locations and the same sample widths as sampled by COMIBOL. The second generation of samples is a selective sampling with variable widths that considers the behaviour (splitting and development of veinlets) of the vein. Data comparison shows variability of results that do not allow a correlation factor to be defined. In many locations it was impossible to precisely reconstruct the COMIBOL sample location and/or the COMIBOL samples never included disseminated mineralization in the hanging or foot walls. Hence COMIBOL samples returned in most cases higher grades over more narrow widths. Both data sets were used in the mineral resource/reserve estimation and treated as two different populations which were superimposed once the grade interpolation was established on each population. Blocks containing only historical sample information have not been included in the mineral reserve estimation and remain in the indicated resource category. A second round of channel re-sampling was completed during 2005 by collecting 2,562 channel samples from different veins and levels. Refer to Appendix C for detailed sample results.

The samples were collected under the supervision of PASB geologists, who ensured the quality of the collected samples, and verified that they were properly labelled; identifying them with an alpha numeric label (i.e. CH-99-30-001, being CH for channel sample, collected in the year 99 in level 30 and finally the sample number). These samples were then transported by PASB personnel to Bondar-Clegg laboratories (now ALS Chemex) in Oruro, Bolivia for sample preparation and analyses.

The typical core sampling procedure was to half-saw the HQ core after descriptive geological and geotechnical logging and core recovery estimation by PASB employees. Half of the core was submitted for analysis to the same laboratories as the underground channel samples, while the remaining half is stored at the San Vicente site. The rock mass at San Vicente is generally good to excellent and diamond drill core recovery on the whole was excellent. There are no core or sample recovery problems which could have materially impacted the accuracy and reliability of the results.

The data used for the estimation of mineral reserves and resources consists almost entirely of drill hole samples and underground chip channel samples from the backs of drifts, the ribs of crosscuts, the backs of stopes and the ribs of raises. The channel samples are taken using hammer and chisel, every 4 metres across the veins in 20 cm wide channels approximately 3 cm deep. Stopes are channel sampled every vertical cut (1.6 metres) on 2-metre centers along strike. Due to the dense and regular nature of the underground channel sample pattern the sample results are representative for this type of polymetallic vein deposit. There is a bias inherent in the COMIBOL methodology to narrower vein widths and higher grades. The methodology used to mitigate this effect is as follows: Ordinary kriging was applied in two phases, first to PAS sampling data only (channels and drill holes) and later to remnant blocks containing data collected by COMIBOL. Variogram models were obtained for each variable and for each vein which has been divided in blocks of 40 x 20 m (strike and dip).

The lithology of the San Vicente Mine area is relatively simple. Included are the fanglomerate facies of the San Vicente formation, which are in contact with Ordovician shales along the San Vicente fault. The fanglomerate consists of poorly sorted conglomerate with clastic sub angular fragments of Palaeozoic sediments cross cut by quartz veins. The matrix is red in colour and consists of iron bearing sandstone. Mineralization is in structurally controlled veins. Sample width is based on visible vein width, which varies

from 0.2 metres to 7.5 metres. Wide vein intersections are sampled in several intervals dependant on the visible mineralization changes. In areas where the wall rock shows disseminated mineralization, additional samples were taken in regular intervals from 0.7 metres to 1.0 metres in length.

A summary of samples with grades and measured true widths is shown in Appendix C.

In conclusion, it is Michael Steinmann's opinion that the sampling method applied at San Vicente by PASB gives representative results and meets industry standards.

15.0 SAMPLE PREPARATION, ANALYSES, AND SECURITY

PASB employees prepared the various drill and channel samples and sent them to commercial laboratories for sample preparation and analysis. None of the sample preparation and analysis done at the commercial laboratories was conducted by an employee, officer, director, or associate of PASB.

Drill hole samples are taken from half cores cut with a diamond saw after the core logging took place. The second half of the core is stored in a secured location on site for cross checks and further analysis. Samples are sent to Oruro (ALS Chemex) or La Paz (SGS) for sample preparation where samples are crushed, split and milled for Atomic Absorption Spectroscopy (AA) analysis. The prepared samples are then shipped by the laboratories to their respective Lima facilities and analyzed for Ag, Zn, Pb and Cu. If Ag grades are higher than 500 g/t, a fire assay is performed; if values for zinc are greater than 10%, a titrimetric analysis is performed. During the entire procedure from sampling to analysis, sample security is controlled by PASB employees or by the certified laboratories once samples have been delivered to the Bolivian preparation facilities. Both of these laboratories fulfill the requirement of ISO 9001:2000 standards. In addition the SGS laboratory in Lima is accredited for ISO 17025. Both laboratories report assay results by e-mail and by certified paper copy to PASB.

The standard sample flow, preparation, analysis, and database entry consists of the following steps:

1. PASB geologists make lithologic logs and mark core for assay sample selection.
2. Core is half-sawed at San Vicente site.
3. Each half-sawed sample is placed into a plastic bag with sample number and stapled shut (remaining half core is stored in warehouse facility at San Vicente site).
4. Bagged samples are transported by PASB personnel by light truck to Oruro or La Paz.
5. ALS or SGS receives core, logs it in, and weighs it as received.
6. ALS or SGS crushes entire sample to 70% -10 mesh (Tyler Series basis).
7. ALS or SGS splits sample with riffle splitter down to 1000 grams, retaining the coarse reject until instructed by PASB as to disposition.
8. ALS or SGS pulverizes the entire split to 85% -200 mesh (Tyler Series basis).
9. ALS or SGS performs Atomic Absorption (AA) on Ag, Zn, Pb and Cu
10. ALS or SGS performs a 50 gram fire assay for Ag grades > 500 g/t.
11. ALS or SGS performs a titrimetric analysis on Zn grades > 10%
12. ALS or SGS reports assay by email and by paper copy to PASB, both as spreadsheet and as certificate

13. PASB personnel assign the assay data to hole and depth interval, keying on sample number.

14. Incremental assay data are combined into a global drill and sampling database.

Historically, no duplicate assays have been systematically performed. QA/QC for drill samples was applied in the second phase drilling starting in the year 2003, including the re-assaying of about 3% of the samples. Comparison of results are shown in Table 8c . (Sample results from check assays from diamond drilling). Check assays were performed on the same samples on pulps by the same primary laboratory and on rejects by a secondary laboratory. In 2007 PASB implemented certified standards as an additional QA/QC control. One standard is submitted in every batch of 20 samples. All of the drilling, sampling and QA/QC programs were conducted under the direct supervision of Pan American s geology staff. In addition, 21 mineral reserve blocks have been resampled for quality control.

In conclusion, it is Dr. Michael Steinmann's opinion that the San Vicente sampling, sample preparation, security, analytical procedures, and quality assurance program meets industry standards.

Table 8c Diamond Drilling Check Assays

SAMPLES			SILVER			ZINC		
<i>SAMPLE NUMBER</i>	<i>SAMPLE NUMBER</i>	<i>SAMPLE NUMBER</i>	<i>1st. Analisis</i>	<i>2nd. Analisis</i>	<i>3rd. Analisis</i>	<i>1st. Analisis</i>	<i>2nd. Analisis</i>	<i>3rd. Analisis</i>
<i>ORIGINAL</i>	<i>SGS-Pulps</i>	<i>CHEMEX-rechazos</i>	<i>Ag g/t</i>	<i>SGS Pulps</i>	<i>CHEMEX Rejects</i>	<i>Zn %</i>	<i>SGS Pulps</i>	<i>CHEMEX Rejects</i>
7020	30001	7020	1788.0	1706.0	2040.0	0.76	0.76	0.80
7041	30005	7041	8.0	5.2	1.4	0.27	0.29	0.03
7060	30002	7060	8.4	42.4	10.6	0.07	0.08	0.08
7083	30006	7083	33.0	7.2	69.7	0.11	0.12	0.13
7104	30003	7104	344.0	38.8	331.0	0.03	0.03	0.03
7120	30007	7120	3893.0	4014.0	4330.0	18.00	20.90	19.25
7140	30004	7140	13.0	7.2	10.3	0.32	0.35	0.40
7160	30008	7160	203.0	224.0	168.0	0.19	0.26	0.23
7181	30009	7181	3.2	3.2	1.8	0.03	0.02	0.02
7200	30010	7200	1453.0	1446.0	1540.0	1.36	1.36	1.38
7221	30015	7221	42.0	55.6	52.5	1.28	1.44	1.34
7222	30014	7222	23.0	27.2	27.7	0.68	0.80	0.88
7227	30013	7227	4.8	4.8	4.3	0.56	0.56	0.64
7230	30012	7230	45.0	56.8	55.1	0.44	0.48	0.55
7240	30011	7240	4.0	1.0	2.0	0.60	0.60	0.63
7260	30016	7260	1467.0	1997.0	1930.0	6.40	6.71	6.33
7280	30018	7280	12.0	12.3	12.6	1.16	1.20	1.17
7304	30017	7304	173.0	164.6	171.0	0.26	0.28	0.27
7320	30020	7320	39.5	42.5	41.9	6.80	7.03	6.71
7339	30019	7339	2231.0	2227.0	2310.0	7.20	7.13	7.48
7361	30021	7361	15.0	13.2	14.3	0.12	0.16	0.14
7383	30022	7383	185.0	155.7	164.0	2.40	2.45	2.40
7415	30024	7415	1433.0	1490.0	1465.0	2.80	3.29	2.92
7420	30025	7420	62.4	12.4	10.3	0.64	0.69	0.68
7440	30023	7440	110.0	96.4	99.0	0.52	0.66	0.60
7460	30026	7460	27.2	26.5	24.7	0.09	0.11	0.11
7477	7477	30027	500.0	579.0	592.0	3.95	4.00	4.31
7497	7497	30028	7.1	7.0	4.2	0.11	0.11	0.06
7515	7515	30029	130.0	131.0	137.0	0.91	0.93	0.93
7538	7538	30030	4.3	3.3	4.5	0.26	0.25	0.27
7569	7569	30031	101.0	98.0	98.0	5.28	5.29	5.28
7590	7590	30032	256.0	255.0	244.0	16.35	16.00	15.60
7608	7608	30033	677.0	682.0	571.0	9.54	9.47	9.35
7630	7630	30034	20.1	21.0	21.0	1.88	2.09	1.90
7666	7666	30035	192.0	208.0	174.0	5.43	5.43	4.85
7683	7683	30036	3740.0	3757.0	2950.0	1.23	1.34	1.11
7701	7701	30037	625.0	664.0	774.0	0.38	0.38	0.44
7724	7724	30038	36.1	37.0	40.6	0.34	0.33	0.36

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

7748	7748	30039	876.0	953.0	983.0	0.19	0.19	0.21
7775	7775	30040	776.0	782.0	165.0	0.15	0.15	0.05
7788	7788	30041	9.1	9.0	9.4	0.13	0.13	0.14
7809	7809	30042	107.0		96.0	0.23		0.22
7830	7830	30043	87.2		85.5	0.07		0.07
7853	7853	30044	678.0		630.0	0.77		0.73
7874	7874	30045	2270.0		2160.0	6.60		6.69
7892	7892	30046	90.2		90.3	4.14		3.81

16.0 DATA VERIFICATION

Sampling results returning from the laboratories are plotted on level plans and visually checked for outliers. Check samples are plotted against each other for every element analysed. Most of the data verification is done using Data Mine[®], commercial mine modeling software. Samples are plotted on plans and sections to verify the correct location in the drifts or stopes. Further details about data verification and applied geostatistics are given in Section 19.

PASB performs routine assay data verification by primary and secondary laboratory check sample analyses. In addition, ALS Chemex and SGS perform numerous internal standard determinations and checks.

Historically, no duplicate assays have been systematically performed because this was not a standard procedure for COMIBOL at their operations.

Data analysis and verification evaluations have been performed for the San Vicente mine by Mr. Elmer Ildefonso, Geostatistical consultant to PASB. Mr. Ildefonso is an accomplished expert in mineral resource and reserve model development; however, he is not a Qualified Person. As such, PASB's Dr. Michael Steinmann has reviewed and verified the work of Mr. Elmer Ildefonso.

17.0 ADJACENT PROPERTIES

There is no information on adjacent properties in this Technical Report.

18.0 MINERAL PROCESSING AND METALLURGICAL TESTING

PASB employed the engineering firm Lyntek Inc, based in Denver, Colorado, to design the process plant flow sheet and to estimate the plant capital costs. PASB provided Lyntek with engineering reports and operating data from the Chilcobija Concentrator when processing San Vicente ore. Detailed below is a summary of the most significant information contained in these sources that Lyntek used in developing the flow sheet for the new concentrator at San Vicente.

1. Grinding to 65% -200 mesh (80% -150 mesh) provides sufficient liberation for selective flotation of the San Vicente ore.
2. Bond Work Index = 11.64 KwH/T
3. Regrinding of the ore is not necessary.
4. Two stages of cleaning are required for the copper/silver concentrate;
5. Total flotation times of more than 10 minutes are required in the copper/silver flotation stages;
6. It is possible to produce zinc concentrate with grades higher than 48% zinc with recoveries approaching 90% depending upon the depression of zinc in the copper/silver flotation stages;
7. Grinding to 65% -200 mesh (80% -150 mesh) is required for optimum selective separation of the silver, zinc, and copper.
8. Tests indicate that the Cu/Ag concentrate will recover 80% of the Ag, 73% of the CU, and 17% of the Zn and the Zn/Ag concentrate will recover 12% of the Ag, 16% of the Cu, and 78% of the Zn (pilot test number PS-105).

Mr. Douglas Maxwell, P.E, one of the authors of this Technical Report, has reviewed the foregoing information and approves it. He has determined that in his professional judgement the conclusions reached are sound and approves of and confirms the use of this information.

Metallurgical Testwork includes the following:

1. Determination of Bond Work Index Universidad Nacional de Ingenieria, September 2005.
 - o This comminution testing was performed at the Mineral Processing Laboratory of the National University of Engineering College of Mining, Metallurgical and Geological Engineering located in Lima Peru. The conclusion was that the Bond Work Index = 11.64 Kwh/T. The procedure used was to determine the amount of fines minus 150 mesh generated in each turn of a grinding mill over a number of 100 revolution cycles, with the fines being replaced with fresh sample after each cycle until equilibrium was reached.
2. Metallurgical Study of the Metallic Minerals at the San Vicente mine conducted at Tecsup Laboratories Alfredo Vargas, October, 2004.
3. This study was conducted in Lima, Peru. The objective was to produce silver and zinc concentrates with the highest grades and recoveries that could be reproduced in new plant. Five samples that were provided by San Vicente from different levels of the Litoral and 6 de Agosto veins were crushed separately to 10 mesh, mixed and separated into 1 kilogram samples and stored in a freezer until used. The samples were milled in a laboratory 21 centimetre by 24-centimetre ball mill with a 12 kilogram soft steel ball charge to reproduce industrial conditions. Natural flotation and selective flotation tests were performed.

Metallurgical Study of the Metallic Minerals of the San Vicente mine conducted at Quiruvilca mine, Peru G. Portales, September 2005.

4. Additional floatation testwork was performed by A. Vargas, P.E.. The purpose of the testwork was to verify the results of Test 105 in the metallurgical study conducted by A. Vargas. The conclusion of the work was that the test results were confirmed. In order to obtain a representative sample, the 4,500 tonne stockpile at the San Vicente mine was sampled and the size reduced to 1/2 inch. The total weight of the sample was 180 kilograms. The sample had an average head grade of 384 g/t silver, 0.34% copper, 0.12% lead, 5.92% zinc. The flotation testwork was conducted at the Quiruvilca mine who have a long history of production using the flotation process.
5. Metallurgical Testwork on San Vicente Ore. Carried out in the Metallurgical Laboratory of the National University of Peru, Faculty of Mining, Geological and Metallurgical Engineering. By Julio Uza Teruya, September 2005.
6. Determination of Work Index, Carried out in the Metallurgical Laboratory of the National University of Peru, Faculty of Mining, Geological and Metallurgical Engineering, by Julio Uza Teruya. September 2005.
7. Information gathered from 3 phases of toll milling San Vicente ore at Chilcobija mill from 2001 to present, consisting of a 200,00 tonne, 55,000 tonne and a 35,000 tonne program.

Mr. Douglas Maxwell, P.E, an author of this Technical Report, has reviewed the foregoing information and approves it. He has determined that in his professional judgement the conclusions reached are sound and approves of and confirms this information.

A zinc-silver flotation concentrate and a copper-silver flotation concentrate are currently being produced at Chilcobija and in the future will be produced at the new plant.

The zinc-silver concentrate that will be produced in the new mill to be constructed as part of the San Vicente Mine Expansion Project is forecast to average a concentrate grade of 56% zinc and contain 12% of the recovered silver. The amount of zinc concentrate produced each year will vary depending on the zinc head grade with an average at full production of 13,700 tonnes per annum. Zinc concentrates are currently sold under a long-term contract to Trafigura which has been used to establish the economic terms for the zinc concentrate that have been used in the economic

model. Deleterious elements are forecast to be below the thresholds that require the payment of penalties. The copper-silver concentrate that will be produced in the new mill to be constructed as part of the San Vicente Mine Expansion Project is forecast to contain a concentrate grade of 16% copper and to average

2% silver. At full production, some 3,500 tonnes of concentrate will be produced per annum. Deleterious elements in the copper-silver concentrate include antimony and bismuth and the penalties for these elements are estimated to total \$160 per tonne. In order to construct an economic model of the process it has been necessary to make an assumption for the copper head grade. Copper assays have not been routinely taken at San Vicente and therefore no estimate of copper grades in the mineral resource is possible. In October 2006 when it was recognized that the optimum process flowsheet would include producing a copper-silver concentrate, PAS initiated taking copper feed grade assays to the Chilcobija plant. In the seven months since then the copper grade has averaged 0.37% with a low of 0.35% and a high of 0.41%. By back calculating a copper head grade from previous smelter concentrate assays, the copper head grade has averaged 0.4%. For the purpose of modelling of the process, a copper grade of 0.3% has been assumed, however for the purposes of sizing the flotation cells, Lyntek has used a copper grade of 0.4%. As the economic analysis considers only proven and probable mineral reserves, the life of mine revenue from copper has been eliminated from the economic analysis. It is recommended however, that copper be routinely assayed for and eventually included in the resource calculation when sufficient data permits. This process should start in earnest on the construction of the assay laboratory at the new plant site.

Lyntek reviewed flow sheet and mass balance information provided by PAS and provided recommendations for the design of a new process plant. The flowsheet design for the new San Vicente Plant utilizes conventional unit operations, including primary crushing, SAG and ball milling, copper and zinc flotation circuits, thickening, filtration, and tailings disposal. Figure 1-9 provides a drawing of the plant flow diagram.

The design basis for the ore processing facility is an average of 750 dry tonnes per day (DTPD), 35 tonnes per hour, and 270,000 dry tonnes per year (DTPY at 100% utilization) on an operating basis of 360 days per year. Figure 1-10 is a general arrangement drawing showing the process facilities.

Using the results obtained from processing San Vicente ore at Chilcobija and test results from crushing, grinding and flotation tests, Lyntek has designed a plant which they report will achieve the metal recoveries shown in Table 9.

Table 9 Lyntek Recommended Metal Recoveries

Stream	Grade Range	Total % Recovery (2 and 4)					
		Ag (2)	Ag (4)	Zn (2)	Zn (4)	Cu (2)	Cu (4)
Zinc	2.8 - 5.92%			80%	90%		
Silver	444 - 458.9 g/t	85%	88%				
Copper	0.2 to 0.4%					53%	75%

Item	Recovery by Concentrate (3)		
	Ag	Zn	Cu
Cu/Ag Concentrate	80%	17%	73%
Zn/Ag Concentrate	12%	78%	16%
Tailings	8%	5%	11%

Notes:

- 1) The ore grades vary by sample.

The Average
Grade for each
metal is
calculated to be:

Ag = 444 g/t /
Zn = 3.8 % /
Copper 0.38 %.

- 2) % Recovery
from PASB
Feasibility
Study 2005
- 3) % Recovery
from A. Vargas
Test Report
2004 Test 105
- 4) Lyntek/Vargas
projected
Recovery
values.
Chilcobija is
currently
recovering
86.34% Ag.

The recoveries projected by Lyntek are a considerable improvement over that currently being achieved in the Chilcobija plant; however the data is supported by testwork and as previously stated the Chilcobija plant is in poor condition. The testwork was however geared towards the proven and probable mineral reserve average grade at the end of 2005 (2.38 million tonnes at 436 g/t Ag and 3.82% Zn). At the end of

2006, the tonnes had increased and the grades decreased to 3.06 million tonnes at 348 g/t Ag and 3.44% Zn. This change was primarily due to the impact of higher metal price assumptions. In order to recognize this change, the recoveries used for the economic assessment used in the report were reduced to the values shown in Table 10.

Table 10 Anticipated Plant Metal Recoveries

	Ultimate Design Recoveries	Recoveries Used for Economics in this report
Silver	88%	85%
Zinc	90%	85%
Copper	75%	70%

19.0 MINERAL RESOURCE AND MINERAL RESERVE ESTIMATES

The mineral resources at the San Vicente mine were estimated by a consultant to PAS, Elmer Ildefonso, under the supervision of Dr. Michael Steinmann, P. Geo. Senior Vice-President of Exploration and Geology for PAS. Following the application of mining parameters, preparation of a mine plan, and an economic analysis, the measured and indicated portions of the mineral resources were converted to proven and probable mineral reserves under the supervision of Mr. Martin Wafforn, P. Eng. PAS's Vice-President of Mine Engineering. All mineral resources and mineral reserves quoted are estimated in accordance with accepted industry practices, are in accordance with the Canadian Institute of Mining, Metallurgy and Petroleum definitions on Mineral Resources and Mineral Reserves, and are in compliance with NI 43-101.

Block models were constructed in Datamine for the major veins 6 de Agosto, Litoral, Litoral Ramo 2, Unión, Adela, San Lorenzo, Guernica II, Cantera, Artola, San Jose and Deseada veins. These veins were previously identified as having the potential of having wider mineralization and being economically more significant. They were subsequently the focus of the exploration campaigns conducted by PASB and therefore have a more complete data set.

The Project's database has been used for metals exploration, resource modeling, geotechnical studies, metallurgical studies, and hydrological exploration/studies. The resource models were derived from the following data sets:

Diamond core drill hole location, orientation, and assays for both surface and underground drilling

Diamond core density determinations

Underground channel samples by PAS

Underground channel samples by COMIBOL

The underground channel samples were entered into the database as pseudo diamond drill holes with collar co-ordinates, length, azimuth and grade. In many cases, the COMIBOL channel samples did not fully sample the entire width of the structure, focusing instead on the high-grade core of the vein. This contrasted with the samples taken by PAS, where the entire width of the vein out to its economic limits was sampled. In the major veins, the PAS sampling replaced the COMIBOL sampling, however in the minor veins it was decided to use the old COMIBOL data uncorrected. The potential impact of the COMIBOL data to the overall resource calculation (overestimating grades but underestimating tonnes and contained metal in the minor veins) is reduced each year as new channel sample data is added.

A statistical and geostatistical analysis of each vein was conducted. From this analysis, a top cut for each vein was estimated and applied as well as the search radius for resource categorization. A geometric model for each vein was constructed in Datamine that considered the intersections of drill holes and

channel samples with the vein, the underground and surface surveys, and the geologic interpretation. The method of grade interpolation used was ordinary kriging.

The variography of the samples of each major vein has been reviewed and shows the continuity of the silver and zinc grade distribution to be greater than the current block size of 40 m along strike and 20 m along dip. The following classification scheme has been applied to the resources:

Measured resources 20 m up and down dip with samples on at least one level.

Indicated resources 10 m up and down dip as a continuation of the measured resource blocks. In the case of individual drill hole intercepts with no support from channel samples the indicated resource is for 20 m diameter. This is valid for all veins except Litoral R2 where variography allows 70 m along strike and 30 m up and down dip.

Inferred resources 10 m up and down dip as a continuation of the indicated resource blocks, or an additional 10 m diameter donut outside the indicated resource.

The average specific gravity for the entire deposit had been assumed to be 2.90 in previous resource calculations. Owing to the significantly different base metal grades of some of the veins, it was recognized by PASB that this SG data quality needed to be improved. In order to acquire the data necessary to make this improvement, a sampling and specific gravity measurement program was conducted in 2005. More than 3,800 samples were collected from the different structures in the mine and tested to determine their specific gravity. The results were grouped by vein in order to determine the average specific gravity for each vein that is shown in Table 11.

Table 11 Specific Gravity by Vein

Vein	New S.G.
6 de Agosto	2.81
Union	2.91
San Lorenzo	2.83
Guernica II	2.85
Cantera	2.82
Artola	2.72
Adela	2.71
San Jose	2.64
Litoral	2.81
Litoral Ramal 2	2.81
Deseada	2.72

For the end of 2006 resource calculation, dilution was added utilizing an empirical formula similar to that proposed by T. Alan O Hara. The formula takes into account the vein width and dip angle when calculating the dilution percentage. The calculated amount of dilution decreases as a percentage as the dip and or the vein width increase. This is consistent with PAS experience in Peru in similar mining and ground conditions. Consideration was given to modifying the dilution formula to increase the amount of dilution for the Litoral Ramal 2 vein where longhole mining will be used. The co-authors reviewed the formulae proposed and concluded that for a mine with such good ground conditions the proposed formula for longhole mining resulted in an excessive amount of dilution and decided to use one formula for the entire deposit. The co-authors recommend that as mining progresses at San Vicente actual dilution measurements be taken that will allow the formula to be modified or replaced based on actual experience. The formula used for calculating dilution is as shown in Table 12.

Table 12 Dilution Calculation

The minimum mining width at the San Vicente mine is 0.8 m, based on observations and measurements of stopes at the mine the stope miners there have demonstrated their ability to mine down to these narrow widths. After the application of O Hara dilution, however as all of the blocks were greater than 0.8 metres wide there was no need to apply a minimum mining width restriction to the resource calculation.

As permanent ore pillars must be left for stability and safety as well as other mining losses, a mining recovery factor of 90% has been applied to each blocks tonnage while leaving the grades unchanged. The majority of these losses occur in sill, manway (rib), and crown pillars.

Following the calculation of the diluted tonnes and grade in each block, economic parameters were applied to the measured and indicated mineral resources to calculate the proven and probable mineral reserves. The measured and indicated mineral resources remaining are that portion of the overall resource that have the necessary data density and geologic confidence to be assigned to those mineral resource categories but require improvements in the economic conditions or assumptions in order to convert to mineral reserves.

The first economic parameter applied was a Net Smelter Return (NSR) value per tonne. This was calculated for each block by applying metal prices and using the existing and projected smelter terms to derive NSR or Value per Tonne (VPT) factors. The concentrates are sold under a contract with Consorcio Minero S.A. (CORMIN), a division of Trafigura, under a contract that runs until 2010. The factors and metal prices calculated are shown in Table 13.

Table 13 Resource Metal Prices and Factors

Metal	Price	Factor
Silver	\$9.00 / ounce	6.6730
Zinc	\$2,100 / tonne	8.9667

The second economic parameter was applied in the overall mine plan by considering the economic merits of each zone to ensure that small isolated blocks that do not justify development are not included in the proven and probable mineral reserves.

The third economic parameter applied was the calculation of a cut off VPT. In consideration of the estimated operating costs and metallurgical recoveries, a cut off VPT of \$34 was calculated for shrinkage

stopping and a VPT of \$30 was calculated for longhole stopping. All measured mineral resource blocks with the application of the mining parameters that have a VPT higher than shown above for the respective mining methods were converted to proven mineral reserves. Similarly, all indicated mineral resource blocks that met the requirements above were converted to probable mineral reserves. As all mineral resources must have a potential to be economic, all remaining measured and indicated mineral resource blocks as well as any inferred mineral resource blocks (no inferred mineral resource blocks were converted to proven or probable mineral reserves) with a VPT of less than \$17 per tonne were eliminated from the mineral resource summary.

As a final step, and in order to be conservative, the proven and probable mineral reserves were reduced by a further 5% to account for the potential losses that may occur where ore is left behind in stopes. This could be for a variety of reasons such as local poor ground conditions that cause a stope or a part of a stope to be abandoned and/or the inability to recover all of the ore on the walls or between drawpoints. The co-authors recommend that reconciliations be conducted when the mine is in full production in order to calculate the actual mining losses.

In late 2005, a national election in Bolivia resulted in the emergence of a left-wing government. This has caused some concerns amongst foreign companies doing business in Bolivia due to the government's policy objective of nationalizing the oil and gas industries. There is no certainty the government will not take steps to implement such measures targeting the mining industry. Risks of doing business in Bolivia include being subject to higher taxes, and mining royalties, some of which have already been proposed or threatened, revision of contracts and threatened expropriation of assets, all of which could have a material adverse impact on the Company's operations or profitability. The co-authors conclude that PAS has taken reasonable steps to include the likely taxes that the property will be subject to in the economic model. There are no other known issues relating to environmental, permitting, legal, title, taxation, socio-economic, marketing, political, metallurgical, infrastructure, or other relevant factors that would materially affect the reported mineral resource and mineral reserve estimates reported in this Technical Report.

19.1. Mineral Reserves

The proven and probable mineral reserves at the San Vicente mine as of December 31, 2006 are estimated to be as follows:

Table 14 San Vicente Mineral Reserves

Structure	Proven			Probable			TOTAL		
	DMT	Ag (g/t)	Zn (%)	DMT	Ag (g/t)	Zn (%)	DMT	Ag (g/t)	Zn (%)
Stockpiles	44,323	325	3.58				44,323	325	3.58
6 de Agosto	587,248	172	3.46	72,067	114	2.34	659,315	165	3.33
Adela	209,449	298	4.01	21,703	277	4.94	231,153	297	4.10
Artola	17,925	203	1.20				17,925	203	1.20
Cantera	150,182	179	3.42	35,517	201	4.04	185,699	184	3.54
Deseada	279,080	237	6.48	52,394	268	7.04	331,474	242	6.57
Guernica II	136,379	665	0.93	40,321	539	1.13	176,700	636	0.97
Litoral R2	146,752	521	3.57	655,143	504	2.08	801,895	507	2.36
Litoral	116,239	410	5.42	96,846	376	2.42	213,085	394	4.05
San Jose	83,164	448	2.39				83,164	448	2.39
San Lorenzo	43,371	395	2.79	2,386	445	2.47	45,756	398	2.77
Union	174,426	352	3.94	93,271	374	4.40	267,697	359	4.10
TOTAL	1,988,538	304	3.85	1,069,647	430	2.66	3,058,185	348	3.44

Notes:

1. Total grades of silver and zinc are shown before mill recoveries of 85.0% percent for both metals are applied.
2. PAS's share is 94.999% of the total mineral reserves.
3. San Vicente's mineral reserves have been estimated at a minimum mineralized width of 0.8 metres and at a cut off value per tonne of \$34 for shrinkage stoping and \$30 for longhole stoping.
4. The geological model employed for San Vicente involves geological interpretations on sections and plans derived from core drill hole information and channel sampling.
5. Mineral reserves have been estimated using the O'Hara dilution

formula, which typically adds 20% to 50% dilution at zero grade depending on dip angle and vein width.

6. Mineral reserves have been estimated using a mining recovery of 90% with a further 5% subtracted for other mining losses.

7. Mineral reserves were estimated based on the use of longhole stoping in the Litoral Ramal 2 vein and shrinkage stoping in all other veins. The mining and processing rate is assumed to be 750 tonnes per day on completion of the new plant.
8. Mineral reserves for the principal structures are estimated with a 3 dimensional block model using datamine software. Mineral reserves for minor structures are estimated using polygonal methods on longitudinal sections.
9. Mineral reserves were estimated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc.
10. Environmental, permitting, legal, title, taxation, socio

economic,
political,
marketing or
other issues are
not expected to
materially effect
the above
estimate of
mineral
reserves.

19.2. Mineral Resources

The measured and indicated mineral resource estimates for the San Vicente mine as of December 31, 2006 are in addition to the mineral reserves and are estimated to be as follows:

Table 15 San Vicente Measured and Indicated Mineral Resources

Structure	Measured			Indicated			TOTAL		
	DMT	Ag (g/t)	Zn (%)	DMT	Ag (g/t)	Zn (%)	DMT	Ag (g/t)	Zn (%)
6 de Agosto	94,616	71	1.28	24,332	58	0.90	118,947	68	1.20
Adela	64851	81	0.81	4,950	86	0.58	69,801	81	0.79
Artola	0	0	0.00				0	0	0.00
Cantera	28,015	63	1.51	10,088	83	5.28	38,103	68	2.51
Deseada	14,462	58	2.15	4,252	86	0.98	18,715	64	1.89
Guernica II				8,875	91.49	0.17	8,875	91	0.17
Litoral R2				14,229	81	0.59	14,229	81	0.59
San Jose	18,553	99	0.54				18,553	99	0.54
San Lorenzo	1,271	55	1.53	9,747	129	0.13	11,017	121	0.29
Union	3,186	72	0.38	2,433	22	2.69	5,619	50	1.38
Jesus Maria*				6,490	402	0.14	6,490	402	0.14
Pepitas*				24,720	218	8.71	24,720	218	8.71
Inca*				78,839	455	0.00	78,839	455	
Tajos*				62,167	369	0.00	62,167	369	
6 de Agosto split 3*				39,994	458	6.39	39,994	458	6.39
6 de Agosto split 4*				32,400	377	4.70	32,400	377	4.70
Guernica I *				11,648	340	2.27	11,648	340	2.27
Arturo*				105,662	207	8.19	105,662	207	8.19
Artola Ramo A*				4,419	358	3.95	4,419	358	3.95
TOTAL	224,953	74	1.15	445,244	294	3.67	670,198	220	2.82

Notes:

1. PAS reports mineral resources and mineral reserves separately. Reported mineral resources do not include amounts identified as mineral reserves.
2. PAS's share is 94.999% of the total mineral resources.
3. The geological model employed for San Vicente involves geological interpretations on sections and plans derived from core drill hole information and channel sampling.

4. Mineral resources have been estimated using the O Hara dilution formula, which typically adds 20% to 50% dilution at zero grade depending on dip angle and vein width.
5. Mineral resources have been estimated using a mining recovery of 90%.
6. Mineral resources were estimated based on the use of longhole stoping in the Litoral Ramal 2 vein and shrinkage stoping in all other veins. The mining and processing rate is assumed to be 750 tonnes per day on completion of the new plant.
7. Mineral resources for the principal structures are estimated with a 3 dimensional block model using datamine software. Mineral resources for minor structures are estimated using polygonal methods on longitudinal sections.
8. Mineral resources were estimated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc.
9. Environmental, permitting, legal, title, taxation, socio economic, political, marketing or other issues are not expected to materially effect the above estimate of mineral resources.
10. Mineral resources that are not mineral reserves do not have demonstrated economic viability.
11. A cut off value per tonne of \$17.00 was used for inclusion in the mineral resources.

Table 16 San Vicente Inferred Mineral Resources

Structure	DMT	Inferred Ag (g/t)	Zn (%)
6 de Agosto	66,956	98	2.16
Adela	2108	99	0.62
Artola	0	0	0.00
Cantera	0	0	0.00
Deseada	49,655	255	7.28
Guernica 2	45,982	418	0.82
Litoral R2	212,729	214	1.55
Litoral	74,899	363	2.15
San Jose	0	0	0.00
San Lorenzo	14038	131	0.56
Union	64856	247	3.05
TOTAL	531,223	243	2.34

Notes:

1. PAS reports mineral resources and mineral reserves separately. Reported mineral resources do not include amounts identified as mineral reserves.
2. PAS's share is 94.999% of the total mineral resources.
3. Inferred mineral resources have a great amount of uncertainty as to their existence and as to whether, they can be mined legally or

economically. It cannot be assumed that all or any part of the inferred mineral resources will ever be upgraded to a higher category.

4. The geological model employed for San Vicente involves geological interpretations on sections and plans derived from core drill hole information and channel sampling.
5. Mineral resources have been estimated using the O Hara dilution formula, which typically adds 20% to 50% dilution at zero grade depending on dip angle and vein width.
6. Mineral resources have been estimated using a mining recovery of 90%.
7. Mineral resources were estimated based on the use of longhole stoping in the Litoral Ramal 2 vein

and shrinkage stoping in all other veins. The mining and processing rate is assumed to be 750 tonnes per day on completion of the new plant.

8. Mineral resources for the principal structures are estimated with a 3 dimensional block model using datamine software. Mineral resources for minor structures are estimated using polygonal methods on longitudinal sections.
9. Mineral resources were estimated using a price of \$9.00 per ounce of silver and \$2,100 per tonne of zinc.
10. Environmental, permitting, legal, title, taxation, socio economic, political, marketing or other issues are not expected to materially effect the above estimate of mineral

resources.

11. Mineral resources that are not mineral reserves do not have demonstrated economic viability.

Ordinary kriging was applied in two phases, first to Pan American silver sampling data only (channels and drill holes) and later to remnant blocks containing data collected by COMIBOL. Variogram models have been obtained for each variable and for each vein which have been divided in blocks of 40 x 20 m (strike and dip). The blocks have been classified as measured, indicated or inferred based on the relative confidence of the supporting data for each evaluated block.

Mineral resources that are not mineral reserves do not have demonstrated economic viability and therefore were not included in the economic analysis contained in this Technical Report.

20.0 OTHER RELEVANT DATA AND INFORMATION

No other data or information is relevant for the review of the San Vicente Mine Expansion Project.

21.0 INTERPRETATION AND CONCLUSIONS

In the opinion of the co-authors, the diamond drilling and channel sampling information that has been collected is of sufficient quality, density and reliability for mineral resource and mineral reserve estimation.

The quality assurance/quality control programs are conducted under the direct supervision of Pan American's geology staff and periodically reviewed and revised by Michael Steinmann, P.Ge.

This Technical Report details the methodology employed and demonstrates why the co-authors conclude that the expansion of the San Vicente mine is technically feasible and economically viable at the assumed metal prices (i.e. based on \$9.00 per ounce silver and \$2,100 per tonne zinc). It is the opinion of Martin Wafforn P. Eng., Michael Steinmann P.Ge. and Douglas Maxwell, P.E, co-authors of this Technical Report, that the data contained herein is of sufficient quality and reliability to make the conclusions stated.

The economics take into account an increase in the mining taxation rate that has been discussed by the Bolivian government but not yet implemented. The project will provide jobs and economic stimulus to an area that is economically depressed, and can be constructed in and operated in an environmentally sound manner. The project enjoys strong support from the union that represents the current employees at the mine and current indications are that the Bolivian national mining company COMIBOL and joint venture partner in the project will provide support as well. There have been some threats of nationalization of mining projects in Bolivia, however this has not occurred to date and the risk is balanced by the high projected IRR of the project and the relatively small cash outlay that is required when considering the cash benefits that will be received from on-going operations during the construction period.

The results of the metallurgical testwork as well as the previous processing of San Vicente ore at the Vetillas plant and the current processing of San Vicente ore at the Chilcobija plant give the authors a high degree of confidence that the projected metallurgical recoveries of 85% for silver and 85% for zinc will be realized.

The economic analysis calculates an Internal Rate of Return of 22% and capital payback in 2.9 years. The Net Present Value is \$23.6 million at a 10% discount rate and is \$14.4 million at a 15% discount rate. The undiscounted after tax cash flow is \$53.8 million. PAS's 95% share of the undiscounted after tax cash flow is estimated to be \$50.9 million. The Capital Cost is estimated to total \$40.5 million in 2007 and 2008. The San Vicente Mine Expansion Project is not sensitive to capital fluctuations of up to 25%.

The life of mine plan presented in this study is based solely on proven and probable mineral reserves. The life of mine plan extends until 2019. Any conversion of the mineral resources to proven and probable mineral reserves and any new exploration discoveries will add to the mine life.

The environmental license for the San Vicente mine is now in the process of being updated to reflect the proposed expansion of the mine, construction of a new processing plant, new tailings facility and associated infrastructure. PAS is committed to developing the San Vicente Mine Expansion Project by minimizing and mitigating environmental impacts in accordance with Bolivian regulations, industry best management practices and its own Environmental Policy.

22.0 RECOMMENDATIONS

The co-authors recommend that the San Vicente Mine Expansion Project should proceed according to the designs and schedules contained in this Technical Report. PAS currently has sufficient cash to develop this project and does not need to arrange for project financing. The next key step will be the award of an EPCM contract for the construction of the new process plant and upgraded infrastructure. The co-authors recommend that the reserve and resource statements presented herein be adopted.

Further the co-authors recommend that the following procedures be followed to enhance further mineral resource calculations:

- Continue the program of replacing channel samples in the database that do not sample the full economic width of the deposit. The purchase of a small compressed air powered diamond drill would assist with this.

- Analyse all future channel and diamond drill hole samples for copper grades.

- When the San Vicente Mine Expansion Project is complete, conduct regular reconciliations of the mineral reserves to the mill actual results. This combined with actual dilution and ore loss observations underground

will allow the resource and reserve assumptions to be optimized.

It is recommended that additional water supply wells be drilled to ensure a more plentiful supply of water. The agreement with COMIBOL stipulates that this construction must be completed within 18 months of approval by COMIBOL of an engineering report that was presented to them (the permission was received in July 2007).

23.0 REFERENCES

Report

Assessment of Borrow Sources for concrete Aggregates Worley, Parson , Komex April 4, 2007
San Vicente Mine Site D Tailings Facility Preliminary Design Worley, Parsons, Komex April 12, 2007
Interim Report Geotechnical Engineering Assessment of the Proposed Process Plant Worley, Parsons, Komex January 22, 2007
Evaluation of Water Sources for the San Vicente Mine Worley, Parsons, Komex October 31, 2006
PASB Internal Report Updating COMIBOL on Project power supply E. Robles January, 2007
Shaft and Hoist Review and Recommendations Dynatec Mining Corporation October 19, 2005
Metallurgical Study of the Metallic Minerals at the San Vicente Mine conducted at TECSUP lab, Lima, Peru- A. Vargas October, 2004
Metallurgical Study of the Metallic Minerals at the San Vicente Mine conducted at Quiruvilca Mine, Peru- G. Portales September, 2005
Determination of Bond Work Index Universidad Nacional de Ingeniería, September, 2005
Numerous correspondences and reports Estudios Mineros latest in May, 2007
Preliminary Design and Evaluation of Alternate Tailings Disposal Sites Komex October 28, 2005
Electrical Project of San Vicente (Upgrading transmission lines and sub-stations) Alicon SRL August 29, 2005
Upgrading existing electrical facilities Empresa de Servicios Eléctricos
Feasibility Study Report San Vicente, Bolivia Lyntek Inc. October, 2006
Basic Engineering Interim Report San Vicente, Bolivia Lyntek Inc. December, 2006

24.0 DATE

The information in this report is current as of June 6, 2007.

25.0 ADDITIONAL REQUIREMENTS FOR TECHNICAL REPORTS ON DEVELOPMENT PROPERTIES AND PRODUCTION PROPERTIES

25.1. Underground Mine Operations

Estudios Mineros, a third party Peruvian engineering company, completed the San Vicente mine plan. Martin Wafforn, who is a co-author of this Technical Report, has reviewed and determined, in his professional judgement that the mine plan and other work performed by Estudios Mineros discussed in this section 25 is sound and that this mine plan be adopted. The plan is based on providing 750 TPD of ore to the new mill that will start up in mid 2008 and ramp up production throughout the remainder of 2008 and early 2009. Included in the plan is the provision of 105,850 tonnes in 2007 and a further 100,000 tonnes of ore to the Chilcobija mill in 2008. The planned processing of 100,000 tonnes of ore at Chilcobija in 2008 remains subject to obtaining approval under the joint venture agreement with COMIBOL. At the end of 2006 there was an ore stockpile containing 44,000 tonnes at the San Vicente mine site that is available for processing over the start up and commissioning period.

All of the proven and probable mineral reserves totalling 3.06 million tonnes grading 348 g/t silver and 3.44% zinc are planned to be mined over a mine life that extends until 2019. The mine plan does not include any of the measured, indicated or inferred mineral resources or any possible mineral reserve additions that may occur in the future through exploration.

The plan comprises a continuation of the current shrinkage mining method for the narrow vein deposits that have been mined at San Vicente for many years. Figure 1-5 shows a longitudinal section of a typical shrinkage stope at the San Vicente mine. The wider Litoral Ramal Dos deposit that was discovered over the course of the past 4 years will be mined using a longhole mining method and mechanized equipment. Over the course of the life of mine, longhole mining is expected to account for some 26% of the production tonnage. Figure 1-6 shows a longitudinal section of the modified Avoca longhole mining method that will be used.

The existing mine was designed and built to extract steeply dipping narrow veins using conventional shrinkage stoping. Track levels are established at 30 to 40 metre intervals and include the +70, +35, 0, -30, -70, and -110 levels. For reference the 0 level is at an elevation of 4,440 m above sea level. The main accesses to the mine are via the San Jose adit at the 0 level and the San Juan Adit on the -30 level.

A vertical shaft (Pelayo shaft) extends from surface through the 0, -30, -70 and -110 levels. This shaft has 2 in-balance 1.5 tonne skips and hoists ore from the lower levels to the 0 level where the ore is trammed in rail cars to an ore dump on surface. Dynatec and Spencer Engineering have been retained to replace the existing Allis-Chalmers main production hoist with a refurbished CIR hoist. This work will include replacement of the small headframe as well as strengthening the shaft installations. Although safety was the main reason for replacing the existing hoist, the new hoist will have additional capacity and have the capability to be used in the event of a future shaft deepening program. A separate inclined shaft starts from underground at the -30 level and extends down to the -110 level. Ore hoisted up this shaft is trammed to an ore dump on surface in rail cars via the -35 level. Existing track drift dimensions are 2.4 metres by 2.3 metres restricting the size of mine cars and locomotives to 40 cubic feet and 6 tonnes respectively. The vertical and inclined shafts will hoist all of the production from the shrinkage stopes in the plan to surface. In order to transport the longhole stoping ore to surface, it is planned to develop a ramp from surface to access the Litoral vein with the company owned conventional trackless mining equipment. The ramp will be driven at a grade of minus 12%, at a section profile of 4.5m (wide) by 4.0m (high). Total planned ramp length to the -220 level is 2.5 kilometres. The ramp will connect with the existing tracked development at the -70 and -110 levels in order to be used as part of the ventilation circuit and to provide a large amount of flexibility as an alternate route for escape and for hauling ore and waste to surface. The box cut for the ramp has now been completed and a mine contractor will start development in July 2007.

The shrinkage method that is used at San Vicente does not require backfill of the mined stopes. Broken ore is retained in the stopes to provide a platform for the miners to work off of, with the swell of the broken ore removed after each blast in a set pattern so as to avoid the development of dangerous voids within the broken rock pile. A projection of the shrinkage stoping method is shown in Figure 1-5. The ground conditions in the vein ore bodies are considered good, in fact, the co-authors have observed stopes at the San Vicente mine that have stood open for many years and remain in good condition. The San Vicente miners are experienced in shrinkage stoping and are expected to continue to do an excellent job in recovering the ore body with minimal dilution.

Shrinkage stopes are designed to be 40 m along strike with a vertical interval of either 30 m or 40 m depending on the location in the mine. Level development is all in ore except where development is done between vein systems or in waste areas of vein systems. Timber chutes for extracting the ore are constructed above the track drift. Raises are developed in ore on each side of the stope that are timbered to provide access as the stope progresses up dip. Vertical 2.0 m wide rib pillars are left between stopes and a horizontal 4.0 m thick crown pillar is typically left under the track of the level above (wide shrinkage stopes require a thicker pillar). Productivity varies greatly depending on the width of the vein being mined and the cycle of the stope (as 2/3rds of the ore is retained in the stope during the drilling and blasting phases). The operating cost for shrinkage stoping (excluding energy costs) is estimated from historical

data to be \$15.50 per tonne, an allowance of 10% has been added to this amount due to price escalations that are occurring in the industry for a total of \$17.05 per tonne.

All ore production in 2007 and 2008 will be provided by shrinkage stoping, while the longhole areas are being developed and the mine works up the learning curve with the new longhole mining method.

The discovery by diamond drilling of the extension of the Litoral vein has provided a wide and high grade addition to the mines proven and probable reserve. PASB determined that a significant portion of the mineral reserve is amenable to longhole mining warranting the introduction of longhole mining methods. Longhole mining should result in a reduction in mining cost, compared to shrinkage mining, (Table 17) and will allow a higher mining recovery of the wider ore zones than could be achieved through shrinkage. The shrinkage method requires more permanent ore pillars to ensure stability of the stopes and safety of the miners.

The longhole cost per tonne of \$11.34 was calculated by PAS in Vancouver using a first principles estimate.

Assumptions were made for units of work such as tonnes per metre drilled, productivity, mobile equipment maintenance requirements and the cost of consumables from suppliers in Bolivia, Peru, Argentina and Canada. A unit cost was calculated for each of the primary activities of development, longhole drilling, longhole blasting, mucking, backfilling, and truck haulage. These estimated unit costs were consolidated with the estimates for units of work in order to arrive at a cost per tonne for longhole mining. The operating cost estimates all assume a company workforce.

Table 17 Mining Method Cost per tonne

Mining Method	Op. Cost (US\$/tonne)	Escalation	Model US\$/tonne
Shrinkage	\$ 15.50	10%	\$ 17.05
Longhole	\$ 11.34	10%	\$ 12.47

In June 2006, PASB purchased mechanized equipment from Atlas Copco conjunctively with a maintenance service contract from the supplier. With a positive decision to proceed with the project, the only mechanized equipment remaining to be purchased are two underground trucks. All scoops were purchased with remote control packages to allow the maximum safe extraction of ore from longhole stopes. A listing of the mechanized equipment is as follows in Table 18:

Table 18 Mechanized Equipment

Equipment Type	Model/Capacity	Number Required	Cost Each	Total Cost	Status
Scooptram LHD	ST-3.5G (3.5yd ³ Bucket)	2	\$ 375,000	\$ 750,000	purchased
Scooptram LHD	ST-2G (2.0yd ³ Bucket)	1	\$ 240,000	\$ 240,000	purchased
Longhole Drill (production)	AC281	1	\$ 320,000	\$ 320,000	purchased
Jumbo Drill (development)	H253 single Boom 16	1	\$ 380,000	\$ 380,000	purchased
Haulage Truck	AC2010 20-tonne capacity	2	\$ 335,000	\$ 670,000	included in capital
				\$2,360,000	

PASB has invested \$1.69 million in mechanized equipment required to start the Litoral decline which will access the Litoral vein. The capital estimate made for the economic model in this report contains \$670,000 in capital to purchase two 20 tonne underground low profile haul trucks.

A cost savings of \$4.58 per tonne is estimated for longhole mining as compared to shrinkage mining. When applied to the 800,000 tonnes that are planned to be mined using longhole mining methods a \$3.7 million LOM savings results.

This operating cost savings combined with increased safety from a non-entry mining method and increased ore recovery justifies the capital expenditure of \$2.36 million for longhole equipment. Although not included in this report or analysis there is some potential that the longhole mining equipment will have significant use beyond the current known mineral reserves.

Initial planning considered utilizing longhole mining for all vein structures with a width of greater than 3 metres, a dip greater than 60° and a Rock Mass Rating (RMR) greater than 50. Areas of the Litoral Ramal 2, Litoral and 6 de Agosto veins met these criteria. However, in order to simplify the long-term development and planning it was decided to apply longhole techniques in the Litoral Ramal 2 vein only. Opportunities do exist for cost savings by applying longhole in portions of vein structures as the mining and mine planning progresses.

The longhole mining method selected is a modification of the Avoca method. This low cost mining method is applicable to the ore geometry at San Vicente and particularly to the good ground conditions. Figure 1-6 shows the modified Avoca method intended to be used. Sub levels are to be developed off of the planned decline at 20 vertical metre intervals and used as access for long hole drilling of the block below; backfilling of the block below with unconsolidated waste, and for mucking ore from the block above.

Levels and sub-levels will be developed off the ramp as the ramp passes the designed elevations. This will provide additional working faces to increase productivity of the trackless equipment. Levels are designed at -70, -110, -150, -195 and -220 levels. A 3.8m (wide) and 3.8m (high) haulage drift will be driven in waste in the footwall. Drawpoints will connect the haulage drift with the ore drive. The ore drive will be at a profile of 3.0m (wide) and 3.0m (high) and provide the platform for the longhole drill. Ore from the ore drives will be transported to the mill for processing and therefore are operating costs and not included in the initial capital cost estimate. Broken ore will be extracted from the stopes from the level below with remote control scooptrams.

In order to arrive at a production and development schedule, Estudios Mineros summarised all of the proven and probable mineral reserve blocks by vein and by level. The blocks were then scheduled in a systematic manner in order to meet the expected production requirements of first the Chilcobija mill and later the new mill that will be built at San Vicente. In order to confirm the scheduling logic of the plan the stopes were sequenced on level plans and colour coded by year of mining. The life of mine development requirements were identified in a similar manner. The life of mine plan is summarized in Table 19.

Table 19 Life of Mine Plan

	2007	2008	2009	2010	2011	2012	2013
Mining							
Shrinkage	101,527	141,242	197,808	180,007	143,996	144,004	144,008
Mining Longhole			36,038	90,000	126,003	126,000	126,000
Total Mining	101,527	141,242	233,846	270,007	269,999	270,004	270,008
Opening							
Stockpile	44,323	40,000	29,492	88	95	94	98
Processing							
Chilcobija	105,850	100,000					
Processing New							
Plant		51,750	263,250	270,000	270,000	270,000	270,000
Total Processing	105,850	151,750	263,250	270,000	270,000	270,000	270,000
Silver Grade (g/t)	289	340	324	365	393	398	402
Zinc Grade (%)	3.80	3.74	3.84	3.59	3.48	3.42	3.11
	2014	2015	2016	2017	2018	2019	
Mining Shrinkage	144,001	144,049	223,554	270,068	238,070	139,040	
Mining Longhole	126,000	126,000	46,449				
Total Mining	270,001	270,049	270,003	270,068	238,070	139,040	
Opening Stockpile	106	107	155	158	227		
Processing Chilcobija							
Processing New Plant	270,000	270,000	270,000	270,000	238,296	139,040	

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Total Processing	270,000	270,000	270,000	270,000	238,296	139,040
Silver Grade (g/t)	397	385	316	283	287	251
Zinc Grade (%)	3.02	2.95	3.41	3.52	3.56	3.75

47

25.2. Recoverability

Mineral processing and metallurgical testing are discussed in section 18. This section 25.2 provides additional information on the recoverability of the valuable metals and the amenability of the mineralization to processing by describing the design of the process that will be used to recover the valuable metals.

For calculation of the amount of copper silver concentrate to be produced, a copper weight of 0.3% has been used as an average head grade for the San Vicente ore for the life of the mine. Chilcobija operational data indicates that there could be closer to 0.4% copper in the ore even after losses of copper to the tailings. However, in order to ensure that the economic analysis is based solely on proven and probable reserves, the value of the copper produced has been reduced to zero by setting the revenue for copper to \$0. This is a very conservative method of estimation as the analysis includes smelting and refining charges for the copper content in the copper-silver concentrate. Lyntek was been directed by PASB to use an average head grade of 0.4% for copper for design purposes only, as is indicated in the Design Criteria. The flotation circuits were sized conservatively in order to account for any changes in grade of the desired mineral values in the San Vicente ore as well as any vagaries in the operating characteristics of the concentrator.

Process Design Criteria

Comminution Circuit: The purpose of the Comminution Circuit is to crush/grind the ore to the desired particle size in order to obtain optimum flotation and recovery of the desired mineral values in the downstream Flotation Circuits. The use of either a SAG Mill/Ball arrangement as well as a Two-Stage Crushing/Ball Mill arrangement to perform the comminution of the San Vicente ore was investigated. It was found that the two stage crushing circuit would have required a third stage crushing plant, hence the decision was made to proceed on the basis of a SAG Mill/Ball Mill arrangement.

The circuit will utilize a 800 mm x 550 mm Primary Jaw Crusher and a 14' x 5' SAG Mill, which produces as system discharge of F100 = 10 mesh particles as feed to a 9' x 14' Ball Mill that is equipped with a 500 Hp motor.

Lyntek used a design tonnage of 35 metric tonnes per hour (MTPH), a Bond Work Index = 11.54 KwHrs/Tonne, and the desired P80 = 105 microns Ball Mill discharge to the flotation circuit and contracted two prominent equipment vendors (Metso Minerals and Outokumpu) to provide a recommended size for the SAG Mill/Ball Mill circuit for this project. Both vendors recommended the size for the SAG Mill to be 14' Diameter x 5' long and the size for the Ball Mill to be 9' diameter x 14' long. This recommendation has been reviewed and confirmed by Mr. Douglas Maxwell. Both the SAG Mill and Ball Mill will be equipped with 500 Hp drives. A flow of 35 MTPH is equivalent to a capacity of 756 metric tonnes per day (MTPD) at a concentrator availability of 90%.

Outokumpu (now Outotec Technologies) was asked to conduct a milling analysis for a 9' Diameter x 12' Long Ball Mill that was being considered rather than the previously selected 9' diameter x 14' ball mill given the Bond Work Index = 11.54 KwHrs/Tonne and the desired discharge particle size of P80 = 105 microns. Outokumpu determined that the 9' diameter x 12' long ball mill would be capable of only processing 32 MTPH rather than the desired 35 MTPH and so this option was rejected.

A Regrind Mill was not included into the comminution circuit as Lyntek estimated that the Primary 9' x 14' Ball Mill will be able to produce a particle size of P80 = 74 microns. This will also result in 62% of the particles being -53 microns and approximately 55% of the particles being -37 microns. This particle distribution data is contained in the Determination of Work Index Report of September 2005. This particle sizing would release the majority of the locked Zn particles so that the Cu/Ag flotation concentrate will now have less Zn and be much cleaner and would not report to a regrind circuit; thus a Regrind Mill is not required.

Flotation Circuits: The purpose of the Flotation Circuits is to separate the economic metals from the waste rock and to separate the metals into saleable concentrates.

Lyntek has relied upon the information and data in the following test reports in order to develop the proposed flowsheet: (a) Alfredo Vargas 2004 Test Report, Test No. 105; (b) Guillermo Portales 2005 Test Report; and (c) Chilcobija Concentrator Operating Data when processing the San Vicente ore. The Material Balance for the proposed flowsheet is based upon the laboratory test data from both A. Vargas test report and G. Portales test report as well as Lyntek's experience in designing similar mineral processing concentrators. The flotation circuit design and selection of individual flotation cell volume is based upon the laboratory test data from both A. Vargas test report, G. Portales test report and a review of the Chilcobija operating data when processing the San Vicente ore. Mr. Douglas Maxwell has reviewed these reports and using his professional judgement has determined them to be sound and agrees with the adoption of the results. The flotation circuit design and flotation cell selection is also based upon Lyntek's professional assessment of the flotation requirements to process the San Vicente ore. The flotation circuits have been sized conservatively in order to provide for upsets and increased flow from the upstream Comminution Circuit. The flotation circuits have also been designed to provide for ease of operation by plant personnel. Additionally, the flotation cells have been selected to be as maintenance-free as possible while also providing for optimum metallurgical performance and equipment service and wear life. Both the flotation circuit design and equipment selection incorporate many years of flotation experience and knowledge as well as many years of concentrator trouble-shooting experience.

A single Flash Float or Pre-Float was included in order to take advantage of the natural flotation of desired values contained in the San Vicente ore. This initial flotation process should improve the overall recovery of these desired values while also decreasing the use of reagents to process the ore.

The flotation circuit design will include the following flotation circuits:

1. Flash Float or Pre-Float Circuit;
2. Bulk Cu/Ag Flotation Circuit; and
3. Bulk Zn/Ag Flotation Circuit.

The Flash Float or Pre-Float Flotation Circuit will be one single conventional Flash Flotation cell. The Flash Flotation concentrate will report directly to the Cu/Ag concentrate thickener and the Flash Flotation tailings will report to the conditioner for the Bulk Cu/Ag Rougher Flotation Circuit.

The Bulk Cu/Ag Flotation Circuit will consist of the following flotation stages:

1. Cu/Ag Rougher Flotation using conventional flotation cells;
2. Cu/Ag Scavenger Flotation using conventional flotation cells;
3. Cu/Ag 1st Cleaner Flotation using conventional flotation cells; and
4. Cu/Ag 2nd Cleaner Flotation using conventional flotation cells.

The Cu/Ag Rougher flotation concentrate will report to the 1st Cleaner Flotation, the 1st Cleaner flotation concentrate will report to the 2nd Cleaner Flotation and the 2nd Cleaner flotation concentrate will report to the Cu/Ag concentrate thickener. The Scavenger Flotation concentrate will report back to the Ball Mill feed and the Scavenger Flotation tailings will report to the Zn/Ag conditioner for the Bulk Zn/Ag Rougher Flotation Circuit.

The Bulk Zn/Ag Flotation Circuit will consist of the following flotation stages:

1. Zn/Ag Rougher Flotation using conventional flotation cells;
2. Zn/Ag Scavenger Flotation using conventional flotation cells;
3. Zn/Ag 1st Cleaner Flotation using conventional flotation cells;

4. Zn/Ag 2nd Cleaner Flotation using conventional flotation cells; and
5. Zn/Ag 3rd Cleaner Flotation using conventional flotation cells.

The Zn/Ag Rougher Flotation concentrate will report to the 1st Cleaner Flotation, the 1st Cleaner flotation concentrate will report to the 2nd Cleaner Flotation, the 2nd Cleaner flotation concentrate will report to the 3rd Cleaner Flotation, and the 3rd Cleaner Flotation concentrate will report to the Zn/Ag concentrate thickener. The Scavenger Flotation concentrate will report to the feed to the Zn/Ag Rougher Flotation and the Scavenger Flotation tailings will report to the Tailings thickener.

The same size flotation cells (300 cubic feet (8.5 cubic metres) and 24 cubic feet (0.68 cubic metres)) were selected in both the Cu/Ag and Zn/Ag flotation circuits in order to have a commonality of flotation cell sizes for operating personnel to understand the operating and maintenance characteristics as well as to have a commonality of spare parts for both maintenance and inventory purposes at San Vicente.

All flotation conditioners have been sized at 10 Diameter x 10 Deep (3m x 3m) in order to provide for a minimum of 10 minutes of conditioning time for the particles within the slurry. Each conditioner will also provide for high-intensity conditioning of the slurry particles in the slurry with the reagents via a two- propeller mechanism to assure that the mineral particles are coated with the reagents. Each conditioner tank will be designed with an up-comer (vertical trough) outlet in order to prevent short-circuiting of the conditioning reagents as well as to assure the conditioning of the mineral particles. The up-comer will rise about 5 inches above the slurry surface within the conditioner and extend downward into the conditioning tank to about one foot above the tank bottom so that all conditioned slurry within the tank will be forced to exit from the bottom of the conditioner.

Thickeners and Filtration circuits: The purpose of the Thickeners and the Filtration circuits are to provide solid liquid separation in order to provide target moisture contents for saleable concentrates and for pumping tailings to the tailings storage facility.

The information provided in the Alfredo Vargas 2004 Test Report was relied upon to size both the thickeners and the filters. When test data was missing, Lyntek relied upon professional in-house experience as well as Vendor personnel experience in order to size and select the proper equipment. Both the thickeners and the filters have been sized conservatively in order to provide for optimum dewatering performance as well as to allow for ease of maintenance and equipment longevity.

High-rate thickeners have been selected for use at San Vicente in order to minimize the diameter of the thickener tanks that are required for the process. This also decreases the ground area required outside the plant building for locating the concentrate thickeners. The Cu/Ag and Zn/Ag concentrate thickeners have both been specified to be 20 ft. in diameter. The tailings thickener that will be located on the outside of the building has been specified to be 50 ft. in diameter. All thickeners have been sized conservatively in order to account for any upstream upsets as well as any increase in mineral values within the ore body.

Membrane filter presses have been selected for use in the San Vicente concentrator to allow for adequate dewatering at high altitude. Two filter presses will be installed; one for the Cu/Ag concentrate and the other for the Zn/Ag concentrate. At average mine head grades, approximately 40 tonnes per day of Zn/Ag concentrate and approximately 10 tonnes per day of the Cu/Ag concentrate will be produced.

Process Water and Reagents: Process water and reagents are required for the operation of the circuits within the process plant.

Refer to Table 5 and Section 7.0 Accessibility, Climate, Local Resources, Infrastructure and Physiography for a complete description of the proposed water sources and the water requirement for the San Vicente concentrator.

Reagents used in the concentrator will be a combination of frothers, collectors, depressants, pH adjusters(lime) and flocculants.

General Plant Design Philosophy

It was agreed during several meetings between Lyntek, PAS and PASB that a simple process design with a limited amount of instrumentation would best suit the location of the concentrator as well as the fit with the basic design philosophy. This simplified design philosophy has been utilized by Lyntek throughout the design process for the San Vicente concentrator.

Automation within the plant will be kept to a minimum in order to maintain a simple yet efficient plant. An automated belt scale and feeder will control the ore feed rate to the concentrator and automated samplers will be installed in the various circuits within the concentrator to obtain samples of the plant feed, concentrates and tailings. At this time, it is not considered necessary to fully instrument the plant. All pumps and cyclones will be equipped with pressure gauges for local display to be viewed by the operators. A PLC room has been incorporated into the building design for the instrumentation that will initially be installed as well as for use in the future for continued upgrading of the plant if more automation is justified.

25.3. Markets

Prices for the metals that San Vicente produces have been robust for the last three years, after several years of prolonged weakness. Factors contributing to the recovery in metal prices include demand resulting from strong industrial growth in China, weakness in the US dollar and supply concerns due to under-investment in new production capacity. PAS anticipates that these factors will continue to support prices during 2007 and that the long-term fundamentals for metal prices are positive.

The metal prices used in the mineral reserve calculations and the life of mine plan are considerably lower than the current market prices. Higher metal price assumptions in a range between the mineral reserve prices and the current market prices would positively affect the cash flow in the life of mine plan, but an increase to the mineral reserves would not be significant.

Contracts for the sale of concentrates from the San Vicente mine and from the San Vicente Mine Expansion Project are currently in place. The sale of metal concentrates to smelting companies and metal traders is a common practice in Bolivia and there is an active and competitive market for the concentrates that is expected to continue. PASB with the assistance of PAS intend to negotiate the sale of future concentrates directly with metal trading or smelting companies and do not intend to use agents to assist with this.

25.4. Revenues

The San Vicente mine will produce a zinc-silver and a copper-silver concentrate. Contracts are currently in place for these concentrates until the end of 2010. The concentrates are being sold under an agreement with Trafigura and their trading company Cormin. Both the zinc-silver and the copper-silver concentrates are taken by truck and rail to the port of Antofagasta in Chile for shipment. The smelter terms and conditions used in the economic model are assumed to be the same as those that are currently in place. Although San Vicente has historically received revenues from copper, as there is insufficient data to estimate the copper grade of the mineral reserves or mineral resources, the assumption in the economic analysis is that copper revenue will be zero. The model is not sensitive to reasonable changes in concentrate smelting charges. The assumptions for smelting the concentrates are considered by the co-authors to be reasonable and within industry norms.

25.5. Environmental Considerations

The environmental license for the San Vicente mine is now in the process of being updated to reflect the proposed expansion of the mine, construction of a new processing plant, new tailings facility and associated infrastructure. The existing license only contemplated the operation of the mine where the ore was processed off site by EMUSA at the Chilcobija plant under a toll milling contract. The existing environmental license also included the provision for all tailings produced from the processing of San Vicente ores at the Chilcobija plant to be permanently stored at a tailings facility near the plant. The responsibility for the design, operation and permitting of this tailings facility was part of the responsibilities of EMUSA under the terms of the toll milling contract.

PASB contracted the Bolivian consulting firm of Minco to carry out an environmental baseline study, ALBA, (as they are known for the acronym in Spanish) in 2001. Between 2001 and the present, this

baseline information has been complemented with semi-annual monitoring of air, soil and water quality parameters at various monitoring locations in the vicinity of the San Vicente mine. This existing information will be further complemented by a further round of sampling to establish the baseline conditions for the proposed expansion of the San Vicente mine.

Minco is currently in the stage of preparing the Environmental Impact Study, EEIA, as it is known under Bolivian legislation, for submittal to Bolivian environmental authorities. The main incremental impacts resulting from the proposed expansion of the mine are related to:

Construction of a new tailings facility in a tributary to the San Vicente River, downstream of the mine;

Construction of a new processing plant on the south side of the San Vicente river valley between the proposed location of the tailings facility and mine;

Increased groundwater use in the new plant; and

Wasterock storage from mine development.

PAS is committed to developing the San Vicente Mine Expansion Project by minimizing and mitigating environmental impacts in accordance with Bolivian regulations, industry best management practices and its own Environmental Policy.

A closure cost estimate was conducted by the PAS environmental department at the end of 2005, the remediation and reclamation cost estimate for the San Vicente Mine Expansion Project is shown in Table 20. There is no requirement to post a bond for a portion of the estimated costs.

The unit costs used in the estimate were based on experience gained at other mining projects and are generally accepted in the mining industry. For the economic assessment of the San Vicente mine presented in this report, PAS has escalated the closure cost estimate by 10%. The assumptions used in the preparation of the closure cost estimate are as follows:

Final closure requirements will be optimized and updated as the operation proceeds.

Cyanide destruct will not be required to treat tailings pond solution (although the San Vicente process plant will utilize a flotation process and not a cyanide process, there will be a small amount of cyanide used as a reagent in the flotation process).

The tailings pond area will be capped with approximately one (1) metre of soil material and revegetated to limit infiltration during precipitation events.

The mill area as well as other infrastructure will be reclaimed by removing all equipment, removing/demolishing all buildings and foundations, grading, and revegetating.

When possible waste dumps will be stabilized to a 2/1 slope and revegetated.

Underground adits/portals/etc. will be bulk headed for hazard abatement.

Drainage from the underground will not require active treatment. Instead a passive system will be utilized.

Table 20 San Vicente Closure Cost Estimate

Area	Hectares	Acres	Cost Basis	Cost Estimate (USD)
Tailings Area	15	33.9	Based on \$10K/acre. Includes placement of cover, recontouring, and revegetation.	\$ 339,000
Waste Dump	5	11.3	Based on \$2.7K/acre. Includes stabilization, recontouring and revegetation	\$ 30,510
Underground	N/A	N/A	Three adits/3 vent raises @ \$25K/adit or shaft.	\$ 200,000
Decommissioning	N/A	N/A	Approximately \$.25/dollar of the capital amount (\$5,000,000)	\$ 1,250,000
Roads				
Mine	10	22.6	Based on \$1.5K/acre.	\$ 33,900
Access	10	22.6	Based on \$1.5K/acre.	\$ 33,900
Post Closure Monitoring				
Surface and Ground Water	N/A	N/A	Monitoring (sampling/analysis) on a bi-annual basis for three (3) years. (\$20K/year)	\$ 60,000
Tailings Area	N/A	N/A	Monitoring (sampling/analysis) on a quarterly basis for three (3) years. (\$20K/year)	\$ 60,000
Sub Total (Direct)				\$ 2,007,310

Add Ons

A salvage value for the equipment at the mine and new process plant has been estimated to be \$2,500,000 based on the value of the mobile and plant equipment that will be at the mine. In the economic analysis, the closure costs are expended in 2019 and 2020, while the salvage value is realized in 2020.

25.6. Exploration Expenditures

The mine plan and economic model presented in this report are based on proven and probable mineral reserves only. The exploration expenditures on these mineral reserves have already been made. As no mineral resources or other potential have been included in the plan and no accounting has been made of their value, no exploration expenditures have been included in the economic analysis.

25.7. Taxes

The following is a summary of the Bolivian taxes used in the San Vicente feasibility study economic model. Due to the fact that the current Bolivian government has been proposing substantial changes to the current tax laws, the latest proposed changes to the tax law have been incorporated in the economic model.

Mining Royalty (used in economic model)

1. The new mining royalty has rates similar to the current ICM tax (between 1 and 6%)
2. The royalty is applied to gross metal value (before smelting and refining charges) and rates based on sliding scale to metal prices
 - a. Silver Minimum 3% / Maximum 6%
 - b. Zinc Minimum 1% / Maximum 6%
 - c. Copper Minimum 1% / Maximum 6%

At PAS mineral reserve prices, the royalties are at the maximum rate of 6%

3. The royalty can be credited against income tax
4. The royalty is not income tax deductible

Corporate Tax (used in economic model)

1. The corporate tax rate on taxable income is 25%

Additional Profit Tax (used in economic model)

1. This is a new tax that has been referred to as ICM (complementary tax) and IUM.
2. All mining companies, except for cooperatives, will be subject to the new tax
3. The new tax will be based on annual profit after income tax
4. Exploration expenses are allowed to be deducted twice
5. Tax rate is 12.5%

Value Added Taxes (VAT) (used in economic model)

1. Equipment purchased for the project has an effective VAT rate of 14.94%
2. Because PASB is domiciled in the Province of Potosi, it is expected that it will be exempt from paying VAT for a portion of the equipment purchased.

In order to allow a comparison, the following is a summary of the current tax legislation in Bolivia:

Complimentary Mining Tax (ICM) (current)

The complimentary mining tax is applied to gross metal value (before smelting and refining charges) and the rates based on sliding scale to metal prices.

- a. Silver Minimum 3% / Maximum 6%
- b. Zinc Minimum 1% / Maximum 6%
- c. Copper Minimum 1% / Maximum 6%

The complimentary mining tax can be credited against income tax. The complimentary mining tax is not income tax deductible.

Corporate Tax

The corporate tax rate on taxable income is 25%.

Value Added Taxes (VAT)

Equipment purchased for the project has an effective VAT rate of 14.94%.

Due to the fact that PASB is domiciled in the Province of Potosi, it is expected that it will be exempt from paying VAT for a portion of the equipment purchased.

25.8. Capital and Operating Costs

Capital Cost Estimate

Capital costs were calculated in the 3rd quarter of 2006. These costs have been escalated by 7.5% for the costs that will be incurred in 2007, 15% for the costs in 2008 and 22.5% for the costs that will be incurred in 2009. Much of the major mining equipment required has already been purchased and the majority of it is at the San Vicente mine working on starting the new ramp access to the Litoral vein. As these expenditures have already been made, they have not been considered in the cash flow analysis other than from the perspective of being on the books for depreciation purposes. The capital expenditures that are included in the economic analysis are shown in Table 21. The economic analysis that was used to confirm the economic viability of the proven and probable mineral reserves that are detailed in this report is summarized in Table 23.

Capital expenditures in 2007 and 2008 are expected to total \$40.5 million. The new processing plant is expected to start operating in 2008 and ramp up production to near to its full capacity of 750 TPD by the end of 2008. Further capital expenditures for items required to sustain production such as raises to the tailings storage dam are projected to cost a further \$2.5 million in 2009 and a further \$8.5 million from 2010 to the end of the mine life in 2019.

Table 21 Capital Cost Estimate Summary

	2007	2008	2009	2010 to LOM
Mining				
Mining Equipment for Trackless Development & Longhole	\$ 111	\$ 64		
Mining Equipment for Track Development & Shrinkage	\$ 177	\$ 54	\$ 59	
Hoisting & Tramming	\$ 408	\$ 8		
Haulage Fleet	\$ 335	\$ 510		
Service Fleet	\$ 337	\$ 172		
Ore Reserves / Geology				
Underground Electrical Distribution	\$ 384	\$ 46		
Mine Rescue Equipment				
Sustaining Equipment and Capital			\$ 200	\$ 1,900
Engineering / Geology				
Sub Total Mine Equipment	\$ 1,751	\$ 854	\$ 259	\$ 1,900
Existing Mine				
Rebuild Rail Car Dump on 0 Level	\$ 14			
Rebuild Rail Car Dump on -35 Level	\$ 14			
Alimak Ventilation Raise For Shrinkage Stoping	\$ 120			
Deepen Vertical Shaft to -150 Level				\$ 380
Shaft Station and Ore Dumps on -150 Level				\$ 50
Shaft Loading Pockets on -150 Level				\$ 100
Ventilation Raise -150 to -110 Level				\$ 32
Litoral Access				
Develop Litoral Ramp	\$ 1,200	\$ 820		
Develop Sub Level Lateral Access	\$ 263	\$ 788	\$ 788	\$ 265
Alimak Ventilation Raise For Longhole Stoping		\$ 176	\$ 176	\$ 176
Alimak Waste Backfill Raise For Longhole Stoping			\$ 264	
Sustaining Equipment and Capital			\$ 150	\$ 1,425
Sub Total Mine	\$ 1,611	\$ 1,784	\$ 1,378	\$ 2,428
750tpd SAG Mill Ore Porcessing Plant				
Total Area 10 - Primary Crushing to SAG Mill	\$ 1,385	\$ 154		
Total Area 20 - Grinding & Classification, SAG and Ball Mills	\$ 1,537	\$ 171		
Total Area 30 - Flotation & Cleaner Silver, Copper, & Lead	\$ 1,376	\$ 153		
Total Area 40 - Flotation and Cleaner, Zinc	\$ 1,072	\$ 119		
Total Area 50 - Tailings Thickening	\$ 238	\$ 26		
Total Area 70 - Water Treatment and Supply	\$ 114	\$ 13		
Total Area 100 - Reagents	\$ 175	\$ 19		
Total Area 145 - Mill Electrical System	\$ 757	\$ 252		
Total Area 160 - Plant/Mine Water and Plant Air	\$ 16	\$ 2		

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Total Area 170 - Standby Power		\$ 450		
Total Area 180 - Piping and Steel	\$ 680	\$ 227		
Total Area 200 - Flotation Plant Building, HVAC	\$ 550	\$ 550		
Total Area 700 - Tailings and Reclaim	\$ 843	\$ 94		\$ 1,431
Total Area 800 - Infrastructure & Gen. Site Serv.	\$ 1,154			
Total Area 810 - Main Access Roads Const.	\$ 350	\$ 150		
Total Area 825 - Water Supply, Plant & Domestic	\$ 1,900	\$ 211		
Total Area 900 - Power Supply	\$ 2,300			
Total Area 925 - Freight and Insurance	\$ 828	\$ 276		
Mobilization	\$ 40	\$ 0		
Construction Power	\$ 173	\$ 173		
Improvement to Housing for Permanent Plant Workers	\$ 150			
Camp and Transportation Costs	\$ 505	\$ 337		
EPCM @ 20%	\$ 1,694	\$ 726		
Lyntek Pre-EPCM Engineering	\$ 100			
Detailed Engineering EPCM	\$ 630			
Komex Pre-EPCM Engineering	\$ 72			
Tailings Dam EPCM Phases I, II	\$ 282			
Owner's Project Admin Costs 2006, 2007, & 2008	\$ 890	\$ 357		
Construction Insurance	\$ 60	\$ 40		
Commissioning and Spares	\$ 70	\$ 209		
Working Capital	\$ 196	\$ 589		
First Fills	\$ 145	\$ 434		
Startup Labor		\$ 148		
ADR Environmental costs				
Sustaining Equipment and Capital			\$ 150	\$ 1,425
Sub Total Mill, Tailings Dam, Water, Electricity	\$ 20,280	\$ 5,881	\$ 150	\$ 2,856
Community Sustainability and Infrastructure				
Fixing of Existing Prefabricated Housing	\$ 84	\$ 0		\$ 60
School Repair and Expansion	\$ 50	\$ 10		\$ 30
Cooperative Technical Assistance	\$ 20	\$ 10	\$ 10	\$ 60
Sanitary and Drainage	\$ 100	\$ 15		\$ 30
Repair of Theater and Union Facilities	\$ 40	\$ 10		\$ 15
Small Fabrics and Tourist Study for Community	\$ 51	\$ 15	\$ 15	\$ 45
Sub -Total Community Sustainability and Infrastructure	\$ 345	\$ 60	\$ 25	\$ 240
Subtotal Capital	\$ 23,987	\$ 8,578	\$ 1,811	\$ 7,424
Contingency 15%	\$ 3,598	\$ 1,287	\$ 272	\$ 1,114
Cost Escalation	\$ 1,799	\$ 1,287	\$ 407	
TOTAL CAPEX	\$ 29,384	\$ 11,152	\$ 2,490	\$ 8,538

The capital cost estimate for the processing plant was been generated by Lyntek based on a detailed equipment list, flow sheets, electrical one-line drawings, and plant general arrangement drawings. Mr. Douglas Maxwell, one of the authors of this Technical Report, has reviewed this information and determined that in his professional judgement these estimates are sound and approves of these estimates.

A design criteria document was developed from the metallurgical information provided to Lyntek by PASB. The design criteria were used to specify and size the equipment required for the concentrator circuitry and subsequently to submit requests for quotations to a minimum of two vendors for equipment.

Capital equipment costs were estimated from formal quotations obtained from vendors and pricing information obtained from recent similar Lyntek projects. When vendor quotes were exclusive of taxes, freight, import duties, or other fees, the appropriate cost was estimated and added by PASB.

DIRECT PLANT COST DETAIL

When possible, equipment vendors from Bolivia, Brazil, Chile and Peru were selected, to minimize delivery times. Lyntek also received equipment quotations from vendors who had been contacted by PASB. These quotations were utilized as much as possible to take advantage of work already done by in-house personnel. Other local and out of country vendors quotations were incorporated into the capital cost estimate as appropriate.

This capital cost estimate does not include contingency factors applied to the individual quoted items or areas. An over-all contingency factor of 15% has been applied to the final total capital cost, in addition, capital cost escalation factors of 7.5% for expenditures in 2007, 15% for expenditures that are projected to be incurred in 2008 and 22.5% for capital expenditures that will be incurred in 2009 have been added to the totals.

Capital equipment costs used for estimating the transportation and capital spares is the sum of the Crusher area, mill/flotation area, system piping, structural steel and the building, equipment costs only.

The installation and construction costs that are associated with Crushing/Grinding have been developed from Bolivian contractor pricing, Lyntek's recent experience on similar projects in Bolivia and from Lyntek's cost database. Bolivian pricing for civil/site work, concrete and some man-hours associated with placement of the equipment have been provided by PASB and area contractors. The installation cost estimate utilizes contracted labour for installation of specialized and heavy equipment, construction of the process building, heavy structural steel/plate work, and installation of electrical and instrumentation wiring. Equipment rentals for cranes and heavy equipment not currently owned by PASB have been included at current Bolivian rental rates. Small tools with values of less than \$1,000 will be purchased directly by PASB.

Lyntek has developed a built-up construction labour rate of \$11.70 per man-hour that includes base rate, burden, subsistence, safety, management and supervision, craft support (labourers), warehousing, fuel/oil/maintenance and overtime.

The costs associated with installation of the equipment in the concentrator are based upon Lyntek's experience with other plant equipment installations and whenever possible, equipment installation estimates that were obtained from equipment vendors.

The estimated costs for installation of the electrical system and the Motor Control Center (MCC) are based upon the electrical one-line drawings, from vendor quotes.

A diesel generator, quoted at \$450,000 is included in standby power.

The estimated costs for installation of the system piping are based upon a bulk piping material estimate from Lyntek General Arrangement Drawing No. 06023 G-01 (Figure 1-10) and the associated flow diagrams. Material and piping costs were obtained from the Komex reports and from current material costs. The labour hours that are required are an estimate based upon Lyntek's past installation

experience. This section of the estimate is for the flotation plant, tailings line, and water reclaim line only. All water system costs are covered in the plant major equipment capital estimate.

The estimated costs for installation of the structural steel in the concentrator are based upon a bulk materials estimate obtained from the same Figure 1-10 and the associated sections. Steel costs of \$ 0.63/lb. were used and the labour hours that are required are an estimate based upon Lyntek's past installation experience.

Lyntek developed basic architectural drawings of the concentrator building and forwarded these drawings to PASB personnel who obtained local vendor quotations. Lyntek also developed costs for pre-engineered buildings from past experience for comparison purposes. It is assumed that the concentrator building will be supplied and constructed by a local Bolivian contractor; therefore, no freight costs that would be associated with the building have been included in the capital cost estimate. The building required is approximately 73.2m long x 19.1m wide x 15.5 m high. In addition to the main building, a 73.2m long x 6m wide x 4m high lean-to will be added that will house the laboratory, MCC room, PLC room, administration offices, and maintenance shop with a storage area.

The calculated installed costs for the concentrator building are estimated to be \$1,055/ m² for the entire structure. An allowance of \$80,000 has been estimated for heating, ventilation, and air conditioning (HVAC) of the building. This estimate is based upon HVAC for a similar size pre-engineered building.

The main road connecting the San Vicente Mine Expansion Project to Uyuni must be upgraded to provide access for heavy equipment and machinery. PASB will fund the 30 kilometres from the mine towards Uyuni; the Government is upgrading the road from Uyuni towards the mine. Funding of \$500,000 for the PASB portion has been included for this work which is scheduled to be performed in 2007 and 2008.

Lyntek has contacted Transera, a freight forwarding company, and together the two companies have developed a freight estimate based on prior project experience and recent in-country experience by Transera. Freight costs for transporting the major equipment to the plant site have been developed based upon the capital equipment costs. It has been assumed that all of the equipment will require export packaging. Only a small portion of the equipment has been sourced from North America. The ball and SAG mills have been sourced from Europe or Brazil. All items not manufactured in Bolivia are anticipated to be delivered via Ocean freight and will be shipped to the Port of Antofagasta, Chile. The equipment vendor pricing for all equipment is FOB factory. The equipment sources are from Chile, Peru, Brazil and North America. No contingency has been applied to the estimate. The calculated value does not include VAT, duty or other taxes. The total estimated transport costs have been calculated to be \$1,104,088.

The only equipment items that are deemed useable from the existing Vetillas mill are the lime regrind mill and the associated feed conveyor. These two items have been included in the capital equipment list; however, no costs have been assigned to these items as items in Vetillas are included for use under the joint venture. An estimate of the hours required and associated costs, to remove and install this equipment has been included in the capital cost estimate.

INDIRECT PLANT COST DETAIL

Mobilization and demobilization have been included in the hourly rates used in the capital cost estimate and are therefore included in the estimates for each area. The exception to this is a line item of \$40,000 for the mobilization and demobilization of a crane, from a local contractor.

Allocated power costs to the project were based on power demand calculated by Lyntek, using recent power costs. Upgrading the existing bunkhouses in Vetillas is underway. Further housing will be required for construction and operational personnel. Costs associated with room and board of the construction workers and bussing costs from Vetillas to San Vicente.

Spares include one set of liners each for the SAG mill, ball mill, and primary jaw crusher. Spares also include conveyor belting, flotation cell, disc filter, and conveyor components, and oil and lubricants. A total of \$278,899 is budgeted for spares.

Due to the remote location of San Vicente, a three month supply of reagents, grinding media, lubricants and gasoline is included with first fills.

OPERATING COST ESTIMATE

Historic actual costs were used for the operating cost estimates for shrinkage stoping and operating the mine infrastructure at San Vicente. PAS in Vancouver developed an operating cost estimate for longhole stoping. This estimate was a first principles estimate based on assumptions made for units of work such as tonnes per metre drilled, productivity, mobile equipment maintenance requirements and the cost of consumables from suppliers in Bolivia, Peru, Argentina and Canada. A unit cost was calculated for each of the primary activities of development, longhole drilling, longhole blasting, mucking, backfilling, and truck haulage. These estimated unit costs were consolidated with the estimates for units of work in order to arrive at a cost per tonne for longhole mining. The operating cost estimate was later reviewed and confirmed by Estudios Mineros del Perú. Mr. Wafforn has reviewed these estimates and determined in his professional judgement that these estimates are sound and approves of these estimates.

The operating cost estimate for the process plant was developed by Lyntek and various infrastructure costs were estimated by PASB. Labour unit rates and consumable costs for the region are provided by PASB who has access to the operating costs at the Chilcobija plant where the San Vicente ore will be processed while the construction of the new plant is in progress. Other sources for costs include estimates provided by equipment suppliers, contractors, consultants and engineering standard cost estimating guides.

Labour rates have been derived from existing rates paid to San Vicente employees, in 2006, and costs based on Bolivian national averages. Social burdens reflect current legal requirements.

The operating cost estimates exclude any consideration for inflation. The estimates were calculated using 3rd quarter 2006 US dollars and a flat Bolivian Boliviano to US dollar exchange rate of 8.08:1 for the life of the San Vicente Mine Expansion Project. In order to reflect the cost escalations in the industry, all of the operating costs were subsequently escalated by 10%.

The average unit operating costs are summarized in Table 22.

Table 22 Life-of-Mine Unit Operating Costs

Costs		2007	2008	2009	2010 to LOM
Mining Costs	\$/ DMT	\$ 20.35	\$ 16.99	\$ 16.38	\$ 15.75
Mill costs	\$/ DMT	\$ 13.97	\$ 16.18	\$ 13.64	\$ 13.64
Transport Mine-Chilcobija	\$/ DMT	\$ 4.95	\$ 3.36	\$ 0.28	\$ 0.28
Shipping and Selling	\$/ DMT	\$ 5.05	\$ 5.15	\$ 5.34	\$ 4.82
Administration Costs (office)	\$/ DMT	\$ 4.79	\$ 5.07	\$ 3.55	\$ 3.84
Administration San Vicente	\$/ DMT	\$ 2.59	\$ 4.35	\$ 3.05	\$ 3.29
Insurance and legal	\$/ DMT	\$ 3.30	\$ 4.40	\$ 0.00	\$ 0.00
Security & Environmental	\$/ DMT	\$ 0.55	\$ 0.25	\$ 0.21	\$ 0.23
Energy Costs	\$/ DMT	\$ 0.39	\$ 0.00	\$ 0.84	\$ 0.90

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Maintenance Costs	\$/ DMT	\$ 2.59	\$ 3.62	\$ 2.09	\$ 2.26
Vancouver Management Cost	\$/ DMT	\$ 2.59	\$ 5.07	\$ 2.92	\$ 3.16
Operating Cost per tonne	\$/ DMT	\$61.10	\$64.45	\$48.30	\$ 48.16

59

25.9. Economic Analysis

An economic model has been constructed in order to demonstrate the economic viability of the San Vicente mine long range plan and therefore mineral reserves. The PAS metal price assumptions for the end of 2006 mineral reserves have been used. The mine Expansion Project has very positive economics at the mineral reserve metal price assumptions. PAS has committed to funding the San Vicente Mine Expansion Project and has commenced work. A summary of the economic model is shown in Table 23. The metal prices used for 2007 are \$10.00 per ounce for silver and \$3,000 per tonne for zinc which is higher than the long term reserve prices used of \$9.00 per ounce for silver and \$2,100 per tonne for zinc. This only applies to the relatively small amount of production from the Chilcobija plant. The analysis is for the full year in 2007 and metal prices have averaged significantly higher than those values during the first half of the year. Although San Vicente has historically received revenues from copper, as there is insufficient data to estimate the copper grade of the mineral reserves or mineral resources, the assumption in the economic analysis is that copper revenue will be zero. This is a conservative estimate as the economic analysis includes smelting, transportation and refining charges for copper.

The analysis calculates an Internal Rate of Return of 22% and capital payback in 2.9 years. The Net Present Value is \$23.6 million at a 10% discount rate and is \$14.4 million at a 15% discount rate. The undiscounted after tax cash flow is \$53.8 million. PAS's 95% share of the undiscounted after tax cash flow is estimated to be \$50.9 million.

The payback is calculated as the amount of time required to pay back the capital expenditures with undiscounted cash flow starting from the beginning of 2009 when the new plant is assumed to be operating at almost full capacity. The payback period does not include any actual or imputed interest as the economic model assumes that PAS and Trafigura will fund cash calls according to their respective interests in PASB.

Table 23 Economic Model

2009	2010	2011	2012	2013	2014	2015	2016	2017	2018
9.00	\$ 9.00	\$ 9.00	\$ 9.00	\$ 9.00	\$ 9.00	\$ 9.00	\$ 9.00	\$ 9.00	\$ 9.00
2,100	\$ 2,100	\$ 2,100	\$ 2,100	\$ 2,100	\$ 2,100	\$ 2,100	\$ 2,100	\$ 2,100	\$ 2,100
28,549	2,695,536	2,900,839	2,939,728	2,968,078	2,931,913	2,840,512	2,329,223	2,090,841	1,867,390
1,585.4	8,229.3	7,993.2	7,851.9	7,144.3	6,932.6	6,776.5	7,831.3	8,070.3	7,203.0
28,839	\$ 31,326	\$ 32,686	\$ 32,819	\$ 32,130	\$ 31,561	\$ 30,616	\$ 27,834	\$ 26,208	\$ 23,410
12,934	(\$ 12,866)	(\$ 12,670)	(\$ 12,651)	(\$ 12,556)	(\$ 12,528)	(\$ 12,508)	(\$ 13,012)	(\$ 13,258)	(\$ 12,120)
1,283	(\$ 1,538)	(\$ 1,674)	(\$ 6,714)	(\$ 6,513)	(\$ 6,340)	(\$ 6,009)	(\$ 4,860)	(\$ 4,215)	(\$ 3,680)
6,179	(\$ 6,491)	(\$ 6,812)	(\$ 6,893)	(\$ 6,968)	(\$ 7,150)	(\$ 6,116)	(\$ 2,521)	(\$ 1,199)	(\$ 880)
8,443	\$ 10,431	\$ 11,531	\$ 6,561	\$ 6,092	\$ 5,543	\$ 5,982	\$ 7,441	\$ 7,537	\$ 6,710
8,443	\$ 10,431	\$ 11,531	\$ 6,561	\$ 6,092	\$ 5,543	\$ 5,982	\$ 7,441	\$ 7,537	\$ 6,710
2,995	\$ 3,616	\$ 4,096	\$ 2,849	\$ 2,650	\$ 2,637	\$ 2,632	\$ 2,640	\$ 2,653	\$ 2,360
5,447	\$ 6,815	\$ 7,435	\$ 3,712	\$ 3,442	\$ 2,906	\$ 3,350	\$ 4,801	\$ 4,883	\$ 4,340
6,179	\$ 6,491	\$ 6,812	\$ 6,893	\$ 6,968	\$ 7,150	\$ 6,116	\$ 2,521	\$ 1,199	\$ 880
481	(\$ 114)	(\$ 10)	(\$ 95)	(\$ 135)	(\$ 62)	(\$ 96)	(\$ 120)	(\$ 113)	(\$ 400)

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

2,490) (\$	2,566) (\$	650) (\$	604) (\$	1,452) (\$	633) (\$	621) (\$	575) (\$	575) (\$	57
0 \$	0 \$	0 (\$	356) (\$	462) (\$	454) (\$	440) (\$	397) (\$	372) (\$	33
8,656 \$	10,625 \$	13,587 \$	9,550 \$	8,361 \$	8,907 \$	8,309 \$	6,230 \$	5,023 \$	4,28
8,223 \$	10,093 \$	12,908 \$	9,055 \$	7,920 \$	8,439 \$	7,871 \$	5,899 \$	4,753 \$	4,05
38,408	2,482,952	2,675,919	2,712,859	2,742,218	2,709,244	2,624,384	2,141,941	1,918,023	1,713,11
2.46 \$	2.40 \$	2.33 \$	2.50 \$	2.80 \$	2.91 \$	3.04 \$	3.13 \$	3.36 \$	3.5
2.03 \$	1.89 \$	1.87 \$	1.88 \$	1.89 \$	2.01 \$	2.13 \$	2.70 \$	0.17 \$	0.1
4.49 \$	4.29 \$	4.20 \$	4.37 \$	4.70 \$	4.93 \$	5.17 \$	5.83 \$	3.52 \$	3.7
109.55 \$	116.02 \$	121.06 \$	121.55 \$	119.00 \$	116.89 \$	113.39 \$	103.09 \$	97.07 \$	98.2
48.30) (\$	46.84) (\$	46.11) (\$	46.04) (\$	45.69) (\$	45.59) (\$	45.51) (\$	47.38) (\$	48.29) (\$	49.9
61.25 \$	69.18 \$	74.95 \$	75.51 \$	73.31 \$	71.31 \$	67.88 \$	55.71 \$	48.78 \$	48.3

Sensitivity analysis were conducted for variants in metal prices, grade, capital and operating costs. A further sensitivity was conducted to show the economics of the project using a estimate for the copper grade.

Metal Price Sensitivity

A table showing the positive economics of the project over a wide range of metal prices is shown in Table 24. Note that the higher metal prices are used in 2007 for each case. As the date of this report is effective mid-2007 and as the prices have been considerably higher than those used in the first 6 months this is considered by the co-authors to be a reasonable assumption. In addition, metal prices in 2007 are only applied to the small amount of production coming from the Chilcobija plant meaning that this assumption has a relatively minor impact on the calculation of Net Present Value and Internal Rate of Return of the project.

Table 24 Metal Price Sensitivity

	Year	Case 1	Case 2	Case 3
\$/Ounce \$ Silver	2007	10.00	\$ 10.00	\$ 12.50
Zinc \$/Tonne	2007	\$ 3,000	\$ 3,000	\$ 3,600
Silver \$/Ounce	(2008 - 20)	\$ 6.25	\$ 9.00	\$ 12.50
Zinc \$/Tonne	(2008 - 20)	\$ 1,200	\$ 2,100	\$ 3,600
NPV 0%		\$ 3,745	\$ 53,756	\$ 123,951
NPV 10%		(\$10,847)	\$ 23,552	\$ 68,973
NPV 15%		(\$15,405)	\$ 14,368	\$ 52,608
IRR		2%	22%	44%
Pay Back (years)		7.5	2.9	1.5

Grade Sensitivity

In order to test the sensitivity of the project to the grade of the mineral reserves, the estimated head grade for each metal and for each year of operation was multiplied by factors of 100% (the case presented in Table 25), 125%, 110%, 90% and 75%. The cash flow and financial metrics for each case were then recalculated and are shown in Table 25. The co-authors conclude that the economics of the project are clearly very robust when after a 25% reduction in the estimated head grades of each of silver and zinc (essentially a 25% reduction in revenue) the IRR is 6%.

Table 25 Metal Grade Sensitivity

	1	100%	125%	110%	90%	75%
NPV 0%		\$ 53,756	\$ 90,175	\$ 70,490	\$ 39,446	\$ 13,843
NPV 10%		\$ 23,552	\$ 47,174	\$ 34,604	\$ 14,107	(\$3,567)
NPV 15%		\$ 14,368	\$ 34,299	\$ 23,737	\$ 6,294	(\$9,077)
IRR		22%	34%	27%	16%	6%
Pay Back (years)		2.9	2.0	2.5	3.5	5.5

Capital Cost Sensitivity

The economics of the San Vicente Mine Expansion Project are not sensitive to changes in capital cost up to the limits of the engineering estimate that is plus or minus 25%.

Table 26 Capital Cost Sensitivity

	1	100%	125%	110%	90%	75%
NPV 0%		\$ 53,756	\$ 47,891	\$ 49,890	\$ 57,578	\$ 60,001
NPV 10%		\$ 23,552	\$ 16,462	\$ 19,692	\$ 27,391	\$ 30,652
NPV 15%		\$ 14,368	\$ 6,835	\$ 10,504	\$ 18,217	\$ 21,800
IRR		22%	16%	19%	25%	31%
Pay Back (years)		2.9	3.6	3.3	2.6	2.2

Operating Cost Sensitivity

The economics of the project to variances in operating costs were calculated in a similar manner. This calculation further demonstrates the robust economics of the project.

Table 27 Operating Cost Sensitivity

	1	100%	125%	110%	90%	75%
NPV 0%		\$ 53,756	\$ 35,657	\$ 45,700	\$ 61,389	\$ 72,900
NPV 10%		\$ 23,552	\$ 11,924	\$ 18,419	\$ 28,443	\$ 35,813
NPV 15%		\$ 14,368	\$ 4,517	\$ 10,074	\$ 18,465	\$ 24,637
IRR		22%	15%	19%	24%	28%
Pay Back (years)		2.9	3.6	3.2	2.7	2.5

Sensitivity to Copper Head Grade

The economic model presented in this section 25.8 assumes that there will be no revenue from the production of copper from the San Vicente mine. This assumption is used because there is not sufficient copper grade sample data density available to make an estimate of the copper grade in the proven and probable mineral reserves or the measured and indicated mineral resources. Some of the older sampling programs did not include analysis for copper. As this Technical Report presents the economics of the proven and probable mineral reserves only, any revenues from copper have been eliminated. However the expected smelting, refining and transportation costs for a copper head grade of 0.3% have been retained. This is a degree of conservatism inherent in the calculation of the economics of the San Vicente Mine Expansion Project. The presence of copper at the mine is well established from the historical records, from the recent processing of San Vicente ores at Chilcobija and from the sampling data base. From a review of the production records at Chilcobija, the copper head grade in the last seven months has ranged between 0.35% and 0.41% with an average of 0.37%. When the copper head grade is back calculated from the smelter returns a grade of 0.4% is suggested. Because of this Lyntek was directed by PASB to design the process plant with the capacity to recover copper with a head grade of 0.4%. From the geology database, of a total of 6,561 samples, 1,521 samples have copper grades. The weighted average of those samples is 0.31% with a coefficient of variation of 1.01. Table 28 shows the sampling data:

Table 28 Copper Grade Samples

Vein	Total samples	Samples with Cu grade	% of data	Resource MT	Average Cu (%)	Stand dev.	CV
Adela	755	85	11.3	300,954	0.25	0.342	1.393
Cantera	356	220	61.8	223,802	0.14	0.134	0.932
Deseada	1,465	178	12.2	350,189	0.49	0.502	1.017
Guernica2	616	213	34.6	185,575	0.57	0.679	1.195
Litoral	383	16	4.2	213,085	0.52	0.218	0.423
Litoral_R2	288	43	14.9	227,314	0.38	0.264	0.689
SanJose	630	131	20.8	101,717	0.27	0.342	1.257
SLorenzo	237	4	1.7	56,773	0.24	0.199	0.845

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Union	534	73	13.7	273,316	0.33	0.422	1.262
6Agosto	1,297	558	43.0	778,262	0.18	0.192	1.091
	6,561	1,521	23.2	2,710,987	0.31	0.329	1.010

63

Table 29 presents the economic sensitivity of the San Vicente Mine Expansion Project with and without the inclusion of the revenues from a copper head grade of 0.3%. All other assumptions are as shown in Table 23 including long-term silver price of \$9.00 per ounce and a long term zinc price of \$2,100 per tonne.

Table 29 Copper Revenue Sensitivity

	Including Copper Revenues at 0.3% Head Grade	As Presented in this Technical Report - Not Including Copper Revenues
NPV 0%	\$ 68,345	\$ 53,756
NPV 10%	\$ 32,996	\$ 23,552
NPV 15%	\$ 22,312	\$ 14,368
IRR	26%	22%
Pay Back (years)	2.6	2.9

25.10. Mine Life

The life of mine plan presented in this study is based solely on proven and probable mineral reserves. The life of mine plan extends until 2019. Any conversion of the mineral resources to proven and probable mineral reserves and any new exploration discoveries will add to the mine life.

In the opinion of the co-authors there is excellent potential for new mineral resource discoveries on the mining claims held by PASB.

This report has been prepared by Martin G. Wafforn, P. Eng., Michael Steinmann P. Geo., and Douglas Maxwell, P.E. each of whom are qualified persons.

Respectfully submitted this 20th day of July 2007.

Signed and Sealed

Martin G. Wafforn, P. Eng.

Signed and Sealed

Michael Steinmann, P. Geo.

Signed and Sealed

Mr. Douglas Maxwell, P.E.

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

(SEAL)

**Technical Report for the
San Vicente Mine
Potosí Bolivia
Appendix A
Certificates and Consents**

CERTIFICATE OF QUALIFIED PERSON

I, Dr. Michael Steinmann, P.Geo., Ph.D., of Pan American Silver Corp., 1500-625 Howe St., Vancouver, B. C., Canada V6C 2T6, do hereby certify that:

1. I graduated with a degree in Master of Science in Geology from the University of Zurich In 1993. In addition, I earned a Doctor of Natural Science in Geology from the Swiss Federal Institute of Technology, Zurich, Switzerland.
2. I am a Professional Geoscientist in good standing in the Province of British Columbia in the areas of mining geology and exploration.
3. I have worked as a geologist for a total of fourteen years since my graduation from the University of Zurich.
4. I have read the definition of qualified person set out in National Instrument 43-101 (NI 43- 101) and certify that by reason of my education, affiliation with a professional association (as defined in NI 43-101) and past relevant work experience, I fulfill the requirements to be a qualified person for the purposes of the NI 43-101.
5. I am currently employed as Senior Vice President of Exploration and Geology for Pan American Silver Corp. and, by reason of my employment, am not independent of Pan American Silver Corp. as described in section 1.4 of NI 43-101.
6. Pan American Silver Corp. is a producing issuer as defined in NI 43-101.
7. I visited the San Vicente mine site from January 21, 2007 to January 23, 2007. I am responsible for the sections 1, 2, 3, 4, 9, 10, 11, 12, 13, 14, 15, 16, 17, 19, 20, 21, 22, 23 and 24 of the report entitled Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia dated effective June 6, 2007 (the Technical Report) and for the Figures 1-1, 1-2, 1-3, 1-4b, 1-7, 1-8,1-11, and 1-12 of the Technical Report.
8. I am co-author of the Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia.
9. I have read NI 43-101 and the Technical Report has been prepared in compliance with NI 43-101.
10. As of the date of this certificate, to the best of my knowledge, information and belief, the Technical Report contains all scientific and technical information that is required to be disclosed to make the Technical Report not misleading.

Dated the 20th day of July, 2007.

(SEAL)

Signature and seal of Qualified Person
Michael Steinmann, P.Geo., Ph.D.
Print Name of Qualified Person

CONSENT OF QUALIFIED PERSON

TO: British Columbia Securities Commission
Alberta Securities Commission
Saskatchewan Financial Services Commission
The Manitoba Securities Commission
Ontario Securities Commission
Autorité des marchés financiers
New Brunswick Securities Commission
Securities Commission of Newfoundland & Labrador
Nova Scotia Securities Commission
Registrar of Securities, Prince Edward Island
Government of Northwest Territories, Department of Justice, Securities Registry
Nunavut Legal Registries
Registrar of Securities, Government of the Yukon Territory

I, Dr. Michael Steinmann, P.Geo., Ph.D., do hereby consent to the filing, with the regulatory authorities referred to above, of the technical report titled Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia dated effective June 6, 2007 (the Technical Report) and to extracts from, or a summary of, the Technical Report in Pan American Silver Corp. s news release dated June 6, 2007 and material change report dated June 6, 2007, as updated by Pan American Silver Corp. s news release dated July 20, 2007 (collectively, the Written Disclosure). I hereby confirm that I have read the Written Disclosure and the Written Disclosure fairly and accurately represents the information in the Technical Report that supports the Written Disclosure.

Dated the 20 day of July, 2007.

(SEAL)

Signature and seal of Qualified Person

Michael Steinmann, P.Geo., Ph.D.

Print Name of Qualified Person

CERTIFICATE OF QUALIFIED PERSON

I, Martin Wafforn, P.Eng, of Pan American Silver Corp., 1500-625 Howe St., Vancouver, British Columbia, Canada V6C 2T6, do hereby certify that:

1. I graduated with a degree in Bachelor's of Science in Mining from Camborne School of Mines in Cornwall, England in 1980.
2. I am a Professional Engineer in good standing in the Province of British Columbia in the areas of Mining engineering. I am a Chartered Engineer in good standing in the United Kingdom.
3. I am currently employed as Vice President of Mine Engineering for Pan American Silver Corp. and, by reason of my employment, am not independent of Pan American Silver Corp. as described in section 1.4 of NI 43-101.
4. I have worked as an engineer in the mining industry for a total of twenty six years since my graduation from Camborne School of Mines.
5. I have read the definition of "qualified person" set out in National Instrument 43-101 (NI 43-101) and certify that by reason of my education, affiliation with a professional association (as defined in NI 43-101) and past relevant work experience, I fulfill the requirements to be a "qualified person" for the purposes of NI 43-101.
6. Pan American Silver Corp. is a "Producing Issuer" as defined in NI 43-101.
7. I visited the San Vicente mine site from January 21, 2007 to January 23, 2007. I am responsible for the sections 1, 2, 3, 4, 5, 6, 7, 8, 19, 20, 21, 22, 23, 24 and 25 of the report entitled "Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia" dated effective June 6, 2007 (the "Technical Report") and for the Figures 1-4, 1-4a, 1-5 and 1-6 of the Technical Report.
8. I am co-author of the Technical Report dated June 6th, 2007.
9. I have read NI 43-101 and the Technical Report has been prepared in compliance with NI 43-101.
10. As of the date of this certificate, to the best of my knowledge, information and belief, the Technical Report contains all scientific and technical information that is required to be disclosed to make the Technical Report not misleading.

Dated the 20 day of July, 2007.

(SEAL)
Reg. No. 22636

Signature and Seal of Qualified Person

Martin G. Wafforn, P.Eng.

CONSENT of QUALIFIED PERSON

TO: British Columbia Securities Commission
Alberta Securities Commission
Saskatchewan Financial Services Commission
The Manitoba Securities Commission
Ontario Securities Commission
Autorité des marchés financiers
New Brunswick Securities Commission
Securities Commission of Newfoundland & Labrador
Nova Scotia Securities Commission
Registrar of Securities, Prince Edward Island
Government of the Northwest Territories, Department of Justice, Securities Registry
Nunavut Legal Registries
Registrar of Securities, Government of the Yukon Territories

I, Martin Wafforn P.Eng. do hereby consent to the filing, with the regulatory authorities referred to above, of the technical report titled Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia dated effective June 6, 2007 (the Technical Report) and to extracts from, or a summary of, the Technical Report in Pan American Silver Corp. s news release dated June 6, 2007, as updated by Pan American Silver Corp. s news release dated July 20, 2007 (collectively the Written Disclosure).

I hereby confirm that I have read the Written Disclosure and the Written Disclosure fairly and accurately represents the information in the Technical Report that supports the Written Disclosure.

Dated the 20 day of July, 2007.

(SEAL)
Reg. No. 22636

Signature and seal of Qualified Person

Martin Wafforn P. Eng.

Print name of Qualified Person

CERTIFICATE OF QUALIFIED PERSON

I, Douglas K. Maxwell, of Lyntek Inc., 775 Mariposa Street, Denver CO 80204, do hereby certify that:

1. I graduated from the Colorado School of Mines with a Bachelor of Science Degree in Metallurgical Engineering in 1979 and with a Masters of Engineering in Metallurgy in 1982. In both programs I specialized in Mineral Processing and Extractive Metallurgy.
2. I am a Registered Professional Engineer Metallurgy in the State of Colorado. My registration number is 26758. I have been a member of the Extractive Metallurgy Chapter of Denver for 15 years.
3. I have worked in the mineral processing industry for over 20 years.
4. I am currently employed as Process Engineer by Lyntek Inc.
5. I have read the definition of qualified person set out in National Instrument 43-101 (NI 43-101) and certify that by reason of my education, affiliation with a professional association (as defined in NI 43-101) and past relevant work experience, I fulfill the requirements to be a qualified person for the purposes of the NI 43-101.
6. I am independent of Pan American Silver Corp. as described in section 1.4 of NI 43-101.
7. I am responsible for the sections in the report entitled Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia dated effective June 6, 2007 (the Technical Report) relating to mineral processing and metallurgical testing, as well as process design, capital cost estimates for the plant and infrastructure, and operating cost estimates for the plant and for sections 18 and 25 and Figures 1-9 and 1-10 of this Technical Report, I have not visited the San Vicente mine site.
8. I have read NI 43-101 and the Technical Report as has been prepared in compliance with NI 43-101.
9. I have not had any prior involvement with the San Vicente mine property.
10. As of the date of this certificate, to the best of my knowledge, information and belief, the Technical Report contains all scientific and technical information that is required to be disclosed to make the Technical Report not misleading.

Dated the 20th day of July, 2007.

(SEAL)

Signature and seal of Qualified Person

Douglas K. Maxwell P.E.

Print name of Qualified Person

CONSENT of QUALIFIED PERSON

TO: British Columbia Securities Commission
Alberta Securities Commission
Saskatchewan Financial Services Commission
The Manitoba Securities Commission
Ontario Securities Commission
Autorité des marchés financiers
New Brunswick Securities Commission
Securities Commission of Newfoundland & Labrador
Nova Scotia Securities Commission
Registrar of Securities, Prince Edward Island
Government of the Northwest Territories, Department of Justice, Securities Registry
Nunavut Legal Registries
Registrar of Securities, Government of the Yukon Territories

I, Douglas K. Maxwell, P. E. do hereby consent to the filing, with the regulatory authorities referred to above, of the technical report titled "Technical Report for the San Vicente Mine Expansion Project, Potosi, Bolivia" dated effective June 6, 2007 (the "Technical Report") and to extracts from, or a summary of, the Technical Report in Pan American Silver Corp.'s news release dated June 6, 2007, as updated by Pan American Silver Corp.'s news release dated July 20, 2007 (collectively the "Written Disclosure").

I hereby confirm that I have read the Written Disclosure and the Written Disclosure fairly and accurately represents the information in the Technical Report that supports the Written Disclosure.

Dated the 20th day of July, 2007.

(SEAL)

Signature and seal of Qualified Person

Douglas K. Maxwell, P.E.

Print name of Qualified Person

**Technical Report for the
San Vicente Mine
Potosi Bolivia
Appendix B
Diamond Drill Hole Intercepts**

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu%	Pb%	Zn%
Clavo	DDH-99-001	7,987	7,645	4,440	205.13	31°	-45°		35.44				
	DDH-99-001							35.44	36.11	6.1	0.00	0.02	0.10
	DDH-99-001							36.11	87.27				
	DDH-99-001							87.27	87.49	0.2	0.00	0.01	0.01
	DDH-99-001							87.49	87.66	2	0.00	0.02	0.08
	DDH-99-001							87.66	88.58	1	0.00	0.01	0.04
	DDH-99-001							88.58	89.26	2.6	0.00	0.02	0.05
	DDH-99-001							89.26	89.48	2	0.00	0.01	0.03
	DDH-99-001							89.48	92.01				
	DDH-99-001							92.01	92.35	0.7	0.00	0.01	0.05
	DDH-99-001							92.35	93.75				
	DDH-99-001							93.75	94.09	3.2	0.00	0.01	0.01
	DDH-99-001							94.09	94.31	352.2	0.13	0.07	0.07
	DDH-99-001							94.31	94.95	256.4	0.11	1.25	0.42
	DDH-99-001							94.95	122.63				
	DDH-99-001							122.63	122.84	35.9	0.03	0.01	0.07
	DDH-99-001							122.84	127.98				
	DDH-99-001							127.98	128.23	4	0.00	0.02	0.06
	DDH-99-001							128.23	128.76				
	DDH-99-001							128.76	128.93	3.6	0.00	0.01	0.05
	DDH-99-001							128.93	135.12				
	DDH-99-001							135.12	135.36	191.7	0.02	0.02	0.08
	DDH-99-001							135.36	153.71				
	DDH-99-001							153.71	154.21	81.6	0.04	0.05	0.11
	DDH-99-001							154.21	155.66				
	DDH-99-001							155.66	156.36	131.3	0.08	0.12	0.08
	DDH-99-001							156.36	156.97	179.5	0.11	0.12	0.10
	DDH-99-001							156.97	157.47	199.4	0.12	0.12	0.13
	DDH-99-001							157.47	157.97	125.6	0.07	0.04	0.07
	DDH-99-001							157.97	158.47	166.4	0.09	0.08	0.12
	DDH-99-001							158.47	158.94	98	0.06	0.11	0.15
	DDH-99-001							158.94	159.49	129.5	0.09	0.04	0.13
	DDH-99-001							159.49	159.92	77.5	0.06	0.03	0.10
	DDH-99-001							159.92	160.42	78.9	0.06	0.05	0.11
	DDH-99-001							160.42	160.72				
	DDH-99-001							160.72	161.27	38.3	0.04	0.02	0.07
	DDH-99-001							161.27	163.46				
	DDH-99-001							163.46	163.67	210	0.17	0.02	0.14
	DDH-99-001							163.67	166.60				
	DDH-99-001							166.60	167.70	42.1	0.04	0.03	0.11
	DDH-99-001							167.70	178.50				
	DDH-99-001							178.50	179.03	119.7	0.07	0.08	0.96
	DDH-99-001							179.03	179.91				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-001						179.91	180.43	30.5	0.02	0.02	0.06
DDH-99-001						180.43	180.75	19.4	0.01	0.01	0.02
DDH-99-001						180.75	181.21	17.6	0.01	0.01	0.04
DDH-99-001						181.21	181.65	14.6	0.00	0.01	0.03
DDH-99-001						181.65	182.15	25	0.01	0.02	0.03
DDH-99-001						182.15	182.64	44	0.02	0.05	0.08
DDH-99-001						182.64	183.14	66.6	0.04	0.04	0.08
DDH-99-001						183.14	183.64	140.8	0.08	0.07	0.15
DDH-99-001						183.64	184.14	84.9	0.04	0.03	0.05
DDH-99-001						184.14	184.44	66.4	0.03	0.03	0.02
DDH-99-001						184.44	184.82	85.1	0.05	0.06	0.07
DDH-99-001						184.82	185.22	61.1	0.04	0.03	0.05
DDH-99-001						185.22	185.55	74.2	0.04	0.03	0.05
DDH-99-001						185.55	186.02	19.9	0.01	0.01	0.03
DDH-99-001						186.02	186.46	51.8	0.03	0.02	0.03
DDH-99-001						186.46	186.86	16.4	0.01	0.01	0.02
DDH-99-001						186.86	187.15	19.7	0.01	0.01	0.02
DDH-99-001						187.15	187.75	15.3	0.01	0.01	0.02
DDH-99-001						187.75	188.25	27.4	0.01	0.02	0.03
DDH-99-001						188.25	188.74	114.6	0.05	0.02	0.12
DDH-99-001						188.74	189.57	8.4	0.00	0.01	0.02
DDH-99-001						189.57	190.00	345.7	0.17	0.01	0.06
DDH-99-001						190.50	191.01	83.7	0.04	0.01	0.04
DDH-99-001						191.01	192.56				
DDH-99-001						192.56	192.94	13.4	0.00	0.02	0.05
DDH-99-001						192.94	193.30	64	0.02	0.03	0.04
DDH-99-001						193.30	193.70	33.9	0.01	0.03	0.03
DDH-99-001						193.70	194.12	59.5	0.03	0.02	0.03
DDH-99-001						194.12	194.67	19.2	0.01	0.03	0.03
DDH-99-001						194.67	205.13				
E DDH-99-002	7,658	7,645,624	4,423	214.00	7° -48°			3.96			
DDH-99-002						3.96	4.36	43.9	0.00	0.07	0.01
DDH-99-002						4.36	41.14				
DDH-99-002						41.14	41.49	28.2	0.01	0.01	0.49
DDH-99-002						41.49	53.43				
DDH-99-002						53.43	53.93	5.4	0.00	0.02	0.36
DDH-99-002						53.93	54.31	20.9	0.01	0.09	0.37
DDH-99-002						54.31	54.84	25	0.01	0.12	0.34
DDH-99-002						54.84	55.18	14.1	0.01	0.02	0.37
DDH-99-002						55.18	57.50				
DDH-99-002						57.50	58.79	15.5	0.01	0.08	0.62
DDH-99-002						58.79	59.27				
DDH-99-002						59.27	59.76	58.4	0.07	0.63	0.72
DDH-99-002						59.76	60.48				

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	HOLE N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-99-002							60.48	61.47	29.8	0.01	0.05	0.52
	DDH-99-002							61.47	72.98				
	DDH-99-002							72.98	73.24	3.9	0.00	0.01	0.31
	DDH-99-002							73.24	74.06	14	0.01	0.02	0.46
	DDH-99-002							74.06	75.14	15.2	0.00	0.02	0.39
	DDH-99-002							75.14	75.34	3	0.00	0.02	0.28
	DDH-99-002							75.34	87.65				
	DDH-99-002							87.65	88.25	35.1	0.01	0.01	0.17
	DDH-99-002							88.25	89.30				
	DDH-99-002							89.30	89.92	104.6	0.01	0.02	0.23
	DDH-99-002							89.92	90.12				
	DDH-99-002							90.12	90.66	56.9	0.00	0.01	0.10
	DDH-99-002							90.66	91.26				
	DDH-99-002							91.26	91.54	19.9	0.01	0.01	0.12
	DDH-99-002							91.54	91.79	46.8	0.01	0.01	0.22
	DDH-99-002							91.79	92.29	51.4	0.00	0.01	0.16
	DDH-99-002							92.29	92.55				
	DDH-99-002							92.55	92.90	13.3	0.00	0.01	0.18
	DDH-99-002							92.90	93.50				
	DDH-99-002							93.50	94.00	39.1	0.00	0.01	0.08
	DDH-99-002							94.00	192.14				
	DDH-99-002							192.14	192.44	25.9	0.01	0.03	0.37
	DDH-99-002							192.44	192.94	44.4	0.02	0.02	0.42
	DDH-99-002							192.94	194.04	9.6	0.00	0.04	0.43
	DDH-99-002							194.04	194.34	5.7	0.00	0.02	0.44
	DDH-99-002							194.34	213.97				
Lipeña	DDH-99-003	936	7,646,119	4,571	171.60	20°	-48°		70.07				
	DDH-99-003							70.07	70.25	5.9	0.01	0.02	0.24
	DDH-99-003							70.25	71.51				
	DDH-99-003							71.51	71.72	21.3	0.00	0.27	0.27
	DDH-99-003							71.72	102.00				
	DDH-99-003							102.00	102.26	0.5	0.00	0.04	0.13
	DDH-99-003							102.26	102.56	40.3	0.01	0.17	2.88
	DDH-99-003							102.56	102.77	22	0.00	0.32	0.15
	DDH-99-003							102.77	102.97	45.9	0.01	0.16	0.63
	DDH-99-003							102.97	103.17				
	DDH-99-003							103.17	103.68	62	0.01	0.08	0.39
	DDH-99-003							103.68	154.31				
	DDH-99-003							154.31	154.54	281.5	0.05	0.88	0.71
	DDH-99-003							154.54	171.60				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Desconocido	DDH-99-004	7,792	7,646,151	4,604	241.71	205°	-45°		19.60					
	DDH-99-004								19.60	20.06	17	0.01	0.06	0.54
	DDH-99-004								20.06	63.27				
	DDH-99-004								63.27	63.45	668.9	0.08	0.04	0.06
	DDH-99-004								63.45	95.90				
	DDH-99-004								95.90	96.24	16.9	0.00	0.06	0.44
	DDH-99-004								96.24	165.50				
	DDH-99-004								165.50	165.92	4	0.02	0.18	0.02
	DDH-99-004								165.92	166.24	511.5	0.05	0.17	0.03
	DDH-99-004								166.24	166.66	56.7	0.01	0.05	0.00
	DDH-99-004								166.66	166.98	36.8	0.05	0.03	0.01
	DDH-99-004								166.98	167.63	110.8	0.02	0.04	0.01
	DDH-99-004								167.63	168.11	132.1	0.06	0.09	0.02
	DDH-99-004								168.11	169.55				
	DDH-99-004								169.55	169.98	18.8	0.01	0.03	0.02
	DDH-99-004								169.98	199.73				
	DDH-99-004								199.73	199.98	9.5	0.00	0.09	0.29
	DDH-99-004								199.98	241.71				
D	DDH-99-005	4,453	7,646,045	4,546	171.60	220°	-58°		157.56					
	DDH-99-005								157.56	158.44	67.9	0.02	0.05	0.15
	DDH-99-005								158.44	159.91				
	DDH-99-005								159.91	160.25	3.2	0.00	0.03	0.13
	DDH-99-005								160.25	160.65	7.2	0.00	0.04	0.10
	DDH-99-005								160.65	171.60				
G	DDH-99-006	3,322	7,645,736	4,448	186.84	11°	-47°		113.89					
	DDH-99-006								113.89	114.29	0.4	0.00	0.01	0.03
	DDH-99-006								114.29	114.99				
	DDH-99-006								114.99	115.24	1	0.00	0.02	0.02
	DDH-99-006								115.24	115.51	35.4	0.02	0.21	2.45
	DDH-99-006								115.51	115.95	18.1	0.02	0.19	0.42
	DDH-99-006								115.95	119.78				
	DDH-99-006								119.78	119.89	1.1	0.00	0.01	0.06
	DDH-99-006								119.89	132.38				
	DDH-99-006								132.38	133.02	2.9	0.00	0.05	0.03
	DDH-99-006								133.02	186.84				
Guernica	DDH-99-007	3,385	7,645,641	4,447	253.90	220°	-53°		67.32					
	DDH-99-007								67.32	67.44	1.9	0.02	0.01	0.05
	DDH-99-007								67.44	77.51				
	DDH-99-007								77.51	77.80	2	0.00	0.00	0.07
	DDH-99-007								77.80	102.00				
	DDH-99-007								102.00	102.57	0	0.00	0.00	0.05
	DDH-99-007								102.57	121.49				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole		Collar Co-ordinates			Interval Orientation			Assay Results					
Identification													
HOLE									Ag				
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	(g/t)	Cu %	Pb %	Zn %
DDH-99-007								121.49	121.86	6	0.01	0.00	0.06
DDH-99-007								121.86	123.43				
DDH-99-007								123.43	123.78	4.9	0.01	0.00	0.05
DDH-99-007								123.78	123.96	7.4	0.02	0.00	0.05
DDH-99-007								123.96	124.44	16.1	0.04	0.01	0.07
DDH-99-007								124.44	125.88				
DDH-99-007								125.88	126.46	23.6	0.19	0.01	0.06
DDH-99-007								126.46	126.56	6.1	0.01	0.00	0.06
DDH-99-007								126.56	126.96				
DDH-99-007								126.96	127.55	5.5	0.01	0.01	0.04
DDH-99-007								127.55	127.75				
DDH-99-007								127.75	128.01	2.8	0.00	0.01	0.03
DDH-99-007								128.01	129.93				
DDH-99-007								129.93	130.04	5.4	0.02	0.01	0.05
DDH-99-007								130.04	130.63				
DDH-99-007								130.63	130.74	5.3	0.01	0.00	0.06
DDH-99-007								130.74	130.84				
DDH-99-007								130.84	131.16	3.7	0.03	0.00	0.05
DDH-99-007								131.16	131.98				
DDH-99-007								131.98	132.12	10.3	0.07	0.01	0.06
DDH-99-007								132.12	133.30				
DDH-99-007								133.30	133.68	1.2	0.00	0.00	0.03
DDH-99-007								133.68	152.27				
DDH-99-007								152.27	152.42	3.2	0.00	0.01	0.01
DDH-99-007								152.42	152.60	0.3	0.00	0.01	0.00
DDH-99-007								152.60	153.16	12.4	0.00	0.06	1.05
DDH-99-007								153.16	153.51	0.4	0.00	0.01	0.03
DDH-99-007								153.51	153.99	11.4	0.02	0.06	0.02
DDH-99-007								153.99	154.34	4.7	0.01	0.02	0.04
DDH-99-007								154.34	154.79	531.9	0.66	0.29	0.38
DDH-99-007								154.79	155.27	59.8	0.32	0.02	0.12
DDH-99-007								155.27	155.57	3.5	0.02	0.00	0.03
DDH-99-007								155.57	156.56				
DDH-99-007								156.56	156.94	4	0.01	0.00	0.05
DDH-99-007								156.94	157.26	0.5	0.00	0.00	0.03
DDH-99-007								157.26	157.76				
DDH-99-007								157.76	158.15	167.2	0.34	0.12	0.22
DDH-99-007								158.15	158.75				
DDH-99-007								158.75	159.16	2.1	0.00	0.01	0.03
DDH-99-007								159.16	159.81				
DDH-99-007								159.81	160.20	4.8	0.00	0.00	0.03
DDH-99-007								160.20	161.60				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-007						161.60	162.02	4.7	0.01	0.01	0.03
DDH-99-007						162.02	164.00				
DDH-99-007						164.00	164.53	13.3	0.07	0.05	0.06
DDH-99-007						164.53	169.15				
DDH-99-007						169.15	169.49	2.9	0.00	0.00	0.04
DDH-99-007						169.49	170.59				
DDH-99-007						170.59	170.89	2.2	0.02	0.02	0.04
DDH-99-007						170.89	171.29				
DDH-99-007						171.29	171.52	2.6	0.00	0.00	0.03
DDH-99-007						171.52	174.65				
DDH-99-007						174.65	174.90	1.1	0.00	0.00	0.03
DDH-99-007						174.90	210.38				
DDH-99-007						210.38	210.82	1.3	0.00	0.00	0.04
DDH-99-007						210.82	213.03				
DDH-99-007						213.03	213.20	1	0.00	0.00	0.05
DDH-99-007						213.20	213.68	1.4	0.00	0.00	0.05
DDH-99-007						213.68	216.47				
DDH-99-007						216.47	216.75	29.4	0.00	0.06	0.06
DDH-99-007						216.75	253.90				
DDH-99-008	7,648	7,646,190	4,571	147.22	200°	-45°	26.60				
DDH-99-008						26.60	26.82	941.6	0.04	0.52	0.32
DDH-99-008						26.82	27.16	26.8	0.00	0.20	0.07
DDH-99-008						27.16	37.24				
DDH-99-008						37.24	37.43	1	0.00	0.03	0.02
DDH-99-008						37.43	47.43				
DDH-99-008						47.43	47.70	3.4	0.00	0.01	0.52
DDH-99-008						47.70	51.18				
DDH-99-008						51.18	51.38	1	0.00	0.04	0.16
DDH-99-008						51.38	52.73				
DDH-99-008						52.73	52.90	5	0.00	0.11	0.53
DDH-99-008						52.90	53.23	1.3	0.00	0.07	0.23
DDH-99-008						53.23	58.68				
DDH-99-008						58.68	58.96	9	0.00	0.61	0.24
DDH-99-008						58.96	59.26	14.5	0.00	0.59	0.16
DDH-99-008						59.26	60.96				
DDH-99-008						60.96	61.21	19.6	0.01	0.27	0.30
DDH-99-008						61.21	61.38	36.7	0.01	0.87	0.32
DDH-99-008						61.38	61.60	10.9	0.00	0.34	0.12
DDH-99-008						61.60	61.90				
DDH-99-008						61.90	62.06	12.9	0.00	0.06	0.22
DDH-99-008						62.06	63.06				
DDH-99-008						63.06	63.16	17.1	0.00	0.04	0.36

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	HOLE N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-99-008							63.16	69.67				
	DDH-99-008							69.67	69.84	3.8	0.00	0.03	0.09
	DDH-99-008							69.84	82.64				
	DDH-99-008							82.64	82.90	337.3	0.01	0.74	0.07
	DDH-99-008							82.90	83.21	5.3	0.00	0.21	0.05
	DDH-99-008							83.21	83.51				
	DDH-99-008							83.51	83.81	902.5	0.06	0.47	0.08
	DDH-99-008							83.81	84.31				
	DDH-99-008							84.31	84.62	541.1	0.02	1.23	0.54
	DDH-99-008							84.62	100.50				
	DDH-99-008							100.50	100.70	111.4	0.02	0.02	0.08
	DDH-99-008							100.70	102.50				
	DDH-99-008							102.50	102.69	5.4	0.00	0.04	0.05
	DDH-99-008							102.69	103.69				
	DDH-99-008							103.69	103.78	13.3	0.00	0.02	0.36
	DDH-99-008							103.78	107.10				
	DDH-99-008							107.10	107.24	15.2	0.00	0.02	0.50
	DDH-99-008							107.24	110.24				
	DDH-99-008							110.24	110.45	2.6	0.00	0.06	0.10
	DDH-99-008							110.45	113.84				
	DDH-99-008							113.84	114.27	11.6	0.00	0.02	0.34
	DDH-99-008							114.27	114.55	40.4	0.01	0.02	0.46
	DDH-99-008							114.55	114.77	4.7	0.00	0.01	0.15
	DDH-99-008							114.77	117.14				
	DDH-99-008							117.14	117.30	34.4	0.00	0.02	0.18
	DDH-99-008							117.30	122.19				
	DDH-99-008							122.19	122.34	72.9	0.01	0.19	0.47
	DDH-99-008							122.34	124.38				
	DDH-99-008							124.38	124.72	4.1	0.00	0.07	0.03
	DDH-99-008							124.72	125.06	7.6	0.00	0.10	0.01
	DDH-99-008							125.06	125.50	2.9	0.00	0.07	0.02
	DDH-99-008							125.50	125.77	8.4	0.00	0.20	0.03
	DDH-99-008							125.77	126.17	9.9	0.00	0.20	0.02
	DDH-99-008							126.17	126.47	1.1	0.00	0.08	0.01
	DDH-99-008							126.47	126.87	4.2	0.00	0.04	0.02
	DDH-99-008							126.87	127.05	1.1	0.00	0.02	0.06
	DDH-99-008							127.05	127.51	1.8	0.00	0.03	0.05
	DDH-99-008							127.51	128.74				
	DDH-99-008							128.74	128.93	2.2	0.00	0.09	0.06
	DDH-99-008							128.93	129.68				
	DDH-99-008							129.68	129.91	0	0.00	0.04	0.24
	DDH-99-008							129.91	130.23	2	0.00	0.10	0.20

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

	DDH-99-008						130.23	130.63					
	DDH-99-008						130.63	131.09	0	0.00	0.05	0.08	
	DDH-99-008						131.09	138.32					
	DDH-99-008						138.32	138.59	0	0.00	0.00	0.08	
	DDH-99-008						138.59	147.22					
Desconocido	DDH-99-009	998	7,645,922	4,568	202.08	335°	-54°	3.55					
	DDH-99-009							3.55	20.3	0.01	0.07	0.01	
	DDH-99-009							3.96	4.45	3392	0.03	0.18	0.02
	DDH-99-009							4.45	4.86	18.1	0.02	0.08	0.10
	DDH-99-009							4.86	5.06	364.7	0.06	0.47	1.82
	DDH-99-009							5.06	5.47	3.5	0.00	0.05	0.10
	DDH-99-009							5.47	5.81	4.6	0.00	0.04	0.24
	DDH-99-009							5.81	6.17	12.2	0.01	0.07	0.54
	DDH-99-009							6.17	6.75	55.2	0.11	0.06	0.22
	DDH-99-009							6.75	7.11	59.3	0.02	0.03	0.43
	DDH-99-009							7.11	7.41	10.2	0.01	0.01	0.13
	DDH-99-009							7.41	7.86	7.1	0.00	0.02	0.07
	DDH-99-009							7.86	8.18	2.1	0.00	0.03	0.05
	DDH-99-009							8.18	8.48				
	DDH-99-009							8.48	8.68	22.8	0.02	0.07	0.42
	DDH-99-009							8.68	10.26				
	DDH-99-009							10.26	10.47	1.1	0.00	0.01	0.10
	DDH-99-009							10.47	11.27				
	DDH-99-009							11.27	11.76	2	0.00	0.01	0.08
	DDH-99-009							11.76	12.46				
	DDH-99-009							12.46	12.69	1	0.00	0.02	0.10
	DDH-99-009							12.69	13.11				
	DDH-99-009							13.11	13.47	2.5	0.00	0.01	0.05
	DDH-99-009							13.47	14.47				
	DDH-99-009							14.47	14.88	5.9	0.00	0.01	0.06
	DDH-99-009							14.88	15.93				
	DDH-99-009							15.93	16.15	4.5	0.00	0.01	0.08
	DDH-99-009							16.15	16.90				
	DDH-99-009							16.90	17.09	3.4	0.00	0.01	0.05
	DDH-99-009							17.09	17.39				
	DDH-99-009							17.39	17.49	5.4	0.00	0.01	0.04
	DDH-99-009							17.49	19.85				
	DDH-99-009							19.85	19.99	3.6	0.00	0.01	0.05
	DDH-99-009							19.99	43.04				
	DDH-99-009							43.04	43.16	0.2	0.00	0.00	0.03
	DDH-99-009							43.16	65.92				
	DDH-99-009							65.92	66.36	13.4	0.01	0.07	0.46

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	HOLE N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-99-009							66.36	66.91	9.3	0.00	0.04	0.29
	DDH-99-009							66.91	67.27	138.1	0.01	0.05	0.51
	DDH-99-009							67.27	67.55	26.6	0.00	0.06	0.53
	DDH-99-009							67.55	68.17	417	0.01	0.05	0.61
	DDH-99-009							68.17	68.82	8.8	0.00	0.04	0.17
	DDH-99-009							68.82	83.56				
	DDH-99-009							83.56	83.76	5.1	0.00	0.02	0.04
	DDH-99-009							83.76	84.96				
	DDH-99-009							84.96	85.10	0.5	0.00	0.02	0.31
	DDH-99-009							85.10	88.16				
	DDH-99-009							88.16	88.34	13.8	0.01	0.03	0.14
	DDH-99-009							88.34	88.68	0.7	0.00	0.02	0.04
	DDH-99-009							88.68	88.93	105.1	0.07	0.10	0.29
	DDH-99-009							88.93	100.20				
	DDH-99-009							100.20	100.72	6.3	0.00	0.02	0.36
	DDH-99-009							100.72	100.98	0.6	0.00	0.01	0.09
	DDH-99-009							100.98	104.70				
	DDH-99-009							104.70	105.02	36.8	0.02	0.04	0.38
	DDH-99-009							105.02	105.46	5.3	0.00	0.03	0.13
	DDH-99-009							105.46	118.39				
	DDH-99-009							118.39	118.75	0	0.00	0.01	0.08
	DDH-99-009							118.75	129.23				
	DDH-99-009							129.23	129.48	18	0.02	0.02	0.92
	DDH-99-009							129.48	148.72				
	DDH-99-009							148.72	148.89	0	0.00	0.02	0.05
	DDH-99-009							148.89	173.95				
	DDH-99-009							173.95	174.19	0.7	0.00	0.02	0.04
	DDH-99-009							174.19	189.79				
	DDH-99-009							189.79	190.09	0	0.00	0.01	0.04
	DDH-99-009							190.09	190.79				
	DDH-99-009							190.79	191.08	0	0.00	0.01	0.03
	DDH-99-009							191.08	202.08				
Brum	DDH-99-010	1,166	7,646,090	4,482	156.36	217°	-49°		14.31				
Mirid	DDH-99-010							14.31	14.55	0	0.00	0.01	0.02
	DDH-99-010							14.55	16.55				
	DDH-99-010							16.55	16.86	0	0.00	0.00	0.01
	DDH-99-010							16.86	25.90				
	DDH-99-010							25.90	26.07	0	0.00	0.00	0.02
	DDH-99-010							26.07	31.39				
	DDH-99-010							31.39	31.77	0	0.00	0.00	0.03
	DDH-99-010							31.77	32.27				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-010	32.27	32.63	0.4	0.00	0.01	0.03
DDH-99-010	32.63	33.01	0.5	0.00	0.01	0.04
DDH-99-010	33.01	33.51				
DDH-99-010	33.51	33.75	0	0.00	0.01	0.02
DDH-99-010	33.75	34.20				
DDH-99-010	34.20	34.43	0	0.00	0.01	0.02
DDH-99-010	34.43	37.84				
DDH-99-010	37.84	37.97	0.4	0.00	0.05	0.07
DDH-99-010	37.97	38.18				
DDH-99-010	38.18	38.29	0.5	0.00	0.01	0.04
DDH-99-010	38.29	41.29				
DDH-99-010	41.29	41.44	0.9	0.00	0.03	0.03
DDH-99-010	41.44	44.14				
DDH-99-010	44.14	44.44	0	0.00	0.00	0.03
DDH-99-010	44.44	44.79				
DDH-99-010	44.79	44.94	0.4	0.00	0.00	0.03
DDH-99-010	44.94	45.34				
DDH-99-010	45.34	45.55	0.6	0.00	0.00	0.08
DDH-99-010	45.55	47.08				
DDH-99-010	47.08	47.39	0.2	0.00	0.01	0.03
DDH-99-010	47.39	48.39				
DDH-99-010	48.39	48.51	0.3	0.00	0.01	0.03
DDH-99-010	48.51	49.21				
DDH-99-010	49.21	49.50	0.4	0.00	0.01	0.06
DDH-99-010	49.50	49.98				
DDH-99-010	49.98	50.43	0.3	0.00	0.01	0.02
DDH-99-010	50.43	50.83	2.9	0.02	0.05	0.06
DDH-99-010	50.83	60.38				
DDH-99-010	60.38	60.70	0	0.00	0.03	0.06
DDH-99-010	60.70	65.07				
DDH-99-010	65.07	65.63	1.4	0.00	0.01	0.05
DDH-99-010	65.63	66.38				
DDH-99-010	66.38	66.72	0.4	0.00	0.02	0.03
DDH-99-010	66.72	67.07				
DDH-99-010	67.07	67.24	0	0.00	0.01	0.03
DDH-99-010	67.24	71.02				
DDH-99-010	71.02	71.48	0	0.00	0.02	0.06
DDH-99-010	71.48	77.11				
DDH-99-010	77.11	77.30	0.9	0.00	0.03	0.05
DDH-99-010	77.30	79.82				
DDH-99-010	79.82	80.16	0	0.00	0.01	0.03
DDH-99-010	80.16	80.58	0	0.00	0.01	0.03
DDH-99-010	80.58	81.17	0	0.00	0.01	0.03

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-011	93.84	105.04					
DDH-99-011	105.04	105.34	7.9	0.00	0.02	0.33	
DDH-99-011	105.34	105.92	73.3	0.04	0.06	1.79	
DDH-99-011	105.92	106.36	25.7	0.01	0.11	0.84	
DDH-99-011	106.36	106.76	97	0.06	0.23	6.40	
DDH-99-011	106.76	106.98	13.5	0.00	0.03	0.23	
DDH-99-011	106.98	108.85					
DDH-99-011	108.85	109.06	5	0.00	0.03	0.30	
DDH-99-011	109.06	159.41					
DDH-99-011	159.41	159.71	11	0.01	0.01	0.45	
DDH-99-011	159.71	160.46	21.6	0.03	0.09	3.68	
DDH-99-011	160.46	160.81	10.3	0.05	0.05	0.31	
DDH-99-011	160.81	171.60					

6 de

Ago	DDH-99-012	7,041	7,645,329	4,493	245.36	203°	-67°	69.93											
DDH-99-012	69.93	70.60	1.7	0.00	0.01	0.18													
DDH-99-012	70.60	71.16	2.6	0.00	0.01	0.17													
DDH-99-012	71.16	78.02																	
DDH-99-012	78.02	78.37	2.9	0.00	0.01	0.28													
DDH-99-012	78.37	78.62																	
DDH-99-012	78.62	79.28	3.2	0.00	0.00	0.17													
DDH-99-012	79.28	88.77																	
DDH-99-012	88.77	89.41	1.3	0.00	0.01	0.21													
DDH-99-012	89.41	94.46																	
DDH-99-012	94.46	95.40	8.5	0.03	0.01	0.25													
DDH-99-012	95.40	95.68	257	0.21	0.03	4.70													
DDH-99-012	95.68	96.37	3.4	0.00	0.01	0.16													
DDH-99-012	96.37	96.86	4.6	0.00	0.03	0.20													
DDH-99-012	96.86	97.46	85	0.08	0.02	4.19													
DDH-99-012	97.46	97.93	152	0.14	0.03	6.56													
DDH-99-012	97.93	98.17	12	0.01	0.01	1.08													
DDH-99-012	98.17	98.56	7.2	0.01	0.01	0.35													
DDH-99-012	98.56	99.37	115	0.13	0.10	1.95													
DDH-99-012	99.37	99.66	92.2	0.11	0.03	4.78													
DDH-99-012	99.66	100.47	30.8	0.03	0.01	0.38													
DDH-99-012	100.47	100.98	711	0.47	0.60	15.90													
DDH-99-012	100.98	101.51	1621	0.31	0.36	3.35													
DDH-99-012	101.51	102.05	18	0.04	0.03	0.29													
DDH-99-012	102.05	102.57	11.3	0.02	0.01	0.65													
DDH-99-012	102.57	102.87	5	0.01	0.01	0.15													
DDH-99-012	102.87	103.47																	
DDH-99-012	103.47	103.73	35.8	0.05	0.06	1.58													
DDH-99-012	103.73	105.16																	
DDH-99-012	105.16	106.12	2.2	0.00	0.07	0.31													
DDH-99-012	106.12	106.46	6.8	0.01	0.02	1.84													

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	HOLE N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-99-012							106.46	106.56				
	DDH-99-012							106.56	106.96	3.3	0.00	0.12	0.55
	DDH-99-012							106.96	107.46				
	DDH-99-012							107.46	107.64	5.7	0.01	0.02	1.20
	DDH-99-012							107.64	159.32				
	DDH-99-012							159.32	159.54	2.7	0.01	0.01	0.50
	DDH-99-012							159.54	160.37				
	DDH-99-012							160.37	160.56	0.2	0.00	0.01	0.13
	DDH-99-012							160.56	245.36				
Lit	DDH-99-013	7,686	7,644,905	4,473	236.80	5°	-57°		67.37				
	DDH-99-013							67.37	68.17	0	0.00	0.01	0.02
	DDH-99-013							68.17	68.78	0.4	0.00	0.02	0.03
	DDH-99-013							68.78	69.03	0.3	0.00	0.02	0.08
	DDH-99-013							69.03	69.84	0.3	0.00	0.00	0.02
	DDH-99-013							69.84	70.65	0	0.00	0.00	0.02
	DDH-99-013							70.65	71.45	0	0.00	0.00	0.01
	DDH-99-013							71.45	72.25	0	0.00	0.01	0.02
	DDH-99-013							72.25	73.05	0	0.00	0.00	0.02
	DDH-99-013							73.05	73.85	0	0.00	0.00	0.02
	DDH-99-013							73.85	74.70	0	0.00	0.00	0.01
	DDH-99-013							74.70	89.90				
	DDH-99-013							89.90	90.28	0	0.00	0.00	0.01
	DDH-99-013							90.28	91.48				
	DDH-99-013							91.48	92.02	0	0.00	0.00	0.05
	DDH-99-013							92.02	92.65				
	DDH-99-013							92.65	93.39	0	0.00	0.00	0.03
	DDH-99-013							93.39	94.19	0	0.00	0.00	0.02
	DDH-99-013							94.19	94.89	0	0.00	0.00	0.02
	DDH-99-013							94.89	101.25				
	DDH-99-013							101.25	101.46	0	0.00	0.00	0.01
	DDH-99-013							101.46	108.60				
	DDH-99-013							108.60	109.64	0.5	0.00	0.00	0.04
	DDH-99-013							109.64	117.24				
	DDH-99-013							117.24	117.94	0.8	0.00	0.00	0.01
	DDH-99-013							117.94	118.89	4.3	0.01	0.01	1.37
	DDH-99-013							118.89	119.73	0.6	0.01	0.00	0.01
	DDH-99-013							119.73	120.40	1.9	0.02	0.00	0.01
	DDH-99-013							120.40	120.67	11.3	0.24	0.01	0.06
	DDH-99-013							120.67	121.22	1.3	0.02	0.00	0.02
	DDH-99-013							121.22	121.82	0.5	0.01	0.00	0.01
	DDH-99-013							121.82	123.68				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-013							123.68	124.32	0	0.01	0.00	0.01
DDH-99-013							124.32	124.52				
DDH-99-013							124.52	124.87	0.4	0.01	0.00	0.01
DDH-99-013							124.87	125.37				
DDH-99-013							125.37	125.83	0.7	0.01	0.00	0.01
DDH-99-013							125.83	126.06	2	0.01	0.00	0.02
DDH-99-013							126.06	126.50	0.7	0.00	0.00	0.01
DDH-99-013							126.50	126.89	2.3	0.02	0.00	0.03
DDH-99-013							126.89	127.19				
DDH-99-013							127.19	127.49	0.4	0.00	0.00	0.02
DDH-99-013							127.49	167.00				
DDH-99-013							167.00	167.38	2.2	0.09	0.00	0.03
DDH-99-013							167.38	167.86	42.5	0.74	0.02	0.05
DDH-99-013							167.86	168.37	2.3	0.03	0.00	0.02
DDH-99-013							168.37	169.45				
DDH-99-013							169.45	169.71	0.5	0.00	0.00	0.01
DDH-99-013							169.71	169.97	0.7	0.00	0.00	0.01
DDH-99-013							169.97	170.78	1.6	0.00	0.00	0.01
DDH-99-013							170.78	171.21	2.4	0.01	0.00	0.02
DDH-99-013							171.21	172.75				
DDH-99-013							172.75	173.00	1.3	0.00	0.00	0.01
DDH-99-013							173.00	173.20				
DDH-99-013							173.20	173.55	1	0.00	0.00	0.01
DDH-99-013							173.55	173.92	11.2	0.29	0.03	0.12
DDH-99-013							173.92	174.31	2.4	0.01	0.01	0.04
DDH-99-013							174.31	177.80				
DDH-99-013							177.80	178.08	3.9	0.37	0.00	0.07
DDH-99-013							178.08	195.99				
Art DDH-99-013	103	7,644,881	4,497	180.75	213°	-59°		85.70				
Ramo												
Art DDH-99-014							85.70	86.26	4.4	0.36	0.00	0.07
DDH-99-014							86.26	87.29	1.1	0.00	0.00	0.07
DDH-99-014							87.29	87.59				
DDH-99-014							87.59	88.39	1.2	0.00	0.00	0.08
DDH-99-014							88.39	89.23	1.3	0.00	0.00	0.17
DDH-99-014							89.23	89.53	2.3	0.00	0.00	0.26
DDH-99-014							89.53	90.13	9	0.03	0.01	2.88
DDH-99-014							90.13	90.68	2.6	0.00	0.00	0.49
DDH-99-014							90.68	91.52	2	0.00	0.00	0.11
DDH-99-014							91.52	92.60	1.3	0.00	0.00	0.20
DDH-99-014							92.60	110.89				
DDH-99-014							110.89	111.17	3.6	0.00	0.01	0.32
DDH-99-014							111.17	111.62				
DDH-99-014							111.62	112.11	0	0.00	0.00	0.22

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole		Collar Co-ordinates			Interval Orientation			Assay Results					
Identification	HOLE		Northing	Elevation	Length	Azimuth	Dip	From	To	Ag			
Vein	N°	Easting								(g/t)	Cu %	Pb %	Zn %
DDH-99-014								112.11	112.52	71.7	0.08	0.07	12.90
DDH-99-014								112.52	113.03	8.5	0.02	0.03	1.38
DDH-99-014								113.03	113.78	0.4	0.00	0.00	0.17
DDH-99-014								113.78	114.23				
DDH-99-014								114.23	114.69	0	0.00	0.00	0.15
DDH-99-014								114.69	114.97	2.6	0.00	0.00	0.47
DDH-99-014								114.97	115.59	1.3	0.00	0.00	0.25
DDH-99-014								115.59	115.98	1.7	0.00	0.00	0.61
DDH-99-014								115.98	116.93	1.6	0.00	0.00	0.68
DDH-99-014								116.93	117.63	4.4	0.01	0.01	1.06
DDH-99-014								117.63	118.17	4.3	0.01	0.01	0.56
DDH-99-014								118.17	118.38	98.8	0.63	0.02	3.24
DDH-99-014								118.38	119.37	0.9	0.00	0.00	0.20
DDH-99-014								119.37	124.23				
DDH-99-014								124.23	124.52	0.3	0.00	0.00	0.11
DDH-99-014								124.52	124.94	6.4	0.01	0.01	3.54
DDH-99-014								124.94	125.64	0.2	0.00	0.00	0.16
DDH-99-014								125.64	126.75	0.8	0.00	0.00	0.12
DDH-99-014								126.75	131.63				
DDH-99-014								131.63	132.08	0.7	0.00	0.00	0.11
DDH-99-014								132.08	146.47				
DDH-99-014								146.47	147.24	0.6	0.00	0.00	0.07
DDH-99-014								147.24	147.87	5.1	0.02	0.01	0.13
DDH-99-014								147.87	148.14	81.3	0.10	0.02	10.60
DDH-99-014								148.14	148.74	3.5	0.01	0.01	0.09
DDH-99-014								148.74	152.56				
DDH-99-014								152.56	152.83	3.6	0.01	0.02	0.09
DDH-99-014								152.83	154.16				
DDH-99-014								154.16	154.43	15	0.03	0.01	0.06
DDH-99-014								154.43	154.61	70	0.37	0.03	5.28
DDH-99-014								154.61	155.07	8.5	0.02	0.01	0.11
DDH-99-014								155.07	155.29	9.5	0.04	0.01	0.66
DDH-99-014								155.29	155.75	7.3	0.03	0.01	0.10
DDH-99-014								155.75	155.97	90	0.23	0.02	1.58
DDH-99-014								155.97	156.23	2.6	0.02	0.02	0.19
DDH-99-014								156.23	156.62	124	0.31	0.22	8.16
DDH-99-014								156.62	157.08	6	0.02	0.04	0.48
DDH-99-014								157.08	157.63				
DDH-99-014								157.63	158.36	3.1	0.01	0.02	0.25
DDH-99-014								158.36	158.87	11.9	0.03	0.02	1.00
DDH-99-014								158.87	159.68	3.4	0.01	0.00	16.42
DDH-99-014								159.68	160.32	11.8	0.02	0.02	0.90

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-014	160.32	160.66	16.1	0.04	0.05	4.46
DDH-99-014	160.66	160.98	13.7	0.02	0.02	0.49
DDH-99-014	160.98	161.65	196	0.23	0.18	22.04
DDH-99-014	161.65	162.25	166	0.20	0.18	13.10
DDH-99-014	162.25	162.83	2.6	0.01	0.02	0.12
DDH-99-014	162.83	163.56	1	0.00	0.01	0.07
DDH-99-014	163.56	164.01	4.4	0.01	0.01	0.11
DDH-99-014	164.01	165.15	22.6	0.04	0.01	0.56
DDH-99-014	165.15	166.15	4.6	0.01	0.00	0.18
DDH-99-014	166.15	166.94	27.7	0.05	0.01	7.36
DDH-99-014	166.94	167.86	4.5	0.01	0.00	0.12
DDH-99-014	167.86	180.75				

San													
Francisco	DDH-99-015	4,482	7,644,576	4,430	138.07	197	-53°	20.05					
	DDH-99-015							20.05	20.80	0	0.00	0.00	0.10
	DDH-99-015							20.80	21.78	0.9	0.00	0.00	0.15
	DDH-99-015							21.78	22.45	0.5	0.00	0.01	0.18
	DDH-99-015							22.45	59.03				
	DDH-99-015							59.03	59.28	0	0.00	0.00	0.06
	DDH-99-015							59.28	61.18				
	DDH-99-015							61.18	61.65	0	0.00	0.00	0.16
	DDH-99-015							61.65	69.07				
	DDH-99-015							69.07	69.52	0		0.01	0.08
	DDH-99-015							69.52	70.24	0		0.00	0.10
	DDH-99-015							70.24	70.81	0		0.00	0.10
	DDH-99-015							70.81	71.87	0		0.00	0.09
	DDH-99-015							71.87	72.83	0		0.00	0.09
	DDH-99-015							72.83	74.19	0		0.00	0.09
	DDH-99-015							74.19	98.30				
	DDH-99-015							98.30	98.58	0	0.02	0.00	0.07
	DDH-99-015							98.58	114.79				
	DDH-99-015							114.79	115.02	21.8	0.01	0.01	3.28
	DDH-99-015							115.02	115.49	2	0.00	0.01	0.23
	DDH-99-015							115.49	117.44				
	DDH-99-015							117.44	117.77	712	1.06	0.10	5.36
	DDH-99-015							117.77	118.20	21.1	0.06	0.01	2.30
	DDH-99-015							118.20	118.82	3.2	0.01	0.01	0.46
	DDH-99-015							118.82	119.56	6.6	0.02	0.00	2.12
	DDH-99-015							119.56	120.20	0.7	0.00	0.00	0.02
	DDH-99-015							120.20	138.07				

Chicago	DDH-99-016	4,579	7,643,365	4,437	159.42	193°	-45°	89.01					
	DDH-99-016							89.01	89.31	0	0.00	0.01	0.06
	DDH-99-016							89.31	91.21				
	DDH-99-016							91.21	91.43	0.3	0.00	0.01	0.14
	DDH-99-016							91.43	92.70				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-99-016								92.70	93.13	1.5	0.00	0.01	0.07
DDH-99-016								93.13	97.80				
DDH-99-016								97.80	98.13	0.4	0.00	0.01	0.06
DDH-99-016								98.13	104.00				
DDH-99-016								104.00	104.85	0	0.00	0.00	0.06
DDH-99-016								104.85	105.29	0	0.00	0.00	0.07
DDH-99-016								105.29	108.50				
DDH-99-016								108.50	108.79	0	0.00	0.00	0.04
DDH-99-016								108.79	126.23				
DDH-99-016								126.23	127.30	0.4	0.00	0.01	0.06
DDH-99-016								127.30	127.45				
DDH-99-016								127.45	127.68	1.1	0.00	0.00	0.02
DDH-99-016								127.68	128.18				
DDH-99-016								128.18	128.52	0.5	0.00	0.00	0.03
DDH-99-016								128.52	130.18				
DDH-99-016								130.18	130.76	1.3	0.01	0.02	0.06
DDH-99-016								130.76	136.18				
DDH-99-016								136.18	136.51	2.7	0.00	0.01	0.52
DDH-99-016								136.51	158.56				
DDH-99-016								158.56	158.94	3.2	0.01	0.00	0.23
DDH-99-016								158.94	159.41				
Litton Ramo	DDH-99-017	7,998	7,645,073	4,470	192.94	3°	-54°		105.65				
Litton Ramo	DDH-99-017							105.65	106.60	2.3	0.01	0.01	0.02
	DDH-99-017							106.60	106.75				
	DDH-99-017							106.75	107.71	0.9	0.00	0.01	0.01
	DDH-99-017							107.71	108.27	0.7	0.00	0.01	0.01
	DDH-99-017							108.27	108.83	0.5	0.00	0.01	0.02
	DDH-99-017							108.83	109.36	0.9	0.00	0.01	0.02
	DDH-99-017							109.36	119.74				
	DDH-99-017							119.74	119.89	0.6	0.00	0.02	0.06
	DDH-99-017							119.89	127.88				
	DDH-99-017							127.88	128.68	1	0.00	0.01	0.03
	DDH-99-017							128.68	132.58				
	DDH-99-017							132.58	133.58	1.1	0.00	0.04	0.11
	DDH-99-017							133.58	134.03	5.4	0.00	0.05	0.11
	DDH-99-017							134.03	135.06	1.8	0.00	0.01	0.03
	DDH-99-017							135.06	136.03	6.6	0.01	0.04	0.06
	DDH-99-017							136.03	136.96	3.3	0.00	0.02	0.05
	DDH-99-017							136.96	137.73	1.1	0.00	0.04	0.03
	DDH-99-017							137.73	138.32	1.1	0.00	0.00	0.02

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-017	138.32	138.80	0.8	0.00	0.00	0.02
DDH-99-017	138.80	139.71	1.1	0.00	0.01	0.02
DDH-99-017	139.71	140.67	0.4	0.00	0.01	0.03
DDH-99-017	140.67	141.57	0.5	0.00	0.01	0.03
DDH-99-017	141.57	142.49	0.7	0.00	0.00	0.02
DDH-99-017	142.49	143.08	1.4	0.00	0.00	0.04
DDH-99-017	143.08	143.68	1.9	0.00	0.00	0.38
DDH-99-017	143.68	144.11	0.7	0.00	0.00	0.11
DDH-99-017	144.11	144.66	4.8	0.01	0.00	0.78
DDH-99-017	144.66	145.55	1	0.00	0.00	0.02
DDH-99-017	145.55	146.17	1.1	0.00	0.00	0.01
DDH-99-017	146.17	147.09	1.2	0.01	0.01	0.02
DDH-99-017	147.09	147.88	2.4	0.06	0.01	0.04
DDH-99-017	147.88	148.65	2.3	0.09	0.01	0.06
DDH-99-017	148.65	149.10	277	1.77	0.05	0.64
DDH-99-017	149.10	149.63	46.1	0.19	0.01	0.61
DDH-99-017	149.63	150.20	230.2	1.03	0.03	1.92
DDH-99-017	150.20	150.61	145.5	0.37	0.02	0.33
DDH-99-017	150.61	150.96	867.9	0.35	0.09	7.56
DDH-99-017	150.96	151.48	993.8	0.35	0.02	1.84
DDH-99-017	151.48	152.40	3473.8	1.27	0.03	3.96
DDH-99-017	152.40	153.14	1230.9	2.47	0.01	1.28
DDH-99-017	153.14	153.54	57.1	1.23	0.01	0.12
DDH-99-017	153.54	154.00	5.2	0.01	0.00	0.02
DDH-99-017	154.00	154.56	2850.2	1.00	0.01	0.60
DDH-99-017	154.56	155.19	104.5	0.06	0.00	0.06
DDH-99-017	155.19	155.65	1966.1	0.51	0.01	0.34
DDH-99-017	155.65	156.31	606.1	0.23	0.01	0.58
DDH-99-017	156.31	157.04	11	0.01	0.01	1.07
DDH-99-017	157.04	157.96	2.3	0.00	0.00	0.13
DDH-99-017	157.96	158.88	1.1	0.00	0.00	0.01
DDH-99-017	158.88	159.81	2.1	0.00	0.00	0.01
DDH-99-017	159.81	160.73	6.7	0.00	0.01	0.00
DDH-99-017	160.73	161.01	3634.1	1.01	0.03	0.38
DDH-99-017	161.01	161.63	9.7	0.01	0.00	0.69
DDH-99-017	161.63	162.15	18.3	0.02	0.00	1.61
DDH-99-017	162.15	162.58	5.8	0.00	0.01	0.39
DDH-99-017	162.58	163.50	10.5	0.02	0.00	1.46
DDH-99-017	163.50	163.79	22	0.01	0.00	2.02
DDH-99-017	163.79	164.44	6	0.00	0.00	0.38
DDH-99-017	164.44	165.42	4	0.00	0.00	0.16
DDH-99-017	165.42	166.25	39.3	0.01	0.00	0.01
DDH-99-017	166.25	166.60	215.4	0.05	0.01	0.02
DDH-99-017	166.60	167.19	80.5	0.02	0.00	0.78
DDH-99-017	167.19	167.90	17	0.00	0.00	0.04
DDH-99-017	167.90	171.45				
DDH-99-017	171.45	171.74	0.9	0.00	0.00	0.01

Hole		Collar Co-ordinates			Interval Orientation			Assay Results					
Identification	Vein	N° Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
HOLE													
								171.74	172.00				
								172.00	172.67	2.3	0.00	0.00	0.00
								172.67	180.85				
								180.85	181.37	0.3	0.00	0.00	0.01
								181.37	183.79				
								183.79	184.61	0.8	0.00	0.00	0.01
								184.61	188.44				
								188.44	188.74	0.5	0.00	0.00	0.01
								188.74	192.51				
								192.51	192.94	0.8	0.00	0.00	0.01
H	DDH-99-018	7,935	7,646,117	4,411	159.41	156°	-60°		12.86				
	DDH-99-018							12.86	13.12	37.7	0.01	0.05	0.38
	DDH-99-018							13.12	27.70				
	DDH-99-018							27.70	28.12	14.1	0.01	0.03	0.12
	DDH-99-018							28.12	29.20				
	DDH-99-018							29.20	29.48	20.7	0.10	0.07	0.06
	DDH-99-018							29.48	125.63				
	DDH-99-018							125.63	126.23	286.2	0.02	0.07	0.57
	DDH-99-018							126.23	127.93				
	DDH-99-018							127.93	128.11	44.7	0.01	0.07	0.38
	DDH-99-018							128.11	159.41				
E	DDH-99-019	7,617	7,645,980	4,586	199.03	73°	-58°		4.06				
	DDH-99-019							4.06	4.46	0.7	0.00	0.01	0.06
	DDH-99-019							4.46	107.69				
	DDH-99-019							107.69	107.89	50.3	0.03	0.03	0.17
	DDH-99-019							107.89	119.54				
	DDH-99-019							119.54	119.79	28.7	0.01	0.05	0.66
	DDH-99-019							119.79	119.99				
	DDH-99-019							119.99	120.38	7.1	0.00	0.03	0.18
	DDH-99-019							120.38	140.02				
	DDH-99-019							140.02	141.44	13.4	0.00	0.02	0.45
	DDH-99-019							141.44	199.03				
Zona													
stockwork	DDH-99-020	7,067	7,646,273	4,426	168.55	28°	-50°		127.73				
	DDH-99-020							127.73	127.91	1.2	0.00	0.02	0.15
	DDH-99-020							127.91	142.77				
	DDH-99-020							142.77	142.93	0.5	0.00	0.02	0.11
	DDH-99-020							142.93	145.02				
	DDH-99-020							145.02	145.24	1	0.00	0.01	0.08

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-020				145.24	145.64						
DDH-99-020				145.64	145.99	0.4	0.00	0.01	0.06		
DDH-99-020				145.99	147.97						
DDH-99-020				147.97	148.70	0.5	0.00	0.01	0.08		
DDH-99-020				148.70	168.55						
6 de											
Agosto	DDH-99-021	3,333	7,645,147	4,541	67.97	218°	-90°		35.44		
	DDH-99-021				35.44	36.38	0.3	0.00	0.02	0.06	
	DDH-99-021				36.38	37.69					
	DDH-99-021				37.69	38.20	0.3	0.00	0.03	0.07	
	DDH-99-021				38.20	40.29					
	DDH-99-021				40.29	40.54	0.4	0.00	0.01	0.13	
	DDH-99-021				40.54	41.09					
	DDH-99-021				41.09	41.50	0.6	0.00	0.02	0.15	
	DDH-99-021				41.50	42.60					
	DDH-99-021				42.60	42.90	0.3	0.00	0.01	0.09	
	DDH-99-021				42.90	44.89					
	DDH-99-021				44.89	45.11	0	0.00	0.00	0.05	
	DDH-99-021				45.11	46.88					
	DDH-99-021				46.88	47.49	0.6	0.00	0.01	0.28	
	DDH-99-021				47.49	48.62					
	DDH-99-021				48.62	49.68	1.9	0.00	0.02	0.34	
	DDH-99-021				49.68	50.25	5.5	0.00	0.23	1.32	
	DDH-99-021				50.25	51.31	1.7	0.00	0.08	0.36	
	DDH-99-021				51.31	51.50	7.5	0.00	0.12	4.29	
	DDH-99-021				51.50	52.41	4.2	0.00	0.06	1.16	
	DDH-99-021				52.41	52.97	32.1	0.02	0.07	5.06	
	DDH-99-021				52.97	53.55	70.4	0.03	0.06	2.54	
	DDH-99-021				53.55	54.30	174.6	0.15	0.08	1.76	
	DDH-99-021				54.30	55.06	210.9	0.06	0.17	3.08	
	DDH-99-021				55.06	55.58	354.8	0.13	0.16	4.77	
	DDH-99-021				55.58	56.10	270.4	0.23	0.15	5.52	
	DDH-99-021				56.10	58.83					
	DDH-99-021				58.83	59.49	129.4	0.09	0.08	2.28	
	DDH-99-021				59.49	60.19	369.8	0.37	0.08	9.94	
	DDH-99-021				60.19	60.57	56.5	0.09	0.03	1.86	
	DDH-99-021				60.57	60.84	4.5	0.01	0.02	0.65	
	DDH-99-021				60.84	61.08	9.4	0.01	0.07	2.17	
	DDH-99-021				61.08	61.57	1.2	0.00	0.02	0.32	
	DDH-99-021				61.57	62.32					
	DDH-99-021				62.32	62.51	1	0.00	0.01	0.04	
	DDH-99-021				62.51	63.46					
	DDH-99-021				63.46	64.05	5.7	0.01	0.05	0.48	
	DDH-99-021				64.05	64.51	3.6	0.01	0.03	0.88	
	DDH-99-021				64.51	64.92					
	DDH-99-021				64.92	65.60	1.7	0.00	0.02	0.43	
	DDH-99-021				65.60	66.45	2.1	0.01	0.01	0.34	

Hole Identification	Collar Co-ordinates	Interval Orientation			Assay Results							
Vein	N° Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
HOLE												
DDH-99-021							66.45	67.00				
DDH-99-021							67.00	67.20	3	0.01	0.01	0.23
DDH-99-021							67.20	67.49				
DDH-99-021							67.49	67.97	1.7	0.00	0.01	0.28
Ramo San José												
DDH-9101		4,368		310.00	210°	-18°		135.17				
DDH-9101							135.17	136.03	73	0.12	0.03	5.74
DDH-9101							136.03	239.54				
DDH-9101							239.54	240.34	9.8	0.05	0.01	0.51
DDH-9101							240.34	287.09				
DDH-9101							287.09	289.08	9.8	0.05	0.01	0.08
DDH-9101							289.08	299.10				
DDH-9101							299.10	300.06	46.9	1.03	0.01	0.12
DDH-9101							300.06	310.00				
Ramo San José												
DDH-9102		4,368		326.00	180°	-36°		175.55				
DDH-9102							175.55	176.12	1255.1	0.32	0.18	0.32
DDH-9102							176.12	176.74	48.6	0.02	0.02	0.04
DDH-9102							176.74	194.28				
DDH-9102							194.28	195.01	9.5	0.00	0.01	0.02
DDH-9102							195.01	221.60				
DDH-9102							221.60	221.91	6.4	0.00	0.01	0.06
DDH-9102							221.91	227.41				
DDH-9102							227.41	228.46	35.7	0.12	0.06	0.14
DDH-9102							228.46	240.82				
DDH-9102							240.82	241.57	8.6	0.19	0.02	0.03
DDH-9102							241.57	258.88				
DDH-9102							258.88	260.30	2.6	0.02	0.01	0.01
DDH-9102							260.30	321.00				
DDH-9102							321.00	321.60	9	0.01	0.01	0.08
DDH-9102							321.60	322.40	2.8	0.00	0.01	0.05
DDH-9102							322.40	326.00				
Canto												
DDH-52-3				300.05	190°	-65°		14.53				
DDH-52-3							14.53	15.15	20.4	0.01	0.03	0.39
DDH-52-3							15.15	15.63	223.5	0.13	0.79	10.92
DDH-52-3							15.63	16.09	75.8	0.06	0.04	0.43

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

	DDH-52-3						16.09	263.70					
	DDH-52-3						263.70	264.20	4.3	0.00	0.01	0.13	
	DDH-52-3						264.20	264.76	2.7	0.00	0.01	0.08	
	DDH-52-3						264.76	266.20	6.7	0.00	0.02	0.39	
	DDH-52-3						266.20	266.53	1.2	0.00	0.01	0.34	
	DDH-52-3						266.53	266.73	0.8	0.02	0.01	0.07	
	DDH-52-3						266.73	267.47					
	DDH-52-3						267.47	267.96	0.8	0.00	0.01	0.37	
	DDH-52-3						267.96	300.50					
Ad	CH-99-0-001	1,542	7,645,455	4,438	6.50	206°	0°		2.30	12.9	0.01	0.01	0.05
	CH-99-0-001							2.30	4.00	12.9	0.03	0.01	0.10
	CH-99-0-001							4.00	5.30	481.7	0.90	0.04	0.66
	CH-99-0-001							5.30	6.50	198.1	0.35	0.04	0.19
Ad	CH-99-0-002	1,622	7,645,399	4,438	10.95	214°	0°		1.60	11.1	0.01	0.01	0.14
	CH-99-0-002							1.60	3.35	6.2	0.01	0.01	0.15
	CH-99-0-002							3.35	4.75	304.5	0.24	0.13	1.49
	CH-99-0-002							4.75	6.85	263.4	0.12	0.08	0.65
	CH-99-0-002							6.85	8.85	34	0.04	0.02	0.13
	CH-99-0-002							8.85	10.95	9.9	0.03	0.02	0.11
Ad	CH-99-0-003	1,658	7,645,365	4,438	9.05	207°	0°		1.90	166.6	0.23	0.08	0.44
	CH-99-0-003							1.90	4.50	203.3	0.26	0.07	2.91
	CH-99-0-003							4.50	6.75	28.7	0.05	0.02	0.29
	CH-99-0-003							6.75	9.05	34.3	0.02	0.04	0.18
Un	CH-99-0-004	1,513	7,645,139	4,438	4.45	330°	0°		1.55	429.1	0.18	0.07	11.88
	CH-99-0-004							1.55	2.40	2656.2	0.68	0.30	13.70
	CH-99-0-004							2.40	3.75	1305.3	0.48	0.16	27.94
	CH-99-0-004							3.75	4.45	15.4	0.01	0.02	1.23
6 de													
Ag	CH-99-0-005	1,300	7,645,185	4,438	5.75	32°	0°		1.60	17.5	0.02	0.01	2.55
	CH-99-0-005							1.60	2.50	179.6	0.36	0.04	2.74
	CH-99-0-005							2.50	4.20	732.6	0.88	0.10	21.77
	CH-99-0-005							4.20	5.20	307.7	0.14	0.09	3.32
	CH-99-0-005							5.20	5.75	6.7	0.00	0.04	0.78
6 de													
Ag	CH-99-0-006	1,042	7,645,254	4,438	5.75	198°	0°		1.00	47.2	0.07	0.02	0.42
	CH-99-0-006							1.00	2.20	218.2	0.78	0.04	14.06
	CH-99-0-006							2.20	3.05	90.2	0.21	0.02	2.28
	CH-99-0-006							3.05	4.45	58.1	0.12	0.02	1.94
	CH-99-0-006							4.45	5.75	14.9	0.04	0.02	0.56
6 de													
Ag	CH-99-0-007	1,545	7,645,355	4,438	8.00	48°	0°		1.60	38.2	0.04	0.34	0.52
	CH-99-0-007							1.60	3.40	337.1	0.41	2.05	4.13
	CH-99-0-007							3.40	4.60	87	0.11	0.62	4.11
	CH-99-0-007							4.60	6.00	76.9	0.04	1.00	6.37

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

CH-99-0-007							6.00	8.00	39.6	0.02	0.41	1.68
Art CH-99-0-008 ,318	7,645,163	4,438	5.00	21°	0°		1.40	52.3	0.15	0.54	0.45	

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
HOLE													
CH-99-0-008								1.40	2.70	46.1	0.24	0.69	2.11
CH-99-0-008								2.70	5.00	10	0.01	0.50	0.96
Arturo	CH-99-0-009	7,636	7,644,995	4,438	4.35	215°	0°		0.75	2	0.01	0.03	0.47
	CH-99-0-009							0.75	1.95	39.1	0.20	0.07	0.44
	CH-99-0-009							1.95	2.65	36.9	0.39	0.11	0.41
	CH-99-0-009							2.65	3.55	75.5	0.20	0.10	1.80
	CH-99-0-009							3.55	4.35	49.4	0.09	0.04	0.60
Arturo	CH-99-0-010	7,032	7,644,772	4,438	13.17	31°	0°		2.00	12.5	0.06	0.01	1.53
	CH-99-0-010							2.00	4.00	6.8	0.08	0.01	0.94
	CH-99-0-010							4.00	6.50	6.8	0.07	0.02	1.09
	CH-99-0-010							6.50	7.45	160.4	0.32	0.26	21.99
	CH-99-0-010							7.45	8.35	56	0.15	0.06	7.64
	CH-99-0-010							8.35	9.10	162.6	0.32	0.20	21.49
	CH-99-0-010							9.10	9.67	253.7	0.62	0.72	19.97
	CH-99-0-010							9.67	10.87	72.9	0.40	0.08	5.31
	CH-99-0-010							10.87	13.17	11.5	0.08	0.02	1.96
Lito	CH-99-0-011	7,711	7,645,068	4,438	5.20	331°	0°		1.00	104	0.14	0.04	6.93
	CH-99-0-011							1.00	1.85	595.9	0.26	0.05	8.21
	CH-99-0-011							1.85	2.85	47.9	0.11	0.02	3.23
	CH-99-0-011							2.85	4.25	256.6	0.35	0.23	31.54
	CH-99-0-011							4.25	5.20	1.6	0.14	0.01	1.39
Arturo	CH-99-0-012	7,948	7,644,818	4,438	7.29	206°	0°		0.75	17.4	0.02	0.01	1.34
	CH-99-0-012							0.75	1.65	73.6	0.07	0.04	9.43
	CH-99-0-012							1.65	2.70	14.9	0.02	0.01	1.22
	CH-99-0-012							2.70	4.50	31.3	0.06	0.01	0.65
	CH-99-0-012							4.50	5.94	15	0.03	0.01	1.72
	CH-99-0-012							5.94	7.29	5.3	0.01	0.01	0.65
Arturo	CH-99-0-013	7,484	7,645,080	4,438	4.00	30°	0°		0.60	47.1	0.10	0.35	2.72
	CH-99-0-013							0.60	1.70	31.6	0.04	0.56	0.78
	CH-99-0-013							1.70	2.75	53.6	0.17	0.93	1.79
	CH-99-0-013							2.75	4.00	14.6	0.11	0.16	0.26
6 de													
Agosto	CH-00-0-014	7,905	7,645,282	4,438	6.70	10°	0°		1.48	15.8	0.01	0.06	0.41
	CH-00-0-014							1.48	2.81	159.9	0.24	0.07	3.00
	CH-00-0-014							2.81	3.94	42.3	0.03	0.04	4.28
	CH-00-0-014							3.94	4.98	17.5	0.01	0.02	2.32

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

CH-00-0-014							4.98	6.09	8	0.01	0.03	0.70	
CH-00-0-014							6.09	6.70	4.2	0.00	0.01	0.23	
6 de													
Agosto	CH-00-0-015	7,828	7,645,294	4,438	10.00	10°	0°		1.15	3.7	0.47	0.12	0.11
	CH-00-0-015							1.15	2.42	6.7	0.18	0.04	0.08
	CH-00-0-015							2.42	3.74	89.3	0.09	0.04	1.79
	CH-00-0-015							3.74	5.05	76	0.09	0.05	1.91
	CH-00-0-015							5.05	6.55	146.7	0.17	0.05	2.20
	CH-00-0-015							6.55	7.81	44.1	0.05	0.05	0.53
	CH-00-0-015							7.81	9.18	41.7	0.03	0.03	0.38
	CH-00-0-015							9.18	10.00	4.8	0.00	0.02	0.12
6 de													
Agosto	CH-00-0-016	7,759	7,645,306	4,438	4.92	20°	0°		1.13	18.1	0.01	0.04	0.66
	CH-00-0-016							1.13	2.02	65.5	0.04	0.05	2.06
	CH-00-0-016							2.02	3.32	197.9	0.15	0.10	7.86
	CH-00-0-016							3.32	4.92	56.8	0.08	0.07	0.78
6 de													
Agosto	CH-00-0-017	7,610	7,645,339	4,438	6.14	10°	0°		1.60	31.3	0.05	0.05	0.69
	CH-00-0-017							1.60	2.98	656.4	1.40	0.12	6.96
	CH-00-0-017							2.98	3.99	215.8	1.82	0.08	2.41
	CH-00-0-017							3.99	5.23	190.6	0.48	0.10	0.41
	CH-00-0-017							5.23	6.14	26.1	0.05	0.06	0.32
6 de													
Agosto	CH-00-0-018	8,066	7,645,245	4,438	7.70	3°	0°		1.04	3.3	0.00	0.04	0.07
	CH-00-0-018							1.04	2.06	2.8	0.00	0.05	0.02
	CH-00-0-018							2.06	3.13	3.1	0.00	0.05	0.03
	CH-00-0-018							3.13	4.16	5.5	0.00	0.03	0.10
	CH-00-0-018							4.16	5.28	12.4	0.01	0.02	0.44
	CH-00-0-018							5.28	6.52	60	0.21	0.14	1.16
	CH-00-0-018							6.52	7.70	48.8	0.13	0.05	0.71
6 de													
Agosto	CH-00-0-019	8,214	7,645,203	4,438	4.13	21°	0°		0.60	33.6	0.21	0.01	0.18
	CH-00-0-019							0.60	1.99	72.1	0.03	0.04	0.47
	CH-00-0-019							1.99	3.31	73.7	0.02	0.22	0.91
	CH-00-0-019							3.31	4.13	13.1	0.01	0.05	0.60
6 de													
Agosto	CH-00-0-020	8,415	7,645,157	4,438	5.03	22°	0°		0.88	447.5	0.29	0.02	1.11
	CH-00-0-020							0.88	1.71	1018.8	0.55	0.04	1.21
	CH-00-0-020							1.71	2.60	1744.4	0.82	0.12	8.47
	CH-00-0-020							2.60	3.52	970.5	0.31	0.06	6.14
	CH-00-0-020							3.52	5.03	10.9	0.01	0.03	0.15
Ad	CH-99-30-001	8,673	7,645,332	4,408	24.07	0°	0°		1.90	300.3	0.42	0.04	3.33
	CH-99-30-001							1.90	3.90	26.8	0.05	0.01	0.22
	CH-99-30-001							3.90	5.75	7.4	0.06	0.01	0.15

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

CH-99-30-001	5.75	7.18	16.1	0.72	0.02	0.62
CH-99-30-001	7.18	8.89	327.9	1.70	0.22	2.49

Hole Identification	Collar Co-ordinates			Interval Orientation			Assay Results							
	Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
HOLE														
CH-99-30-001									8.89	10.85	85.2	0.71	0.03	0.34
CH-99-30-001									10.85	12.31	4.9	0.07	0.00	0.17
CH-99-30-001									12.31	13.91	11.1	0.08	0.01	0.22
CH-99-30-001									13.91	15.51	39.7	0.17	0.01	0.56
CH-99-30-001									15.51	17.37	417.1	0.89	0.08	1.29
CH-99-30-001									17.37	18.77	176.7	0.52	0.05	0.63
CH-99-30-001									18.77	20.17	188.7	0.78	0.07	0.79
CH-99-30-001									20.17	21.37	6.6	0.05	0.01	0.15
CH-99-30-001									21.37	24.07	448.7	0.60	0.03	0.37
Ado	CH-99-30-002	423	7,645,523	4,408	5.69	32°	0°		1.06	891.9	0.88	0.07	0.45	
	CH-99-30-002								1.06	2.09	853.2	0.55	0.08	0.27
	CH-99-30-002								2.09	3.59	433.9	0.44	0.05	0.54
	CH-99-30-002								3.59	4.89	386	0.47	0.03	1.55
	CH-99-30-002								4.89	5.69	12.2	0.04	0.01	0.18
Lit	CH-99-30-003	665	7,645,046	4,408	7.41	157°	0°		1.78	174.7	0.32	0.03	1.66	
	CH-99-30-003								1.78	3.48	1072.7	2.20	0.02	7.41
	CH-99-30-003								3.48	4.68	9.1	0.06	0.01	0.69
	CH-99-30-003								4.68	5.88	59.3	0.10	0.01	1.09
	CH-99-30-003								5.88	7.41	1328.2	0.72	0.04	5.87
6 de	CH-99-30-004	434	7,645,168	4,408	13.77	194°	0°		2.10	19.6	0.03	0.01	1.20	
Ag	CH-99-30-004								2.10	4.20	47	0.04	0.01	0.81
	CH-99-30-004								4.20	5.72	2649.6	1.00	0.12	13.00
	CH-99-30-004								5.72	7.09	1155.4	0.77	0.11	2.59
	CH-99-30-004								7.09	8.83	465.5	0.27	0.57	12.81
	CH-99-30-004								8.83	11.17	163.4	0.12	0.05	5.27
	CH-99-30-004								11.17	13.77	39.9	0.07	0.03	2.60
6 de	CH-99-30-005	319	7,645,207	4,408	9.30	6°	0°		1.90	657.5	0.66	0.19	20.63	
Ag	CH-99-30-005								1.90	3.80	112.2	0.12	0.02	2.85
	CH-99-30-005								3.80	4.70	229.9	0.25	0.06	8.84
	CH-99-30-005								4.70	6.00	7	0.01	0.05	0.28
	CH-99-30-005								6.00	7.30	390.4	0.27	2.64	11.08
	CH-99-30-005								7.30	9.30	137.4	0.06	1.41	4.35
6 de	CH-99-30-006	281	7,645,207	4,408	6.51	191°	0°		1.60	10.2	0.01	0.16	0.87	
Ag	CH-99-30-006								1.60	3.48	145.3	0.05	0.03	0.85

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

	CH-99-30-006						3.48	4.71	291.5	0.29	0.13	14.77
	CH-99-30-006						4.71	6.51	327.8	0.46	0.04	4.12
Art	CH-99-30-007 ,487	7,645,103	4,408	7.05	6°	0°		1.90	1.3	0.00	0.01	0.28
	CH-99-30-007						1.90	3.05	71.7	0.20	0.13	1.87
	CH-99-30-007						3.05	4.05	65.9	0.19	0.04	1.95
	CH-99-30-007						4.05	5.35	16.2	0.10	0.30	0.59
	CH-99-30-007						5.35	7.05	36.8	0.14	0.03	0.46
6 de												
Ag	CH-99-30-008 ,394	7,645,187	4,408	6.97	192°	0°		0.78	551	0.20	0.01	5.32
	CH-99-30-008						0.78	2.40	1599.8	0.52	0.05	6.91
	CH-99-30-008						2.40	3.60	1176.3	0.46	0.03	5.48
	CH-99-30-008						3.60	5.00	710.5	0.23	0.03	5.88
	CH-99-30-008						5.00	6.97	2250.1	0.79	0.07	18.13
6 de												
Ag	CH-99-30-009 ,044	7,645,273	4,408	5.63	32°	0°		0.73	7.6	0.02	0.01	0.09
	CH-99-30-009						0.73	3.43	8.7	0.03	0.01	0.16
	CH-99-30-009						3.43	5.63	5.3	0.05	0.04	0.26
6 de												
Ag	CH-99-30-010 ,542	7,645,377	4,408	6.22	10°	0°		1.30	3	0.05	0.03	0.35
	CH-99-30-010						1.30	2.23	20.9	0.04	0.05	0.41
	CH-99-30-010						2.23	3.50	153.5	0.10	1.43	3.21
	CH-99-30-010						3.50	5.22	37.9	0.02	0.23	1.27
	CH-99-30-010						5.22	6.22	10.9	0.01	0.13	0.52
Art	CH-99-30-011 ,118	7,644,908	4,408	3.15	210°	0°		1.03	31.5	0.02	0.74	0.98
	CH-99-30-011						1.03	2.15	1158.5	0.40	0.99	2.04
	CH-99-30-011						2.15	3.15	22.4	0.01	0.08	0.88
Ad	CH-00-30-012 ,310	7,645,596	4,408	8.51	36°	0°		1.64	16.4	0.05	0.01	0.08
	CH-00-30-012						1.64	3.17	133.9	0.12	0.02	0.09
	CH-00-30-012						3.17	4.53	77.0	0.11	0.02	0.09
	CH-00-30-012						4.53	6.09	425.6	0.04	0.04	0.06
	CH-00-30-012						6.09	7.51	14.8	0.01	0.02	0.07
	CH-00-30-012						7.51	8.51	17.9	0.02	0.01	0.08
Ad	CH-00-30-013 ,523	7,645,444	4,408	7.68	44°	0°		0.94	151.5	0.13	0.03	0.08
	CH-00-30-013						0.94	1.74	18.9	0.02	0.01	0.04
	CH-00-30-013						1.74	2.24	64.5	0.05	0.03	0.05
	CH-00-30-013						2.24	3.22	133.4	0.13	0.04	0.12
	CH-00-30-013						3.22	4.43	227.6	0.21	0.03	0.14
	CH-00-30-013						4.43	5.65	83.9	0.07	0.02	0.06
	CH-00-30-013						5.65	6.86	218.7	0.17	0.03	0.10
	CH-00-30-013						6.86	7.68	4.1	0.00	0.00	0.04
Ad	CH-00-30-014 ,611	7,645,383	4,408	7.17	36°	0°		0.86	25.3	0.09	0.01	0.07
	CH-00-30-014						0.86	2.04	42.3	0.12	0.02	0.08
	CH-00-30-014						2.04	3.10	112.2	0.19	0.02	0.09

CH-00-30-014

3.10 4.05 29.4 0.12 0.02 0.09

Hole Identification	Collar Co-ordinates			Interval Orientation			Assay Results							
	HOLE	Vein N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	CH-00-30-014								4.05	5.23	19.8	0.04	0.02	0.05
	CH-00-30-014								5.23	6.04	244.9	0.21	0.03	0.11
	CH-00-30-014								6.04	7.17	6.3	0.01	0.00	0.04
Ade	CH-00-30-015	7,729	7,645,298	4,408	7.15	37°	0°		0.88	1.80	156.1	0.09	0.05	0.82
	CH-00-30-015								0.88	1.80	681.7	0.28	0.10	1.78
	CH-00-30-015								1.80	3.02	3001.1	2.16	0.15	8.16
	CH-00-30-015								3.02	4.25	2014.7	2.34	0.18	5.31
	CH-00-30-015								4.25	5.77	2422.0	1.71	0.37	20.35
	CH-00-30-015								5.77	7.15	43.4	0.35	0.02	0.38
Ade	CH-00-30-016	7,845	7,645,243	4,408	2.25	31°	0°		1.32	2.25	7.4	0.01	0.06	0.32
Ran	CH-00-30-016								1.32	2.25	229.9	0.09	0.18	14.06
6 de														
Ago	CH-00-30-017	7,159	7,645,244	4,408	5.84	15°	0°		1.26	2.69	266.5	0.31	0.05	2.70
	CH-00-30-017								1.26	2.69	244.5	0.30	0.17	2.13
	CH-00-30-017								2.69	4.09	329.2	0.35	0.19	3.74
	CH-00-30-017								4.09	5.49	261.3	0.38	0.16	4.33
	CH-00-30-017								5.49	6.34	35.1	0.02	0.06	0.45
Ade	CH-00-30-018	7,816	7,645,233	4,408	4.57	50°	0°		1.12	2.57	9.1	0.02	0.01	0.28
	CH-00-30-018								1.12	2.57	140.9	0.10	0.06	4.58
	CH-00-30-018								2.57	4.08	312.4	0.12	0.02	8.70
	CH-00-30-018								4.08	5.22	3.9	0.00	0.01	0.13
6 de														
Ago	CH-00-30-019	7,255	7,645,214	4,408	7.88	15°	0°		1.10	1.75	44.6	0.15	0.05	2.60
	CH-00-30-019								1.10	1.75	5.0	0.00	0.01	0.13
	CH-00-30-019								1.75	2.95	1804.5	0.64	0.72	15.68
	CH-00-30-019								2.95	4.16	229.3	0.09	0.13	3.75
	CH-00-30-019								4.16	5.51	158.8	0.04	0.01	0.50
	CH-00-30-019								5.51	6.72	202.6	0.03	0.02	0.14
	CH-00-30-019								6.72	7.88	6.6	0.02	0.02	0.33
6 de														
Ago	CH-00-30-020	7,086	7,645,266	4,408	6.14	20°	0°		1.07	2.54	197.2	0.01	0.01	0.28
	CH-00-30-020								1.07	2.54	30.4	0.02	0.08	1.54
	CH-00-30-020								2.54	3.70	273.1	0.30	0.18	14.47
	CH-00-30-020								3.70	4.95	203.6	0.58	0.02	0.72
	CH-00-30-020								4.95	6.14	169.6	0.34	0.02	0.54

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

6 de													
Ago	CH-00-30-021	7,919	7,645,302	4,408	4.59	25°	0°	0.97	12.9	0.01	0.04	0.75	
	CH-00-30-021							0.97	2.84	91.6	0.09	0.09	2.23
	CH-00-30-021							2.84	3.69	25.4	0.03	0.02	0.17
	CH-00-30-021							3.69	4.59	3.3	0.00	0.01	0.15
Adela	CH-00-30-022	7,855	7,645,212	4,408	9.27	45°	0°	1.10	0.7	0.00	0.01	0.05	
	CH-00-30-022							1.10	2.58	3.6	0.01	0.03	0.23
	CH-00-30-022							2.58	3.88	11.6	0.01	0.07	1.03
	CH-00-30-022							3.88	4.76	6.5	0.00	0.01	0.58
	CH-00-30-022							4.76	6.25	17.8	0.04	0.01	0.84
	CH-00-30-022							6.25	7.72	8.5	0.01	0.01	1.26
	CH-00-30-022							7.72	9.27	2.5	0.00	0.01	0.04
Unidad	CH-00-30-023	7,764	7,645,258	4,408	9.40	5°	0°	1.29	2.1	0.00	0.00	0.09	
	CH-00-30-023							1.29	2.39	176.9	0.11	0.05	4.86
	CH-00-30-023							2.39	3.64	198.7	0.20	0.05	8.22
	CH-00-30-023							3.64	4.98	193.9	0.11	0.04	4.63
	CH-00-30-023							4.98	6.10	13.4	0.01	0.01	1.68
	CH-00-30-023							6.10	7.34	61.9	0.04	0.02	1.18
	CH-00-30-023							7.34	8.33	46.6	0.14	0.01	0.67
	CH-00-30-023							8.33	9.40	2.8	0.01	0.01	0.06
6 de													
Ago	CH-00-30-024	7,827	7,645,316	4,408	5.20	15°	0°	1.17	77.5	0.09	0.08	3.56	
	CH-00-30-024							1.17	2.33	107.2	0.11	0.07	7.40
	CH-00-30-024							2.33	3.76	56.9	0.07	0.03	1.69
	CH-00-30-024							3.76	5.20	7.5	0.00	0.01	0.19
6 de													
Ago	CH-00-30-025	7,722	7,645,339	4,408	4.00	355°	0°	0.71	4.5	0.03	0.03	0.23	
	CH-00-30-025							0.71	1.79	161.7	0.07	0.16	0.91
	CH-00-30-025							1.79	3.11	66	0.05	0.06	1.43
	CH-00-30-025							3.11	4.00	9.1	0.00	0.04	0.13
6 de													
Ago	CH-00-30-026	7,640	7,645,355	4,408	4.26	15°	0°	0.71	49.3	0.03	0.10	0.25	
	CH-00-30-026							0.71	1.94	20.9	0.02	0.09	0.44
	CH-00-30-026							1.94	3.33	118.1	0.10	0.78	7.04
	CH-00-30-026							3.33	4.26	174.5	0.10	0.39	6.59
Adela													
Rm	CH-00-30-027	7,900	7,645,204	4,408	1.18	315°	0°	1.18	69.50	0.17	0.02	6.77	
Adela	CH-00-30-028	7,890	7,645,190	4,408	7.94	35°	0°	1.27	1.90	0.00	0.02	0.10	
	CH-00-30-028							1.27	2.96	47.30	0.17	0.02	4.02
	CH-00-30-028							2.96	4.38	40.20	0.19	0.01	3.89
	CH-00-30-028							4.38	6.18	6.80	0.02	0.01	0.40
	CH-00-30-028							6.18	7.94	6.40	0.04	0.03	0.57
Litografía	CH-00-30-029	7,949	7,645,192	4,408	6.29	355°	0°	1.45	2.40	0.00	0.04	0.44	

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

CH-00-30-029	1.45	2.83	240.70	0.70	0.14	7.81
CH-00-30-029	2.83	4.01	9.50	0.03	0.06	1.15
CH-00-30-029	4.01	5.33	9.20	0.07	0.14	2.33

Hole Identification	Collar Co-ordinates			Interval Orientation			Assay Results							
	Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
CH-00-30-029									5.33	6.29	2.50	0.01	0.06	0.55
6 de														
Agosto	CH-00-30-030	030	7,645,557	7,645,094	4,408	3.64	40°	0°		1.09	62.60	0.15	0.01	0.33
	CH-00-30-030								1.09	2.19	186.10	0.15	0.02	2.13
	CH-00-30-030								2.19	3.64	1.80	0.00	0.01	0.07
6 de														
Agosto	CH-00-30-031	031	7,645,587	7,645,073	4,408	4.65	35°	0°		0.48	5.90	0.07	0.01	0.17
	CH-00-30-031								0.48	1.94	210.40	0.17	0.12	1.73
	CH-00-30-031								1.94	2.87	584.60	0.48	0.02	8.22
	CH-00-30-031								2.87	3.90	666.20	0.44	0.03	10.44
	CH-00-30-031								3.90	4.65	13.4	0.03	0.01	0.18
6 de														
Agosto	CH-00-30-032	032	7,645,013	7,645,281	4,408	5.30	37°	0°		1.75	13.13	0.02	0.02	1.10
	CH-00-30-032								1.75	2.95	34.5	0.04	0.03	3.62
	CH-00-30-032								2.95	4.13	173.5	0.19	0.08	18.63
	CH-00-30-032								4.13	5.30	210.4	0.17	0.23	11.16
6 de														
Agosto	CH-00-30-033	033	7,645,469	7,645,395	4,408	2.16	16°	0°		1.01	42.9	0.03	0.26	2.13
	CH-00-30-033								1.01	2.16	67.7	0.08	0.13	0.45
6 de														
Agosto	CH-00-30-034	034	7,645,770	7,645,328	4,408	2.81	13°	0°		1.11	192.9	0.21	0.46	4.74
	CH-00-30-034								1.11	2.19	290.7	0.31	0.49	13.92
	CH-00-30-034								2.19	2.81	145.7	0.15	0.09	0.75
6 de														
Agosto	CH-00-30-035	035	7,645,528	7,645,117	4,408	2.53	37°	0°		1.52	128.2	0.13	0.06	7.03
	CH-00-30-035								1.52	2.53	3.1	0.01	0.01	0.26
Litografía	CH-00-30-036	036	7,645,743	7,645,075	4,408	3.45	331°	0°		0.84	651.1	1.20	0.02	1.04
	CH-00-30-036								0.84	2.16	728.9	0.74	0.08	3.64
	CH-00-30-036								2.16	3.45	1685.6	1.43	0.48	13.11
Litografía	CH-00-30-037	037	7,645,798	7,645,273	4,408	1.71	358°	0°		0.78	9.9	0.01	0.03	0.40
	CH-00-30-037								0.78	1.71	287.7	0.15	0.71	13.14
6 de														
Agosto	CH-00-30-038	038	7,645,458	7,645,159	4,408	3.97	21°	0°		0.95	30.4	0.07	0.02	1.68

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

	CH-00-30-038						0.95	1.93	107.9	0.10	0.09	7.76	
	CH-00-30-038						1.93	2.94	1214.5	0.57	0.44	22.27	
	CH-00-30-038						2.94	3.97	199	0.13	0.08	9.40	
6 de													
Ago	CH-00-30-039	7,868	7,645,313	4,408	9.96	0°	0°	0.85	80.2	0.06	0.04	2.85	
	CH-00-30-039							0.85	1.79	1.7	0.00	0.06	0.08
	CH-00-30-039							1.79	3.19	4.5	0.00	0.02	0.46
	CH-00-30-039							3.19	4.39	38.8	0.02	0.03	0.45
	CH-00-30-039							4.39	5.84	49.1	0.06	0.12	2.79
	CH-00-30-039							5.84	7.03	62.6	0.09	0.06	7.46
	CH-00-30-039							7.03	8.43	138.6	0.14	0.10	7.01
	CH-00-30-039							8.43	9.96	113.5	0.05	0.07	0.93
6 de													
Ago	CH-99-70-001	7,958	7,645,321	4,368	6.02	180°	0°	0.90	19.9	0.02	0.04	0.58	
	CH-99-70-001							0.90	1.76	58.4	0.07	0.08	5.84
	CH-99-70-001							1.76	2.66	22	0.04	0.04	2.19
	CH-99-70-001							2.66	3.86	37.8	0.04	0.04	0.93
	CH-99-70-001							3.86	5.16	72.9	0.08	0.08	1.75
	CH-99-70-001							5.16	6.02	95.7	0.07	0.21	1.12
6 de													
Ago	CH-99-70-002	7,994	7,645,322	4,368	3.93	16°	0°	1.20	639.9	0.57	0.07	10.53	
	CH-99-70-002							1.20	2.40	27.4	0.11	0.01	1.24
	CH-99-70-002							2.40	2.73	156.7	0.26	0.09	7.87
	CH-99-70-002							2.73	3.93	7.9	0.02	0.02	0.29
6 de													
Ago	CH-99-70-003	7,168	7,645,266	4,368	9.75	19°	0°	0.70	162.2	0.17	0.10	7.34	
	CH-99-70-003							0.70	1.15	2.5	0.01	0.02	0.51
	CH-99-70-003							1.15	2.50	112.9	0.18	0.12	2.87
	CH-99-70-003							2.50	4.85	5.4	0.01	0.02	0.33
	CH-99-70-003							4.85	6.65	2.3	0.00	0.01	0.29
	CH-99-70-003							6.65	8.25	2.9	0.01	0.02	0.52
	CH-99-70-003							8.25	9.75	65.6	0.08	0.18	2.97
6 de													
Ago	CH-99-70-004	7,323	7,645,234	4,368	6.75	13°	0°	1.60	98.5	0.06	0.02	1.12	
	CH-99-70-004							1.60	2.50	139.5	0.09	0.01	0.92
	CH-99-70-004							2.50	3.75	225.4	0.16	0.03	1.32
	CH-99-70-004							3.75	5.20	166.6	0.18	0.79	4.26
	CH-99-70-004							5.20	6.75	788.4	0.69	0.11	8.98
Lito	CH-99-70-005	7,678	7,645,034	4,368	5.73	336°	0°	1.05	259.9	0.69	0.02	3.97	
	CH-99-70-005							1.05	2.25	147.9	0.31	0.03	2.52
	CH-99-70-005							2.25	3.45	626.6	1.10	0.07	9.10
	CH-99-70-005							3.45	4.93	626.5	0.97	0.12	6.25
	CH-99-70-005							4.93	5.73	243.7	0.27	0.02	1.17
Lito	CH-99-70-006	7,775	7,645,090	4,368	4.74	152°	0°	1.05	7	0.02	0.02	0.04	

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

CH-99-70-006							1.05	2.30	13.1	0.05	0.01	0.23
CH-99-70-006							2.30	3.44	17.9	0.12	0.01	0.36
CH-99-70-006							3.44	4.74	251.9	0.41	0.03	1.43
Union Pacific	CH-99-70-007	7,526	7,645,203	4,368	6.18	143°	0°	1.00	8.9	0.09	0.02	0.48
	CH-99-70-007						1.00	1.85	325.8	0.44	0.07	6.16
	CH-99-70-007						1.85	2.48	7.2	0.03	0.01	0.99

Hole Identification	Collar Co-ordinates			Interval Orientation			Assay Results							
	Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
CH-99-70-007									2.48	4.18	38	0.19	0.02	1.70
CH-99-70-007									4.18	6.18	271.4	0.89	0.03	5.70
Litochalco	CH-99-70-008	008	7,645,919	7,645,167	4,368	4.05	0°	0°		0.75	8.7	0.01	0.02	0.26
	CH-99-70-008								0.75	1.30	257.6	0.22	0.67	8.52
	CH-99-70-008								1.30	2.30	381.1	0.45	0.03	1.54
	CH-99-70-008								2.30	4.05	381.7	0.71	0.03	2.59
Uniflow	CH-99-70-009	009	7,645,550	7,645,212	4,368	7.25	175°	0°		0.95	102.3	0.37	0.07	4.34
	CH-99-70-009								0.95	2.30	3.2	0.01	0.00	0.18
	CH-99-70-009								2.30	3.80	3.5	0.01	0.01	0.25
	CH-99-70-009								3.80	5.35	27.1	0.05	0.03	0.95
	CH-99-70-009								5.35	6.45	38.4	0.11	0.03	0.33
	CH-99-70-009								6.45	7.25	7.5	0.02	0.01	0.30
Adeco	CH-99-70-010	010	7,645,771	7,645,231	4,368	6.08	30°	0°		1.60	28	0.04	0.02	2.01
	CH-99-70-010								1.60	3.10	20.2	0.03	0.01	2.35
	CH-99-70-010								3.10	4.58	30.3	0.06	0.01	4.90
	CH-99-70-010								4.58	6.08	2.2	0.00	0.00	0.18
Adeco	CH-99-70-011	011	7,645,683	7,645,296	4,368	6.30	34°	0°		1.40	860.8	0.61	0.09	5.85
	CH-99-70-011								1.40	2.30	932	0.61	0.12	3.79
	CH-99-70-011								2.30	3.65	494.9	0.48	0.10	5.32
	CH-99-70-011								3.65	4.90	224.6	0.22	0.10	2.54
	CH-99-70-011								4.90	6.30	172.6	0.13	0.06	0.85
Adeco	CH-99-70-012	012	7,645,321	7,645,555	4,368	4.35	225°	0°		1.15	385.3	0.14	0.06	0.17
	CH-99-70-012								1.15	2.45	556.4	0.27	0.07	0.32
	CH-99-70-012								2.45	3.65	54.2	0.05	0.01	0.08
	CH-99-70-012								3.65	4.35	13.3	0.02	0.01	0.06
Litochalco	CH-99-70-013	013	7,645,086	7,645,187	4,368	4.18	180°	0°		1.15	31.6	0.04	0.03	0.36
	CH-99-70-013								1.15	2.15	122	0.34	0.02	6.95
	CH-99-70-013								2.15	2.68	281.1	0.82	0.28	2.27
	CH-99-70-013								2.68	4.18	4.5	0.01	0.04	0.19
6 de Agosto	CH-99-70-014	014	7,645,232	7,645,251	4,368	4.63	192°	0°		1.28	51.9	0.02	0.06	1.42
	CH-99-70-014								1.28	2.53	266.1	0.09	0.06	2.34
	CH-99-70-014								2.53	3.93	195.2	0.12	0.03	0.73
	CH-99-70-014								3.93	4.63	10.2	0.03	0.01	0.40

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Unico	CH-99-70-015	7,737	7,645,267	4,368	2.00	144°	0°	2.00	179.9	0.14	0.02	2.27	
Unico	CH-99-70-016	7,737	7,645,267	4,368	1.90	144°	0°	1.90	54.7	0.07	0.02	1.44	
6 de													
Agosto	CH-00-70-017	7,934	7,645,326	4,368	5.94	23°	0°	0.76	203.3	0.19	0.04	1.24	
	CH-00-70-017							0.76	2.42	50.4	0.09	0.03	0.26
	CH-00-70-017							2.42	4.03	7.2	0.02	0.01	0.12
	CH-00-70-017							4.03	5.24	28.7	0.04	0.05	1.29
	CH-00-70-017							5.24	5.94	18.1	0.02	0.03	0.97
6 de													
Agosto	CH-00-70-018	7,650	7,645,066	4,368	3.43	37°	0°	1.19	393.5	0.82	0.68	1.33	
	CH-00-70-018							1.19	2.47	540.4	0.67	0.17	21.48
	CH-00-70-018							2.47	3.43	22.3	0.06	0.03	0.72
Unico	CH-00-70-019	7,607	7,645,238	4,368	5.55	324°	0°	1.89	165.4	0.19	0.09	14.28	
	CH-00-70-019							1.89	3.10	29.8	0.06	0.03	2.18
	CH-00-70-019							3.10	4.03	39.5	0.04	0.30	4.14
	CH-00-70-019							4.03	4.70	9.6	0.09	0.04	0.46
	CH-00-70-019							4.70	5.55	31.5	0.07	0.08	3.14
6 de													
Agosto	CH-00-70-020	7,583	7,645,103	4,368	6.88	33°	0°	1.11	3.1	0.01	0.01	0.05	
	CH-00-70-020							1.11	1.96	3.4	0.00	0.01	0.06
	CH-00-70-020							1.96	2.97	118.7	0.12	0.07	3.14
	CH-00-70-020							2.97	4.14	24.7	0.03	0.01	0.45
	CH-00-70-020							4.14	4.98	16.8	0.05	0.01	1.47
	CH-00-70-020							4.98	6.88	2.1	0.00	0.00	0.03
Litona	CH-00-70-021	7,678	7,645,034	4,368	8.72	340°	0°	1.74	50.6	0.04	0.01	0.67	
	CH-00-70-021							1.74	2.96	1545.8	0.93	0.24	13.75
	CH-00-70-021							2.96	4.33	224.1	0.08	0.03	0.21
	CH-00-70-021							4.33	5.80	122.4	0.06	0.01	0.26
	CH-00-70-021							5.80	7.55	390.7	0.52	0.02	4.16
	CH-00-70-021							7.55	8.72	266.1	0.49	0.03	1.03
6 de													
Agosto	CH-00-70-022	7,035	7,645,305	4,368	9.68	10°	0°	0.69	2.4	0.00	0.02	0.16	
	CH-00-70-022							0.69	2.11	3.3	0.00	0.02	0.16
	CH-00-70-022							2.11	3.45	22.5	0.02	0.06	1.70
	CH-00-70-022							3.45	4.55	128	0.14	0.12	10.60
	CH-00-70-022							4.55	5.47	79.4	0.10	0.19	11.33
	CH-00-70-022							5.47	6.58	9.1	0.01	0.03	1.07
	CH-00-70-022							6.58	7.98	40.5	0.04	0.06	4.51
	CH-00-70-022							7.98	8.86	9.3	0.01	0.03	1.02
	CH-00-70-022							8.86	9.68	4.1	0.00	0.03	0.21
6 de													
Agosto	CH-00-70-023	7,452	7,645,185	4,368	9.13	25°	0°	1.18	235.5	0.33	0.04	2.00	
	CH-00-70-023							1.18	2.45	37.2	0.15	0.02	1.14

CH-00-70-023

2.45 3.75 7.6 0.03 0.01 0.06

Hole Identification	Collar Co-ordinates			Interval Orientation			Assay Results							
	Vein	N°	Eastings	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
CH-00-70-023									3.75	4.64	3	0.00	0.00	0.02
CH-00-70-023									4.64	6.09	126.5	0.04	0.01	0.22
CH-00-70-023									6.09	8.06	210.7	0.24	0.02	0.31
CH-00-70-023									8.06	9.13	82.5	0.20	0.02	0.50
Lito	CH-00-70-024	74	7,645,073	7,645,073	4,368	4.71	335°	0°		1.27	1882.7	0.43	0.06	4.54
	CH-00-70-024								1.27	2.25	1698.5	0.42	0.04	2.23
	CH-00-70-024								2.25	3.17	564.9	0.15	0.03	0.64
	CH-00-70-024								3.17	4.71	2484.1	0.94	0.07	1.98
Ade	CH-00-70-025	75	7,645,927	7,645,180	4,368	3.31	340°	0°		1.26	892.5	0.32	0.01	1.80
Ram	CH-00-70-025								1.26	2.11	37.2	0.02	0.00	0.36
	CH-00-70-025								2.11	3.31	261.8	0.08	0.04	2.68
Ade	CH-00-70-026	76	7,645,499	7,645,435	4,368	9.30	27°	0°		1.26	10.6	0.02	0.01	0.05
	CH-00-70-026								1.26	2.11	80	0.08	0.02	0.10
	CH-00-70-026								2.11	3.32	34.4	0.06	0.01	0.07
	CH-00-70-026								3.32	4.35	47.1	0.08	0.02	2.89
	CH-00-70-026								4.35	5.35	45.6	0.03	0.02	0.32
	CH-00-70-026								5.35	6.78	76.8	0.06	0.02	0.19
	CH-00-70-026								6.78	7.95	30.5	0.08	0.01	0.06
	CH-00-70-026								7.95	9.30	3.1	0.00	0.00	0.03
Ade	CH-00-70-027	77	7,645,575	7,645,380	4,368	4.77	41°	0°		1.08	4.9	0.02	0.01	0.03
	CH-00-70-027								1.08	2.63	6.9	0.03	0.01	0.09
	CH-00-70-027								2.63	3.63	69.2	0.19	0.03	3.86
	CH-00-70-027								3.63	4.77	3.9	0.01	0.00	0.03
Ade	CH-00-70-028	78	7,645,223	7,645,223	4,368	8.44	34°	0°		1.55	6.5	0.01	0.01	0.64
	CH-00-70-028								1.55	3.05	23.1	0.02	0.01	1.87
	CH-00-70-028								3.05	4.32	295.9	0.18	0.03	20.38
	CH-00-70-028								4.32	5.97	61.1	0.07	0.02	9.92
	CH-00-70-028								5.97	7.26	10.9	0.02	0.01	0.63
	CH-00-70-028								7.26	8.44	94.6	0.01	0.01	0.13
Ade	CH-00-70-029	79	7,645,692	7,645,290	4,368	9.40	34°	0°		1.48	3.3	0.00	0.00	0.05
	CH-00-70-029								1.48	2.91	1.5	0.00	0.00	0.04
	CH-00-70-029								2.91	3.78	1.4	0.00	0.00	0.03
	CH-00-70-029								3.78	4.81	3.9	0.01	0.03	0.02
	CH-00-70-029								4.81	5.86	201.8	1.54	0.18	0.78
	CH-00-70-029								5.86	6.70	77.1	0.34	0.03	0.37
	CH-00-70-029								6.70	7.68	158.2	0.21	0.03	0.98

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

	CH-00-70-029						7.68	9.40	6.6	0.01	0.00	0.02
Unic	CH-00-70-030	7,645,253	4,368	4.91	174°	0°		1.36	6.9	0.01	0.01	0.34
	CH-00-70-030						1.36	2.54	46.5	0.18	0.07	6.77
	CH-00-70-030						2.54	3.87	483.2	0.50	0.68	33.98
	CH-00-70-030						3.87	4.91	5.1	0.01	0.01	0.21
Adela												
Rm	CH-00-70-031	7,645,262	4,368	1.80	320°	0°		0.69	99.9	0.13	0.02	0.27
	CH-00-70-031						0.69	1.80	165.3	0.09	0.04	0.40
Adela	CH-00-70-032	7,645,188	4,368	6.08	26°	0°		0.94	2.8	0.02	0.00	0.07
	CH-00-70-032						0.94	1.98	6.2	0.09	0.00	0.07
	CH-00-70-032						1.98	2.78	24.3	0.13	0.01	0.97
	CH-00-70-032						2.78	4.27	332.9	0.35	0.08	14.87
	CH-00-70-032						4.27	5.17	25.3	0.01	0.04	1.52
	CH-00-70-032						5.17	6.08	19.4	0.01	0.00	1.38
Lito	CH-00-70-033	7,645,175	4,368	8.17	355°	0°		0.80	5.1	0.06	0.01	0.05
	CH-00-70-033						0.80	1.88	81.4	0.16	0.07	0.33
	CH-00-70-033						1.88	2.86	463.5	0.15	0.48	1.78
	CH-00-70-033						2.86	4.28	1304.9	1.38	0.19	1.46
	CH-00-70-033						4.28	5.13	49.1	0.10	0.02	0.96
	CH-00-70-033						5.13	6.18	184.5	0.53	0.01	1.59
	CH-00-70-033						6.18	7.18	16.3	0.10	0.01	0.46
	CH-00-70-033						7.18	8.17	31.2	0.62	0.01	0.49
Lito	CH-00-70-034	7,645,103	4,368	1.89	0°	0°		0.61	207.0	0.23	0.01	0.06
	CH-00-70-034						0.61	1.89	1170.9	2.32	0.02	1.54
6 de												
Agos	CH-00-70-035	7,645,210	4,368	2.73	24°	0°		1.39	79.7	0.17	0.05	10.41
	CH-00-70-035						1.39	2.73	91.5	0.10	0.03	3.45
6 de												
Agos	CH-00-70-036	7,645,245	4,368	3.84	9°	0°		0.89	8771.9	2.08	0.44	4.98
	CH-00-70-036						0.89	2.40	493.7	0.11	0.06	0.95
	CH-00-70-036						2.40	3.84	820.0	0.23	0.19	3.17
6 de												
Agos	CH-00-110-001	7,645,340	4,328	4.72	195°	0°		1.67	35.6	0.06	0.08	1.65
	CH-00-110-001						1.67	2.57	28.1	0.06	0.10	3.59
	CH-00-110-001						2.57	3.37	49.8	0.06	0.09	5.74
	CH-00-110-001						3.37	4.72	98.7	0.08	0.10	0.74
6 de												
Agos	CH-00-110-002	7,645,334	4,328	3.97	190°	0°		0.80	123.3	0.10	0.17	4.64
	CH-00-110-002						0.80	1.80	29.7	0.04	0.09	3.68
	CH-00-110-002						1.80	3.00	34.4	0.05	0.10	2.16
	CH-00-110-002						3.00	3.97	55.4	0.07	0.09	0.91

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE								Ag					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	(g/t)	Cu %	Pb %	Zn %
DDH-99-70-001	701	571	7,645,277	4,370	66.00	193°	-40°		5.46				
DDH-99-70-001								5.46	6.01	2.8	0.00	0.01	0.02
DDH-99-70-001								6.01	6.34	8.5	0.03	0.02	0.03
DDH-99-70-001								6.34	6.76	1	0.00	0.00	0.03
DDH-99-70-001								6.76	23.23				
DDH-99-70-001								23.23	24.19	2.3	0.00	0.01	0.02
DDH-99-70-001								24.19	26.90				
DDH-99-70-001								26.90	28.38	1.6	0.00	0.00	0.02
DDH-99-70-001								28.38	40.50				
DDH-99-70-001								40.50	40.90	57.6	0.02	0.01	0.23
DDH-99-70-001								40.90	41.27	10.4	0.01	0.01	0.15
DDH-99-70-001								41.27	41.55	47.2	0.02	0.06	1.57
DDH-99-70-001								41.55	41.98	2.2	0.00	0.02	0.19
DDH-99-70-001								41.98	53.23				
DDH-99-70-001								53.23	53.96	3.8	0.01	0.01	0.13
DDH-99-70-001								53.96	54.35	1.1	0.00	0.01	0.09
DDH-99-70-001								54.35	55.03	4.4	0.01	0.02	0.22
DDH-99-70-001								55.03	55.48	2.8	0.01	0.03	0.07
DDH-99-70-001								55.48	56.07	0.2	0.00	0.00	0.02
DDH-99-70-001								56.07	56.69	0.5	0.00	0.00	0.04
DDH-99-70-001								56.69	59.80				
DDH-99-70-001								59.80	60.08	0.4	0.00	0.00	0.03
DDH-99-70-001								60.08	60.70	1.6	0.00	0.02	0.02
DDH-99-70-001								60.70	61.20	16.2	0.19	0.06	0.16
DDH-99-70-001								61.20	61.63	0	0.00	0.00	0.03
DDH-99-70-001								61.63	62.50	14.2	0.03	0.01	2.62
DDH-99-70-001								62.50	66.00				
DDH-99-70-002	702	616	7,645,321	4,371	26.35	38°	-22°		5.00				
DDH-99-70-002								5.00	5.70	2.9	0.00	0.01	0.05
DDH-99-70-002								5.70	6.00				
DDH-99-70-002								6.00	6.80	2.1	0.00	0.01	0.03
DDH-99-70-002								6.80	11.40				
DDH-99-70-002								11.40	12.35	3.1	0.00	0.01	0.02
DDH-99-70-002								12.35	12.66	18.3	0.04	0.03	1.29
DDH-99-70-002								12.66	13.77	4.8	0.02	0.01	0.03
DDH-99-70-002								13.77	14.35	14.2	0.02	0.02	0.23
DDH-99-70-002								14.35	15.16	4.5	0.00	0.01	0.04
DDH-99-70-002								15.16	15.74	17.1	0.03	0.11	0.68
DDH-99-70-002								15.74	16.29	5.2	0.00	0.01	0.03
DDH-99-70-002								16.29	16.63	2.5	0.00	0.01	0.02
DDH-99-70-002								16.63	17.51	8.5	0.01	0.02	0.16

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-70-002						17.51	18.18	2.2	0.00	0.01	0.04		
DDH-99-70-002						18.18	18.85	3.6	0.00	0.01	0.03		
DDH-99-70-002						18.85	20.55						
DDH-99-70-002						20.55	21.48	1.4	0.00	0.01	0.02		
DDH-99-70-002						21.48	22.80						
DDH-99-70-002						22.80	24.16	1.2	0.00	0.00	0.03		
DDH-99-70-002						24.16	26.35						
DDH-99-70-003	UN	667	7,645,300	4,370	49.75	180°	-39°						
								2.01					
DDH-99-70-003								2.01	2.50	388.9	0.23	0.04	1.03
DDH-99-70-003								2.50	3.35	40.9	0.03	0.01	0.70
DDH-99-70-003								3.35	4.14	4.2	0.01	0.01	0.48
DDH-99-70-003								4.14	5.42	803.6	1.00	0.12	4.90
DDH-99-70-003								5.42	6.11	7.7	0.02	0.02	0.41
DDH-99-70-003								6.11	9.80				
DDH-99-70-003								9.80	10.22	46	0.07	0.02	1.00
DDH-99-70-003								10.22	11.65				
DDH-99-70-003								11.65	12.16	14.5	0.02	0.03	0.21
DDH-99-70-003								12.16	13.81				
DDH-99-70-003								13.81	15.09	3.3	0.00	0.01	0.23
DDH-99-70-003								15.09	19.05				
DDH-99-70-003								19.05	19.69	2.3	0.00	0.00	0.01
DDH-99-70-003								19.69	25.57				
DDH-99-70-003								25.57	26.03	50.7	0.15	0.04	3.69
DDH-99-70-003								26.03	26.90	2.2	0.00	0.01	0.10
DDH-99-70-003								26.90	27.49	13.9	0.03	0.02	0.64
DDH-99-70-003								27.49	32.75				
DDH-99-70-003								32.75	33.53	2.1	0.00	0.00	0.14
DDH-99-70-003								33.53	34.65	244.2	0.23	0.03	0.41
DDH-99-70-003								34.65	36.65	2.6	0.00	0.00	0.02
DDH-99-70-003								36.65	37.54	4.3	0.00	0.01	0.26
DDH-99-70-003								37.54	38.16	8.6	0.00	0.02	0.03
DDH-99-70-003								38.16	39.07	298.3	0.20	0.14	4.98
DDH-99-70-003								39.07	40.00	3845	1.82	0.58	5.00
DDH-99-70-003								40.00	40.97	12.5	0.01	0.03	0.03
DDH-99-70-003								40.97	41.80	9.3	0.01	0.02	0.04
DDH-99-70-003								41.80	42.85	2.8	0.00	0.01	0.04
DDH-99-70-003								42.85	44.05	0			
DDH-99-70-003								44.05	49.75				
DDH-99-70-004	LI	921	7,645,158	4,371	46.30	337°	-49°						
								0.84					
Ramo													
Adela													
2 DDH-99-70-004								0.84	2.22	1.8	0.01	0.01	0.05
DDH-99-70-004								2.22	3.60	2.3	0.01	0.01	0.31
DDH-99-70-004								3.60	4.68	2.4	0.01	0.01	0.05
DDH-99-70-004								4.68	5.40	2.4	0.01	0.01	0.03
DDH-99-70-004								5.40	7.25	6.4	0.01	0.01	0.09

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-99-70-004								7.25	8.10	2329	0.95	0.41	19.92
DDH-99-70-004								8.10	9.04	7.8	0.00	0.02	0.40
DDH-99-70-004								9.04	9.92	31.5	0.01	0.03	0.39
DDH-99-70-004								9.92	11.12	564.2	0.16	0.05	2.98
DDH-99-70-004								11.12	13.22	7	0.00	0.00	0.01
DDH-99-70-004								13.22	14.38	337.5	0.31	0.01	2.70
DDH-99-70-004								14.38	15.97	14.7	0.01	0.00	0.01
DDH-99-70-004								15.97	16.69	12.5	0.00	0.01	0.02
DDH-99-70-004								16.69	18.24	2.3	0.00	0.00	0.20
DDH-99-70-004								18.24	19.04	1641	0.73	0.05	7.97
DDH-99-70-004								19.04	19.65	7.4	0.00	0.00	0.21
DDH-99-70-004								19.65	21.25				
DDH-99-70-004								21.25	22.51	2.6	0.00	0.00	0.02
DDH-99-70-004								22.51	23.74	0.7	0.00	0.00	0.01
DDH-99-70-004								23.74	25.71	1.6	0.00	0.00	0.03
DDH-99-70-004								25.71	27.18	22.4	0.04	0.02	2.53
DDH-99-70-004								27.18	28.29	12.2	0.01	0.01	1.23
DDH-99-70-004								28.29	29.67	5.9	0.01	0.01	0.47
DDH-99-70-004								29.67	30.41	84.9	0.08	0.02	2.34
DDH-99-70-004								30.41	31.51	4.8	0.01	0.00	0.55
DDH-99-70-004								31.51	32.52	148.5	0.11	0.02	2.95
DDH-99-70-004								32.52	33.89	3.6	0.00	0.00	0.41
DDH-99-70-004								33.89	34.85	1.6	0.00	0.00	0.02
DDH-99-70-004								34.85	35.79	9.5	0.02	0.01	0.79
DDH-99-70-004								35.79	36.76	70.7	0.17	0.01	6.38
DDH-99-70-004								36.76	37.73	28.8	0.06	0.01	0.97
DDH-99-70-004								37.73	38.69	48.9	0.06	0.01	1.53
DDH-99-70-004								38.69	39.66	1726	1.55	0.04	18.75
DDH-99-70-004								39.66	40.62	11.9	0.03	0.01	1.28
DDH-99-70-004								40.62	42.17	3.4	0.00	0.00	0.12
DDH-99-70-004								42.17	46.30				
6 de													
Ag	DDH-99-70-005	10	7,645,186	4,389	34.00	194°	-38°		8.60				
	DDH-99-70-005							8.60	11.13	2.8	0.03	0.01	0.07
	DDH-99-70-005							11.13	15.80				
	DDH-99-70-005							15.80	16.74	2.4	0.00	0.00	0.07
	DDH-99-70-005							16.74	17.09				
	DDH-99-70-005							17.09	18.19	1.3	0.00	0.01	0.05
	DDH-99-70-005							18.19	18.49				
	DDH-99-70-005							18.49	20.25	5.5	0.02	0.01	0.87
	DDH-99-70-005							20.25	21.19	6.3	0.07	0.01	0.66

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-99-70-005						21.19	22.46	5.3	0.01	0.01	0.10
DDH-99-70-005						22.46	23.62	6.1	0.00	0.02	0.10
DDH-99-70-005						23.62	24.50	6.6	0.00	0.01	0.07
DDH-99-70-005						24.50	25.37	3.5	0.00	0.01	0.05
DDH-99-70-005						25.37	26.31	433.3	0.56	0.11	0.37
DDH-99-70-005						26.31	27.11	13.2	0.11	0.02	0.11
DDH-99-70-005						27.11	27.70	0.8	0.00	0.00	0.02
DDH-99-70-005						27.70	34.00				
6 de											
Ag DDH-99-70-006	DDH-99-70-006	164	7,645,247	4,370	87.90	71°	-30°			69.35	
DDH-99-70-006								69.35	71.81	3.5	0.01 0.01 0.44
DDH-99-70-006								71.81	75.20		
DDH-99-70-006								75.20	76.42	20	0.13 0.01 1.71
DDH-99-70-006								76.42	76.86	192.9	0.25 0.03 2.60
DDH-99-70-006								76.86	77.85	85.1	0.14 0.05 11.67
DDH-99-70-006								77.85	78.87	68	0.19 0.04 9.18
DDH-99-70-006								78.87	79.70	112.9	0.33 0.36 18.75
DDH-99-70-006								79.70	80.64	60.1	0.14 0.06 3.90
DDH-99-70-006								80.64	82.04	23.3	0.06 0.04 3.09
DDH-99-70-006								82.04	82.59	112.8	0.18 0.13 5.85
DDH-99-70-006								82.59	83.52	113.2	0.16 0.07 5.00
DDH-99-70-006								83.52	84.45	6.6	0.01 0.02 0.27
DDH-99-70-006								84.45	85.59	7.7	0.01 0.03 0.10
DDH-99-70-006								85.59	86.27	1.6	0.00 0.05 0.05
DDH-99-70-006								86.27	86.98	1.6	0.00 0.04 0.05
DDH-99-70-006								86.98	87.90	1.2	0.00 0.02 0.16
Ad DDH-99-70-007											
DDH-99-70-007	DDH-99-70-007	307	7,645,533	4,369	45.00	16°	-45°			4.45	
DDH-99-70-007								4.45	5.05	474.6	0.44 0.05 2.48
DDH-99-70-007								5.05	26.50		
DDH-99-70-007								26.50	27.28	150.5	0.21 0.05 0.94
DDH-99-70-007								27.28	29.35		
DDH-99-70-007								29.35	29.75	9.3	0.05 0.02 0.03
DDH-99-70-007								29.75	32.58		
DDH-99-70-007								32.58	33.00	1.7	0.02 0.01 0.06
DDH-99-70-007								33.00	41.40		
DDH-99-70-007								41.40	41.85	21.5	0.22 0.04 0.07
DDH-99-70-007								41.85	45.20		
Ad DDH-99-70-008											
DDH-99-70-008	DDH-99-70-008	306	7,645,533	4,369	50.00	60°	-40°			4.94	
DDH-99-70-008								4.94	5.45	197.8	0.15 0.04 0.58
DDH-99-70-008								5.45	12.15		
DDH-99-70-008								12.15	14.68	3.6	0.00 0.01 0.03
DDH-99-70-008								14.68	15.30		
DDH-99-70-008								15.30	15.79	2.5	0.00 0.01 0.02
DDH-99-70-008								15.79	22.65		
DDH-99-70-008								22.65	24.73	5.3	0.01 0.01 0.04

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results				
Vein	N° Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
							24.73	31.85				
							31.85	32.60	4.5	0.03	0.02	0.03
							32.60	50.00				
Lit	DDH-03-022	7,644,905	4,473	203.65	337°	-51°		7.20				
	DDH-03-022						7.20	174.45				
	DDH-03-022						174.45	175.01	21	0.01	0.02	0.03
	DDH-03-022						175.01	175.63	37	0.23	0.04	0.22
	DDH-03-022						175.63	176.31	2.4	0.03	0.02	0.03
	DDH-03-022						176.31	190.79				
	DDH-03-022						190.79	191.65	9.6	0.05	0.04	0.03
	DDH-03-022						191.65	192.03	18	3.29	0.03	0.13
	DDH-03-022						192.03	192.85	4.8	0.05	0.02	0.04
	DDH-03-022						192.85	193.73	121	0.84	0.03	0.12
	DDH-03-022						193.73	194.70	93	1.24	0.80	1.00
	DDH-03-022						194.70	203.65				
Lit	DDH-03-023	7,645,074	4,470	222.00	358°	-67°		12.00				
	DDH-03-023						12.00	135.60				
	DDH-03-023						135.60	136.27	9.6	0.01	0.11	0.80
	DDH-03-023						136.27	141.35				
	DDH-03-023						141.35	142.42	61	0.05	0.04	2.20
	DDH-03-023						142.42	143.32	53	0.04	0.31	1.16
	DDH-03-023						143.32	144.20	8	0.01	0.10	0.68
	DDH-03-023						144.20	151.95				
	DDH-03-023						151.95	152.61	78	0.48	0.02	1.88
	DDH-03-023						152.61	153.59	11	0.06	0.03	0.10
	DDH-03-023						153.59	154.29	1881	3.53	0.38	4.40
	DDH-03-023						154.29	157.98				
	DDH-03-023						157.98	159.00	1387	2.24	0.03	2.60
	DDH-03-023						159.00	159.81	1341	0.96	0.03	1.84
	DDH-03-023						159.81	160.76	924	0.64	0.04	0.84
	DDH-03-023						160.76	161.70	662	0.52	0.04	0.64
	DDH-03-023						161.70	162.83	1788	1.04	0.04	0.76
	DDH-03-023						162.83	163.62	1199	0.09	0.04	1.32
	DDH-03-023						163.62	164.59	74	0.04	0.05	1.48
	DDH-03-023						164.59	165.78	261	0.11	0.10	13.20
	DDH-03-023						165.78	167.40	19	0.01	0.10	0.96
	DDH-03-023						167.40	168.27	26	0.04	0.12	3.40
	DDH-03-023						168.27	170.15	21	0.03	0.06	1.84
	DDH-03-023						170.15	171.00	147	0.12	0.16	1.80
	DDH-03-023						171.00	172.33	1310	0.60	0.30	1.00
	DDH-03-023						172.33	173.44	2977	0.68	0.04	0.76

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-03-023						173.44	173.89	723	1.84	0.72	28.90	
DDH-03-023						173.89	174.74	17	0.01	0.04	0.26	
DDH-03-023						174.74	222.00					
Arturo	DDH-03-023	1,112	7,644,882	4,498	219.25	215°	-72°					
							18.45					
DDH-03-024							18.45	128.17				
DDH-03-024							128.17	128.85	16	0.05	0.06	0.48
DDH-03-024							128.85	129.58	0.8	0.01	0.02	0.16
DDH-03-024							129.58	130.05	35	0.08	0.02	1.12
DDH-03-024							130.05	138.72				
DDH-03-024							138.72	139.74	2.4	0.02	0.02	0.76
DDH-03-024							139.74	195.77				
DDH-03-024							195.77	196.36	36	0.11	0.09	3.10
DDH-03-024							196.36	196.92	8	0.01	0.04	0.03
DDH-03-024							196.92	197.26	11	0.02	0.04	1.56
DDH-03-024							197.26	197.92	4	0.01	0.02	0.18
DDH-03-024							197.92	198.82	7.2	0.01	0.04	1.16
DDH-03-024							198.82	199.67	17	0.48	0.05	0.88
DDH-03-024							199.67	200.60	79	0.20	0.10	4.10
DDH-03-024							200.60	201.36	148	0.29	0.22	6.50
DDH-03-024							201.36	202.03	34	0.03	0.19	3.00
DDH-03-024							202.03	202.60	2.4	0.01	0.06	0.22
DDH-03-024							202.60	214.47				
DDH-03-024							214.47	214.99	18	0.03	0.04	4.20
DDH-03-024							214.99	219.25				
San												
Loreto	DDH-03-025	1,812	7,644,949	4,478	215.45	331°	-52°					
Litor							2.81					
DDH-03-025							2.81	104.79				
DDH-03-025							104.79	105.87	5.6	0.12	0.02	0.11
DDH-03-025							105.87	107.05	1084	1.40	0.17	6.00
DDH-03-025							107.05	107.94	22	0.06	0.02	0.13
DDH-03-025							107.94	123.70				
DDH-03-025							123.70	124.15	4	0.01	0.02	0.03
DDH-03-025							124.15	125.13	11	0.01	0.06	0.09
DDH-03-025							125.13	126.11	2.4	0.01	0.03	0.03
DDH-03-025							126.11	126.97	2.4	0.01	0.03	0.02
DDH-03-025							126.97	145.31				
DDH-03-025							145.31	146.49	4.8	0.01	0.05	1.16
DDH-03-025							146.49	190.15				
DDH-03-025							190.15	191.43	16	0.14	0.06	0.40
DDH-03-025							191.43	192.08	9.6	0.01	0.02	0.02
DDH-03-025							192.08	192.43	2.4	0.01	0.02	0.12
DDH-03-025							192.43	193.13	4	0.01	0.02	0.11
DDH-03-025							193.13	194.24	3.2	0.03	0.03	0.03
DDH-03-025							194.24	195.29	10	0.02	0.05	0.08

Hole		Collar Co-ordinates			Interval Orientation			Assay Results						
Identification	HOLE	Vein N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-03-025									195.29	196.20	70	0.19	0.12	2.00
DDH-03-025									196.20	197.36	28	0.20	0.04	0.18
DDH-03-025									197.36	198.22	4.8	0.01	0.02	0.04
DDH-03-025									198.22	199.50	33	0.56	0.01	0.11
DDH-03-025									199.50	200.98	60	0.52	0.02	0.11
DDH-03-025									200.98	201.74	8	0.02	0.01	0.02
DDH-03-025									201.74	203.27	3.2	0.01	0.02	0.02
DDH-03-025									203.27	204.23	8	0.02	0.04	0.12
DDH-03-025									204.23	204.98	214	3.18	0.02	0.21
DDH-03-025									204.98	205.56	4	0.01	0.02	0.14
DDH-03-025									205.56	215.45				
Lit	DDH-03-026	7,939	7,645,060	4,466	220.15	2°	-53°			9.65				
	DDH-03-026								9.65	96.62				
	DDH-03-026								96.62	97.15	133	0.21	0.03	0.03
	DDH-03-026								97.15	98.06	49	0.18	0.02	0.08
	DDH-03-026								98.06	99.27	778	0.80	0.04	0.08
	DDH-03-026								99.27	99.80	2790	2.71	0.19	0.16
	DDH-03-026								99.80	100.80	22	0.52	0.03	0.03
	DDH-03-026								100.80	102.05	4.8	0.06	0.02	0.03
	DDH-03-026								102.05	103.28	10	0.09	0.04	0.05
	DDH-03-026								103.28	104.57	10	0.17	0.02	0.04
	DDH-03-026								104.57	105.24	1003	0.80	0.05	0.23
	DDH-03-026								105.24	106.02	344	1.32	0.08	0.03
	DDH-03-026								106.02	126.80				
	DDH-03-026								126.80	128.24				
	DDH-03-026								128.24	132.53				
	DDH-03-026								132.53	141.69				
	DDH-03-026								141.69	142.57	18	0.03	0.37	1.56
	DDH-03-026								142.57	143.54	16	0.04	0.16	0.34
	DDH-03-026								143.54	144.51	3.2	0.01	0.06	0.12
	DDH-03-026								144.51	145.72	3.2	0.01	0.05	0.06
	DDH-03-026								145.72	146.35	7.2	0.02	0.11	1.28
	DDH-03-026								146.35	147.30	8	0.01	0.12	0.32
	DDH-03-026								147.30	148.34	3.2	0.01	0.04	0.15
	DDH-03-026								148.34	149.18	5.6	0.01	0.08	0.34
	DDH-03-026								149.18	150.05	30	0.01	0.44	1.28
	DDH-03-026								150.05	150.99	35	0.01	0.60	1.96
	DDH-03-026								150.99	151.91	38	0.01	0.40	1.84
	DDH-03-026								151.91	152.83	36	0.01	0.06	4.20
	DDH-03-026								152.83	153.76	33	0.01	0.07	3.00
	DDH-03-026								153.76	154.63	13	0.05	0.06	2.80
	DDH-03-026								154.63	155.32	210	0.15	0.06	0.18

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-03-026				155.32	155.79	3893	1.28	0.64	18.00
DDH-03-026				155.79	156.74	138	0.10	0.06	1.28
DDH-03-026				156.74	157.78	33	0.03	0.03	1.60
DDH-03-026				157.78	158.46	13	0.01	0.03	0.23
DDH-03-026				158.46	159.14	540	0.16	0.05	0.44
DDH-03-026				159.14	159.85	208	0.17	0.03	6.00
DDH-03-026				159.85	161.01	18	0.01	0.02	0.10
DDH-03-026				161.01	161.95	676	0.13	0.02	0.52
DDH-03-026				161.95	162.62	25	0.03	0.02	0.96
DDH-03-026				162.62	163.83	5.6	0.01	0.02	0.20
DDH-03-026				163.83	164.80	48	0.04	0.03	0.23
DDH-03-026				164.80	166.13	10	0.01	0.01	1.12
DDH-03-026				166.13	167.57	14	0.01	0.01	1.20
DDH-03-026				167.57	168.53	8	0.01	0.02	0.03
DDH-03-026				168.53	169.18	4	0.01	0.01	0.02
DDH-03-026				169.18	169.64	759	0.33	0.04	7.00
DDH-03-026				169.64	171.25	9.6	0.01	0.02	0.48
DDH-03-026				171.25	172.14	4	0.01	0.01	0.04
DDH-03-026				172.14	173.10	20	0.01	0.02	1.20
DDH-03-026				173.10	173.51	8.8	0.01	0.01	0.01
DDH-03-026				173.51	174.66	13	0.01	0.01	0.32
DDH-03-026				174.66	175.58	12	0.01	0.02	0.34
DDH-03-026				175.58	176.49	16	0.01	0.02	0.08
DDH-03-026				176.49	177.93	12	0.01	0.01	0.20
DDH-03-026				177.93	179.26	20	0.02	0.03	1.68
DDH-03-026				179.26	180.16	8	0.01	0.01	0.60
DDH-03-026				180.16	181.07	14	0.01	0.01	0.68
DDH-03-026				181.07	198.05				
DDH-03-026				198.05	198.49	4	0.01	0.01	0.04
DDH-03-026				198.49	199.22	8	0.01	0.02	1.28
DDH-03-026				199.22	200.11	3.2	0.01	0.02	0.03
DDH-03-026				200.11	207.50				
DDH-03-026				207.50	208.28	4	0.01	0.05	0.09
DDH-03-026				208.28	209.02	4.8	0.01	0.02	0.40
DDH-03-026				209.02	209.73	43	0.06	0.06	5.00
DDH-03-026				209.73	210.44	4.8	0.01	0.02	0.34
DDH-03-026				210.44	216.25				
DDH-03-026				216.25	217.15	4.8	0.01	0.08	0.13
DDH-03-026				217.15	217.81	3.2	0.01	0.03	0.03
DDH-03-026				217.81	218.61	2.4	0.01	0.04	0.05
DDH-03-026				218.61	219.27	5.6	0.01	0.02	0.22
DDH-03-026				219.27	220.15				
DDH-03-027	7,939	7,645,059	4,466	228.34	355°	-68°		6.54	
DDH-03-027								6.54	106.94

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE													
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-03-027					106.94			107.77		874	2.12	0.21	0.09
DDH-03-027					107.77			109.54		10	0.06	0.02	0.04
DDH-03-027					109.54			110.45		203	0.68	0.07	0.19
DDH-03-027					110.45			111.30		18	0.04	0.02	0.08
DDH-03-027					111.30			112.31		8	0.03	0.01	0.56
DDH-03-027					112.31			113.26		8.8	0.04	0.01	0.04
DDH-03-027					113.26			114.40		10	0.06	0.02	0.09
DDH-03-027					114.40			115.06		20	0.23	0.04	0.22
DDH-03-027					115.06			115.99		17	0.06	0.02	0.26
DDH-03-027					115.99			117.11		78	0.35	0.03	0.20
DDH-03-027					117.11			117.88		967	1.32	0.10	0.18
DDH-03-027					117.88			118.84		2189	2.12	0.05	0.64
DDH-03-027					118.84			119.75		1690	1.44	0.15	0.36
DDH-03-027					119.75			120.62		1847	1.32	0.14	0.26
DDH-03-027					120.62			121.02		10201	2.47	0.72	0.40
DDH-03-027					121.02			121.53		57	0.22	0.02	0.06
DDH-03-027					121.53			149.70					
DDH-03-027					149.70			150.34		14	0.01	0.01	0.03
DDH-03-027					150.34			150.61		38	0.26	0.02	6.00
DDH-03-027					150.61			151.75		6	0.01	0.01	0.04
DDH-03-027					151.75			152.60		71	0.12	0.02	4.60
DDH-03-027					152.60			153.98		2.4	0.01	0.01	0.03
DDH-03-027					153.98			155.47		14	0.04	0.02	1.80
DDH-03-027					155.47			156.25		11	0.09	0.02	0.96
DDH-03-027					156.25			157.17		3.2	0.01	0.01	0.03
DDH-03-027					157.17			158.11		7.2	0.01	0.01	0.72
DDH-03-027					158.11			159.31		14	0.01	0.02	1.76
DDH-03-027					159.31			159.75		505	0.40	0.06	17.00
DDH-03-027					159.75			160.99		19	0.03	0.01	0.48
DDH-03-027					160.99			162.32		22	0.02	0.02	0.21
DDH-03-027					162.32			163.70		5.6	0.02	0.02	0.72
DDH-03-027					163.70			164.64		235	0.30	0.02	1.04
DDH-03-027					164.64			165.31		519	0.64	0.02	0.96
DDH-03-027					165.31			165.89		25	0.06	0.02	0.04
DDH-03-027					165.89			166.53		635	0.64	0.02	2.70
DDH-03-027					166.53			167.47		69	0.16	0.02	0.19
DDH-03-027					167.47			168.40		4	0.01	0.01	0.12
DDH-03-027					168.40			169.37		101	0.42	0.02	3.30
DDH-03-027					169.37			170.70		27	0.10	0.01	0.10
DDH-03-027					170.70			171.20		1232	4.90	0.04	4.50
DDH-03-027					171.20			172.20		7.2	0.03	0.01	0.06
DDH-03-027					172.20			173.14		296	0.48	0.04	0.33
DDH-03-027					173.14			174.05		1327	1.40	0.06	1.88

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-03-027						174.05	174.74	1453	2.24	0.04	1.36
DDH-03-027						174.74	175.13	13138	13.50	0.05	3.90
DDH-03-027						175.13	175.90	230	0.48	0.03	0.12
DDH-03-027						175.90	176.89	62	0.23	0.02	0.08
DDH-03-027						176.89	177.43	944	4.20	0.22	0.80
DDH-03-027						177.43	178.08	10	0.08	0.04	0.07
DDH-03-027						178.08	178.88	26	0.05	0.04	0.26
DDH-03-027						178.88	180.14				
DDH-03-027						180.14	183.34				
DDH-03-027						183.34	193.70				
DDH-03-027						193.70	194.39	7.2	0.03	0.03	0.19
DDH-03-027						194.39	195.34	10	0.03	0.70	2.00
DDH-03-027						195.34	196.65	27	0.04	0.13	0.64
DDH-03-027						196.65	197.61	59	0.08	0.06	0.28
DDH-03-027						197.61	198.51	15	0.04	0.03	0.04
DDH-03-027						198.51	199.50	75	0.16	0.04	0.19
DDH-03-027						199.50	207.34				
DDH-03-027						207.34	208.37	2.4	0.01	0.02	0.05
DDH-03-027						208.37	209.22	5.6	0.01	0.02	0.03
DDH-03-027						209.22	210.38	5.6	0.02	0.02	0.68
DDH-03-027						210.38	220.41				
DDH-03-027						220.41	221.52	4.8	0.01	0.02	0.06
DDH-03-027						221.52	223.00	5.6	0.01	0.03	0.20
DDH-03-027						223.00	223.80	7.2	0.01	0.02	0.03
DDH-03-027						223.80	228.34				
6 de											
Ag DDH-03-70-009	7,645,341	4,369	122.90	190°	-45°		82.56				
DDH-03-70-009						82.56	83.40	8.4	0.01	0.05	0.07
DDH-03-70-009						83.40	84.27	6.4	0.01	0.04	0.17
DDH-03-70-009						84.27	90.58				
DDH-03-70-009						90.58	93.68				
DDH-03-70-009						93.68	94.86	4	0.01	0.01	0.25
DDH-03-70-009						94.86	101.37				
DDH-03-70-009						101.37	101.90	34	0.08	0.07	0.17
DDH-03-70-009						101.90	103.19	35	0.08	0.08	0.92
DDH-03-70-009						103.19	122.90				
De DDH-03-70-010	7,645,166	4,369	87.00	199°	-59°		59.58				
DDH-03-70-010						59.58	60.00	8.8	0.01	0.04	0.03
DDH-03-70-010						60.00	60.74	174	0.48	0.18	1.88
DDH-03-70-010						60.74	61.22	18	0.02	0.12	0.38
DDH-03-70-010						61.22	87.00				
Lito DDH-04-028	7,644,928	4,463	264.50	337°	-50°		3.00				
DDH-04-028						3.00	138.84				

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE								Ag					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	(g/t)	Cu %	Pb %	Zn %
DDH-04-028					138.84			138.84	139.65	13	0.01	0.06	0.10
DDH-04-028					139.65			139.65	219.50				
DDH-04-028					219.50			219.50	219.83	6.6	0.06	0.02	0.04
DDH-04-028					219.83			219.83	220.27	42	0.21	0.09	1.28
DDH-04-028					220.27			220.27	221.22	23	0.17	0.05	0.68
DDH-04-028					221.22			221.22	222.11	53	0.25	0.04	1.68
DDH-04-028					222.11			222.11	223.05	9.6	0.06	0.05	0.44
DDH-04-028					223.05			223.05	223.62	2.4	0.01	0.02	0.06
DDH-04-028					223.62			223.62	230.59				
DDH-04-028					230.59			230.59	231.04	2.4	0.01	0.03	0.88
DDH-04-028					231.04			231.04	231.50	4.8	0.01	0.09	0.56
DDH-04-028					231.50			231.50	231.93	6.4	0.01	0.04	0.11
DDH-04-028					231.93			231.93	240.50				
DDH-04-028					240.50			240.50	241.05	2.4	0.02	0.03	0.09
DDH-04-028					241.05			241.05	242.50	45	0.52	0.38	0.44
DDH-04-028					242.50			242.50	243.41	3.2	0.01	0.04	0.08
DDH-04-028					243.41			243.41	244.60	8.8	0.09	0.04	0.15
DDH-04-028					244.60			244.60	245.56	2.4	0.01	0.02	0.09
DDH-04-028					245.56			245.56	246.44	5.6	0.01	0.02	0.03
DDH-04-028					246.44			246.44	246.86	3.2	0.01	0.04	0.05
DDH-04-028					246.86			246.86	247.44	22	0.59	0.34	0.64
DDH-04-028					247.44			247.44	248.30	1.6	0.01	0.02	0.04
DDH-04-028					248.30			248.30	249.44	2.4	0.01	0.02	0.03
DDH-04-028					249.44			249.44	250.22	4	0.01	0.03	0.02
DDH-04-028					250.22			250.22	251.14	4	0.01	0.03	0.60
DDH-04-028					251.14			251.14	252.09	5.6	0.04	0.03	0.10
DDH-04-028					252.09			252.09	264.50				
DDH-04-70-011	1693	7,645,110	4,373	141.40	29°	-25°			77.97				
DDH-04-70-011								77.97	78.17				
DDH-04-70-011								78.17	78.65				
DDH-04-70-011								78.65	79.60				
DDH-04-70-011								79.60	80.74				
DDH-04-70-011								80.74	81.12				
DDH-04-70-011								81.12	81.88				
DDH-04-70-011								81.88	82.18				
DDH-04-70-011								82.18	85.36				
DDH-04-70-011								85.36	87.40				
DDH-04-70-011								87.40	87.50				
DDH-04-70-011								87.50	116.01				
DDH-04-70-011								116.01	117.14	15	0.04	0.04	0.26
DDH-04-70-011								117.14	117.53	10	0.01	0.05	0.99
DDH-04-70-011								117.53	118.59	8	0.01	0.04	0.36

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-70-011							118.59	119.35	21	0.01	0.05	0.80
DDH-04-70-011							119.35	120.58	26	0.01	0.06	1.32
DDH-04-70-011							120.58	124.03				
DDH-04-70-011							124.03	124.65	15	0.01	0.04	0.10
DDH-04-70-011							124.65	127.60				
DDH-04-70-011							127.60	128.21	1	0.01	0.02	0.01
DDH-04-70-011							128.21	129.01	9.5	0.04	0.05	0.18
DDH-04-70-011							129.01	129.48	1	0.01	0.07	0.01
DDH-04-70-011							129.48	141.40				
Lit	DDH-04-029	7,645,044	4,483	213.13	359°	-59°		7.63				
	DDH-04-029						7.63	69.82				
	DDH-04-029						69.82	70.42	2.5	0.02	0.10	0.03
	DDH-04-029						70.42	71.37	2.5	0.01	0.02	0.03
	DDH-04-029						71.37	72.13				
	DDH-04-029						72.13	95.63				
	DDH-04-029						95.63	97.47				
	DDH-04-029						97.47	99.13				
	DDH-04-029						99.13	102.69				
	DDH-04-029						102.69	104.78				
	DDH-04-029						104.78	105.13				
	DDH-04-029						105.13	106.48				
	DDH-04-029						106.48	113.12				
	DDH-04-029						113.12	135.13				
	DDH-04-029						135.13	137.99				
	DDH-04-029						137.99	183.44				
	DDH-04-029						183.44	183.91	8.5	0.01	0.02	0.72
	DDH-04-029						183.91	185.34	2	0.01	0.02	0.06
	DDH-04-029						185.34	186.16	5	0.01	0.15	0.40
	DDH-04-029						186.16	187.19	13.5	0.02	0.03	0.76
	DDH-04-029						187.19	188.11	52	0.03	0.03	0.09
	DDH-04-029						188.11	189.07	230	0.07	0.13	0.18
	DDH-04-029						189.07	189.97	3059	0.76	0.44	4.40
	DDH-04-029						189.97	190.88	1467	0.56	0.26	6.40
	DDH-04-029						190.88	192.07	1032	0.52	0.26	29.10
	DDH-04-029						192.07	192.95	44.5	0.02	0.04	0.98
	DDH-04-029						192.95	193.94	6.0	0.01	0.04	0.12
	DDH-04-029						193.94	194.43	2.5	0.01	0.04	0.03
	DDH-04-029						194.43	195.21	5	0.01	0.03	0.32
	DDH-04-029						195.21	196.41	12	0.01	0.02	0.56
	DDH-04-029						196.41	197.34	15	0.01	0.02	1.30
	DDH-04-029						197.34	198.24	6.5	0.01	0.02	0.44
	DDH-04-029						198.24	199.27	15	0.01	0.02	1.16
	DDH-04-029						199.27	213.13				

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
6 de													
Ag	DDH-04-030	7012	7,645,221	4,371	120.00	181°	-38°		36.65				
	DDH-04-70-012							36.65	36.97	7	0.01	0.05	0.06
	DDH-04-70-012							36.97	37.34	12	0.03	0.08	0.52
	DDH-04-70-012							37.34	37.93	2.5	0.01	0.03	0.07
	DDH-04-70-012							37.93	85.20				
	DDH-04-70-012							85.20	85.78	4	0.01	0.07	0.22
	DDH-04-70-012							85.78	86.27	101	0.28	0.05	2.00
	DDH-04-70-012							86.27	86.79	1	0.01	0.04	0.05
	DDH-04-70-012							86.79	105.00				
	DDH-04-70-012							105.00	105.96	3.5	0.05	0.06	0.14
	DDH-04-70-012							105.96	106.48	27	0.08	0.05	0.09
	DDH-04-70-012							106.48	107.17	120	0.10	0.15	15.20
	DDH-04-70-012							107.17	108.11	41.2	0.35	0.09	2.00
	DDH-04-70-012							108.11	111.68				
	DDH-04-70-012							111.68	112.25	12	0.01	0.03	1.16
	DDH-04-70-012							112.25	120.00				
6 de													
Ag	DDH-04-030	030	7,644,926	4,479	210.15	11°	-58°		3.77				
	DDH-04-030							3.77	151.75				
	DDH-04-030							151.75	152.58	4.5	0.04	0.03	0.03
	DDH-04-030							152.58	153.45	573	1.04	0.15	0.40
	DDH-04-030							153.45	154.39	2	0.01	0.03	0.05
	DDH-04-030							154.39	172.19				
	DDH-04-030							172.19	173.23	3.5	0.01	0.04	0.07
	DDH-04-030							173.23	174.11	170	1.24	0.36	0.84
	DDH-04-030							174.11	174.71	182	0.96	2.20	0.84
	DDH-04-030							174.71	175.31	3	0.01	0.04	0.08
	DDH-04-030							175.31	177.06				
	DDH-04-030							177.06	177.49	5.5	0.60	0.02	0.10
	DDH-04-030							177.49	179.18				
	DDH-04-030							179.18	179.75	2	0.01	0.02	0.02
	DDH-04-030							179.75	180.15	44.5	0.38	0.02	0.06
	DDH-04-030							180.15	181.60	1.5	0.01	0.14	0.02
	DDH-04-030							181.60	182.30	5	0.05	0.02	0.06
	DDH-04-030							182.30	183.23	101	0.72	0.03	0.17
	DDH-04-030							183.23	188.30				
	DDH-04-030							188.30	189.15	7	0.06	0.03	0.06
	DDH-04-030							189.15	189.83	3.5	0.01	0.08	0.06
	DDH-04-030							189.83	190.48	5.5	0.09	0.03	0.10
	DDH-04-030							190.48	192.24	355	4.60	0.44	2.00
	DDH-04-030							192.24	193.54	6.5	0.10	0.05	0.10

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-030						193.54	194.49	5	0.07	0.04	0.07
DDH-04-030						194.49	195.36	3	0.01	0.03	0.05
DDH-04-030						195.36	196.36	2	0.01	0.02	0.03
DDH-04-030						196.36	197.53	2.5	0.01	0.04	0.02
DDH-04-030						197.53	204.53				
DDH-04-030						204.53	204.79	5	0.01	0.03	0.01
DDH-04-030						204.79	205.24	173	1.44	0.05	0.26
DDH-04-030						205.24	205.67	4.8	0.01	0.02	0.02
DDH-04-030						205.67	210.15				
Litoc DDH-04-030	1,148	7,645,081	4,496	186.10	2° -60°		8.14				
DDH-04-031						8.14	28.80				
DDH-04-031						28.80	29.68				
DDH-04-031						29.68	40.52				
DDH-04-031						40.52	43.10				
DDH-04-031						43.10	161.20				
DDH-04-031						161.20	162.15	2.5	0.01	0.11	0.25
DDH-04-031						162.15	162.94	186	0.18	0.04	6.80
DDH-04-031						162.94	163.80	9.5	0.02	0.03	0.04
DDH-04-031						163.80	164.73	1.0	0.01	0.02	0.34
DDH-04-031						164.73	165.64	4.5	0.01	0.03	0.96
DDH-04-031						165.64	166.54	16	0.05	0.03	0.96
DDH-04-031						166.54	167.47	62.5	0.15	0.03	2.40
DDH-04-031						167.47	168.38	11	0.02	0.03	0.60
DDH-04-031						168.38	169.33	33.5	0.03	0.03	1.68
DDH-04-031						169.33	170.25	125	0.06	0.06	0.88
DDH-04-031						170.25	171.19	121	0.20	0.05	1.68
DDH-04-031						171.19	172.16	24	0.08	0.03	0.84
DDH-04-031						172.16	173.12	4.5	0.01	0.04	0.40
DDH-04-031						173.12	174.37	3	0.01	0.03	0.11
DDH-04-031						174.37	174.99	39.5	0.04	0.03	6.80
DDH-04-031						174.99	175.94	2.5	0.01	0.02	0.06
DDH-04-031						175.94	177.33	12	0.01	0.02	0.32
DDH-04-031						177.33	177.85	49.5	0.04	0.08	10.10
DDH-04-031						177.85	178.80	3	0.01	0.02	0.60
DDH-04-031						178.80	179.77	2.5	0.01	0.03	0.14
DDH-04-031						179.77	186.10				
Litoc DDH-04-032	1,075	7,645,187	4,497	75.50	356° -45°		8.00				
DDH-04-032						8.00	56.56				
DDH-04-032						56.56	57.44	1.5	0.01	0.01	0.03
DDH-04-032						57.44	57.92	1.5	0.01	0.01	0.03
DDH-04-032						57.92	58.43	1.5	0.01	0.01	0.02
DDH-04-032						58.43	75.50				
Litoc DDH-04-033	1,882	7,645,141	4,484	54.50	360° -45°		7.50				
DDH-04-033						7.50	13.13				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-70-013						154.79	155.50	1.5	0.01	0.01	0.02		
DDH-04-70-013						155.50	156.35	3	0.01	0.02	0.05		
DDH-04-70-013						156.35	156.74	15	0.02	0.05	0.12		
DDH-04-70-013						156.74	158.10	1.5	0.01	0.01	0.02		
DDH-04-70-013						158.10	159.06	1.5	0.01	0.02	0.02		
DDH-04-70-013						159.06	159.58	3	0.01	0.03	0.06		
DDH-04-70-013						159.58	160.01	18.5	0.02	0.07	0.26		
DDH-04-70-013						160.01	160.47	2	0.02	0.02	0.04		
DDH-04-70-013						160.47	173.28						
DDH-04-70-013						173.28	174.22	2	0.03	0.03	0.24		
DDH-04-70-013						174.22	175.00	4.5	0.08	0.07	0.12		
DDH-04-70-013						175.00	176.09	30	0.24	0.04	0.10		
DDH-04-70-013						176.09	176.98	405	2.80	0.18	2.20		
DDH-04-70-013						176.98	177.66	196	0.72	0.10	0.44		
DDH-04-70-013						177.66	178.87	16	0.08	0.02	0.09		
DDH-04-70-013						178.87	180.13	2	0.01	0.01	0.03		
DDH-04-70-013						180.13	181.06	4.5	0.01	0.02	0.03		
DDH-04-70-013						181.06	203.22						
DDH-04-70-013						203.22	203.64	2.5	0.01	0.02	0.04		
DDH-04-70-013						203.64	204.03	12.5	0.01	0.09	0.26		
DDH-04-70-013						204.03	204.41	1.5	0.01	0.03	0.03		
DDH-04-70-013						204.41	208.00						
Litona	DDH-04-034	7,009	7,645,129	4,482	111.60	357°	-45°				9.60		
	DDH-04-034										9.60	62.58	
	DDH-04-034										62.58	94.48	
	DDH-04-034							1.5	0.01	0.02	0.01		
	DDH-04-034							0.5	0.01	0.03	0.01		
	DDH-04-034							1	0.01	0.02	0.01		
	DDH-04-034							0.5	0.01	0.02	0.02		
	DDH-04-034							66	0.16	0.44	4.60		
	DDH-04-034							185	1.16	0.23	2.40		
	DDH-04-034							7.5	0.03	0.10	0.26		
	DDH-04-034							5	0.02	0.06	0.42		
	DDH-04-034							100.71	101.65	12.5	0.08	0.08	0.96
	DDH-04-034							101.65	102.35	1.5	0.03	0.02	0.07
	DDH-04-034							102.35	111.60				
Guernica													
II	DDH-04-035	8,835	7,645,549	4,518	256.70	193	-67°				7.59		
	DDH-04-035										7.59	141.49	
	DDH-04-035							775	0.56	0.13	0.28		
	DDH-04-035							1509	0.88	0.07	0.27		
	DDH-04-035							146.49	246.49				
	DDH-04-035							246.49	246.77	8	0.04	0.08	0.05

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-70-014						72.70	73.41	5.6	0.01	0.02	0.31
DDH-04-70-014						73.41	74.73	17.6	0.01	0.04	0.52
DDH-04-70-014						74.73	84.10				
DDH-04-036	7,758	7,645,366	4,529	208.60	151°	-65°		6.10			
DDH-04-036							6.10	46.60			
DDH-04-036							46.60	47.30	21.6	0.19	0.20
DDH-04-036							47.30	48.26	6.4	0.01	0.04
DDH-04-036							48.26	49.22	2932	0.74	0.50
DDH-04-036							49.22	50.16	81.6	0.27	0.04
DDH-04-036							50.16	51.13	12	0.05	0.07
DDH-04-036							51.13	52.06	8	0.01	0.04
DDH-04-036							52.06	52.61	36.8	0.17	0.19
DDH-04-036							52.61	106.06			
DDH-04-036							106.06	106.60	7.2	0.01	0.01
DDH-04-036							106.60	107.08	164	0.07	0.04
DDH-04-036							107.08	107.67	4.8	0.01	0.02
DDH-04-036							107.67	127.17			
DDH-04-036							127.17	127.72	22.4	0.01	0.02
DDH-04-036							127.72	128.23	1993	0.56	5.80
DDH-04-036							128.23	128.76	2	0.01	0.02
DDH-04-036							128.76	132.85			
DDH-04-036							132.85	133.49	3.2	0.01	0.02
DDH-04-036							133.49	134.52	110	0.02	0.04
DDH-04-036							134.52	135.56	323	0.80	0.64
DDH-04-036							135.56	136.22	5.6	0.01	0.03
DDH-04-036							136.22	189.00			
DDH-04-036							189.00	189.65	24	0.17	0.07
DDH-04-036							189.65	190.60	221	1.04	0.38
DDH-04-036							190.60	191.25	7.2	0.01	0.03
DDH-04-036							191.25	195.96			
DDH-04-036							195.96	196.45	11.2	0.01	0.01
DDH-04-036							196.45	197.08	275	0.56	0.05
DDH-04-036							197.08	197.56	5.6	0.01	0.02
DDH-04-036							197.56	208.60			
DDH-04-70-015	15,641	7,645,252	4,370	76.80	61°	-61°		54.30			
DDH-04-70-015							54.30	54.80	4	0.01	0.03
DDH-04-70-015							54.80	55.76	7.2	0.01	0.03
DDH-04-70-015							55.76	56.70	11.2	0.04	0.04
DDH-04-70-015							56.70	57.25	8	0.01	0.04
DDH-04-70-015							57.25	76.80			
DDH-04-70-016	16,520	7,645,319	4,370	130.80	177°	-46°		4.31			
DDH-04-70-016							4.31	5.27	8	0.01	0.02

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE								Ag					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	(g/t)	Cu %	Pb %	Zn %
								5.27	5.80	37.6	0.48	0.27	0.17
								5.80	9.04				
								9.04	9.39	4.8	0.01	0.02	0.04
								9.39	10.73	27.2	0.07	0.08	0.09
								10.73	11.50	7.2	0.01	0.03	0.05
								11.50	20.80				
								20.80	21.32	28	0.03	0.06	0.06
								21.32	22.15	13.6	0.01	0.02	0.04
								22.15	44.80				
								44.80	45.55	9.6	0.01	0.04	0.03
								45.55	54.83				
								54.83	55.27	13.6	0.01	0.01	0.04
								55.27	56.21	34.4	0.14	0.08	0.08
								56.21	56.78	4.8	0.01	0.02	0.04
								56.78	95.65				
								95.65	104.80				
								104.80	111.23				
								111.23	111.53	6	0.01	0.04	0.16
								111.53	130.80				
Desert	DDH-03-037	7,877	7,645,241	4,515	181.80	194°	-63°		6.90				
	DDH-03-037							6.90	173.82				
	DDH-03-037							173.82	174.62	12.8	0.01	0.03	0.24
	DDH-03-037							174.62	175.14	348	0.72	0.12	2.60
	DDH-03-037							175.14	176.22	4	0.01	0.03	0.17
	DDH-03-037							176.22	176.90	16	0.02	0.02	0.52
	DDH-03-037							176.90	181.80				
Lito	DDH-04-038	8,947	7,645,010	4,461	280.70	357°	-70°		7.00				
	DDH-04-038							7.00	10.00				
	DDH-04-038							10.00	13.00				
	DDH-04-038							13.00	100.87				
	DDH-04-038							100.87	101.86	0.8	0.01	0.01	0.21
	DDH-04-038							101.86	103.70				
	DDH-04-038							103.70	104.89	0.6	0.01	0.01	0.06
	DDH-04-038							104.89	105.45	6.2	0.00	0.14	0.85
	DDH-04-038							105.45	106.69	2.6	0.00	0.06	0.32
	DDH-04-038							106.69	107.58	0.6	0.00	0.02	0.09
	DDH-04-038							107.58	108.52	0.6	0.01	0.01	0.38
	DDH-04-038							108.52	108.97	1.9	0.01	0.02	0.92
	DDH-04-038							108.97	134.15				
	DDH-04-038							134.15	134.59	85.3	0.12	0.01	0.87
	DDH-04-038							134.59	134.93	500	1.00	0.03	3.95

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-038	134.93	136.05	10.6	0.16	0.01	0.24
DDH-04-038	136.05	137.03	37.6	0.14	0.01	0.43
DDH-04-038	137.03	137.90	2.4	0.21	0.01	0.25
DDH-04-038	137.90	138.82	463	1.75	0.04	9.40
DDH-04-038	138.82	139.87	7.1	0.14	0.01	0.28
DDH-04-038	139.87	147.13				
DDH-04-038	147.13	148.10	59.9	0.10	0.01	0.97
DDH-04-038	148.10	149.02	516	0.55	0.03	1.67
DDH-04-038	149.02	149.95	32.1	0.12	0.01	0.14
DDH-04-038	149.95	150.75	22.7	0.18	0.01	0.07
DDH-04-038	150.75	151.26	627	1.18	0.01	0.04
DDH-04-038	151.26	151.77	65.9	0.12	0.01	?
DDH-04-038	151.77	152.83	78.1	0.15	0.01	0.05
DDH-04-038	152.83	153.98	12.8	0.16	0.01	0.84
DDH-04-038	153.98	154.70	6.9	0.05	0.01	0.13
DDH-04-038	154.70	167.85				
DDH-04-038	167.85	168.70	6.9	0.07	0.01	0.03
DDH-04-038	168.70	169.72	12.8	0.10	0.01	0.52
DDH-04-038	169.72	170.52	100	1.62	0.02	0.61
DDH-04-038	170.52	170.97	8.8	0.03	0.02	0.04
DDH-04-038	170.97	171.46	32.6	0.63	0.05	0.29
DDH-04-038	171.46	172.42	7.1	0.02	0.03	0.11
DDH-04-038	172.42	173.27	11.0	0.26	0.06	0.18
DDH-04-038	173.27	174.17	6.7	0.04	0.03	0.17
DDH-04-038	174.17	175.11	5.5	0.06	0.02	0.14
DDH-04-038	175.11	234.59				
DDH-04-038	234.59	235.42				
DDH-04-038	235.42	240.87				
DDH-04-038	240.87	241.70	2.7	0.09	0.01	0.01
DDH-04-038	241.70	242.65	5.2	0.19	0.01	0.04
DDH-04-038	242.65	243.98	2.1	0.11	0.01	0.02
DDH-04-038	243.98	245.67	1	0.01	0.02	0.01
DDH-04-038	245.67	246.83	10	0.75	0.01	0.08
DDH-04-038	246.83	247.88	11.6	0.81	0.00	0.12
DDH-04-038	247.88	248.75	20.9	2.21	0.01	0.16
DDH-04-038	248.75	249.72	21.2	2.51	0.01	0.20
DDH-04-038	249.72	250.67	20.2	1.85	0.01	0.19
DDH-04-038	250.67	251.57	24.4	2.20	0.00	0.19
DDH-04-038	251.57	252.04	34.4	1.54	0.01	0.16
DDH-04-038	252.04	253.07	15.7	0.85	0.01	0.14
DDH-04-038	253.07	254.30	1.1	0.01	0.01	0.09
DDH-04-038	254.30	255.24	0.2	0.00	0.01	0.08
DDH-04-038	255.24	256.17	0.2	0.00	0.00	0.08
DDH-04-038	256.17	257.10	0.2	0.00	0.00	0.07
DDH-04-038	257.10	258.08	0.4	0.00	0.00	0.16

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE													
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
								258.08	258.98	0.6	0.00	0.00	0.07
								258.98	259.96	0.3	0.00	0.00	0.09
								259.96	260.91	0.4	0.00	0.02	0.18
								260.91	262.16	2.7	0.01	0.09	0.84
								262.16	262.79	130	0.44	0.30	0.91
								262.79	263.63	12.7	0.16	0.06	0.62
								263.63	264.59	62	0.23	0.05	0.23
								264.59	265.53	169	0.11	0.04	0.14
								265.53	266.48	37.7	0.11	0.03	0.07
								266.48	267.45	5.2	0.01	0.03	0.10
								267.45	268.41	3.5	0.04	0.03	0.18
								268.41	269.10	3.9	0.06	0.02	0.22
								269.10	274.70				
								274.70	275.14	1.9	0.00	0.01	0.01
								275.14	276.09	1.2	0.00	0.01	0.02
								276.09	277.05	0.2	0.00	0.00	0.02
								277.05	277.72	0.2	0.00	0.01	0.07
								277.72	280.70				
Described	DDH-04-039	7,713	7,645,257	4,512	181.60	194°	-74°		5.39				
	DDH-04-039							5.39	169.37				
	DDH-04-039							169.37	170.48	19.4	0.01	0.01	4.23
	DDH-04-039							170.48	173.24				
	DDH-04-039							173.24	174.17	9.4	0.01	0.01	0.72
	DDH-04-039							174.17	175.03	160	0.08	0.05	8.76
	DDH-04-039							175.03	175.79	183	0.10	0.04	6.09
	DDH-04-039							175.79	176.58	4.2	0.00	0.01	0.05
	DDH-04-039							176.58	181.60				
6 de	DDH-04-30-017	7,530	7,645,294	4,413	174.00	188°	-47°		54.20				
Ag	DDH-04-30-017							54.20	57.00				
	DDH-04-30-017							57.00	78.26				
	DDH-04-30-017							78.26	78.92	1.1	0.00	0.01	0.04
	DDH-04-30-017							78.92	80.33	34.7	0.02	0.04	0.23
	DDH-04-30-017							80.33	81.02	2.1	0.00	0.01	0.06
	DDH-04-30-017							81.02	81.67	0.7	0.00	0.00	0.03
	DDH-04-30-017							81.67	90.12				
	DDH-04-30-017							90.12	91.09	4.3	0.01	0.01	0.26
	DDH-04-30-017							91.09	91.79	17.3	0.02	0.02	1.69
	DDH-04-30-017							91.79	93.01	63.1	0.22	0.01	1.00
	DDH-04-30-017							93.01	93.96	8.6	0.01	0.00	0.48
	DDH-04-30-017							93.96	94.93	0.2	0.02	0.00	0.54

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-30-017						94.93	95.50	9.4	0.01	0.01	0.22
DDH-04-30-017						95.50	109.08				
DDH-04-30-017						109.08	109.75	0.8	0.00	0.01	0.10
DDH-04-30-017						109.75	110.90	6.5	0.03	0.03	0.33
DDH-04-30-017						110.90	111.83	4.2	0.01	0.06	1.00
DDH-04-30-017						111.83	112.29	0.9	0.00	0.00	0.03
DDH-04-30-017						112.29	122.08				
DDH-04-30-017						122.08	123.20	2.2	0.00	0.01	0.31
DDH-04-30-017						123.20	124.31	1.3	0.00	0.01	0.06
DDH-04-30-017						124.31	167.83				
DDH-04-30-017						167.83	168.97	1.5	0.01	0.00	0.05
DDH-04-30-017						168.97	169.45	2.9	0.01	0.01	0.07
DDH-04-30-017						169.45	170.16	169	1.94	0.33	2.77
DDH-04-30-017						170.16	171.09	27.9	0.15	0.06	1.07
DDH-04-30-017						171.09	171.86	6.8	0.25	0.03	0.17
DDH-04-30-017						171.86	172.84	2.9	0.00	0.02	0.11
DDH-04-30-017						172.84	174.00				
Arturo	DDH-04-040	7,432	7,645,168	4,535	93.20	213°	-49°				2.72
	DDH-04-040										2.72
	DDH-04-040										72.20
	DDH-04-040							17.5	0.01	0.24	1.23
	DDH-04-040							5.3	0.00	0.07	0.31
	DDH-04-040							57.9	0.06	0.30	6.63
	DDH-04-040							2	0.00	0.04	0.26
	DDH-04-040							17	0.03	0.19	0.96
	DDH-04-040							18.1	0.02	0.26	1.16
	DDH-04-040							4.2	0.00	0.21	0.49
	DDH-04-040							9.6	0.01	0.31	0.79
	DDH-04-040							101	0.22	0.42	5.28
	DDH-04-040							16.8	0.01	0.18	0.56
	DDH-04-040							5.8	0.00	0.18	0.62
	DDH-04-040							6.8	0.01	0.17	0.46
	DDH-04-040							55	0.26	0.28	1.22
	DDH-04-040							114	0.26	0.35	3.00
	DDH-04-040							32.4	0.06	0.32	1.20
	DDH-04-040										88.31
	DDH-04-040										93.20
6 de											
Agosto	DDH-04-30-018	27	7,645,293	4,413	150.40	231°	-36°				105.55
	DDH-04-30-018										105.55
	DDH-04-30-018										113.83
	DDH-04-30-018										113.83
	DDH-04-30-018							2.2	0.00	0.01	0.14
	DDH-04-30-018										114.03
	DDH-04-30-018							2.6	0.01	0.01	0.29
	DDH-04-30-018							49.5	0.14	0.05	0.16
	DDH-04-30-018							36.1	0.16	0.10	1.73
	DDH-04-30-018							1.0	0.00	0.00	0.09

Hole		Collar Co-ordinates			Interval Orientation			Assay Results					
Identification	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-04-30-018								142.50	143.53	6.5	0.02	0.02	0.41
DDH-04-30-018								143.53	144.46	290	0.68	0.16	2.41
DDH-04-30-018								144.46	145.46	61.9	0.21	0.17	0.44
DDH-04-30-018								145.46	145.89	27.9	0.06	0.01	0.12
DDH-04-30-018								145.89	146.54	4.6	0.01	0.01	0.11
DDH-04-30-018								146.54	152.40				
Unid	DDH-04-041	7,829	7,645,364	4,536	171.10	167°	-60°		8.15				
	DDH-04-041							8.15	132.90				
	DDH-04-041							132.90	133.60	1.5	0.00	0.01	0.26
	DDH-04-041							133.60	134.96	0.7	0.00	0.01	0.09
	DDH-04-041							134.96	136.25	1.8	0.00	0.06	0.30
	DDH-04-041							136.25	137.19	2.1	0.00	0.03	0.26
	DDH-04-041							137.19	138.16	256	0.30	0.18	16.35
	DDH-04-041							138.16	139.11	3.6	0.00	0.06	0.12
	DDH-04-041							139.11	140.03	2.6	0.00	0.01	0.05
	DDH-04-041							140.03	163.09				
	DDH-04-041							163.09	163.60	109	0.09	0.48	14.10
	DDH-04-041							163.60	171.10				
Lito	DDH-04-042	7,008	7,645,006	4,466	253.80	359°	-62°		10.80				
	DDH-04-042							10.80	114.17				
	DDH-04-042							114.17	115.25	205	0.56	0.10	3.58
	DDH-04-042							115.25	132.51				
	DDH-04-042							132.51	133.20	3.3	0.01	0.02	0.25
	DDH-04-042							133.20	133.80	12.9	0.05	0.02	5.04
	DDH-04-042							133.80	134.26	9.9	0.03	0.03	0.07
	DDH-04-042							134.26	157.96				
	DDH-04-042							157.96	158.35	10.3	0.08	0.01	0.14
	DDH-04-042							158.35	158.87	61.8	0.22	0.05	6.33
	DDH-04-042							158.87	159.30	15.2	0.03	0.01	0.59
	DDH-04-042							159.30	193.80				
	DDH-04-042							193.80	194.58	1.8	0.00	0.00	0.45
	DDH-04-042							194.58	195.11	34.1	0.16	0.01	2.08
	DDH-04-042							195.11	195.68	3.1	0.01	0.01	0.14
	DDH-04-042							195.68	196.24	4.9	0.01	0.01	0.89
	DDH-04-042							196.24	196.94	2.3	0.00	0.00	0.21
	DDH-04-042							196.94	197.49	265	0.40	0.01	1.86
	DDH-04-042							197.49	198.57	3	0.01	0.00	0.55
	DDH-04-042							198.57	199.23	677	0.94	0.02	9.54
	DDH-04-042							199.23	200.44	1.7	0.00	0.00	0.03
	DDH-04-042							200.44	201.11	33.2	0.34	0.01	0.91
	DDH-04-042							201.11	202.82	1.8	0.00	0.00	0.06

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-042	202.82	204.34	110	0.30	0.01	2.78
DDH-04-042	204.34	206.05	11.1	0.05	0.00	0.20
DDH-04-042	206.05	207.35	101	0.24	0.01	0.93
DDH-04-042	207.35	208.29	9.0	0.10	0.01	0.12
DDH-04-042	208.29	209.21	52.2	0.31	0.01	0.49
DDH-04-042	209.21	210.00	3.2	0.03	0.00	0.05
DDH-04-042	210.00	210.74	154	1.46	0.02	5.54
DDH-04-042	210.74	211.93	3.8	0.00	0.01	0.07
DDH-04-042	211.93	213.07	5.5	0.02	0.01	0.25
DDH-04-042	213.07	214.05	41	0.38	0.01	4.61
DDH-04-042	214.05	215.03	2.5	0.01	0.00	0.38
DDH-04-042	215.03	216.40	10.2	0.04	0.01	0.97
DDH-04-042	216.40	218.31	0.7	0.00	0.00	0.01
DDH-04-042	218.31	219.25	6.3	0.06	0.00	0.73
DDH-04-042	219.25	221.08	1.5	0.00	0.00	0.01
DDH-04-042	221.08	222.20	5.9	0.11	0.00	0.39
DDH-04-042	222.20	222.85	6.1	0.08	0.00	0.93
DDH-04-042	222.85	224.36	1.3	0.00	0.00	0.01
DDH-04-042	224.36	225.41				
DDH-04-042	225.41	226.68				
DDH-04-042	226.68	237.45				
DDH-04-042	237.45	237.92	20.1	0.07	0.02	1.88
DDH-04-042	237.92	238.80	3.7	0.02	0.01	0.02
DDH-04-042	238.80	239.72	202	0.33	0.01	0.10
DDH-04-042	239.72	240.62	7.5	0.01	0.01	0.01
DDH-04-042	240.62	241.43	90	1.56	0.01	0.10
DDH-04-042	241.43	242.15	6.8	0.01	0.01	0.84
DDH-04-042	242.15	235.80				

6 de						
Agosto	DDH-04-30-019	7,645,294	4,413	166.50	231° -50°	0.99
	DDH-04-30-019					0.99
	DDH-04-30-019					1.52
	DDH-04-30-019					100.84
	DDH-04-30-019					100.84
	DDH-04-30-019					102.00
	DDH-04-30-019					102.00
	DDH-04-30-019					102.74
	DDH-04-30-019					102.74
	DDH-04-30-019					103.52
	DDH-04-30-019					103.52
	DDH-04-30-019					105.16
	DDH-04-30-019					105.16
	DDH-04-30-019					105.16
	DDH-04-30-019					125.55
	DDH-04-30-019					125.55
	DDH-04-30-019					132.93
	DDH-04-30-019					132.93
	DDH-04-30-019					133.69
	DDH-04-30-019					133.69
	DDH-04-30-019					134.79
	DDH-04-30-019					134.79
	DDH-04-30-019					135.75
	DDH-04-30-019					135.75
	DDH-04-30-019					136.70
	DDH-04-30-019					136.70
	DDH-04-30-019					143.17
	DDH-04-30-019					143.17
	DDH-04-30-019					144.23
	DDH-04-30-019					144.23

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	HOLE N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-04-30-019				144.92			150.93					
	DDH-04-30-019				150.93			151.93	3.6	0.01	0.02	0.67	
	DDH-04-30-019				151.93			156.00					
	DDH-04-30-019				156.00			156.37					
	DDH-04-30-019				156.37			157.03	4.1	0.02	0.02	0.25	
	DDH-04-30-019				157.03			158.25	0.7	0.00	0.01	0.29	
	DDH-04-30-019				158.25			159.39	3.9	0.00	0.01	0.08	
	DDH-04-30-019				159.39			160.21	31.8	0.03	0.04	0.47	
	DDH-04-30-019				160.21			166.50					
Unión	DDH-04-043	3,874	7,645,335	4,529	123.05	166°	-57°		9.05				
	DDH-04-043				9.05			87.85					
	DDH-04-043				87.85			89.09	0.2	0.00	0.01	0.04	
	DDH-04-043				89.09			90.01	0.2	0.00	0.02	0.04	
	DDH-04-043				90.01			90.91	4.0	0.01	0.16	0.43	
	DDH-04-043				90.91			91.81	0.4	0.00	0.02	0.03	
	DDH-04-043				91.81			92.73	0.3	0.01	0.01	0.03	
	DDH-04-043				92.73			93.51	2.2	0.01	0.27	0.31	
	DDH-04-043				93.51			96.74					
	DDH-04-043				96.74			97.27	0.9	0.00	0.01	0.07	
	DDH-04-043				97.27			111.05					
	DDH-04-043				111.05			111.82	0.8	0.00	0.02	0.08	
	DDH-04-043				111.82			113.78					
	DDH-04-043				113.78			114.33	2.7	0.00	0.08	0.29	
	DDH-04-043				114.33			117.34					
	DDH-04-043				117.34			117.87	1	0.00	0.04	0.13	
	DDH-04-043				117.87			123.05					
Desea	DDH-04-044	3,586	7,645,319	4,471	156.20	201°	-56°		2.50				
	DDH-04-044				2.50			138.54					
	DDH-04-044				138.54			139.20	5.2	0.00	0.02	0.36	
	DDH-04-044				139.20			139.82	2.4	0.00	0.01	0.15	
	DDH-04-044				139.82			140.50	4.8	0.01	0.01	1.10	
	DDH-04-044				140.50			156.20					
Zona de Altera	DDH-04-30-020	3,838	7,645,014	4,418	182.80	175°	-09°		12.96				
	DDH-04-30-020				12.96			13.72	128	0.80	0.19	1.01	
	DDH-04-30-020				13.72			14.66	192	1.06	0.13	5.43	
	DDH-04-30-020				14.66			15.57	32.6	0.04	0.07	1.40	
	DDH-04-30-020				15.57			16.48	31.5	0.08	0.02	0.18	
	DDH-04-30-020				16.48			111.94					
	DDH-04-30-020				111.94			131.17					
	DDH-04-30-020				131.17			131.80					

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-30-020						131.80	132.56	13.6	0.03	0.23	2.84		
DDH-04-30-020						132.56	133.45	24.8	0.03	0.44	3.70		
DDH-04-30-020						133.45	134.78	2.9	0.01	0.10	0.39		
DDH-04-30-020						134.78	156.56						
DDH-04-30-020						156.56	157.34	1.9	0.01	0.09	0.30		
DDH-04-30-020						157.34	158.11	0.8	0.00	0.03	0.06		
DDH-04-30-020						158.11	159.05	0.7	0.01	0.01	0.01		
DDH-04-30-020						159.05	159.92	6.4	0.03	0.11	0.33		
DDH-04-30-020						159.92	160.62	85.8	0.12	1.42	14.05		
DDH-04-30-020						160.62	161.63	111	0.33	0.73	5.37		
DDH-04-30-020						161.63	162.88						
DDH-04-30-020						162.88	163.85	2.1	0.01	0.08	0.41		
DDH-04-30-020						163.85	174.86						
DDH-04-30-020						174.86	175.79	37	0.03	0.56	1.86		
DDH-04-30-020						175.79	176.87	2.5	0.01	0.17	0.31		
DDH-04-30-020						176.87	182.80						
Unión	DDH-04-045	7,898	7,645,399	4,542	195.05	167°	-58°				6.05		
	DDH-04-045							6.05			172.12		
	DDH-04-045							172.12	172.82	18.3	0.01	0.01	1.49
	DDH-04-045							172.82	178.28				
	DDH-04-045							178.28	178.80	3.9	0.00	0.09	0.25
	DDH-04-045							178.80	195.05				
Litora	DDH-04-046	7,078	7,644,983	4,485	321.06	358°	-58°					11.64	
	DDH-04-046							11.64				24.76	
	DDH-04-046							24.76				27.88	
	DDH-04-046							27.88				29.96	
	DDH-04-046							29.96				35.66	
	DDH-04-046							35.66				129.06	
	DDH-04-046							129.06				130.48	
	DDH-04-046							130.48				140.31	
	DDH-04-046							140.31				142.06	
	DDH-04-046							142.06				196.72	
	DDH-04-046							196.72	197.34	3740	1.13	0.62	1.23
	DDH-04-046							197.34				208.54	
	DDH-04-046							208.54				210.96	
	DDH-04-046							210.96				266.72	
	DDH-04-046							266.72				267.97	
	DDH-04-046							267.97				321.06	
Sophia	DDH-04-047	7,688	7,645,838	4,385	82.35	187°	-40°					7.99	
	DDH-04-047							7.99				73.51	
	DDH-04-047							73.51	74.36	29	0.02	0.25	0.64
	DDH-04-047							74.36	74.82	42.1	0.01	0.16	0.15

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE								Ag					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	(g/t)	Cu %	Pb %	Zn %
								74.82	75.31	390	0.19	1.00	0.21
								75.31	76.17	97.2	0.02	0.33	0.14
								76.17	77.18	6.1	0.00	0.34	0.36
								77.18	77.70	0.9	0.00	0.06	0.47
								77.70	82.35				
Vein	DDH-04-30-02	7,645,137	7,645,018	4,415	153.00	169°	-10°		38.53				
Vein	DDH-04-30-021							38.53	39.20	16.4	0.03	0.00	0.72
	DDH-04-30-021							39.20	40.00	324	0.24	0.01	1.30
	DDH-04-30-021							40.00	40.35	11.6	0.02	0.00	0.25
	DDH-04-30-021							40.35	78.68				
	DDH-04-30-021							78.68	79.35	77.6	0.22	0.02	2.84
	DDH-04-30-021							79.35	79.88	18.5	0.03	0.01	0.16
	DDH-04-30-021							79.88	80.71	114	0.21	0.03	1.99
	DDH-04-30-021							80.71	124.17				
	DDH-04-30-021							124.17	124.63	127	0.08	0.01	0.36
	DDH-04-30-021							124.63	136.59				
	DDH-04-30-021							136.59	137.11	6.2	0.01	0.00	0.38
	DDH-04-30-021							137.11	137.55	37.8	0.11	0.01	0.58
	DDH-04-30-021							137.55	138.12	27.1	0.27	0.01	0.53
	DDH-04-30-021							138.12	153.00				
Column	DDH-04-048	7,853	7,645,746	4,491	139.35	209°	-76°		12.70				
	DDH-04-048							12.70	39.23				
	DDH-04-048							39.23	40.00	34.5	0.02	0.05	0.04
	DDH-04-048							40.00	54.54				
	DDH-04-048							54.54	55.62	420	0.07	0.08	0.36
	DDH-04-048							55.62	56.71	140	0.04	0.07	0.58
	DDH-04-048							56.71	123.52				
	DDH-04-048							123.52	124.25	475	0.04	0.02	0.15
	DDH-04-048							124.25	128.96				
	DDH-04-048							128.96	130.20	71.8	0.00	0.04	0.11
	DDH-04-048							130.20	131.53	625	0.07	0.12	0.38
	DDH-04-048							131.53	132.74	1530	0.57	0.33	0.61
	DDH-04-048							132.74	139.35				
Unit	DDH-04-049	7,705	7,645,407	4,523	267.75	160°	-58°		10.83				
	DDH-04-049							10.83	11.45				
	DDH-04-049							11.45	12.22	2.5	0.00	0.01	0.01
	DDH-04-049							12.22	13.12	1.3	0.00	0.01	0.01
	DDH-04-049							13.12	13.90	0.4	0.00	0.00	0.01
	DDH-04-049							13.90	53.23				
	DDH-04-049							53.23	54.15	13.8	0.00	0.24	1.41

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-049						54.15	131.07						
DDH-04-049						131.07	131.71	8.4	0.00	0.01	0.08		
DDH-04-049						131.71	133.25	300	0.03	0.06	1.27		
DDH-04-049						133.25	134.04	5.1	0.00	0.01	0.14		
DDH-04-049						134.04	168.53						
DDH-04-049						168.53	169.30	14.9	0.00	0.03	0.12		
DDH-04-049						169.30	178.23						
DDH-04-049						178.23	179.20	59.3	0.01	0.07	0.35		
DDH-04-049						179.20	179.99	6.5	0.00	0.01	0.06		
DDH-04-049						179.99	181.26	12.6	0.00	0.03	0.12		
DDH-04-049						181.26	182.06	167	0.02	0.50	1.98		
DDH-04-049						182.06	182.85	17	0.00	0.06	0.12		
DDH-04-049						182.85	217.53						
DDH-04-049						217.53	218.32	14.1	0.00	0.05	0.17		
DDH-04-049						218.32	250.91						
DDH-04-049						250.91	251.39	0.5	0.00	0.01	0.03		
DDH-04-049						251.39	252.08	374	1.62	0.48	2.40		
DDH-04-049						252.08	252.40	3.2	0.00	0.01	0.02		
DDH-04-049						252.40	252.90	36.1	0.00	0.03	0.34		
DDH-04-049						252.90	253.34	3.1	0.00	0.02	0.07		
DDH-04-049						253.34	258.12						
DDH-04-049						258.12	258.60	1.5	0.00	0.01	0.13		
DDH-04-049						258.60	259.16	202	0.02	0.14	1.04		
DDH-04-049						259.16	259.78	38.4	0.00	0.10	0.47		
DDH-04-049						259.78	260.69	32.9	1.08	0.05	0.35		
DDH-04-049						260.69	261.72	178	0.02	0.11	0.85		
DDH-04-049						261.72	262.23	2.9	0.01	0.01	0.09		
DDH-04-049						262.23	267.75						
Desd	DDH-04-050	9,979	7,645,215	4,525	197.50	185°	-67°				5.83		
	DDH-04-050							5.83	154.20				
	DDH-04-050							154.20	154.61	7.2	0.00	0.01	0.08
	DDH-04-050							154.61	155.12	118	0.01	0.05	5.35
	DDH-04-050							155.12	156.05	215	0.02	0.05	6.44
	DDH-04-050							156.05	157.00	113	0.01	0.05	4.48
	DDH-04-050							157.00	157.73	2.9	0.00	0.01	0.28
	DDH-04-050							157.73	185.89				
	DDH-04-050							185.89	186.56	5.7	0.00	0.01	0.32
	DDH-04-050							186.56	187.43	6.5	0.00	0.02	0.28
	DDH-04-050							187.43	188.31	5.4	0.00	0.02	0.03
	DDH-04-050							188.31	197.50				
6 de	Agos	DDH-04-051	7,642	7,645,463	4,430	136.60	191°	-69°				6.69	
		DDH-04-051						6.69	126.06				
		DDH-04-051						126.06	127.02	30.1	0.00	0.01	0.28

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results				
Vein	HOLE N° Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-04-051						127.02	127.95	14.7	0.00	0.01	0.22
	DDH-04-051						127.95	128.51	10	0.00	0.01	0.50
	DDH-04-051						128.51	136.60				
Colonial	DDH-04-052	7,947	7,645,726	4,481	117.30	207°		6.80				
	DDH-04-052						6.80	81.78				
	DDH-04-052						81.78	82.74	165	0.02	0.07	0.13
	DDH-04-052						82.74	83.75	6.8	0.00	0.01	0.01
	DDH-04-052						83.75	99.41				
	DDH-04-052						99.41	99.95	3.4	0.00	0.01	0.00
	DDH-04-052						99.95	100.78	171	0.02	1.00	0.74
	DDH-04-052						100.78	101.71	0.1	0.01	0.05	0.10
	DDH-04-052						101.71	102.35	876	0.09	0.08	0.19
	DDH-04-052						102.35	103.21	3.6	0.00	0.01	0.02
	DDH-04-052						103.21	106.39				
	DDH-04-052						106.39	106.97	5.7	0.00	0.02	0.02
	DDH-04-052						106.97	117.30				
Desconocido	DDH-04-053	7,358	7,645,886	4,377	89.35	187°		3.45				
	DDH-04-053						3.45	19.20				
	DDH-04-053						19.20	19.89	113	0.01	0.24	0.06
	DDH-04-053						19.89	21.17				
	DDH-04-053						21.17	21.80	8.7	0.00	0.20	0.06
	DDH-04-053						21.80	51.60				
	DDH-04-053						51.60	52.59	1.2	0.00	0.13	0.28
	DDH-04-053						52.59	54.10	607	0.01	0.16	0.02
	DDH-04-053						54.10	55.65	5.3	0.01	0.45	0.03
	DDH-04-053						55.65	56.33	9.7	0.00	0.26	0.04
	DDH-04-053						56.33	58.85				
	DDH-04-053						58.85	59.35				
	DDH-04-053						59.35	61.37				
	DDH-04-053						61.37	89.35				
Unión	DDH-04-054	4,817	7,645,399	4,538	251.00	170°		9.00				
	DDH-04-054						9.00	73.59				
	DDH-04-054						73.59	74.13	10.2	0.49	0.21	0.45
	DDH-04-054						74.13	95.70				
	DDH-04-054						95.70	96.48	2.2	0.00	0.06	0.29
	DDH-04-054						96.48	109.77				
	DDH-04-054						109.77	110.56	21	0.03	0.04	3.71
	DDH-04-054						110.56	182.50				
	DDH-04-054						182.50	183.08	3	0.00	0.00	0.09
	DDH-04-054						183.08	184.31	16.7	0.00	0.04	0.09

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-054						184.31	184.93	1.4	0.00	0.01	0.04	
DDH-04-054						184.93	199.76					
DDH-04-054						199.76	200.74	4.5	0.01	0.02	0.05	
DDH-04-054						200.74	201.52	144	0.11	0.15	0.55	
DDH-04-054						201.52	202.31	201	0.44	0.18	1.65	
DDH-04-054						202.31	203.21	190	0.22	0.11	2.84	
DDH-04-054						203.21	204.12	9.1	0.02	0.03	0.13	
DDH-04-054						204.12	205.06	2.1	0.01	0.01	0.12	
DDH-04-054						205.06	241.28					
DDH-04-054						241.28	242.00	169	0.40	0.10	0.60	
DDH-04-054						242.00	243.09	2.9	0.00	0.02	0.09	
DDH-04-054						243.09	243.64	402	0.05	0.06	0.62	
DDH-04-054						243.64	251.00					
Litoral DDH-04-055	1,153	7,645,020	4,502	253.10	360°	-61°	0.20					
DDH-04-055							0.20					
DDH-04-055							67.29					
DDH-04-055							67.63					
DDH-04-055							67.63					
DDH-04-055							83.43					
DDH-04-055							83.43					
DDH-04-055							84.98					
DDH-04-055							84.98					
DDH-04-055							230.59					
DDH-04-055							230.59	231.53	6.1	0.01	0.01	0.12
DDH-04-055							231.53	232.39	34.1	0.02	0.01	0.45
DDH-04-055							232.39	233.35	0.9	0.00	0.00	0.02
DDH-04-055							233.35	234.30	0.2	0.00	0.00	0.01
DDH-04-055							234.30	235.24	0.2	0.00	0.00	0.01
DDH-04-055							235.24	236.17	0.2	0.00	0.00	0.01
DDH-04-055							236.17	237.08	0.3	0.00	0.00	0.01
DDH-04-055							237.08	237.65	50.3	0.10	0.01	0.98
DDH-04-055							237.65	238.94	4.2	0.06	0.01	0.11
DDH-04-055							238.94	240.28	2.6	0.07	0.01	0.02
DDH-04-055							240.28	241.09	437	0.54	0.01	0.34
DDH-04-055							241.09	241.81	310	0.98	0.01	0.94
DDH-04-055							241.81	242.73	272	0.47	0.01	1.28
DDH-04-055							242.73	243.66	152	0.19	0.00	0.52
DDH-04-055							243.66	244.58	118	0.46	0.00	0.03
DDH-04-055							244.58	245.50	776	4.06	0.01	0.15
DDH-04-055							245.50	246.47	161	4.49	0.01	0.05
DDH-04-055							246.47	247.39	247	1.11	0.01	0.11
DDH-04-055							247.39	248.34	14	0.02	0.01	2.06
DDH-04-055							248.34	249.29	0.8	0.00	0.00	0.01
DDH-04-055							249.29	250.24	0.3	0.00	0.00	0.01
DDH-04-055							250.24	253.10				
Desconocido DDH-04-056	1,948	7,645,728	4,481	160.00	206°	-82°	2.17					
ColonialDDH-04-056							2.17	56.63				

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	HOLE N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
	DDH-04-056							56.63	57.28	128	0.02	0.06	0.62
	DDH-04-056							57.28	130.58				
	DDH-04-056							130.58	131.17	11.4	0.01	0.23	0.13
	DDH-04-056							131.17	137.42				
	DDH-04-056							137.42	138.88	77.6	0.05	0.41	0.42
	DDH-04-056							138.88	160.00				
Colonial	DDH-04-057	052	7,645,722	4,476	147.00	208°	-64°		3.10				
	DDH-04-057							3.10	7.80				
	DDH-04-057							7.80	8.36	1015	0.01	0.05	0.01
	DDH-04-057							8.36	23.76				
	DDH-04-057							23.76	24.36	16.7	0.01	0.02	0.04
	DDH-04-057							24.36	28.45				
	DDH-04-057							28.45	29.17	6.4	0.01	0.02	0.01
	DDH-04-057							29.17	30.34	16.5	0.00	0.01	0.00
	DDH-04-057							30.34	31.34	392	0.02	0.05	0.01
	DDH-04-057							31.34	32.55	4.9	0.00	0.02	0.00
	DDH-04-057							32.55	33.27	1.8	0.00	0.01	0.00
	DDH-04-057							33.27	34.48	79.5	0.01	0.03	0.00
	DDH-04-057							34.48	35.02	10.9	0.01	0.02	0.00
	DDH-04-057							35.02	60.46				
	DDH-04-057							60.46	61.26	21.2	0.01	0.02	0.03
	DDH-04-057							61.26	104.88				
	DDH-04-057							104.88	105.40	61.9	0.02	0.03	0.05
	DDH-04-057							105.40	119.53				
	DDH-04-057							119.53	120.09	107	0.04	0.46	0.23
	DDH-04-057							120.09	128.24				
	DDH-04-057							128.24	129.06	167	0.14	0.60	0.97
	DDH-04-057							129.06	142.95				
	DDH-04-057							142.95	143.71	72.7	0.02	0.04	0.03
	DDH-04-057							143.71	147.00				
Colonial	DDH-04-058	052	7,645,721	4,476	178.60	208°	-78°		2.07				
	DDH-04-058							2.07	14.03				
	DDH-04-058							14.03	15.23	21.4	0.01	0.03	0.02
	DDH-04-058							15.23	17.82				
	DDH-04-058							17.82	19.00	12.7	0.04	0.02	0.04
	DDH-04-058							19.00	19.92	110	0.02	0.05	0.01
	DDH-04-058							19.92	51.66				
	DDH-04-058							51.66	52.73	645	0.28	0.16	0.28
	DDH-04-058							52.73	54.08	4.6	0.00	0.01	0.07
	DDH-04-058							54.08	54.77	963	0.08	0.10	0.15
	DDH-04-058							54.77	100.55				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-058						100.55	101.39	56.5	0.06	0.02	0.11
DDH-04-058						101.39	102.54	38.7	0.03	0.01	0.08
DDH-04-058						102.54	104.05	105	0.06	1.71	0.14
DDH-04-058						104.05	114.20				
DDH-04-058						114.20	114.78	19.6	0.01	0.01	0.08
DDH-04-058						114.78	126.40				
DDH-04-058						126.40	127.00	18.5	0.04	0.02	0.05
DDH-04-058						127.00	127.53	59.2	0.04	0.07	0.05
DDH-04-058						127.53	127.96	17.3	0.05	0.02	0.03
DDH-04-058						127.96	128.35	177	0.14	0.04	0.06
DDH-04-058						128.35	129.05	3.3	0.00	0.01	0.05
DDH-04-058						129.05	129.60	41.8	0.03	0.07	0.05
DDH-04-058						129.60	134.84				
DDH-04-058						134.84	135.67	23.3	0.01	0.02	0.03
DDH-04-058						135.67	137.94				
DDH-04-058						137.94	138.70	87.2	0.01	0.02	0.07
DDH-04-058						138.70	148.91				
DDH-04-058						148.91	149.77	67.6	0.03	0.04	0.07
DDH-04-058						149.77	157.00				
DDH-04-058						157.00	157.68	32.7	0.01	0.02	0.02
DDH-04-058						157.68	158.49	22.4	0.01	0.08	0.03
DDH-04-058						158.49	166.48				
DDH-04-058						166.48	167.22	4	0.00	0.01	0.04
DDH-04-058						167.22	168.09	9.9	0.00	0.01	0.05
DDH-04-058						168.09	175.09				
DDH-04-058						175.09	175.57	19.9	0.01	0.01	0.17
DDH-04-058						175.57	178.60				
Colonial	DDH-04-058	1,151	7,645,697	4,461	171.00	208°	-61°				1.95
	DDH-04-059										1.95
	DDH-04-059										6.82
	DDH-04-059							25.8	0.01	0.02	0.01
	DDH-04-059							8.19			10.42
	DDH-04-059							10.42	0.01	0.02	0.01
	DDH-04-059							11.04			11.04
	DDH-04-059							42.23			42.23
	DDH-04-059							43.49	0.26	0.15	0.49
	DDH-04-059							43.49			95.80
	DDH-04-059							95.80	0.02	0.09	0.06
	DDH-04-059							96.24			96.24
	DDH-04-059							129.43			129.43
	DDH-04-059							129.43	0.17	0.15	0.36
	DDH-04-059							130.00			130.00
	DDH-04-059							171.00			171.00
Desconocido	DDH-04-060	938	7,645,785	4,394	82.00	197°	-40°				31.17
	DDH-04-060										31.17
	DDH-04-060							5.9	0.01	0.03	0.38
	DDH-04-060							32.23			70.00
	DDH-04-060							70.00	0.05	0.23	0.35
	DDH-04-060							71.35			71.35

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-04-065								190.23	191.20	2080	1.22	0.08	0.22
DDH-04-065								191.20	191.71	825	0.29	0.04	0.08
DDH-04-065								191.71	192.35	1280	0.29	0.02	0.06
DDH-04-065								192.35	193.27	6310	1.30	0.07	0.25
DDH-04-065								193.27	194.27	1050	0.22	0.03	0.05
DDH-04-065								194.27	194.83	5530	1.41	0.15	0.28
DDH-04-065								194.83	195.81	1850	0.78	0.21	0.49
DDH-04-065								195.81	196.54	497	0.15	0.53	2.83
DDH-04-065								196.54	197.24	118	0.06	0.09	0.09
DDH-04-065								197.24	209.70				
Lit DDH-04-066	DDH-04-066	7,366	7,645,091	4,471	143.50	359°	-49°		122.75				
	DDH-04-066							122.75	124.10	2.6	0.01	0.02	0.07
	DDH-04-066							124.10	124.37	19.8	0.05	0.04	0.64
	DDH-04-066							124.37	125.52	55.7	0.06	0.08	0.50
	DDH-04-066							125.52	126.45	3	0.04	0.05	0.18
	DDH-04-066							126.45	127.33	2.6	0.08	0.03	0.12
	DDH-04-066							127.33	128.39	1.3	0.02	0.01	0.09
	DDH-04-066							128.39	129.18	0.8	0.00	0.03	0.07
	DDH-04-066							129.18	130.14	6.6	0.01	0.05	0.40
	DDH-04-066							130.14	131.23	0.6	0.01	0.01	0.05
	DDH-04-066							131.23	143.50				
Lit DDH-04-067	DDH-04-067	7,366	7,645,091	4,471	164.50	359°	-66°		140.50				
	DDH-04-067							140.50	141.81	2.6	0.01	0.12	0.51
	DDH-04-067							141.81	142.65	2.7	0.03	0.03	0.48
	DDH-04-067							142.65	143.50	5.6	0.02	0.18	0.77
	DDH-04-067							143.50	144.48	9	0.01	0.01	0.31
	DDH-04-067							144.48	145.05	11.6	0.01	0.01	1.03
	DDH-04-067							145.05	146.43	473	0.15	0.15	6.44
	DDH-04-067							146.43	146.85	197	0.04	1.16	7.30
	DDH-04-067							146.85	147.36	10.5	0.00	0.03	1.27
	DDH-04-067							147.36	148.30	5.4	0.00	0.03	0.98
	DDH-04-067							148.30	149.23	7.6	0.00	0.03	1.31
	DDH-04-067							149.23	150.22	7.0	0.00	0.04	0.77
	DDH-04-067							150.22	164.50				
Lit DDH-04-068	DDH-04-068	7,366	7,645,091	4,471	203.70	359°	-79°		182.22				
	DDH-04-068							182.22	183.15	136	0.14	0.01	0.06
	DDH-04-068							183.15	184.10	157	0.24	0.02	0.08
	DDH-04-068							184.10	185.02	201	0.22	0.04	0.08
	DDH-04-068							185.02	185.93	210	0.35	0.04	0.09
	DDH-04-068							185.93	186.80	95.6	0.25	0.02	0.08

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-068						186.80	187.71	485	1.13	0.03	0.25
DDH-04-068						187.71	188.59	310	0.09	0.90	0.49
DDH-04-068						188.59	189.37	438	0.19	0.69	1.30
DDH-04-068						189.37	190.32	49	0.01	0.03	0.08
DDH-04-068						190.32	191.38	84.4	0.03	0.03	0.09
DDH-04-068						191.38	192.19	4.1	0.00	0.01	0.09
DDH-04-068						192.19	193.11	3.7	0.00	0.01	0.15
DDH-04-068						193.11	194.02	0.9	0.00	0.00	0.00
DDH-04-068						194.02	194.94	1	0.00	0.00	0.00
DDH-04-068						194.94	203.70				
Lit DDH-04-069	4,436	7,645,096	4,467	185.70	359°	-72°		151.75			
DDH-04-069							151.75	152.70	0.5	0.01	0.01
DDH-04-069							152.70	154.19	6.9	0.00	0.11
DDH-04-069							154.19	154.91	19.4	0.00	0.19
DDH-04-069							154.91	156.15	471	0.03	1.26
DDH-04-069							156.15	157.48	7.2	0.00	0.09
DDH-04-069							157.48	158.44	2.2	0.00	0.03
DDH-04-069							158.44	176.70			
DDH-04-069							176.70	177.64	3.5	0.00	0.01
DDH-04-069							177.64	178.80	5.9	0.01	0.01
DDH-04-069							178.80	179.26	4.7	0.01	0.01
DDH-04-069							179.26	185.70			
Lit DDH-04-070	4,505	7,645,102	4,456	164.60	359°	-73°		0.23			
DDH-04-070							0.23	142.92			
DDH-04-070							142.92	143.85	0.5	0.00	0.00
DDH-04-070							143.85	144.51	9.8	0.01	0.04
DDH-04-070							144.51	145.40	494	0.46	0.15
DDH-04-070							145.40	146.82	260	0.27	0.06
DDH-04-070							146.82	147.94	2.6	0.00	0.00
DDH-04-070							147.94	148.70	2.1	0.00	0.00
DDH-04-070							148.70	160.67			
DDH-04-070							160.67	162.20	10.7	0.00	0.02
DDH-04-070							162.20	164.60			
Lit DDH-04-071	4,576	7,645,097	4,442	144.00	359°	-67°		1.20			
DDH-04-071							1.20	134.50			
DDH-04-071							134.50	135.28	4.4	0.01	0.01
DDH-04-071							135.28	136.14	29.3	0.02	0.30
DDH-04-071							136.14	137.01	118	0.02	0.90
DDH-04-071							137.01	137.66	34	0.01	0.12
DDH-04-071							137.66	138.40	3.7	0.00	0.00
DDH-04-071							138.40	139.12	6.9	0.00	0.01
DDH-04-071							139.12	140.01	5.1	0.00	0.01

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
Vein	N°	Eastings	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-04-071								140.01	144.00				
Lit	DDH-04-072	7,649,649	7,645,098	4,431	128.50	359°	-64°		17.50				
	DDH-04-072							17.50	116.50				
	DDH-04-072							116.50	117.52	3.5	0.05	0.01	0.19
	DDH-04-072							117.52	117.97	13.9	0.05	0.04	1.20
	DDH-04-072							117.97	118.94	702	0.69	0.63	7.78
	DDH-04-072							118.94	119.56	117	0.24	0.03	3.59
	DDH-04-072							119.56	120.10	4.2	0.05	0.01	0.09
	DDH-04-072							120.10	120.77	3.3	0.03	0.07	0.13
	DDH-04-072							120.77	128.50				
Lit	DDH-04-073	7,719,719	7,645,090	4,423	152.50	359°	-64°		13.70				
	DDH-04-073							13.70	113.50				
	DDH-04-073							113.50	114.16	2.4	0.01	0.01	0.43
	DDH-04-073							114.16	115.10	3.3	0.03	0.01	0.20
	DDH-04-073							115.10	115.71	0.8	0.01	0.01	0.11
	DDH-04-073							115.71	116.51	2	0.01	0.01	0.15
	DDH-04-073							116.51	117.72	3.8	0.02	0.01	0.14
	DDH-04-073							117.72	118.51	41.2	0.44	0.05	0.28
	DDH-04-073							118.51	119.32	4	0.01	0.01	0.15
	DDH-04-073							119.32	123.22				
	DDH-04-073							123.22	123.88	7.4	0.01	0.01	0.09
	DDH-04-073							123.88	124.39	4.6	0.00	0.01	0.41
	DDH-04-073							124.39	124.95	1.7	0.00	0.00	0.00
	DDH-04-073							124.95	138.17				
	DDH-04-073							138.17	138.70	9.9	0.01	0.01	0.24
	DDH-04-073							138.70	139.34	15.4	0.01	0.03	0.19
	DDH-04-073							139.34	139.98	39.1	0.01	0.04	0.07
	DDH-04-073							139.98	140.73	4.1	0.00	0.01	0.01
	DDH-04-073							140.73	141.30	21.6	0.00	0.06	0.11
	DDH-04-073							141.30	142.28	1.7	0.00	0.00	0.02
	DDH-04-073							142.28	143.10	1.3	0.00	0.00	0.00
	DDH-04-073							143.10	143.74	2.9	0.00	0.00	0.11
	DDH-04-073							143.74	144.20	23	0.01	0.05	0.10
	DDH-04-073							144.20	144.74	8.7	0.00	0.00	0.00
	DDH-04-073							144.74	145.33	7.5	0.00	0.01	0.01
	DDH-04-073							145.33	146.08	10	0.00	0.01	0.02
	DDH-04-073							146.08	146.88	99	0.04	0.01	0.05
	DDH-04-073							146.88	147.62	3.8	0.00	0.01	0.02
	DDH-04-073							147.62	148.26	2.7	0.00	0.01	0.00
	DDH-04-073							148.26	152.50				

Hole		Collar Co-ordinates			Interval Orientation			Assay Results						
Identification	HOLE	Vein N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
DDH-04-076									195.81	196.74	4.5	0.01	0.00	0.73
DDH-04-076									196.74	197.71	323	0.09	0.03	1.11
DDH-04-076									197.71	198.68	3.2	0.00	0.04	0.65
DDH-04-076									198.68	199.54	2.7	0.00	0.02	0.28
DDH-04-076									199.54	200.56	252	0.14	0.01	0.94
DDH-04-076									200.56	201.53	8.3	0.00	0.00	0.17
DDH-04-076									201.53	202.52	62.2	0.03	0.01	1.60
DDH-04-076									202.52	203.48	22.8	0.01	0.03	0.72
DDH-04-076									203.48	204.44	231	0.10	0.04	0.92
DDH-04-076									204.44	205.40	253	0.14	0.06	1.00
DDH-04-076									205.40	206.46	193	0.14	0.03	2.85
DDH-04-076									206.46	207.26	30.2	0.02	0.00	0.01
DDH-04-076									207.26	208.23	66.1	0.03	0.01	0.01
DDH-04-076									208.23	209.20	223	0.13	0.03	0.07
DDH-04-076									209.20	210.59	235	0.15	0.05	0.09
DDH-04-076									210.59	211.28	2220	0.48	0.19	6.97
DDH-04-076									211.28	211.79	267	0.06	0.05	0.06
DDH-04-076									211.79	212.40	309	0.05	0.18	0.08
DDH-04-076									212.40	213.63	3600	0.83	0.21	5.90
DDH-04-076									213.63	214.87	226	0.08	0.06	2.82
DDH-04-076									214.87	215.79	439	0.09	0.17	0.28
DDH-04-076									215.79	216.70	176	0.04	0.02	0.31
DDH-04-076									216.70	217.64	244	0.06	0.03	0.03
DDH-04-076									217.64	218.55	260	0.08	0.02	0.02
DDH-04-076									218.55	219.45	169	0.06	0.02	0.03
DDH-04-076									219.45	220.38	526	0.14	0.32	5.38
DDH-04-076									220.38	221.72	18.1	0.02	0.02	1.21
DDH-04-076									221.72	236.80				
Lit DDH-04-077	DDH-04-077	19,228	7,645,055	4,488	285.00	357°	-82°			0.63				
DDH-04-077									0.63	263.13				
DDH-04-077									263.13	264.08	1.5	0.01	0.00	0.16
DDH-04-077									264.08	265.05	9.8	0.03	0.01	0.03
DDH-04-077									265.05	265.95	6.6	0.02	0.00	0.01
DDH-04-077									265.95	266.91	5.8	0.04	0.00	0.01
DDH-04-077									266.91	267.89	6.6	0.03	0.00	0.01
DDH-04-077									267.89	268.85	8.0	0.02	0.00	0.02
DDH-04-077									268.85	269.82	2.7	0.01	0.00	0.07
DDH-04-077									269.82	270.70	4.7	0.01	0.00	0.01
DDH-04-077									270.70	271.83	3.3	0.01	0.00	0.01
DDH-04-077									271.83	272.53	5	0.01	0.01	0.01
DDH-04-077									272.53	273.49	49	0.01	0.03	1.38
DDH-04-077									273.49	274.45	44.4	0.04	0.01	0.54

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-077						274.45	275.41	7.5	0.00	0.01	0.67
DDH-04-077						275.41	285.00				
Lit DDH-04-078	1,153	7,645,020	4,502	306.00	360°	-69°		0.49			
DDH-04-078							0.49	2.00			
DDH-04-078							2.00	2.51	0.8	0.00	0.05
DDH-04-078							2.51	3.75	0.4	0.00	0.05
DDH-04-078							3.75	4.72	1	0.00	0.06
DDH-04-078							4.72	5.59	1	0.00	0.06
DDH-04-078							5.59	6.69	0.4	0.00	0.05
DDH-04-078							6.69	7.63	0.9	0.00	0.05
DDH-04-078							7.63	71.69			
DDH-04-078							71.69	73.26			
DDH-04-078							73.26	89.77			
DDH-04-078							89.77	92.31			
DDH-04-078							92.31	250.77			
DDH-04-078							250.77	251.48	0.9	0.00	0.00
DDH-04-078							251.48	252.08	6.8	0.01	0.02
DDH-04-078							252.08	252.81	1.3	0.00	0.01
DDH-04-078							252.81	253.29	59	0.18	0.02
DDH-04-078							253.29	253.99	2.3	0.01	0.01
DDH-04-078							253.99	254.56	1.2	0.01	0.01
DDH-04-078							254.56	255.81	0.6	0.02	0.00
DDH-04-078							255.81	256.58	3.2	0.08	0.01
DDH-04-078							256.58	257.71	1.2	0.00	0.00
DDH-04-078							257.71	260.79			
DDH-04-078							260.79	261.74	3.2	0.04	0.01
DDH-04-078							261.74	262.70	7.5	0.60	0.01
DDH-04-078							262.70	263.65	6.3	0.18	0.01
DDH-04-078							263.65	264.35	35.9	1.82	0.01
DDH-04-078							264.35	265.14	2.5	0.05	0.01
DDH-04-078							265.14	265.77	6.9	0.11	0.00
DDH-04-078							265.77	266.70	43.9	2.41	0.01
DDH-04-078							266.70	268.07	44.8	1.38	0.01
DDH-04-078							268.07	269.28	4.2	0.00	0.01
DDH-04-078							269.28	269.92	1.9	0.00	0.00
DDH-04-078							269.92	292.68			
DDH-04-078							292.68	293.47	10.8	4.55	0.01
DDH-04-078							293.47	294.38	0.4	0.01	0.00
DDH-04-078							294.38	306.00			
Lit DDH-04-079	1,221	7,645,128	4,499	125.50	359°	-53°		0.25			
DDH-04-079							0.25	104.95			
DDH-04-079							104.95	105.65	1	0.05	0.01
DDH-04-079							105.65	106.42	2	0.05	0.01

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Hole Identification		Collar Co-ordinates			Interval Orientation			Assay Results					
HOLE													
Vein	N°	Easting	Northing	Elevation	Length	Azimuth	Dip	From	To	Ag (g/t)	Cu %	Pb %	Zn %
								106.42	107.24	101	1.17	0.04	0.01
								107.24	108.31	229	0.68	0.10	0.49
								108.31	109.25	4.2	0.09	0.02	0.10
								109.25	110.09	4.1	0.08	0.01	0.09
								110.09	110.96	11.6	0.08	0.02	0.05
								110.96	112.16	3.4	0.10	0.02	0.11
								112.16	112.83	159	0.89	0.16	0.94
								112.83	113.71	3.9	0.11	0.04	0.18
								113.71	114.48	766	6.33	0.37	1.20
								114.48	115.54	2	0.05	0.01	0.02
								115.54	116.44	0.9	0.03	0.01	0.01
								116.44	125.50				
Lit	DDH-04-080	7,300	7,645,046	4,472	258.00	359°	-76°			0.66			
	DDH-04-080							0.66	235.89				
	DDH-04-080							235.89	236.60	5.5	0.06	0.00	0.05
	DDH-04-080							236.60	237.70	13.4	0.12	0.01	0.07
	DDH-04-080							237.70	238.65	29.1	0.09	0.03	0.10
	DDH-04-080							238.65	239.17	131	0.12	0.02	0.05
	DDH-04-080							239.17	240.01	289	0.22	0.15	0.47
	DDH-04-080							240.01	240.90	170	0.05	0.43	2.59
	DDH-04-080							240.90	241.47	17.5	0.01	0.02	1.29
	DDH-04-080							241.47	242.43	7.3	0.00	0.01	0.67
	DDH-04-080							242.43	258.00				
Lit	DDH-04-081	7,439	7,645,059	4,460	213.00	359°	-72°			0.98			
	DDH-04-081							0.98	193.34				
	DDH-04-081							193.34	194.29	201	0.02	0.01	2.51
	DDH-04-081							194.29	195.00	21.5	0.04	0.01	1.46
	DDH-04-081							195.00	195.80	6.4	0.02	0.00	2.19
	DDH-04-081							195.80	196.54	15.7	0.03	0.02	0.89
	DDH-04-081							196.54	197.50	82.1	0.07	0.05	1.23
	DDH-04-081							197.50	198.10	157	0.06	1.70	1.58
	DDH-04-081							198.10	199.04	516	0.13	2.04	2.99
	DDH-04-081							199.04	199.52	10.9	0.01	0.04	0.09
	DDH-04-081							199.52	200.23	18	0.02	0.02	0.08
	DDH-04-081							200.23	201.24	76.1	0.03	0.03	0.21
	DDH-04-081							201.24	213.00				
Lit	DDH-04-082	7,439	7,645,059	4,460	252.00	359°	-81°			2.20			
	DDH-04-082							2.20	235.17				
	DDH-04-082							235.17	236.09	12.4	0.00	0.06	0.24

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

DDH-04-082							236.09	237.00	1.3	0.00	0.00	0.00
DDH-04-082							237.00	237.70	1.3	0.00	0.00	0.02
DDH-04-082							237.70	238.39	1.3	0.00	0.00	0.00
DDH-04-082							238.39	239.56	10.6	0.00	0.02	0.08
DDH-04-082							239.56	240.50	12.6	0.01	0.01	0.02
DDH-04-082							240.50	241.41	17.5	0.01	0.02	0.20
DDH-04-082							241.41	242.37	52.6	0.02	0.33	0.84
DDH-04-082							242.37	243.50	114	0.03	0.26	0.98
DDH-04-082							243.50	244.03	2.5	0.00	0.02	0.06
DDH-04-082							244.03	244.74	1.4	0.00	0.01	0.06
DDH-04-082							244.74	252.00				
Lit DDH-04-082	511	7,645,042	4,457	213.00	359°	-68°		2.00				
DDH-04-083							2.00	196.76				
DDH-04-083							196.76	197.37	80	0.04	0.14	0.21
DDH-04-083							197.37	198.00	19.7	0.01	0.02	0.05
DDH-04-083							198.00	198.89	109	0.06	0.07	0.23
DDH-04-083							198.89	200.08	83.1	0.07	0.03	0.04
DDH-04-083							200.08	201.01	139	0.72	0.02	0.09
DDH-04-083							201.01	201.91	891	1.23	0.07	0.31
DDH-04-083							201.91	202.83	1420	2.35	2.24	1.74
DDH-04-083							202.83	203.83	42.1	0.02	0.16	0.36
DDH-04-083							203.83	204.68	7.5	0.01	0.01	0.03
DDH-04-083							204.68	213.00				
Lit DDH-04-084	511	7,645,042	4,457	264.00	359°	-78°		1.09				
DDH-04-084							1.09	249.17				
DDH-04-084							249.17	249.86	39.7	0.03	0.03	0.03
DDH-04-084							249.86	250.68	24.4	0.01	0.01	0.02
DDH-04-084							250.68	251.58	7	0.01	0.03	0.05
DDH-04-084							251.58	252.26	15.5	0.01	0.02	0.05
DDH-04-084							252.26	253.19	12.8	0.00	0.01	0.02
DDH-04-084							253.19	254.10	10.3	0.01	0.01	0.01
DDH-04-084							254.10	255.04	32.2	0.02	0.01	0.02
DDH-04-084							255.04	255.97	1115	0.26	4.14	3.59
DDH-04-084							255.97	256.51	192	0.06	0.85	0.74
DDH-04-084							256.51	257.26	14.4	0.01	0.04	0.08
DDH-04-084							257.26	264.00				

**Technical Report for the
San Vicente Mine
Potosí Bolivia
Appendix C
Channel Sampling Results**

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	PASB	5260.13	5622.97	4437.61	4.03	219	0.09	0.03	0.08
Adela	PASB	5267.90	5576.32	4397.61	3.26	337	0.16	0.05	0.19
Adela	PASB	5375.55	5546.72	4437.61	4.43	609	0.56	0.06	0.74
Adela	PASB	5454.27	5457.43	4397.61	0.92	47	0.08	0.02	2.89
Adela	PASB	5480.41	5466.55	4437.61	4.14	167	0.15	0.03	0.10
Adela	PASB	5494.52	5469.89	4467.61	2.24	346	0.63	0.04	0.43
Adela	PASB	5532.86	5399.72	4397.61	0.90	69	0.19	0.03	3.86
Adela	PASB	5570.00	5403.35	4437.61	6.50	62	0.11	0.02	0.08
Adela	PASB	5576.37	5412.70	4467.61	3.17	280	0.17	0.10	0.99
Adela	PASB	5615.28	5379.91	4467.61	4.04	188	0.25	0.07	1.87
Adela	PASB	5631.75	5367.71	4437.61	6.35	293	0.60	0.05	0.65
Adela	PASB	5643.81	5313.45	4397.61	5.71	513	0.40	0.09	3.67
Adela	PASB	5647.31	5275.68	4356.54	1.15	36	0.02	0.01	0.15
Adela	PASB	5650.78	5273.02	4356.54	0.85	18	0.01	0.02	0.04
Adela	PASB	5654.59	5270.00	4356.54	1.80	28	0.02	0.02	0.09
Adela	PASB	5654.81	5309.84	4397.61	2.60	150	0.73	0.08	0.73
Adela	PASB	5657.83	5267.90	4356.54	1.37	17	0.06	0.02	0.06
Adela	PASB	5661.67	5265.57	4356.54	1.70	104	0.39	0.03	3.03
Adela	PASB	5665.18	5263.08	4356.54	1.51	11	0.10	0.02	0.41
Adela	PASB	5669.27	5260.63	4356.54	1.15	16	0.02	0.01	0.10
Adela	PASB	5673.49	5258.13	4356.54	1.90	14	0.04	0.01	0.31
Adela	PASB	5677.38	5255.75	4356.54	1.88	18	0.25	0.06	0.34
Adela	PASB	5681.34	5253.34	4356.54	1.38	29	0.11	0.10	1.05
Adela	PASB	5685.02	5251.05	4356.54	1.70	353	1.32	0.03	2.57
Adela	PASB	5688.39	5248.59	4356.54	1.50	58	0.13	0.03	2.19
Adela	PASB	5691.43	5315.56	4437.61	4.43	2,137	1.71	0.22	10.03
Adela	PASB	5692.03	5246.22	4356.54	1.35	26	0.06	0.03	1.20
Adela	PASB	5695.47	5244.13	4356.54	1.40	29	0.16	0.04	4.58
Adela	PASB	5698.77	5242.01	4356.54	1.40	47	0.15	0.02	7.04
Adela	PASB	5702.53	5240.38	4356.54	0.88	12	0.04	0.03	1.03
Adela	PASB	5705.98	5238.02	4356.54	0.95	27	0.10	0.01	2.62
Adela	PASB	5709.31	5235.80	4356.54	0.75	8	0.03	0.01	0.42
Adela	PASB	5712.91	5233.67	4356.54	0.93	23	0.01	0.01	0.04
Adela	PASB	5716.11	5231.26	4356.54	0.70	4	0.01	0.01	0.01
Adela	PASB	5719.67	5229.07	4356.54	0.70	5	0.02	0.01	0.04
Adela	PASB	5723.29	5226.98	4356.54	0.70	12	0.05	0.02	0.78
Adela	PASB	5726.49	5225.02	4356.54	0.70	10	0.03	0.02	0.54
Adela	PASB	5729.76	5223.26	4356.54	0.70	14	0.02	0.02	0.20
Adela	PASB	5733.15	5221.16	4356.54	0.70	9	0.07	0.02	0.96
Adela	PASB	5733.84	5245.87	4397.61	4.14	26	0.04	0.01	3.06
Adela	PASB	5736.38	5219.19	4356.54	0.75	26	0.10	0.06	1.55
Adela	PASB	5739.64	5217.16	4356.54	0.70	52	0.05	0.05	1.85
Adela	PASB	5743.23	5215.05	4356.54	0.90	24	0.06	0.02	0.28
Adela	PASB	5746.12	5238.77	4397.61	4.01	116	0.09	0.02	10.19
Adela	PASB	5747.15	5212.67	4356.54	1.05	37	0.03	0.14	1.21

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	PASB	5750.96	5210.84	4356.54	0.85	62	0.05	0.02	0.60
Adela	PASB	5754.44	5208.67	4356.54	0.90	31	0.28	0.02	0.19
Adela	PASB	5758.10	5206.74	4356.54	0.85	17	0.06	0.01	0.09
Adela	PASB	5761.86	5204.52	4356.54	0.75	40	0.00	0.01	0.07
Adela	PASB	5765.06	5202.54	4356.54	0.73	9	0.00	0.01	0.12
Adela	PASB	5768.35	5200.58	4356.54	0.70	6	0.00	0.00	0.03
Adela	PASB	5772.12	5198.93	4356.54	0.70	5	0.01	0.01	0.02
Adela	PASB	5775.81	5196.67	4356.54	0.70	10	0.03	0.02	0.05
Adela	PASB	5779.37	5194.94	4356.54	0.70	37	0.01	0.02	0.20
Adela	PASB	5781.03	5247.62	4437.61	2.59	228	0.11	0.04	6.68
Adela	PASB	5783.56	5192.77	4356.54	0.80	34	0.06	0.24	1.96
Adela	PASB	5787.06	5191.12	4356.54	0.70	42	0.13	0.01	1.31
Adela	PASB	5790.96	5189.25	4356.54	0.70	18	0.01	0.01	0.08
Adela	PASB	5794.50	5187.28	4356.54	0.80	13	0.05	0.01	2.16
Adela	PASB	5797.72	5185.39	4356.54	0.78	28	0.06	0.01	0.31
Adela	PASB	5801.71	5182.96	4356.54	0.70	13	0.05	0.02	0.05
Adela	PASB	5804.71	5181.33	4356.54	0.70	20	0.06	0.02	0.07
Adela	PASB	5805.70	5203.58	4397.61	2.95	163	0.16	0.05	7.51
Adela	PASB	5808.23	5179.45	4356.54	0.70	6	0.02	0.01	0.12
Adela	PASB	5811.50	5177.76	4356.54	1.10	9	0.02	0.01	0.32
Adela	PASB	5815.49	5175.78	4356.54	1.22	11	0.03	0.01	0.92

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	PASB	5819.71	5173.71	4356.54	1.10	8	0.01	0.01	0.86
Adela	PASB	5822.85	5227.96	4437.61	4.59	12	0.02	0.03	0.97
Adela	PASB	5823.39	5172.21	4356.54	1.05	111	0.16	0.01	1.17
Adela	PASB	5827.44	5170.92	4356.54	1.10	36	0.07	0.01	0.61
Adela	PASB	5831.16	5169.65	4356.54	1.65	343	0.24	0.03	0.28
Adela	PASB	5835.20	5168.00	4356.54	2.00	390	0.35	0.02	0.37
Adela	PASB	5838.30	5165.72	4356.54	1.45	389	0.39	0.06	0.39
Adela	PASB	5841.11	5165.46	4356.54	2.10	131	0.17	0.02	0.09
Adela	PASB	5843.37	5163.62	4356.54	3.30	326	0.44	0.05	0.35
Adela	PASB	5845.45	5162.19	4356.54	2.10	91	0.08	0.02	0.09
Adela	PASB	5847.35	5160.79	4356.54	2.95	39	0.03	0.26	0.57
Adela	PASB	5851.03	5158.48	4356.54	2.00	851	0.43	1.27	8.01
Adela	PASB	5856.88	5203.97	4437.61	2.82	44	0.18	0.02	3.96
Adela	COMIBOL	5211.67	5595.09	4399.50	1.93	411			
Adela	COMIBOL	5226.24	5577.47	4399.50	2.26	700			
Adela	COMIBOL	5227.65	5615.89	4437.75	1.93	411			1.66
Adela	COMIBOL	5235.51	5569.86	4399.50	1.60	570			
Adela	COMIBOL	5237.16	5568.86	4399.50	2.30	520			14.82
Adela	COMIBOL	5238.91	5567.79	4399.50	1.20	690			
Adela	COMIBOL	5240.48	5566.82	4399.50	1.80	560			15.90
Adela	COMIBOL	5242.28	5565.53	4399.50	1.20	610			
Adela	COMIBOL	5243.59	5564.59	4399.50	1.80	1,120			17.19
Adela	COMIBOL	5245.11	5563.50	4399.50	1.40	700			
Adela	COMIBOL	5246.43	5603.74	4437.75	2.26	700			1.42
Adela	COMIBOL	5246.68	5562.30	4399.50	1.30	400			7.70
Adela	COMIBOL	5248.32	5560.88	4399.50	2.30	1,260			
Adela	COMIBOL	5249.61	5559.78	4399.50	2.30	320			5.98
Adela	COMIBOL	5251.07	5558.52	4399.50	2.60	260			
Adela	COMIBOL	5252.78	5557.20	4399.50	2.30	400			8.59
Adela	COMIBOL	5254.32	5556.03	4399.50	2.20	1,160			
Adela	COMIBOL	5255.98	5554.76	4399.50	2.00	700			5.53
Adela	COMIBOL	5257.27	5553.78	4399.50	2.70	890			5.40
Adela	COMIBOL	5258.82	5552.71	4399.50	2.40	1,070			
Adela	COMIBOL	5260.91	5551.46	4399.50	2.20	830			5.40
Adela	COMIBOL	5262.64	5550.42	4399.50	2.60	860			
Adela	COMIBOL	5264.18	5549.50	4399.50	2.80	350			2.20
Adela	COMIBOL	5266.14	5548.27	4399.50	2.60	720			
Adela	COMIBOL	5267.81	5547.18	4399.50	2.50	560			4.50
Adela	COMIBOL	5269.36	5546.18	4399.50	1.60	870			
Adela	COMIBOL	5271.16	5545.00	4399.50	0.70	286			2.21
Adela	COMIBOL	5273.03	5543.70	4399.50	1.20	430			
Adela	COMIBOL	5274.83	5542.38	4399.50	0.90	27			4.40
Adela	COMIBOL	5276.21	5541.36	4399.50	0.80	1,420			
Adela	COMIBOL	5277.77	5540.21	4399.50	1.00	370			6.60
Adela	COMIBOL	5279.66	5538.82	4399.50	0.70	150			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5281.11	5537.79	4399.50	0.70	20	0.29
Adela	COMIBOL	5282.95	5536.47	4399.50	1.00	80	
Adela	COMIBOL	5302.54	5523.21	4399.50	0.70	21	
Adela	COMIBOL	5304.28	5521.99	4399.50	0.70	11	0.34
Adela	COMIBOL	5306.21	5520.64	4399.50	0.70	17	
Adela	COMIBOL	5307.80	5519.69	4399.50	0.70	17	1.12
Adela	COMIBOL	5309.66	5518.67	4399.50	0.70	9	
Adela	COMIBOL	5311.43	5517.70	4399.50	0.70	6	0.40
Adela	COMIBOL	5313.10	5516.70	4399.50	0.70	13	
Adela	COMIBOL	5314.91	5515.45	4399.50	0.70	3	0.01
Adela	COMIBOL	5316.40	5514.42	4399.50	0.70	6	
Adela	COMIBOL	5318.19	5513.17	4399.50	0.80	20	1.60
Adela	COMIBOL	5319.82	5511.88	4399.50	1.00	20	
Adela	COMIBOL	5321.31	5510.70	4399.50	1.00	20	0.50
Adela	COMIBOL	5323.13	5509.26	4399.50	0.70	9	
Adela	COMIBOL	5324.02	5551.27	4437.75	0.70	16	
Adela	COMIBOL	5324.52	5508.16	4399.50	0.70	6	0.14
Adela	COMIBOL	5326.04	5549.94	4437.75	0.70	69	
Adela	COMIBOL	5326.12	5506.96	4399.50	0.70	3	
Adela	COMIBOL	5327.71	5505.88	4399.50	0.70	9	0.17
Adela	COMIBOL	5327.77	5548.80	4437.75	0.70	0	

2

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5329.25	5547.83	4437.75	0.70	3			
Adela	COMIBOL	5329.29	5504.81	4399.50	0.70	3			
Adela	COMIBOL	5330.98	5546.69	4437.75	0.70	17			
Adela	COMIBOL	5331.12	5503.56	4399.50	0.70	6			0.17
Adela	COMIBOL	5332.77	5545.30	4437.75	0.70	5			
Adela	COMIBOL	5332.88	5502.36	4399.50	0.70	14			
Adela	COMIBOL	5333.04	5502.26	4400.29	1.40	30			6.81
Adela	COMIBOL	5333.04	5502.26	4402.37	1.00	10			
Adela	COMIBOL	5333.04	5502.26	4404.46	0.70	50			6.11
Adela	COMIBOL	5333.04	5502.26	4406.26	1.30	80			
Adela	COMIBOL	5333.04	5502.26	4408.29	1.00	140			4.89
Adela	COMIBOL	5333.04	5502.26	4410.04	1.00	10			
Adela	COMIBOL	5333.04	5502.26	4411.95	0.90	20			1.73
Adela	COMIBOL	5333.04	5502.26	4413.92	0.70	13			0.63
Adela	COMIBOL	5333.04	5502.26	4415.90	0.70	7			
Adela	COMIBOL	5333.04	5502.26	4417.53	0.70	242			14.39
Adela	COMIBOL	5333.04	5502.26	4419.50	0.70	86			
Adela	COMIBOL	5333.04	5502.26	4421.48	0.70	89			3.81
Adela	COMIBOL	5333.04	5502.26	4423.33	0.70	56			
Adela	COMIBOL	5333.04	5502.26	4425.19	0.70	9			0.57
Adela	COMIBOL	5333.04	5502.26	4427.05	0.70	86			1.67
Adela	COMIBOL	5333.04	5502.26	4429.03	0.70	6			0.34
Adela	COMIBOL	5333.04	5502.26	4430.94	0.70	69			1.89
Adela	COMIBOL	5333.04	5502.26	4432.86	0.70	20			
Adela	COMIBOL	5333.04	5502.26	4434.89	0.70	17			0.54
Adela	COMIBOL	5333.04	5502.26	4436.97	0.70	7			
Adela	COMIBOL	5334.39	5544.02	4437.75	0.70	21			
Adela	COMIBOL	5334.44	5501.24	4399.50	0.70	3			0.07
Adela	COMIBOL	5335.77	5542.93	4437.75	0.70	26			
Adela	COMIBOL	5336.44	5499.69	4399.50	0.70	44			0.10
Adela	COMIBOL	5337.40	5541.60	4437.75	0.70	4			
Adela	COMIBOL	5337.87	5498.59	4399.50	0.70	6			0.07
Adela	COMIBOL	5339.03	5540.25	4437.75	0.70	82			
Adela	COMIBOL	5339.95	5497.32	4399.50	0.70	36			
Adela	COMIBOL	5340.63	5538.91	4437.75	0.70	155			
Adela	COMIBOL	5341.51	5496.38	4399.50	0.70	6			0.09
Adela	COMIBOL	5342.02	5537.75	4437.75	0.70	165			
Adela	COMIBOL	5343.46	5495.02	4399.50	0.70	9			
Adela	COMIBOL	5343.65	5536.39	4437.75	0.90	333			
Adela	COMIBOL	5345.20	5535.10	4437.75	0.90	468			
Adela	COMIBOL	5345.30	5493.71	4399.50	0.70				0.45
Adela	COMIBOL	5346.83	5492.36	4399.50	0.70				0.39
Adela	COMIBOL	5346.86	5533.70	4437.75	0.90	944			
Adela	COMIBOL	5348.16	5532.54	4437.75	0.70	377			
Adela	COMIBOL	5348.32	5490.80	4399.50	0.70				0.30

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5349.86	5531.04	4437.75	0.70	59	
Adela	COMIBOL	5349.87	5489.17	4399.50	0.70	157	
Adela	COMIBOL	5351.24	5487.60	4399.50	0.70	23	0.12
Adela	COMIBOL	5351.42	5529.65	4437.75	0.70	91	
Adela	COMIBOL	5352.61	5528.59	4437.75	0.70	579	
Adela	COMIBOL	5352.66	5485.97	4399.50	0.70	6	
Adela	COMIBOL	5354.22	5484.24	4399.50	0.70	11	0.17
Adela	COMIBOL	5354.43	5526.95	4437.75	0.70	53	
Adela	COMIBOL	5355.90	5482.53	4399.50	0.70	26	
Adela	COMIBOL	5355.96	5525.53	4437.75	0.70	14	
Adela	COMIBOL	5357.30	5481.11	4399.50	0.70	411	0.14
Adela	COMIBOL	5357.50	5524.11	4437.75	0.70	9	
Adela	COMIBOL	5358.69	5479.62	4399.50	0.70	109	
Adela	COMIBOL	5358.86	5522.85	4437.75	0.70	36	
Adela	COMIBOL	5360.05	5478.05	4399.50	0.70	26	0.72
Adela	COMIBOL	5360.32	5521.50	4437.75	0.70	116	
Adela	COMIBOL	5361.52	5476.40	4399.50	0.70	57	
Adela	COMIBOL	5361.77	5520.16	4437.75	0.70	104	
Adela	COMIBOL	5363.54	5518.58	4437.75	0.70	329	
Adela	COMIBOL	5363.59	5474.95	4399.50	0.70	43	0.47
Adela	COMIBOL	5364.95	5517.34	4437.75	0.70	46	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5365.36	5473.72	4399.50	0.70	43			
Adela	COMIBOL	5366.56	5515.91	4437.75	0.70	82			
Adela	COMIBOL	5366.88	5473.02	4399.50	0.70	6			0.29
Adela	COMIBOL	5367.90	5514.72	4437.75	0.70	393			
Adela	COMIBOL	5369.04	5472.40	4399.50	0.70	3			
Adela	COMIBOL	5369.42	5513.35	4437.75	0.70	37			
Adela	COMIBOL	5371.01	5471.77	4399.50	0.70	1			0.14
Adela	COMIBOL	5371.11	5511.75	4437.75	0.70	1,022			
Adela	COMIBOL	5371.79	5531.13	4467.75	0.70	789			
Adela	COMIBOL	5372.54	5510.39	4437.75	0.70	819			
Adela	COMIBOL	5372.95	5470.97	4399.50	0.70	9			
Adela	COMIBOL	5373.49	5529.88	4467.75	0.70	317			
Adela	COMIBOL	5374.06	5508.94	4437.75	0.70	32			
Adela	COMIBOL	5374.90	5470.15	4399.50	0.70	6			0.34
Adela	COMIBOL	5374.96	5528.79	4467.75	0.80	270			
Adela	COMIBOL	5375.58	5507.54	4437.75	0.70	39			
Adela	COMIBOL	5376.75	5468.85	4399.50	0.70	3			
Adela	COMIBOL	5376.99	5506.29	4437.75	0.70	1,369			
Adela	COMIBOL	5378.21	5526.79	4467.75	0.75	590			
Adela	COMIBOL	5378.39	5467.71	4399.50	0.70	6			0.28
Adela	COMIBOL	5378.64	5504.84	4437.75	0.70	7			
Adela	COMIBOL	5379.85	5466.71	4399.50	0.70	9			
Adela	COMIBOL	5379.94	5525.75	4467.75	0.80	384			
Adela	COMIBOL	5380.20	5503.46	4437.75	0.70	9			
Adela	COMIBOL	5381.60	5502.21	4437.75	0.70	7			
Adela	COMIBOL	5381.70	5524.70	4467.75	0.70	1,325			
Adela	COMIBOL	5381.78	5465.43	4399.50	0.70	9			0.39
Adela	COMIBOL	5383.22	5500.78	4437.75	0.70	21			
Adela	COMIBOL	5383.35	5464.39	4399.50	0.70	11			
Adela	COMIBOL	5383.42	5523.36	4467.75	0.70	9			
Adela	COMIBOL	5384.60	5499.56	4437.75	0.70	8			
Adela	COMIBOL	5384.73	5522.27	4467.75	0.80	90			
Adela	COMIBOL	5385.53	5462.96	4399.50	0.70	9			1.08
Adela	COMIBOL	5386.24	5498.01	4437.75	0.70	37			
Adela	COMIBOL	5387.01	5461.82	4399.50	0.70	14			
Adela	COMIBOL	5387.83	5496.40	4437.75	0.70	10			
Adela	COMIBOL	5388.52	5460.61	4399.50	0.70	86			8.39
Adela	COMIBOL	5390.17	5459.29	4399.50	0.70	17			
Adela	COMIBOL	5391.95	5457.86	4399.50	0.70	28			0.26
Adela	COMIBOL	5391.98	5492.46	4437.75	0.70	159			
Adela	COMIBOL	5393.37	5456.76	4399.50	0.70	268			
Adela	COMIBOL	5393.51	5491.29	4437.75	0.70	50			
Adela	COMIBOL	5395.23	5489.99	4437.75	0.70	9			
Adela	COMIBOL	5395.30	5455.44	4399.50	0.70	126			6.82
Adela	COMIBOL	5396.75	5488.81	4437.75	0.70	57			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5397.04	5454.24	4399.50	0.70	324	
Adela	COMIBOL	5398.12	5487.66	4437.75	0.70	39	
Adela	COMIBOL	5398.69	5453.10	4399.50	0.70	414	25.09
Adela	COMIBOL	5399.69	5486.34	4437.75	0.70	61	
Adela	COMIBOL	5400.23	5452.13	4399.50	0.70	129	
Adela	COMIBOL	5401.25	5485.03	4437.75	0.70	41	
Adela	COMIBOL	5402.19	5451.07	4399.50	0.70	26	2.17
Adela	COMIBOL	5402.81	5483.71	4437.75	0.70	93	
Adela	COMIBOL	5403.62	5450.31	4399.50	0.70	40	
Adela	COMIBOL	5404.48	5482.35	4437.75	0.70	39	
Adela	COMIBOL	5405.43	5449.33	4399.50	0.70	46	2.27
Adela	COMIBOL	5405.88	5481.40	4437.75	0.70	33	
Adela	COMIBOL	5406.81	5448.53	4399.50	0.70	20	0.88
Adela	COMIBOL	5407.44	5480.33	4437.75	0.70	117	
Adela	COMIBOL	5408.49	5447.49	4399.50	0.70	46	
Adela	COMIBOL	5410.03	5446.53	4399.50	0.70	29	1.19
Adela	COMIBOL	5411.53	5445.61	4399.50	0.70	60	
Adela	COMIBOL	5412.09	5477.06	4437.75	0.70	30	
Adela	COMIBOL	5413.26	5444.69	4399.50	0.70	34	1.70
Adela	COMIBOL	5413.98	5475.68	4437.75	0.70	17	
Adela	COMIBOL	5414.89	5443.86	4399.50	1.00	60	

4

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5415.55	5474.54	4437.75	0.70	23			
Adela	COMIBOL	5416.48	5443.06	4399.50	1.00	230			26.68
Adela	COMIBOL	5416.89	5473.59	4437.75	0.70	6			
Adela	COMIBOL	5418.04	5442.12	4399.50	1.30	410			
Adela	COMIBOL	5418.64	5472.40	4437.75	0.70	9			
Adela	COMIBOL	5419.61	5441.11	4399.50	1.40	500			25.54
Adela	COMIBOL	5420.19	5471.35	4437.75	0.70	6			
Adela	COMIBOL	5421.25	5440.05	4399.50	0.70	274			
Adela	COMIBOL	5422.70	5439.12	4399.50	0.70	591			14.43
Adela	COMIBOL	5423.11	5469.30	4437.75	0.70	17			
Adela	COMIBOL	5424.23	5438.12	4399.50	0.70	450			
Adela	COMIBOL	5424.49	5468.29	4437.75	0.70	22			
Adela	COMIBOL	5425.69	5437.08	4399.50	0.70	326			1.75
Adela	COMIBOL	5426.00	5467.17	4437.75	0.70	42			
Adela	COMIBOL	5427.14	5436.04	4399.50	0.70	200			
Adela	COMIBOL	5427.30	5466.22	4437.75	0.70	106			
Adela	COMIBOL	5428.76	5434.89	4399.50	0.70	2,246			10.86
Adela	COMIBOL	5428.87	5465.07	4437.75	0.70	37			
Adela	COMIBOL	5430.34	5464.00	4437.75	0.70	11			
Adela	COMIBOL	5430.40	5433.72	4399.50	0.80	340			
Adela	COMIBOL	5431.76	5462.96	4437.75	0.70	12			
Adela	COMIBOL	5431.93	5432.63	4399.50	0.70	266			4.24
Adela	COMIBOL	5433.31	5431.64	4399.50	0.70	309			
Adela	COMIBOL	5433.34	5461.80	4437.75	0.70	13			
Adela	COMIBOL	5434.72	5430.51	4399.50	0.70	63			1.24
Adela	COMIBOL	5434.89	5460.67	4437.75	0.70				
Adela	COMIBOL	5436.29	5429.13	4399.50	0.70	42			
Adela	COMIBOL	5436.34	5459.61	4437.75	0.70	8			
Adela	COMIBOL	5437.78	5458.56	4437.75	0.70	12			
Adela	COMIBOL	5438.13	5427.65	4399.50	1.10	80			0.99
Adela	COMIBOL	5439.24	5457.49	4437.75	0.70	4			
Adela	COMIBOL	5439.70	5426.44	4399.50	0.90	80			
Adela	COMIBOL	5440.69	5456.46	4437.75	0.70	12			
Adela	COMIBOL	5441.57	5425.00	4399.50	0.70	26			
Adela	COMIBOL	5442.27	5455.34	4437.75	0.70	8			
Adela	COMIBOL	5443.12	5423.78	4399.50	0.70	46			
Adela	COMIBOL	5443.59	5454.41	4437.75	0.70	6			
Adela	COMIBOL	5444.83	5422.42	4399.50	0.70	23			
Adela	COMIBOL	5445.12	5453.33	4437.75	0.70	11			
Adela	COMIBOL	5446.58	5421.03	4399.50	0.70	18			0.28
Adela	COMIBOL	5446.72	5452.19	4437.75	0.70	6			
Adela	COMIBOL	5447.96	5419.88	4399.50	0.70	11			
Adela	COMIBOL	5448.37	5451.02	4437.75	0.70	21			
Adela	COMIBOL	5449.65	5418.43	4399.50	0.70	9			0.38
Adela	COMIBOL	5449.68	5450.07	4437.75	0.70	12			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5451.22	5417.08	4399.50	0.70	26	
Adela	COMIBOL	5451.33	5448.87	4437.75	0.70	7	
Adela	COMIBOL	5452.67	5415.83	4399.50	0.70	9	0.34
Adela	COMIBOL	5453.43	5447.32	4437.75	0.70	15	
Adela	COMIBOL	5454.28	5414.44	4399.50	0.70	4	
Adela	COMIBOL	5454.85	5446.28	4437.75	0.70	17	
Adela	COMIBOL	5455.96	5413.01	4399.50	0.70	4	0.30
Adela	COMIBOL	5456.73	5444.87	4437.75	0.70	15	
Adela	COMIBOL	5457.71	5411.52	4399.50	0.70	11	
Adela	COMIBOL	5458.25	5443.74	4437.75	0.70	35	
Adela	COMIBOL	5459.17	5410.27	4399.50	0.70	17	0.38
Adela	COMIBOL	5460.02	5442.43	4437.75	0.70	20	
Adela	COMIBOL	5460.97	5408.76	4399.50	0.70	0	
Adela	COMIBOL	5461.86	5441.13	4437.75	0.70	91	
Adela	COMIBOL	5462.75	5407.28	4399.50	0.70	17	0.47
Adela	COMIBOL	5463.61	5439.94	4437.75	0.70	78	
Adela	COMIBOL	5464.00	5406.24	4399.50	0.70	29	0.94
Adela	COMIBOL	5464.52	5405.81	4405.02	0.70	45	1.55
Adela	COMIBOL	5464.52	5405.81	4407.11	0.70	29	
Adela	COMIBOL	5464.52	5405.81	4409.70	0.70	29	1.22
Adela	COMIBOL	5464.52	5405.81	4411.90	0.70	34	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5464.52	5405.81	4414.04	0.70	51			1.12
Adela	COMIBOL	5464.52	5405.81	4416.35	1.20	90			
Adela	COMIBOL	5464.52	5405.81	4418.54	1.25	230			2.01
Adela	COMIBOL	5464.52	5405.81	4420.74	1.35	100			
Adela	COMIBOL	5464.52	5405.81	4423.17	1.30	160			1.71
Adela	COMIBOL	5464.52	5405.81	4425.53	1.25	60			
Adela	COMIBOL	5464.52	5405.81	4427.62	1.10	70			1.81
Adela	COMIBOL	5464.52	5405.81	4429.98	1.10	40			
Adela	COMIBOL	5464.52	5405.81	4432.13	0.70	77			1.64
Adela	COMIBOL	5464.52	5405.81	4434.44	0.70	23			
Adela	COMIBOL	5464.52	5405.81	4436.75	0.80	140			1.71
Adela	COMIBOL	5465.37	5438.76	4437.75	0.70	73			
Adela	COMIBOL	5465.79	5404.75	4399.50	0.70	20			
Adela	COMIBOL	5467.08	5437.59	4437.75	0.70	55			
Adela	COMIBOL	5467.29	5403.51	4399.50	0.70	37			1.50
Adela	COMIBOL	5468.69	5436.27	4437.75	0.70	2			
Adela	COMIBOL	5468.97	5402.11	4399.50	0.80	60			
Adela	COMIBOL	5470.11	5401.16	4399.50	0.85	100			1.91
Adela	COMIBOL	5470.42	5434.85	4437.75	0.70	14			
Adela	COMIBOL	5471.84	5399.68	4399.50	0.80	120			
Adela	COMIBOL	5472.02	5433.53	4437.75	0.70	62			
Adela	COMIBOL	5473.34	5398.39	4399.50	0.70	189			6.72
Adela	COMIBOL	5473.52	5432.30	4437.75	0.70				
Adela	COMIBOL	5474.85	5397.12	4399.50	1.10	180			
Adela	COMIBOL	5475.10	5431.08	4437.75	0.70				
Adela	COMIBOL	5476.15	5396.07	4399.50	0.70	21			1.71
Adela	COMIBOL	5476.86	5429.73	4437.75	0.70				
Adela	COMIBOL	5477.80	5394.74	4399.50	0.70	14			1.29
Adela	COMIBOL	5478.62	5428.38	4437.75	0.70				
Adela	COMIBOL	5479.32	5393.51	4399.50	0.70	11			
Adela	COMIBOL	5480.39	5427.02	4437.75	0.70	31			
Adela	COMIBOL	5480.79	5392.36	4399.50	0.70	0			0.98
Adela	COMIBOL	5482.03	5425.76	4437.75	0.70	37			
Adela	COMIBOL	5482.55	5391.08	4399.50	1.20	290			
Adela	COMIBOL	5483.79	5424.41	4437.75	0.70	22			
Adela	COMIBOL	5483.96	5390.06	4399.50	0.70	69			0.75
Adela	COMIBOL	5485.29	5423.25	4437.75	0.70	8			
Adela	COMIBOL	5485.76	5388.75	4399.50	0.70	170			
Adela	COMIBOL	5487.06	5421.89	4437.75	0.70	48			
Adela	COMIBOL	5487.13	5387.75	4399.50	0.70	11			0.81
Adela	COMIBOL	5488.61	5420.69	4437.75	0.70	71			
Adela	COMIBOL	5488.84	5386.46	4399.50	0.70	26			
Adela	COMIBOL	5490.32	5419.35	4437.75	0.70	66			
Adela	COMIBOL	5490.36	5385.33	4399.50	0.70	0			1.22
Adela	COMIBOL	5490.69	5472.02	4505.25	0.80	49			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5491.73	5418.24	4437.75	0.70	26	
Adela	COMIBOL	5492.01	5470.86	4505.25	0.80	96	
Adela	COMIBOL	5492.03	5384.08	4399.50	0.70	0	
Adela	COMIBOL	5493.36	5469.68	4505.25	1.00	180	
Adela	COMIBOL	5493.39	5383.27	4399.50	0.90	20	2.81
Adela	COMIBOL	5493.46	5416.87	4437.75	0.70	51	
Adela	COMIBOL	5494.81	5468.35	4505.25	1.20	160	
Adela	COMIBOL	5494.90	5415.75	4437.75	0.70	110	
Adela	COMIBOL	5495.22	5382.18	4399.50	0.70	163	
Adela	COMIBOL	5495.95	5467.30	4505.25	1.20	10	
Adela	COMIBOL	5496.69	5414.39	4437.75	0.80	216	
Adela	COMIBOL	5496.97	5381.01	4399.50	0.70	11	0.65
Adela	COMIBOL	5497.08	5466.27	4505.25	1.30	190	
Adela	COMIBOL	5498.36	5413.13	4437.75	0.80	40	
Adela	COMIBOL	5498.52	5465.08	4505.25	1.30	200	
Adela	COMIBOL	5498.67	5379.73	4399.50	1.80	30	
Adela	COMIBOL	5499.77	5464.04	4505.25	1.30	400	
Adela	COMIBOL	5500.01	5411.88	4437.75	0.90	27	
Adela	COMIBOL	5500.41	5378.43	4399.50	0.95	40	0.41
Adela	COMIBOL	5501.22	5462.85	4505.25	1.50	30	
Adela	COMIBOL	5501.51	5410.75	4437.75	0.70	123	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5501.58	5377.56	4399.50	0.70	51			
Adela	COMIBOL	5502.59	5461.74	4505.25	1.60	580			
Adela	COMIBOL	5503.12	5409.56	4437.75	0.70	143			
Adela	COMIBOL	5503.34	5376.28	4399.50	1.40	80			2.19
Adela	COMIBOL	5504.00	5460.65	4505.25	1.60	140			
Adela	COMIBOL	5504.87	5408.28	4437.75	0.70	196			
Adela	COMIBOL	5505.27	5374.90	4399.50	1.25	260			
Adela	COMIBOL	5505.39	5459.59	4505.25	1.60	180			
Adela	COMIBOL	5506.36	5407.18	4437.75	0.70	91			
Adela	COMIBOL	5506.82	5458.48	4505.25	1.70	390			
Adela	COMIBOL	5506.92	5373.74	4399.50	1.20	240			11.87
Adela	COMIBOL	5508.01	5405.97	4437.75	0.70	279			
Adela	COMIBOL	5508.16	5457.37	4505.25	1.50	420			
Adela	COMIBOL	5508.71	5372.47	4399.50	1.50	120			
Adela	COMIBOL	5509.41	5456.27	4505.25	1.60	660			
Adela	COMIBOL	5509.80	5404.64	4437.75	0.70	0			
Adela	COMIBOL	5510.46	5371.22	4399.50	1.40	150			8.68
Adela	COMIBOL	5510.64	5455.21	4505.25	1.60	250			
Adela	COMIBOL	5511.38	5403.47	4437.75	0.70	14			
Adela	COMIBOL	5512.14	5454.03	4505.25	2.00	340			
Adela	COMIBOL	5512.16	5369.93	4399.50	2.00	60			
Adela	COMIBOL	5513.05	5402.18	4437.75	0.70	30			
Adela	COMIBOL	5513.30	5369.07	4399.50	2.50	50			7.48
Adela	COMIBOL	5513.68	5452.87	4505.25	2.00	360			
Adela	COMIBOL	5514.63	5400.89	4437.75	0.70	27			
Adela	COMIBOL	5515.31	5367.56	4399.50	2.10	646			
Adela	COMIBOL	5516.20	5399.62	4437.75	0.70	22			
Adela	COMIBOL	5517.07	5366.30	4399.50	0.85	0			1.80
Adela	COMIBOL	5517.66	5398.42	4437.75	0.70	73			
Adela	COMIBOL	5518.70	5365.17	4399.50	1.10	240			
Adela	COMIBOL	5519.38	5397.02	4437.75	0.70	9			
Adela	COMIBOL	5520.35	5364.03	4399.50	1.60	40			1.60
Adela	COMIBOL	5520.83	5395.87	4437.75	0.70	18			
Adela	COMIBOL	5522.16	5362.74	4399.50	1.30	20			
Adela	COMIBOL	5522.43	5394.70	4437.75	0.90	585			
Adela	COMIBOL	5523.76	5361.55	4399.50	1.20	0			6.00
Adela	COMIBOL	5524.05	5393.51	4437.75	0.90	270			
Adela	COMIBOL	5525.44	5360.29	4399.50	0.95	30			
Adela	COMIBOL	5525.58	5392.40	4437.75	0.80	90			
Adela	COMIBOL	5527.05	5359.09	4399.50	0.90	20			1.20
Adela	COMIBOL	5527.37	5391.06	4437.75	0.70	7			
Adela	COMIBOL	5528.70	5389.91	4437.75	0.70	14			
Adela	COMIBOL	5528.92	5357.69	4399.50	0.90	120			
Adela	COMIBOL	5530.25	5356.71	4399.50	0.70	26			0.94
Adela	COMIBOL	5530.28	5388.56	4437.75	0.80	16			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5531.71	5387.33	4437.75	0.90	576	
Adela	COMIBOL	5532.05	5355.40	4399.50	0.80	40	
Adela	COMIBOL	5533.13	5386.12	4437.75	0.90	360	
Adela	COMIBOL	5533.64	5354.25	4399.50	0.70	60	1.03
Adela	COMIBOL	5534.84	5384.64	4437.75	0.80	112	
Adela	COMIBOL	5535.42	5352.95	4399.50	0.70	49	
Adela	COMIBOL	5536.05	5383.61	4437.75	0.70	280	
Adela	COMIBOL	5536.86	5351.91	4399.50	0.80	50	1.40
Adela	COMIBOL	5537.69	5382.20	4437.75	0.70	140	
Adela	COMIBOL	5538.77	5350.66	4399.50	0.80	60	
Adela	COMIBOL	5539.09	5380.99	4437.75	0.70	196	
Adela	COMIBOL	5540.22	5349.73	4399.50	0.80	80	4.79
Adela	COMIBOL	5540.60	5379.69	4437.75	0.70	4,907	
Adela	COMIBOL	5542.02	5348.21	4399.50	1.10	70	6.08
Adela	COMIBOL	5542.52	5378.00	4437.75	0.70	3,374	
Adela	COMIBOL	5543.38	5346.91	4399.50	1.30	70	
Adela	COMIBOL	5543.62	5377.05	4437.75	0.90	4,907	
Adela	COMIBOL	5544.96	5345.40	4399.50	1.10	10	1.00
Adela	COMIBOL	5545.10	5375.78	4437.75	0.70	1,461	
Adela	COMIBOL	5546.47	5344.08	4399.50	1.70	30	
Adela	COMIBOL	5546.80	5374.37	4437.75	1.50	690	

7

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5547.90	5342.85	4399.50	0.80	60			2.89
Adela	COMIBOL	5549.44	5341.53	4399.50	0.70	7			
Adela	COMIBOL	5550.80	5340.37	4399.50	0.70	29			4.14
Adela	COMIBOL	5551.40	5370.55	4437.75	0.90	243			
Adela	COMIBOL	5552.80	5338.92	4399.50	2.60	10			
Adela	COMIBOL	5552.91	5369.29	4437.75	0.90	144			
Adela	COMIBOL	5554.32	5337.85	4399.50	0.70	20			5.29
Adela	COMIBOL	5554.63	5368.10	4437.75	0.90	54			
Adela	COMIBOL	5556.13	5336.59	4399.50	0.80	10			
Adela	COMIBOL	5556.22	5367.09	4437.75	0.90	36			
Adela	COMIBOL	5557.79	5335.63	4399.50	0.85	0			
Adela	COMIBOL	5558.28	5365.77	4437.75	0.95	135			
Adela	COMIBOL	5559.71	5334.59	4399.50	0.70	257			2.98
Adela	COMIBOL	5559.89	5364.74	4437.75	0.70	15			
Adela	COMIBOL	5561.25	5363.82	4437.75	0.70	6			
Adela	COMIBOL	5561.41	5333.68	4399.50	0.70	114			
Adela	COMIBOL	5562.05	5414.12	4505.25	1.00	489			
Adela	COMIBOL	5562.65	5332.86	4399.50	0.80	200			1.79
Adela	COMIBOL	5563.10	5362.41	4437.75	0.70	6			
Adela	COMIBOL	5563.40	5412.74	4505.25	2.50	180			
Adela	COMIBOL	5564.50	5331.16	4399.50	0.70	257			
Adela	COMIBOL	5564.52	5411.22	4505.25	2.80	310			
Adela	COMIBOL	5564.81	5361.10	4437.75	0.70	3			
Adela	COMIBOL	5565.56	5409.47	4505.25	1.00	220			
Adela	COMIBOL	5566.01	5329.80	4399.50	2.40	100			2.19
Adela	COMIBOL	5566.34	5359.93	4437.75	0.70	5			
Adela	COMIBOL	5567.06	5407.77	4505.25	0.90	150			
Adela	COMIBOL	5567.54	5328.57	4399.50	0.85	700			
Adela	COMIBOL	5567.73	5358.87	4437.75	0.70	4			
Adela	COMIBOL	5568.41	5406.48	4505.25	1.00	340			
Adela	COMIBOL	5569.15	5327.27	4399.50	0.70	686			2.13
Adela	COMIBOL	5569.62	5357.58	4437.75	0.70	18			
Adela	COMIBOL	5569.87	5405.15	4505.25	0.80	489			
Adela	COMIBOL	5570.89	5326.03	4399.50	0.70	1,389			
Adela	COMIBOL	5571.29	5356.44	4437.75	0.70	20			
Adela	COMIBOL	5571.40	5404.03	4505.25	0.90	120			
Adela	COMIBOL	5572.41	5324.99	4399.50	0.70	7,097			7.08
Adela	COMIBOL	5573.13	5355.18	4437.75	0.70	15			
Adela	COMIBOL	5573.31	5402.62	4505.25	0.70	195			
Adela	COMIBOL	5574.18	5323.76	4399.50	0.70	3,754			
Adela	COMIBOL	5574.45	5354.28	4437.75	0.70	55			
Adela	COMIBOL	5574.72	5401.63	4505.25	0.70	114			
Adela	COMIBOL	5575.79	5322.70	4399.50	0.80	1,010			2.39
Adela	COMIBOL	5576.39	5352.96	4437.75	0.95	798			
Adela	COMIBOL	5576.73	5400.54	4505.25	0.70	55			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5577.48	5321.58	4399.50	0.90	6,400	
Adela	COMIBOL	5577.60	5351.87	4437.75	0.80	392	
Adela	COMIBOL	5578.58	5399.52	4505.25	0.70	57	
Adela	COMIBOL	5579.03	5320.55	4399.50	1.00	4,000	2.29
Adela	COMIBOL	5581.03	5319.13	4399.50	1.40	6,100	
Adela	COMIBOL	5581.75	5348.11	4437.75	1.00	600	
Adela	COMIBOL	5582.61	5318.00	4399.50	1.60	4,400	6.67
Adela	COMIBOL	5583.35	5346.84	4437.75	0.80	248	
Adela	COMIBOL	5584.45	5316.64	4399.50	2.00	3,100	6.95
Adela	COMIBOL	5584.71	5345.76	4437.75	0.70	149	
Adela	COMIBOL	5585.89	5315.41	4399.50	1.90	850	
Adela	COMIBOL	5586.00	5344.76	4437.75	0.70	103	
Adela	COMIBOL	5587.35	5314.16	4399.50	1.90	7,460	3.37
Adela	COMIBOL	5587.48	5343.61	4437.75	0.80	176	
Adela	COMIBOL	5588.82	5312.90	4399.50	1.90	100	
Adela	COMIBOL	5588.88	5342.50	4437.75	0.70	30	
Adela	COMIBOL	5590.40	5341.23	4437.75	0.70	97	
Adela	COMIBOL	5590.67	5311.46	4399.50	1.80	400	4.62
Adela	COMIBOL	5591.62	5340.22	4437.75	0.70	50	
Adela	COMIBOL	5592.34	5310.18	4399.50	2.00	1,210	
Adela	COMIBOL	5593.08	5339.00	4437.75	0.90	81	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5593.69	5309.15	4399.50	2.10	480			3.62
Adela	COMIBOL	5594.72	5337.90	4437.75	0.90	351			
Adela	COMIBOL	5595.17	5307.76	4399.50	2.40	2,560			
Adela	COMIBOL	5596.12	5337.09	4437.75	0.70	175			
Adela	COMIBOL	5596.35	5306.41	4399.50	1.90	1,060			19.57
Adela	COMIBOL	5597.81	5336.10	4437.75	0.70	272			
Adela	COMIBOL	5597.94	5304.79	4399.50	1.95	540			
Adela	COMIBOL	5599.28	5303.43	4399.50	3.00	400			5.63
Adela	COMIBOL	5600.80	5301.88	4399.50	2.00	400			
Adela	COMIBOL	5602.01	5300.46	4399.50	0.80	320			5.73
Adela	COMIBOL	5603.39	5298.85	4399.50	0.70	377			
Adela	COMIBOL	5604.90	5297.43	4399.50	1.00	470			2.91
Adela	COMIBOL	5606.67	5296.02	4399.50	1.45	3,240			
Adela	COMIBOL	5608.34	5294.74	4399.50	0.90	1,220			2.81
Adela	COMIBOL	5609.81	5293.75	4399.50	1.70	2,080			
Adela	COMIBOL	5609.82	5326.74	4437.75	0.90	144			
Adela	COMIBOL	5611.23	5325.84	4437.75	0.70	49			
Adela	COMIBOL	5611.70	5292.49	4399.50	0.80	510			
Adela	COMIBOL	5613.38	5291.36	4399.50	1.15	810			19.57
Adela	COMIBOL	5613.39	5324.35	4437.75	0.70	41			
Adela	COMIBOL	5614.78	5323.38	4437.75	0.70	154			
Adela	COMIBOL	5614.79	5290.28	4399.50	0.70	57			
Adela	COMIBOL	5616.47	5288.95	4399.50	0.70	60			5.74
Adela	COMIBOL	5616.49	5322.18	4437.75	0.70	10			
Adela	COMIBOL	5617.99	5321.13	4437.75	0.70	154			
Adela	COMIBOL	5618.18	5287.52	4399.50	0.70	240			0.82
Adela	COMIBOL	5619.62	5286.16	4399.50	1.75	300			1.62
Adela	COMIBOL	5619.63	5319.98	4437.75	0.70	57			
Adela	COMIBOL	5621.13	5284.72	4399.50	1.10	210			0.96
Adela	COMIBOL	5621.39	5318.73	4437.75	0.70	6			
Adela	COMIBOL	5622.47	5283.46	4399.50	1.30	310			0.92
Adela	COMIBOL	5623.16	5317.43	4437.75	0.70	1,768			
Adela	COMIBOL	5624.00	5282.03	4399.50	1.00	2,040			34.30
Adela	COMIBOL	5624.75	5316.25	4437.75	0.70	49			
Adela	COMIBOL	5625.29	5280.88	4399.50	1.10	240			0.74
Adela	COMIBOL	5626.50	5314.96	4437.75	0.70	294			
Adela	COMIBOL	5627.29	5279.26	4399.50	1.20	240			0.74
Adela	COMIBOL	5627.83	5313.80	4437.75	0.70	203			
Adela	COMIBOL	5628.74	5278.08	4399.50	0.80	140			2.24
Adela	COMIBOL	5630.12	5276.75	4399.50	0.70	266			13.03
Adela	COMIBOL	5631.58	5275.27	4399.50	0.70	351			1.78
Adela	COMIBOL	5632.85	5273.98	4399.50	0.70	64			3.52
Adela	COMIBOL	5633.89	5308.51	4437.75	0.70	158			
Adela	COMIBOL	5634.13	5272.49	4399.50	0.70	64			0.92
Adela	COMIBOL	5635.47	5270.94	4399.50	0.70	350			3.83

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5635.57	5307.15	4437.75	0.70	511	
Adela	COMIBOL	5636.92	5269.49	4399.50	0.70	90	0.73
Adela	COMIBOL	5637.07	5305.93	4437.75	0.70	100	
Adela	COMIBOL	5638.50	5268.09	4399.50	0.70	1,493	7.19
Adela	COMIBOL	5638.78	5304.53	4437.75	0.80	1,136	
Adela	COMIBOL	5639.64	5356.92	4505.25	0.70	2,400	
Adela	COMIBOL	5640.02	5266.75	4399.50	0.80	160	0.40
Adela	COMIBOL	5640.19	5303.36	4437.75	0.80	1,291	
Adela	COMIBOL	5641.38	5265.54	4399.50	1.20	150	0.25
Adela	COMIBOL	5641.73	5302.12	4437.75	0.70	1,352	
Adela	COMIBOL	5642.87	5264.41	4399.50	0.90	30	0.73
Adela	COMIBOL	5643.75	5300.61	4437.75	0.70	251	
Adela	COMIBOL	5643.79	5354.20	4505.25	0.70	115	
Adela	COMIBOL	5644.53	5263.19	4399.50	1.00	290	4.32
Adela	COMIBOL	5645.16	5299.56	4437.75	0.70	69	
Adela	COMIBOL	5646.27	5261.92	4399.50	1.20	90	0.54
Adela	COMIBOL	5646.76	5298.40	4437.75	0.70	189	
Adela	COMIBOL	5647.69	5351.97	4505.25	1.30	141	
Adela	COMIBOL	5647.79	5260.85	4399.50	1.05	90	11.23
Adela	COMIBOL	5648.35	5297.36	4437.75	0.70	1,157	
Adela	COMIBOL	5649.24	5259.90	4399.50	1.20	1,530	26.40

9

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5650.15	5296.19	4437.75	0.70	1,092			
Adela	COMIBOL	5651.22	5258.61	4399.50	1.30	530			3.03
Adela	COMIBOL	5651.57	5295.28	4437.75	0.70	679			
Adela	COMIBOL	5651.59	5349.77	4505.25	1.20	1,260			
Adela	COMIBOL	5652.46	5257.80	4399.50	1.40	930			14.70
Adela	COMIBOL	5653.47	5294.07	4437.75	0.70	476			
Adela	COMIBOL	5654.40	5256.54	4399.50	1.80	220			2.16
Adela	COMIBOL	5655.01	5293.09	4437.75	0.70	370			
Adela	COMIBOL	5655.43	5347.52	4505.25	1.70	2,425			
Adela	COMIBOL	5656.27	5255.27	4399.50	0.80	1,530			3.92
Adela	COMIBOL	5658.28	5253.86	4399.50	1.10	360			2.08
Adela	COMIBOL	5659.17	5345.26	4505.25	0.80	328			
Adela	COMIBOL	5660.16	5252.60	4399.50	0.80	700			3.11
Adela	COMIBOL	5661.19	5344.01	4505.25	1.20	1,056			
Adela	COMIBOL	5661.58	5288.47	4437.75	0.80	220			7.13
Adela	COMIBOL	5662.40	5251.13	4399.50	0.80	356			1.30
Adela	COMIBOL	5663.11	5287.64	4437.75	0.90	1,380			19.70
Adela	COMIBOL	5664.34	5249.87	4399.50	0.80	180			24.37
Adela	COMIBOL	5665.22	5286.49	4437.75	0.90	110			14.50
Adela	COMIBOL	5666.51	5248.36	4399.50	0.80	95			9.75
Adela	COMIBOL	5666.76	5285.65	4437.75	1.10	280			20.89
Adela	COMIBOL	5668.55	5246.85	4399.50	0.80	30			1.24
Adela	COMIBOL	5668.60	5284.64	4437.75	1.00	460			35.25
Adela	COMIBOL	5670.15	5283.59	4437.75	0.90	250			22.67
Adela	COMIBOL	5670.64	5245.43	4399.50	0.80	40			1.39
Adela	COMIBOL	5671.60	5282.47	4437.75	1.00	500			32.97
Adela	COMIBOL	5672.49	5244.23	4399.50	0.80	54			7.06
Adela	COMIBOL	5673.05	5281.33	4437.75	2.30	130			
Adela	COMIBOL	5674.68	5242.79	4399.50	0.80	470			36.20
Adela	COMIBOL	5676.76	5241.32	4399.50	1.20	300			18.90
Adela	COMIBOL	5678.89	5239.82	4399.50	1.20	90			7.03
Adela	COMIBOL	5679.07	5303.82	4467.75	0.70	113			
Adela	COMIBOL	5680.59	5238.56	4399.50	1.40	280			38.40
Adela	COMIBOL	5680.72	5302.16	4467.75	0.70	775			
Adela	COMIBOL	5682.16	5301.03	4467.75	0.70	550			
Adela	COMIBOL	5682.43	5237.12	4399.50	1.60	360			23.00
Adela	COMIBOL	5683.84	5299.84	4467.75	0.70	130			
Adela	COMIBOL	5684.70	5235.34	4399.50	1.20	1,600			21.10
Adela	COMIBOL	5685.52	5298.62	4467.75	0.70	260			
Adela	COMIBOL	5686.52	5233.80	4399.50	1.40	1,000			6.90
Adela	COMIBOL	5687.33	5297.04	4467.75	0.70	429			
Adela	COMIBOL	5688.32	5232.00	4399.50	1.50	240			12.84
Adela	COMIBOL	5688.73	5295.82	4467.75	0.70	26			
Adela	COMIBOL	5689.95	5230.35	4399.50	1.80	140			14.43
Adela	COMIBOL	5690.38	5294.55	4467.75	0.70	8			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5691.83	5293.37	4467.75	0.70	6	
Adela	COMIBOL	5691.92	5229.42	4399.50	1.80	490	18.80
Adela	COMIBOL	5693.38	5291.90	4467.75	0.70	42	
Adela	COMIBOL	5693.71	5228.27	4399.50	2.20	2,410	21.70
Adela	COMIBOL	5694.83	5290.54	4467.75	0.70	13	
Adela	COMIBOL	5695.17	5227.36	4399.50	1.30	320	8.20
Adela	COMIBOL	5696.55	5289.35	4467.75	0.70	38	
Adela	COMIBOL	5697.21	5226.10	4399.50	1.30	320	3.20
Adela	COMIBOL	5698.35	5288.15	4467.75	0.70	9	
Adela	COMIBOL	5698.94	5225.03	4399.50	1.20	400	12.70
Adela	COMIBOL	5699.75	5287.22	4467.75	1.30	70	
Adela	COMIBOL	5700.63	5223.98	4399.50	1.30	40	7.20
Adela	COMIBOL	5701.47	5285.92	4467.75	0.70	84	
Adela	COMIBOL	5702.60	5222.76	4399.50	1.00	150	12.72
Adela	COMIBOL	5703.12	5284.49	4467.75	1.50	60	
Adela	COMIBOL	5704.25	5221.71	4399.50	1.60	200	23.20
Adela	COMIBOL	5704.44	5283.44	4467.75	0.80	420	
Adela	COMIBOL	5706.23	5220.46	4399.50	1.50	220	24.40
Adela	COMIBOL	5707.82	5281.02	4467.75	1.50	90	
Adela	COMIBOL	5707.87	5219.42	4399.50	0.95	150	27.50
Adela	COMIBOL	5708.02	5254.76	4437.75	2.80	1,456	11.13

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5709.30	5279.97	4467.75	1.50	290			
Adela	COMIBOL	5709.71	5253.66	4437.75	4.50	1,532			
Adela	COMIBOL	5709.87	5218.17	4399.50	1.50	560			37.10
Adela	COMIBOL	5710.93	5252.86	4437.75	2.00	619			6.26
Adela	COMIBOL	5711.10	5278.69	4467.75	0.70	36			
Adela	COMIBOL	5711.20	5217.36	4399.50	1.65	220			24.10
Adela	COMIBOL	5712.48	5251.86	4437.75	2.00	402			
Adela	COMIBOL	5713.40	5216.04	4399.50	1.25	260			19.50
Adela	COMIBOL	5714.21	5250.62	4437.75	2.00	424			4.20
Adela	COMIBOL	5714.38	5276.23	4467.75	1.10	84			
Adela	COMIBOL	5714.99	5215.09	4399.50	1.10	150			15.30
Adela	COMIBOL	5715.61	5275.16	4467.75	0.90	292			
Adela	COMIBOL	5716.12	5249.28	4437.75	2.80	240			
Adela	COMIBOL	5716.89	5213.94	4399.50	0.80	190			25.00
Adela	COMIBOL	5717.11	5273.86	4467.75	1.00	460			
Adela	COMIBOL	5718.00	5247.96	4437.75	2.60	220			39.85
Adela	COMIBOL	5718.55	5212.95	4399.50	0.80	210			20.30
Adela	COMIBOL	5718.78	5272.52	4467.75	1.00	160			
Adela	COMIBOL	5719.79	5246.73	4437.75	2.40	280			
Adela	COMIBOL	5720.50	5211.74	4399.50	0.80	220			20.10
Adela	COMIBOL	5720.50	5271.30	4467.75	0.70	366			
Adela	COMIBOL	5721.50	5245.55	4437.75	2.40	240			30.49
Adela	COMIBOL	5721.81	5270.25	4467.75	0.70	460			
Adela	COMIBOL	5722.21	5210.66	4399.50	0.80	190			16.15
Adela	COMIBOL	5723.25	5269.00	4467.75	1.10	760			
Adela	COMIBOL	5723.30	5244.37	4437.75	2.10	650			
Adela	COMIBOL	5723.99	5209.54	4399.50	0.80	360			35.41
Adela	COMIBOL	5724.95	5267.86	4467.75	1.10	290			
Adela	COMIBOL	5725.36	5208.68	4399.50	0.85	170			29.63
Adela	COMIBOL	5725.37	5243.07	4437.75	1.90	380			26.79
Adela	COMIBOL	5726.70	5266.93	4467.75	1.10	120			
Adela	COMIBOL	5727.08	5241.99	4437.75	2.00	390			
Adela	COMIBOL	5727.85	5207.12	4399.50	0.90	110			23.79
Adela	COMIBOL	5728.25	5241.25	4445.69	1.60	90			
Adela	COMIBOL	5728.25	5241.25	4448.12	1.00	470			42.33
Adela	COMIBOL	5728.25	5241.25	4450.43	1.70	350			
Adela	COMIBOL	5728.25	5241.25	4452.63	0.70	363			5.23
Adela	COMIBOL	5728.25	5241.25	4454.99	0.70	100			
Adela	COMIBOL	5728.25	5241.25	4457.25	1.30	100			16.53
Adela	COMIBOL	5728.25	5241.25	4459.39	1.30	400			
Adela	COMIBOL	5728.25	5241.25	4461.87	0.90	110			
Adela	COMIBOL	5728.25	5241.25	4464.18	1.20	80			18.51
Adela	COMIBOL	5728.25	5241.25	4466.71	1.60	30			
Adela	COMIBOL	5728.37	5266.06	4467.75	0.90	198			
Adela	COMIBOL	5729.14	5240.70	4437.75	2.30	310			30.89

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Adela	COMIBOL	5729.68	5205.98	4399.50	0.75	240	29.19
Adela	COMIBOL	5730.07	5265.17	4467.75	0.80	184	
Adela	COMIBOL	5730.62	5239.76	4437.75	2.80	260	
Adela	COMIBOL	5731.36	5204.92	4399.50	1.20	500	22.60
Adela	COMIBOL	5731.71	5264.31	4467.75	1.40	250	
Adela	COMIBOL	5732.75	5238.52	4437.75	2.50	200	29.65
Adela	COMIBOL	5733.41	5203.62	4399.50	0.80	110	6.55
Adela	COMIBOL	5733.44	5263.40	4467.75	1.20	90	
Adela	COMIBOL	5734.56	5237.46	4437.75	2.00	120	
Adela	COMIBOL	5734.97	5202.63	4399.50	1.15	80	33.44
Adela	COMIBOL	5735.09	5262.48	4467.75	1.10	120	
Adela	COMIBOL	5736.40	5236.39	4437.75	2.20	220	30.99
Adela	COMIBOL	5736.69	5261.60	4467.75	1.20	140	
Adela	COMIBOL	5737.04	5201.32	4399.50	1.00	510	41.53
Adela	COMIBOL	5738.09	5235.41	4437.75	1.10	300	15.74
Adela	COMIBOL	5738.41	5260.65	4467.75	0.70	17	
Adela	COMIBOL	5738.68	5200.33	4399.50	1.00	760	23.90
Adela	COMIBOL	5739.78	5234.31	4437.75	1.20	270	
Adela	COMIBOL	5740.06	5259.65	4467.75	1.30	450	
Adela	COMIBOL	5740.72	5199.11	4399.50	0.80	105	17.41
Adela	COMIBOL	5741.68	5258.57	4467.75	2.10	206	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Adela	COMIBOL	5741.84	5232.99	4437.75	1.00	110			8.92
Adela	COMIBOL	5742.59	5197.99	4399.50	0.80	15			3.13
Adela	COMIBOL	5743.41	5257.41	4467.75	1.10	60			
Adela	COMIBOL	5743.49	5231.93	4437.75	0.70	60			14.25
Adela	COMIBOL	5744.53	5196.93	4399.50	0.80	206			15.62
Adela	COMIBOL	5744.81	5231.08	4437.75	0.70	266			
Adela	COMIBOL	5744.81	5256.47	4467.75	1.30	7			
Adela	COMIBOL	5746.36	5230.04	4437.75	0.70	160			17.03
Adela	COMIBOL	5746.52	5195.90	4399.50	1.00	280			15.90
Adela	COMIBOL	5746.54	5255.29	4467.75	2.20	120			
Adela	COMIBOL	5747.78	5229.02	4437.75	0.70	31			
Adela	COMIBOL	5748.41	5194.93	4399.50	0.80	120			8.85
Adela	COMIBOL	5749.09	5228.06	4437.75	0.70	4			0.51
Adela	COMIBOL	5750.53	5193.84	4399.50	0.80	50			3.62
Adela	COMIBOL	5750.65	5226.92	4437.75	1.00	800			1.98
Adela	COMIBOL	5752.21	5225.77	4437.75	0.70	84			
Adela	COMIBOL	5753.98	5224.48	4437.75	0.70	600			7.78
Adela	COMIBOL	5755.66	5223.21	4437.75	1.30	200			
Adela	COMIBOL	5756.93	5222.19	4437.75	0.70	29			0.28
Adela	COMIBOL	5758.45	5220.95	4437.75	1.10	700			
Adela	COMIBOL	5760.01	5219.69	4437.75	0.70	86			1.14
Adela	COMIBOL	5761.63	5218.33	4437.75	0.80	500			
Adela	COMIBOL	5763.14	5217.79	4437.75	1.30	400			2.77
Artola	COMIBOL	5370.83	5226.08	4469.25	0.70	697			
Artola	COMIBOL	5372.63	5226.83	4469.25	0.70	593			
Artola	COMIBOL	5374.10	5227.63	4469.25	0.70	3,187			
Artola	COMIBOL	5374.19	5220.83	4437.25	0.70	35			
Artola	COMIBOL	5375.58	5228.57	4469.25	0.70	2,700			
Artola	COMIBOL	5375.74	5221.57	4437.25	0.70	2			
Artola	COMIBOL	5376.95	5229.44	4469.25	0.70	917			
Artola	COMIBOL	5377.33	5222.39	4437.25	0.70	1			
Artola	COMIBOL	5378.33	5230.61	4469.25	0.70	796			
Artola	COMIBOL	5378.95	5223.38	4437.25	0.70	1			
Artola	COMIBOL	5379.69	5231.83	4469.25	0.70	728			
Artola	COMIBOL	5380.58	5224.39	4437.25	0.70	10			
Artola	COMIBOL	5381.01	5233.03	4469.25	0.70	549			
Artola	COMIBOL	5382.11	5225.44	4437.25	0.70	12			
Artola	COMIBOL	5382.27	5234.20	4469.25	0.70	152			
Artola	COMIBOL	5383.60	5226.47	4437.25	0.70	27			
Artola	COMIBOL	5383.71	5235.57	4469.25	0.70	282			
Artola	COMIBOL	5384.99	5236.79	4469.25	0.70	49			
Artola	COMIBOL	5385.14	5227.54	4437.25	0.70	52			
Artola	COMIBOL	5386.14	5237.86	4469.25	0.70	133			
Artola	COMIBOL	5386.72	5228.74	4437.25	0.70	62			
Artola	COMIBOL	5387.46	5239.04	4469.25	0.70	375			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Artola	COMIBOL	5388.04	5229.75	4437.25	0.70	64
Artola	COMIBOL	5388.82	5240.24	4469.25	0.70	746
Artola	COMIBOL	5389.51	5230.86	4437.25	0.70	50
Artola	COMIBOL	5390.06	5241.34	4469.25	0.70	56
Artola	COMIBOL	5390.98	5231.95	4437.25	0.70	93
Artola	COMIBOL	5391.15	5242.38	4469.25	0.70	114
Artola	COMIBOL	5392.54	5233.09	4437.25	0.70	93
Artola	COMIBOL	5392.61	5243.83	4469.25	0.80	300
Artola	COMIBOL	5393.93	5234.11	4437.25	0.70	28
Artola	COMIBOL	5395.51	5235.27	4437.25	0.70	71
Artola	COMIBOL	5396.85	5236.38	4437.25	0.70	134
Artola	COMIBOL	5398.49	5237.55	4437.25	0.70	42
Artola	COMIBOL	5400.63	5238.72	4437.25	0.70	47
Artola	COMIBOL	5402.34	5239.66	4437.25	0.70	27
Artola	COMIBOL	5404.36	5240.78	4437.25	0.70	156
Artola	COMIBOL	5406.15	5241.95	4437.25	0.70	55
Artola	COMIBOL	5408.02	5243.16	4437.25	0.70	10
Artola	COMIBOL	5409.60	5244.19	4437.25	0.70	359
Artola	COMIBOL	5411.45	5245.46	4437.25	0.70	114
Artola	COMIBOL	5413.33	5246.79	4437.25	0.70	26
Artola	COMIBOL	5415.02	5248.02	4437.25	0.70	8

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Artola	COMIBOL	5416.60	5249.42	4437.25	0.70	19			
Artola	COMIBOL	5418.28	5250.90	4437.25	0.70	22			
Artola	COMIBOL	5418.56	5262.80	4469.25	0.70	90			
Artola	COMIBOL	5419.81	5252.49	4437.25	0.70	76			
Artola	COMIBOL	5420.34	5263.72	4469.25	0.70	180			
Artola	COMIBOL	5421.29	5254.20	4437.25	0.70	1			
Artola	COMIBOL	5422.24	5264.70	4469.25	0.70	457			
Artola	COMIBOL	5424.24	5265.63	4469.25	0.70	390			
Artola	COMIBOL	5426.13	5266.52	4469.25	0.70	190			
Artola	COMIBOL	5427.92	5267.35	4469.25	0.70	380			
Artola	COMIBOL	5430.06	5268.31	4469.25	0.70	1,196			
Artola	COMIBOL	5431.88	5269.12	4469.25	0.70	840			
Artola	COMIBOL	5433.91	5270.03	4469.25	0.70	345			
Artola	COMIBOL	5435.53	5270.90	4469.25	0.70	373			
Artola	COMIBOL	5437.46	5271.99	4469.25	0.70	206			
Artola	COMIBOL	5439.25	5273.02	4469.25	0.70	87			
Artola	COMIBOL	5441.11	5274.34	4469.25	0.70	53			
Artola	COMIBOL	5452.60	5282.96	4469.25	0.70	20			
Artola	COMIBOL	5456.50	5285.17	4469.25	0.70	347			
Artola	COMIBOL	5458.53	5286.35	4469.25	0.70	179			
Artola	COMIBOL	5460.50	5287.85	4469.25	0.70	120			
Artola	COMIBOL	5462.21	5289.23	4469.25	0.70	8			
Artola	COMIBOL	5462.94	5282.04	4437.25	0.70	77			
Artola	COMIBOL	5464.53	5283.01	4437.25	0.70	350			
Artola	COMIBOL	5465.78	5292.12	4469.25	0.70	11			
Artola	COMIBOL	5466.38	5284.15	4437.25	0.70	334			
Artola	COMIBOL	5467.61	5293.58	4469.25	0.70	94			
Artola	COMIBOL	5467.83	5285.04	4437.25	0.70	1,682			
Artola	COMIBOL	5469.37	5285.98	4437.25	0.70	252			
Artola	COMIBOL	5469.42	5294.66	4469.25	0.70	22			
Artola	COMIBOL	5471.23	5286.90	4437.25	0.70	51			
Artola	COMIBOL	5471.64	5295.75	4469.25	0.70	293			
Artola	COMIBOL	5473.16	5287.32	4437.25	0.70	258			
Artola	COMIBOL	5474.92	5287.70	4437.25	0.70	94			
Artola	COMIBOL	5476.78	5288.11	4437.25	0.70	2			
Artola	COMIBOL	5478.75	5288.54	4437.25	0.70	30			
Artola	COMIBOL	5480.49	5288.92	4437.25	0.70	24			
Artola	COMIBOL	5482.42	5289.35	4437.25	0.70	51			
Artola	COMIBOL	5484.24	5289.85	4437.25	0.70	26			
Artola	COMIBOL	5486.18	5290.38	4437.25	0.70	21			
Artola	COMIBOL	5487.86	5291.19	4437.25	0.70	13			
Artola	COMIBOL	5489.14	5302.54	4469.25	0.70	1,841			
Artola	COMIBOL	5489.49	5292.27	4437.25	0.70	16			
Artola	COMIBOL	5491.08	5293.23	4437.25	0.70	114			
Artola	COMIBOL	5491.90	5302.71	4469.25	0.70	239			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Artola	COMIBOL	5492.97	5294.39	4437.25	0.70	494
Artola	COMIBOL	5494.34	5295.29	4437.25	0.70	28
Artola	COMIBOL	5494.91	5302.94	4469.25	0.70	38
Artola	COMIBOL	5496.01	5296.39	4437.25	0.70	83
Artola	COMIBOL	5497.75	5297.57	4437.25	0.70	41
Artola	COMIBOL	5498.54	5304.11	4469.25	0.70	257
Artola	COMIBOL	5499.19	5298.52	4437.25	0.70	1,970
Artola	COMIBOL	5500.75	5299.49	4437.25	0.70	8
Artola	COMIBOL	5502.02	5305.67	4469.25	0.70	242
Artola	COMIBOL	5502.52	5300.62	4437.25	0.70	37
Artola	COMIBOL	5504.12	5301.63	4437.25	0.70	1
Artola	COMIBOL	5505.31	5307.85	4469.25	0.70	811
Artola	COMIBOL	5505.52	5302.52	4437.25	0.70	32
Artola	COMIBOL	5507.19	5303.59	4437.25	0.70	11
Artola	COMIBOL	5508.42	5304.59	4437.25	0.70	26
Artola	COMIBOL	5508.74	5309.77	4469.25	0.70	1,510
Artola	COMIBOL	5510.03	5305.89	4437.25	0.90	1,008
Artola	COMIBOL	5511.48	5307.14	4437.25	0.70	23
Artola	COMIBOL	5512.06	5311.47	4469.25	0.70	441
Artola	COMIBOL	5512.84	5308.52	4437.25	0.70	7
Artola	COMIBOL	5514.13	5309.74	4437.25	0.70	34

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Artola	COMIBOL	5515.74	5312.92	4469.25	0.70	378			
Artola	COMIBOL	5515.91	5310.40	4437.25	0.70	62			
Artola	COMIBOL	5517.63	5311.05	4437.25	0.70	165			
Artola	COMIBOL	5518.85	5313.60	4469.25	0.70	522			
Artola	COMIBOL	5519.48	5311.67	4437.25	0.70	175			
Artola	COMIBOL	5520.57	5314.29	4469.25	0.70	64			
Artola	COMIBOL	5521.30	5312.13	4437.25	0.70	90			
Artola	COMIBOL	5522.60	5315.06	4469.25	0.70	129			
Artola	COMIBOL	5522.77	5312.51	4437.25	0.70	37			
Artola	COMIBOL	5524.48	5313.54	4437.25	0.70	164			
Artola	COMIBOL	5524.62	5315.81	4469.25	0.70	41			
Artola	COMIBOL	5526.09	5314.61	4437.25	0.70	6			
Artola	COMIBOL	5526.54	5316.54	4469.25	0.70	10			
Artola	COMIBOL	5527.74	5315.65	4437.25	0.70	9			
Artola	COMIBOL	5528.49	5317.32	4469.25	0.70	53			
Artola	COMIBOL	5529.24	5316.56	4437.25	0.70	14			
Artola	COMIBOL	5530.33	5318.06	4469.25	0.70	36			
Cantera	PASB	4924.05	5560.38	4395.19	1.47	140	0.05	0.15	2.51
Cantera	PASB	4928.12	5559.37	4395.19	1.51	149	0.05	0.16	1.87
Cantera	PASB	4932.11	5558.38	4395.19	1.36	92	0.02	0.08	0.74
Cantera	PASB	4936.05	5557.40	4395.19	1.38	292	0.10	0.22	2.84
Cantera	PASB	4939.97	5556.47	4395.18	1.38	476	0.06	0.21	2.13
Cantera	PASB	4943.99	5555.53	4395.17	1.30	245	0.08	0.22	2.47
Cantera	PASB	4948.04	5554.64	4395.17	1.43	562	0.14	0.31	3.60
Cantera	PASB	4951.93	5553.77	4395.14	1.38	493	0.18	0.35	6.21
Cantera	PASB	4955.82	5552.65	4395.09	1.30	144	0.05	0.21	1.38
Cantera	PASB	4959.79	5551.52	4395.03	1.30	205	0.10	0.17	2.92
Cantera	PASB	4963.81	5550.41	4395.00	0.95	118	0.04	0.20	0.96
Cantera	PASB	4967.87	5549.29	4394.98	1.38	114	0.04	0.15	1.05
Cantera	PASB	4967.92	5571.43	4356.54	1.10	151	0.14	0.62	1.66
Cantera	PASB	4971.70	5548.23	4394.96	1.64	267	0.11	0.14	1.86
Cantera	PASB	4972.04	5570.40	4356.51	0.73	110	0.13	0.74	2.97
Cantera	PASB	4975.13	5568.86	4356.51	1.01	107	0.14	0.81	3.65
Cantera	PASB	4975.76	5547.11	4394.95	1.35	80	0.02	0.10	0.52
Cantera	PASB	4979.87	5545.78	4394.96	1.07	102	0.04	0.12	0.91
Cantera	PASB	4980.28	5567.83	4356.50	1.84	372	0.31	1.24	11.00
Cantera	PASB	4983.88	5566.80	4356.45	1.00	41	0.06	0.09	0.74
Cantera	PASB	4984.16	5544.20	4395.00	1.28	148	0.06	0.71	2.45
Cantera	PASB	4987.78	5543.54	4394.93	1.13	389	0.07	0.30	1.71
Cantera	PASB	4988.00	5565.77	4356.37	1.70	141	0.20	0.12	6.91
Cantera	PASB	4991.71	5542.83	4394.85	0.99	58	0.03	0.22	0.84
Cantera	PASB	4992.12	5564.74	4356.30	1.45	130	0.15	0.16	7.36
Cantera	PASB	4995.67	5541.82	4394.83	1.13	392	0.11	0.72	2.37
Cantera	PASB	4995.73	5563.19	4356.36	2.10	75	0.11	0.07	5.83
Cantera	PASB	4999.66	5540.63	4394.84	1.13	158	0.08	0.15	1.56

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Cantera	PASB	4999.85	5562.16	4356.40	1.75	167	0.19	0.05	3.41
Cantera	PASB	5003.45	5561.13	4356.34	1.05	458	0.12	0.15	11.20
Cantera	PASB	5003.63	5539.45	4394.89	1.37	603	0.22	0.28	5.57
Cantera	PASB	5007.56	5538.27	4395.03	1.63	460	0.11	1.06	2.34
Cantera	PASB	5007.57	5560.10	4356.27	2.05	458	0.15	0.22	3.90
Cantera	PASB	5011.47	5537.25	4394.96	1.13	286	0.10	0.25	2.34
Cantera	PASB	5011.69	5559.07	4356.20	2.30	61	0.05	0.10	1.92
Cantera	PASB	5015.30	5558.04	4356.19	1.90	282	0.09	0.12	3.90
Cantera	PASB	5015.54	5536.19	4394.88	1.39	562	0.18	0.62	3.83
Cantera	PASB	5019.42	5557.01	4356.23	0.76	105	0.08	0.12	1.52
Cantera	PASB	5019.47	5535.04	4394.91	1.71	490	0.18	0.17	2.45
Cantera	PASB	5023.40	5533.82	4394.98	1.88	253	0.09	0.15	2.43
Cantera	PASB	5023.54	5556.50	4356.26	0.70	343	0.14	0.78	3.99
Cantera	PASB	5027.45	5532.57	4395.06	1.54	603	0.27	0.21	3.83
Cantera	PASB	5027.66	5555.87	4356.27	1.10	172	0.10	0.26	5.40
Cantera	PASB	5031.22	5531.44	4395.08	1.14	145	0.06	0.12	1.55
Cantera	PASB	5031.26	5554.95	4356.26	1.30	304	0.13	0.16	4.00
Cantera	PASB	5035.24	5530.30	4395.15	1.39	115	0.06	0.10	1.01
Cantera	PASB	5035.38	5553.92	4356.26	0.70	494	0.09	0.16	2.57
Cantera	PASB	5039.50	5552.38	4356.25	0.70	171	0.09	0.20	5.89
Cantera	PASB	5039.51	5529.11	4395.16	1.09	83	0.05	0.11	1.01

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Cantera	PASB	5043.62	5551.35	4356.24	0.70	337	0.24	0.20	8.82
Cantera	PASB	5043.66	5527.82	4395.07	0.70	297	0.10	0.06	2.16
Cantera	PASB	5045.60	5527.12	4395.02	0.82	256	0.13	0.05	2.38
Cantera	PASB	5047.54	5526.43	4394.98	1.17	419	0.19	0.07	4.20
Cantera	PASB	5047.74	5550.83	4356.21	0.90	140	0.22	0.16	10.00
Cantera	PASB	5049.56	5525.92	4394.95	1.74	480	0.24	0.07	5.50
Cantera	PASB	5051.52	5525.32	4394.92	0.84	325	0.14	0.12	1.74
Cantera	PASB	5051.86	5549.80	4356.18	1.95	98	0.15	0.32	3.00
Cantera	PASB	5053.47	5524.62	4394.89	0.74	910	0.31	0.08	3.80
Cantera	PASB	5055.49	5524.09	4394.86	0.70	192	0.10	0.03	0.86
Cantera	PASB	5055.98	5548.77	4356.15	0.90	251	0.40	0.68	19.60
Cantera	PASB	5057.48	5523.63	4394.86	0.70	310	0.17	0.05	1.36
Cantera	PASB	5059.42	5522.94	4394.88	0.70	233	0.11	0.06	2.53
Cantera	PASB	5060.10	5547.74	4356.12	1.00	190	0.24	0.23	9.50
Cantera	PASB	5061.49	5522.60	4394.91	0.76	241	0.13	0.04	3.20
Cantera	PASB	5063.44	5521.91	4394.96	1.00	230	0.08	0.04	1.80
Cantera	PASB	5063.71	5547.23	4356.09	0.80	464	0.30	1.04	19.60
Cantera	PASB	5065.37	5521.21	4395.03	1.11	745	0.22	0.14	7.50
Cantera	PASB	5067.36	5520.63	4395.10	1.05	307	0.19	1.68	9.80
Cantera	PASB	5067.83	5546.71	4356.05	0.70	108	0.11	0.31	5.71
Cantera	PASB	5069.31	5519.94	4395.17	0.80	1,086	0.47	0.18	15.10
Cantera	PASB	5071.23	5519.25	4395.11	1.14	472	0.19	0.10	8.00
Cantera	PASB	5072.46	5545.68	4356.03	0.70	1,080	0.19	1.06	10.86
Cantera	PASB	5073.19	5518.57	4395.05	1.02	804	0.32	0.17	14.70
Cantera	PASB	5075.15	5517.95	4394.98	2.18	356	0.14	0.07	6.69
Cantera	PASB	5076.58	5544.65	4356.05	0.70	247	0.13	1.28	9.26
Cantera	PASB	5077.13	5517.38	4394.92	2.14	512	0.22	0.19	10.73
Cantera	PASB	5079.14	5516.90	4394.87	2.13	869	0.30	0.26	8.71
Cantera	PASB	5080.62	5544.32	4356.08	0.70	1,097	0.14	0.65	5.14
Cantera	PASB	5081.22	5516.55	4394.93	1.18	654	0.28	0.20	16.30
Cantera	PASB	5084.82	5543.11	4356.10	0.70	229	0.20	0.85	15.77
Cantera	PASB	5088.94	5542.08	4356.12	0.70	446	0.34	6.86	16.54
Cantera	PASB	5090.99	5515.19	4395.10	1.83	193	0.09	0.10	3.25
Cantera	PASB	5093.06	5541.05	4356.14	0.70	247	0.13	0.91	5.36
Cantera	PASB	5094.99	5514.41	4395.03	1.78	86	0.04	0.08	3.28
Cantera	PASB	5096.67	5538.99	4356.16	1.30	1,097	0.19	0.13	3.00
Cantera	PASB	5098.91	5513.53	4394.98	1.77	507	0.20	0.14	7.83
Cantera	PASB	5100.27	5537.44	4356.16	1.20	166	0.22	0.23	10.90
Cantera	PASB	5102.98	5512.32	4394.99	1.58	322	0.20	0.13	8.56
Cantera	PASB	5103.88	5535.38	4356.06	0.70	53	0.09	0.07	4.29
Cantera	PASB	5107.03	5511.11	4394.99	1.75	132	0.11	0.15	4.35
Cantera	PASB	5107.48	5532.81	4355.95	0.70	26	0.05	0.03	1.94
Cantera	PASB	5110.57	5530.75	4355.86	0.70	98	0.08	0.10	7.66
Cantera	PASB	5110.87	5509.86	4394.98	1.33	34	0.03	0.16	1.40
Cantera	PASB	5114.69	5508.12	4394.85	1.77	98	0.05	0.08	1.04

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Cantera	PASB	5114.69	5528.17	4355.82	1.00	408	0.12	0.10	6.30
Cantera	PASB	5117.78	5526.11	4355.81	0.70	79	0.77	0.16	12.07
Cantera	PASB	5118.10	5506.83	4394.79	1.58	234	0.13	0.13	3.60
Cantera	PASB	5120.87	5523.54	4355.80	0.70	75	0.04	0.09	7.76
Cantera	PASB	5122.15	5505.61	4394.79	1.58	322	0.14	0.12	3.24
Cantera	PASB	5124.48	5520.96	4355.71	0.70	81	0.04	0.07	4.00
Cantera	PASB	5126.11	5504.18	4394.82	2.04	96	0.09	0.07	0.95
Cantera	PASB	5127.57	5518.39	4355.62	0.70	230	0.15	0.30	20.57
Cantera	PASB	5129.95	5502.54	4394.87	2.06	62	0.06	0.07	1.20
Cantera	PASB	5131.17	5515.81	4355.51	0.70	112	0.04	0.15	4.64
Cantera	PASB	5133.52	5500.93	4394.93	1.25	370	0.22	0.15	6.91
Cantera	PASB	5134.26	5513.24	4355.46	1.10	22	0.02	0.04	0.50
Cantera	PASB	5136.86	5498.45	4394.86	1.24	202	0.22	0.15	3.77
Cantera	PASB	5137.35	5510.66	4355.43	0.70	74	0.01	0.04	1.30
Cantera	PASB	5140.44	5507.57	4355.38	0.70	55	0.02	0.05	1.04
Cantera	PASB	5143.43	5493.57	4394.72	2.09	108	0.13	0.10	1.93
Cantera	PASB	5143.53	5505.00	4355.32	0.70	41	0.02	0.04	1.39
Cantera	PASB	5146.71	5491.01	4394.68	1.48	134	0.16	0.12	1.27
Cantera	PASB	5147.14	5502.94	4355.30	0.70	66	0.02	0.12	4.07
Cantera	PASB	5149.82	5488.36	4394.69	0.94	134	0.09	0.09	2.15
Cantera	PASB	5150.23	5499.85	4355.31	0.70	36	0.02	0.07	1.98

15

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Cantera	PASB	5152.87	5485.10	4394.68	1.28	184	0.15	0.08	1.66
Cantera	PASB	5153.90	5498.28	4355.31	1.40	155	0.06	0.03	1.36
Cantera	PASB	5155.76	5481.88	4394.76	1.70	158	0.14	0.08	2.31
Cantera	PASB	5156.92	5494.70	4355.31	1.35	96	0.16	0.07	8.29
Cantera	PASB	5158.65	5478.95	4394.78	1.94	64	0.05	0.05	0.67
Cantera	PASB	5160.01	5492.12	4355.32	0.90	309	0.16	0.08	8.06
Cantera	PASB	5161.16	5476.06	4394.72	1.98	98	0.07	0.11	1.55
Cantera	PASB	5162.59	5489.03	4355.32	0.70	53	0.09	0.09	0.45
Cantera	PASB	5164.04	5472.78	4394.64	1.79	100	0.17	0.09	2.62
Cantera	PASB	5165.68	5485.94	4355.24	0.70	8	0.01	0.01	0.46
Cantera	PASB	5167.14	5470.18	4394.70	1.23	54	0.07	0.12	0.74
Cantera	PASB	5168.25	5483.37	4355.18	0.70	9	0.01	0.01	0.62
Cantera	PASB	5170.12	5467.89	4394.81	0.74	83	0.14	0.08	0.25
Cantera	PASB	5171.34	5480.28	4355.17	0.70	9	0.01	0.01	0.10
Cantera	PASB	5173.11	5464.98	4394.86	0.82	67	0.08	0.09	0.41
Cantera	PASB	5174.43	5477.70	4355.24	0.70	18	0.03	0.01	0.78
Cantera	PASB	5176.50	5461.32	4394.88	0.75	36	0.07	0.06	0.15
Cantera	PASB	5177.52	5474.61	4355.28	0.70	60	0.05	0.02	3.45
Cantera	PASB	5180.61	5471.52	4355.27	0.75	31	0.04	0.01	0.75
Cantera	PASB	5181.57	5456.07	4394.71	1.09	19	0.03	0.07	1.43
Cantera	PASB	5183.70	5468.43	4355.27	1.30	31	0.06	0.01	1.65
Cantera	PASB	5184.59	5452.95	4394.61	1.12	38	0.06	0.09	3.09
Cantera	PASB	5186.28	5465.86	4355.34	1.60	44	0.10	0.01	0.92
Cantera	PASB	5187.53	5450.16	4394.65	1.17	22	0.04	0.06	1.89
Cantera	PASB	5187.82	5462.77	4355.38	1.54	52	0.11	0.01	0.51
Cantera	PASB	5190.49	5447.49	4394.75	0.70	77	0.11	0.06	3.96
Cantera	PASB	5190.91	5459.68	4355.27	1.95	45	0.06	0.01	0.15
Cantera	PASB	5193.46	5444.87	4394.73	0.70	148	0.24	0.08	3.53
Cantera	PASB	5193.49	5457.10	4355.17	2.05	74	0.08	0.01	0.27
Cantera	PASB	5196.38	5441.89	4394.73	0.70	339	0.24	0.17	2.45
Cantera	PASB	5196.58	5454.53	4355.13	0.70	44	0.05	0.01	0.70
Cantera	PASB	5198.81	5439.40	4394.73	0.87	57	0.10	0.10	2.18
Cantera	PASB	5199.67	5451.95	4355.18	0.70	18	0.02	0.01	0.41
Cantera	PASB	5201.86	5435.90	4394.82	1.24	97	0.26	0.09	3.09
Cantera	PASB	5202.76	5448.86	4355.23	0.70	2	0.00	0.01	0.02
Cantera	PASB	5204.51	5432.87	4394.90	1.41	144	0.23	0.09	5.82
Cantera	PASB	5205.85	5445.77	4355.33	0.70	23	0.06	0.01	0.53
Cantera	PASB	5207.49	5429.69	4394.83	0.77	124	0.28	0.16	5.42
Cantera	PASB	5208.94	5442.68	4355.44	0.90	28	0.09	0.01	0.16
Cantera	PASB	5210.48	5426.93	4394.86	1.23	64	0.10	0.11	2.25
Cantera	PASB	5212.03	5439.59	4355.56	1.00	95	0.12	0.03	5.15
Cantera	PASB	5213.46	5424.24	4394.89	1.04	107	0.20	0.09	4.32
Cantera	PASB	5215.12	5437.02	4355.48	0.70	39	0.07	0.02	3.98
Cantera	PASB	5216.60	5421.47	4394.94	1.06	234	0.40	0.15	9.42
Cantera	PASB	5218.19	5433.95	4355.38	0.90	219	0.02	0.17	1.25

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Cantera	PASB	5219.74	5418.58	4394.90	1.72	79	0.15	0.07	2.39
Cantera	PASB	5221.30	5431.35	4355.34	0.70	38	0.01	0.11	0.88
Cantera	PASB	5222.93	5415.59	4394.83	1.45	175	0.22	0.08	2.68
Cantera	PASB	5224.39	5428.78	4355.29	0.70	91	0.02	0.23	4.00
Cantera	PASB	5225.93	5413.27	4394.84	1.20	286	0.24	0.07	2.38
Cantera	PASB	5227.48	5425.69	4355.27	0.90	43	0.02	0.09	2.13
Cantera	PASB	5229.36	5410.79	4394.92	0.87	92	0.23	0.11	1.70
Cantera	PASB	5230.05	5422.60	4355.28	1.50	149	0.04	0.18	8.50
Cantera	PASB	5232.78	5408.33	4395.01	0.82	131	0.31	0.09	2.50
Cantera	PASB	5233.14	5419.51	4355.29	0.75	103	0.03	0.11	4.00
Cantera	PASB	5236.02	5405.92	4395.05	0.70	109	0.19	0.06	3.16
Cantera	PASB	5236.23	5416.42	4355.43	0.70	21	0.02	0.03	1.77
Cantera	PASB	5239.27	5403.30	4394.96	0.70	90	0.19	0.07	0.27
Cantera	PASB	5239.32	5413.84	4355.46	0.70	41	0.02	0.10	1.01
Cantera	PASB	5242.41	5410.75	4355.39	0.70	9	0.02	0.01	0.15
Cantera	PASB	5242.43	5400.81	4394.90	0.70	51	0.23	0.07	0.72
Cantera	PASB	5245.59	5398.72	4394.99	0.70	13	0.08	0.04	0.43
Cantera	PASB	5248.26	5396.05	4395.01	0.70	41	0.13	0.13	2.47
Cantera	PASB	5251.20	5392.76	4395.01	0.99	63	0.20	0.09	1.64
Cantera	PASB	5254.12	5389.46	4395.01	0.71	27	0.10	0.07	1.39
Cantera	PASB	5257.05	5386.15	4395.01	0.93	77	0.16	0.10	0.84

16

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Cantera	PASB	5260.03	5383.22	4395.04	1.05	3	0.00	0.05	0.05
Cantera	PASB	5262.99	5380.42	4395.07	1.02	608	0.61	0.11	0.35
Cantera	PASB	5265.98	5377.65	4395.09	0.93	27	0.04	0.09	0.96
Cantera	PASB	5269.12	5374.84	4395.09	0.76	14	0.01	0.08	0.34
Cantera	PASB	5272.04	5372.27	4395.06	1.00	71	0.03	0.08	0.79
Cantera	PASB	5275.16	5369.55	4394.99	0.93	55	0.17	0.13	3.37
Cantera	PASB	5278.24	5366.75	4394.94	0.75	29	0.01	0.06	0.21
Cantera	PASB	5280.93	5363.79	4395.01	0.98	98	0.06	0.07	1.14
Cantera	PASB	5283.87	5360.93	4395.33	0.70	240	0.25	0.14	3.15
Cantera	PASB	5288.09	5344.18	4438.84	1.47	383	0.13	0.09	0.05
Cantera	PASB	5288.64	5355.96	4395.90	0.70	208			4.86
Cantera	PASB	5290.06	5354.46	4395.21	0.70	123			4.28
Cantera	PASB	5291.07	5341.29	4438.83	1.58	360	1.10	0.07	3.70
Cantera	PASB	5291.78	5353.28	4395.21	0.70	70			2.91
Cantera	PASB	5293.30	5351.90	4395.22	0.70	163			3.21
Cantera	PASB	5294.27	5338.62	4438.68	1.22	349	0.49	0.23	5.95
Cantera	PASB	5295.00	5350.67	4395.23	0.70	168			2.77
Cantera	PASB	5296.70	5349.51	4395.27	0.70	162			4.19
Cantera	PASB	5297.47	5335.95	4438.53	0.72	310	0.11	0.06	1.32
Cantera	PASB	5298.33	5348.22	4395.31	0.70	154			1.89
Cantera	PASB	5300.00	5347.00	4395.35	0.85	240			7.35
Cantera	PASB	5300.76	5333.29	4438.54	0.99	282	0.14	0.08	2.46
Cantera	PASB	5301.73	5345.83	4395.39	0.70	191			5.77
Cantera	PASB	5303.25	5344.45	4395.41	0.90	260			6.92
Cantera	PASB	5304.01	5330.68	4438.58	0.97	118	0.08	0.06	1.05
Cantera	PASB	5304.99	5343.29	4395.40	0.90	121			8.00
Cantera	PASB	5306.19	5328.82	4438.61	0.77	190	0.22	0.09	3.42
Cantera	PASB	5306.72	5342.13	4395.39	0.80	177			8.97
Cantera	PASB	5307.99	5340.46	4395.38	0.70	178			10.41
Cantera	PASB	5308.79	5325.92	4438.60	0.70	44	0.05	0.08	1.82
Cantera	PASB	5309.46	5339.02	4395.37	0.70	135			9.51
Cantera	PASB	5311.15	5337.82	4395.36	0.70	168			9.93
Cantera	PASB	5312.72	5336.47	4395.36	0.75	159			10.91
Cantera	PASB	5313.47	5322.56	4438.28	0.95	39	0.03	0.09	1.86
Cantera	PASB	5314.28	5335.13	4395.37	0.70	96			4.84
Cantera	PASB	5317.21	5332.23	4395.39	0.80	34			3.19
Cantera	PASB	5317.47	5318.64	4438.51	0.70	12	0.01	0.06	0.34
Cantera	PASB	5321.10	5315.18	4438.53	0.70	263	0.13	0.14	4.55
Cantera	PASB	5323.86	5326.00	4395.43	0.81	60	0.18	0.17	4.58
Cantera	PASB	5325.53	5311.53	4438.19	0.70	69	0.05	0.07	4.99
Cantera	PASB	5326.86	5323.40	4395.44	0.94	57	0.13	0.15	3.99
Cantera	PASB	5328.69	5308.73	4438.39	0.99	1,005	0.26	0.05	2.38
Cantera	PASB	5330.03	5320.63	4395.46	0.97	61	0.16	0.15	5.14
Cantera	PASB	5332.64	5305.25	4438.59	1.12	1,341	0.64	0.13	9.33
Cantera	PASB	5333.32	5317.77	4395.48	0.98	37	0.05	0.10	1.49

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Cantera	PASB	5335.73	5302.67	4438.40	0.94	480	0.18	0.09	6.00
Cantera	PASB	5336.57	5315.05	4395.56	1.17	23	0.04	0.08	0.80
Cantera	PASB	5338.81	5300.10	4438.22	0.74	358	0.17	0.16	10.50
Cantera	PASB	5339.82	5312.48	4395.68	1.24	247	0.11	0.08	0.80
Cantera	PASB	5341.67	5297.56	4438.42	0.70	1,074	0.41	0.12	2.03
Cantera	PASB	5343.05	5310.12	4395.64	0.85	8	0.05	0.06	0.16
Cantera	PASB	5345.41	5294.23	4438.71	1.58	1,341	0.40	0.08	6.63
Cantera	PASB	5346.30	5307.76	4395.60	0.88	161	0.40	0.11	1.87
Cantera	PASB	5348.51	5291.88	4438.60	1.19	980	0.44	0.09	11.63
Cantera	PASB	5351.72	5289.50	4438.42	1.07	455	0.15	0.09	5.23
Cantera	PASB	5356.13	5286.34	4438.36	0.92	105	0.12	0.06	6.63
Cantera	PASB	5360.94	5283.21	4438.89	1.35	65	0.05	0.08	4.08
Cantera	COMIBOL	4860.54	5535.34	4392.50	0.80	280			10.65
Cantera	COMIBOL	4862.82	5534.80	4392.50	0.80	200			8.94
Cantera	COMIBOL	4864.76	5534.34	4392.50	0.80	90			8.84
Cantera	COMIBOL	4866.68	5533.89	4392.50	0.80	172			5.04
Cantera	COMIBOL	4868.81	5533.40	4392.50	0.80	95			2.11
Cantera	COMIBOL	4870.93	5532.90	4392.50	0.80	30			9.65
Cantera	COMIBOL	4872.99	5532.43	4392.50	0.80	997			9.25
Cantera	COMIBOL	4874.93	5531.98	4392.50	0.70	130			3.52
Cantera	COMIBOL	4877.24	5531.54	4392.50	0.80	997			

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Cantera	COMIBOL	4877.48	5510.72	4435.00	1.30	210			2.84
Cantera	COMIBOL	4879.18	5531.23	4392.50	0.80	60			
Cantera	COMIBOL	4879.61	5510.31	4435.00	1.60	200			
Cantera	COMIBOL	4881.33	5530.90	4392.50	0.80	45			1.69
Cantera	COMIBOL	4881.61	5509.93	4435.00	1.70	220			3.29
Cantera	COMIBOL	4883.22	5530.60	4392.50	0.80	40			
Cantera	COMIBOL	4883.99	5509.48	4435.00	1.30	1,070			1.71
Cantera	COMIBOL	4885.49	5530.25	4392.50	0.80	37			4.08
Cantera	COMIBOL	4886.10	5509.08	4435.00	1.20	540			
Cantera	COMIBOL	4887.35	5529.96	4392.50	0.80	260			
Cantera	COMIBOL	4888.23	5508.67	4435.00	0.90	400			1.51
Cantera	COMIBOL	4889.42	5529.56	4392.50	0.80	105			4.89
Cantera	COMIBOL	4890.40	5508.30	4435.00	0.80	1,440			
Cantera	COMIBOL	4891.30	5529.08	4392.50	0.90	240			
Cantera	COMIBOL	4892.26	5507.98	4435.00	0.90	160			3.92
Cantera	COMIBOL	4893.30	5528.56	4392.50	0.80	370			9.65
Cantera	COMIBOL	4894.37	5507.62	4435.00	0.90	340			
Cantera	COMIBOL	4895.03	5528.12	4392.50	0.75	270			7.54
Cantera	COMIBOL	4896.64	5507.23	4435.00	0.70	343			5.08
Cantera	COMIBOL	4897.03	5527.61	4392.50	0.75	350			
Cantera	COMIBOL	4898.87	5506.73	4435.00	0.80	500			
Cantera	COMIBOL	4900.85	5506.20	4435.00	1.10	580			3.52
Cantera	COMIBOL	4902.82	5505.68	4435.00	0.80	1,440			
Cantera	COMIBOL	4904.92	5505.13	4435.00	1.10	20			
Cantera	COMIBOL	4907.09	5504.56	4435.00	0.70	280			2.91
Cantera	COMIBOL	4909.16	5504.08	4435.00	0.90	1,420			
Cantera	COMIBOL	4911.35	5503.65	4435.00	1.20	1,060			8.80
Cantera	COMIBOL	4913.40	5503.25	4435.00	1.10	200			
Cantera	COMIBOL	4915.28	5502.62	4435.00	0.70	320			5.43
Cantera	COMIBOL	4917.73	5502.14	4435.00	0.70	274			
Cantera	COMIBOL	4919.77	5501.75	4435.00	0.70	1,200			1.00
Cantera	COMIBOL	4921.98	5501.30	4435.00	0.70	57			
Cantera	COMIBOL	4924.35	5500.79	4435.00	0.70	50			1.91
Cantera	COMIBOL	4926.43	5500.35	4435.00	0.80	180			
Cantera	COMIBOL	4928.62	5499.93	4435.00	0.80	40			2.37
Cantera	COMIBOL	4930.96	5499.53	4435.00	0.70	21			
Cantera	COMIBOL	4932.98	5499.04	4435.00	0.70	55			1.42
Cantera	COMIBOL	4934.76	5498.59	4435.00	0.70	126			
Cantera	COMIBOL	4937.34	5497.94	4435.00	0.70	236			5.94
Cantera	COMIBOL	4939.66	5497.30	4435.00	0.70	157			
Cantera	COMIBOL	4941.92	5496.64	4435.00	0.70	80			4.99
Cantera	COMIBOL	4943.98	5496.04	4435.00	0.70	29			
Cantera	COMIBOL	4946.21	5495.37	4435.00	0.80	180			5.94
Cantera	COMIBOL	4948.25	5494.75	4435.00	0.90	70			
Cantera	COMIBOL	4950.44	5494.10	4435.00	0.70	309			4.59

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Cantera	COMIBOL	4952.63	5493.61	4435.00	0.70	166	
Cantera	COMIBOL	4955.14	5493.06	4435.00	0.70	300	2.88
Cantera	COMIBOL	4956.67	5492.73	4435.00	0.70	291	
Cantera	COMIBOL	4979.06	5486.57	4435.00	1.00	232	4.42
Cantera	COMIBOL	5020.82	5474.17	4435.00	1.00	273	3.80
Cantera	COMIBOL	5044.82	5441.21	4467.50	0.70	268	5.59
Cantera	COMIBOL	5062.95	5462.47	4435.00	0.70	381	8.77
Cantera	COMIBOL	5070.15	5429.28	4467.50	0.80	199	2.63
Cantera	COMIBOL	5086.59	5497.31	4355.51	1.00	85	9.91
Cantera	COMIBOL	5086.59	5497.31	4357.54	1.00	148	17.34
Cantera	COMIBOL	5086.59	5497.31	4359.83	1.00	162	20.57
Cantera	COMIBOL	5086.59	5497.31	4361.99	1.00	163	11.17
Cantera	COMIBOL	5086.59	5497.31	4363.64	1.00	193	12.47
Cantera	COMIBOL	5086.59	5497.31	4365.99	1.00	106	4.81
Cantera	COMIBOL	5086.59	5497.31	4367.77	1.00	245	13.94
Cantera	COMIBOL	5086.59	5497.31	4370.18	1.00	133	6.66
Cantera	COMIBOL	5086.59	5497.31	4372.28	1.00	80	5.30
Cantera	COMIBOL	5086.59	5497.31	4374.69	1.00	69	4.91
Cantera	COMIBOL	5086.59	5497.31	4376.66	1.00	203	9.67
Cantera	COMIBOL	5086.59	5497.31	4378.76	1.00	154	14.72
Cantera	COMIBOL	5086.59	5497.31	4380.79	1.00	61	2.47

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Cantera	COMIBOL	5086.59	5497.31	4382.95	1.00	112			3.73
Cantera	COMIBOL	5086.59	5497.31	4385.11	1.00	497			12.32
Cantera	COMIBOL	5086.59	5497.31	4387.14	1.00	334			7.51
Cantera	COMIBOL	5086.59	5497.31	4389.30	1.00	331			15.72
Cantera	COMIBOL	5086.59	5497.31	4391.65	1.00	275			9.97
Cantera	COMIBOL	5091.96	5419.80	4467.50	0.98	247			6.58
Cantera	COMIBOL	5103.67	5444.65	4435.00	0.90	207			3.32
Cantera	COMIBOL	5116.55	5406.48	4467.50	0.98	215			7.99
Cantera	COMIBOL	5135.44	5399.10	4467.50	0.75	198			4.89
Cantera	COMIBOL	5139.94	5422.06	4435.00	0.80	129			4.10
Cantera	COMIBOL	5151.70	5389.41	4467.50	0.70	260			4.34
Cantera	COMIBOL	5171.09	5398.00	4435.00	0.80	209			2.82
Cantera	COMIBOL	5171.16	5376.46	4467.50	0.70	110			4.34
Cantera	COMIBOL	5187.83	5365.49	4467.50	0.85	318			6.07
Cantera	COMIBOL	5188.07	5408.96	4355.19	1.00	330			2.83
Cantera	COMIBOL	5188.07	5408.96	4357.35	1.00	63			1.90
Cantera	COMIBOL	5188.07	5408.96	4359.32	1.00	67			0.79
Cantera	COMIBOL	5188.07	5408.96	4361.42	1.00	34			1.97
Cantera	COMIBOL	5188.07	5408.96	4363.39	1.00	46			2.82
Cantera	COMIBOL	5188.07	5408.96	4365.29	1.00	40			3.38
Cantera	COMIBOL	5188.07	5408.96	4367.39	1.00	17			1.13
Cantera	COMIBOL	5188.07	5408.96	4369.48	1.00	64			3.37
Cantera	COMIBOL	5188.07	5408.96	4371.52	1.00	53			1.23
Cantera	COMIBOL	5188.07	5408.96	4373.49	1.00	71			2.37
Cantera	COMIBOL	5188.07	5408.96	4375.45	1.00	93			4.06
Cantera	COMIBOL	5188.07	5408.96	4377.49	1.00	116			4.29
Cantera	COMIBOL	5188.07	5408.96	4379.52	1.00	68			2.65
Cantera	COMIBOL	5188.07	5408.96	4381.42	1.00	25			0.92
Cantera	COMIBOL	5188.07	5408.96	4383.46	1.00	39			0.86
Cantera	COMIBOL	5188.07	5408.96	4385.62	1.00	61			3.33
Cantera	COMIBOL	5188.07	5408.96	4387.52	1.00	101			3.65
Cantera	COMIBOL	5188.07	5408.96	4389.49	1.00	100			3.20
Cantera	COMIBOL	5188.07	5408.96	4391.65	1.00	104			1.36
Cantera	COMIBOL	5201.76	5371.96	4435.00	1.24	254			4.11
Cantera	COMIBOL	5210.04	5348.97	4467.50	0.90	403			6.47
Cantera	COMIBOL	5232.51	5345.74	4435.00	1.00	490			6.26
Cantera	COMIBOL	5250.34	5317.70	4467.50	1.00	616			5.79
Cantera	COMIBOL	5297.34	5279.78	4467.50	1.00	227			2.59
Cantera	COMIBOL	5313.22	5267.54	4467.50	0.85	304			6.22
Cantera	COMIBOL	5328.32	5254.79	4467.50	0.70	228			5.97
Cantera	COMIBOL	5344.45	5242.09	4467.50	0.70	185			5.93
Cantera	COMIBOL	5362.21	5229.58	4467.50	0.85	431			12.22
Cantera	COMIBOL	5365.19	5235.94	4435.00	0.70	170			6.95
Deseada	PASB	4720.00	5160.70	4438.92	1.10	232			4.10
Deseada	PASB	4722.04	5160.34	4438.95	1.78	259			16.60

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	PASB	4724.10	5160.07	4438.97	1.55	390			15.80
Deseada	PASB	4726.11	5159.61	4438.97	1.95	141			3.70
Deseada	PASB	4728.19	5159.40	4438.96	2.00	203			14.20
Deseada	PASB	4730.19	5158.90	4438.96	1.85	253			18.20
Deseada	PASB	4732.23	5158.55	4438.95	1.40	294			25.10
Deseada	PASB	4734.26	5158.16	4438.96	0.90	242			15.70
Deseada	PASB	4736.27	5157.70	4438.96	1.90	251			15.00
Deseada	PASB	4740.19	5156.44	4438.97	1.05	284			12.50
Deseada	PASB	4742.13	5155.72	4438.98	1.60	280			15.00
Deseada	PASB	4744.07	5154.97	4438.98	1.00	237			17.00
Deseada	PASB	4746.00	5154.25	4438.96	1.70	288			17.80
Deseada	PASB	4747.94	5153.53	4439.06	0.70	326			20.00
Deseada	PASB	4749.94	5153.02	4439.16	1.05	304			13.80
Deseada	PASB	4751.93	5152.53	4439.26	1.10	826			23.10
Deseada	PASB	4753.92	5151.95	4439.21	0.80	476			19.00
Deseada	PASB	4755.90	5151.38	4439.15	1.40	974			14.60
Deseada	PASB	4757.87	5150.77	4439.10	1.40	416			8.00
Deseada	PASB	4952.59	5100.63	4439.95	2.73	168	0.26	0.28	0.04
Deseada	PASB	4956.44	5099.15	4439.86	1.98	1	0.00	0.04	0.35
Deseada	PASB	4958.47	5098.55	4439.92	2.70	59	0.10	0.06	0.01
Deseada	PASB	4963.58	5097.13	4440.15	1.42	331	0.48	0.24	0.04

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	PASB	4967.46	5095.76	4440.02	1.48	546	1.10	0.35	9.01
Deseada	PASB	4972.08	5094.10	4440.21	1.70	489	0.93	0.21	0.07
Deseada	PASB	4977.16	5092.90	4440.02	2.25	229	0.47	0.09	0.05
Deseada	PASB	4979.70	5125.12	4396.45	1.30	202	0.56	0.64	7.00
Deseada	PASB	4980.68	5091.91	4439.90	1.71	17	0.04	0.04	0.01
Deseada	PASB	4981.76	5124.73	4396.50	1.10	53	0.09	0.13	1.40
Deseada	PASB	4983.79	5124.28	4396.52	1.45	107	0.29	0.07	3.80
Deseada	PASB	4984.28	5090.57	4439.95	1.65	99	0.20	0.05	2.55
Deseada	PASB	4985.90	5124.04	4396.45	1.30	350	0.84	0.14	7.50
Deseada	PASB	4987.94	5123.58	4396.38	1.72	219	0.60	0.08	5.50
Deseada	PASB	4988.23	5089.55	4440.03	1.60	196	0.40	0.08	1.68
Deseada	PASB	4989.94	5123.05	4396.31	1.90	116	0.31	0.09	6.75
Deseada	PASB	4991.98	5122.63	4396.24	1.55	122	0.29	0.12	3.80
Deseada	PASB	4992.82	5089.04	4440.09	0.90	71	0.12	0.07	2.21
Deseada	PASB	4993.95	5122.02	4396.17	1.60	35	0.10	0.09	1.48
Deseada	PASB	4995.94	5121.45	4396.12	0.75	28	0.06	0.04	1.20
Deseada	PASB	4997.01	5088.73	4439.80	1.05	46	0.09	0.05	0.70
Deseada	PASB	4997.95	5120.92	4396.12	1.10	60	0.13	0.06	1.56
Deseada	PASB	4999.94	5120.35	4396.13	2.08	36	0.06	0.15	0.90
Deseada	PASB	5000.57	5087.81	4439.93	0.91	116	0.33	0.06	0.92
Deseada	PASB	5001.85	5119.60	4396.13	2.00	51	0.09	0.11	1.68
Deseada	PASB	5003.82	5118.99	4396.13	2.00	139	0.20	0.07	0.84
Deseada	PASB	5004.77	5086.79	4440.01	0.70	25	0.08	0.03	0.36
Deseada	PASB	5005.77	5118.31	4396.13	2.30	169	0.30	0.07	2.20
Deseada	PASB	5007.78	5117.78	4396.11	2.15	334	0.64	0.08	5.50
Deseada	PASB	5008.98	5085.07	4440.03	0.78	202	0.32	0.04	1.38
Deseada	PASB	5009.78	5117.28	4396.09	1.80	110	0.18	0.17	3.00
Deseada	PASB	5011.82	5116.83	4396.07	1.70	397	0.68	0.20	3.70
Deseada	PASB	5012.48	5083.46	4440.21	1.40	151	0.31	0.21	2.06
Deseada	PASB	5013.81	5116.26	4396.05	1.20	176	0.40	0.13	10.40
Deseada	PASB	5015.78	5115.66	4396.03	0.70	73	0.16	0.04	1.82
Deseada	PASB	5016.12	5081.43	4440.16	1.15	179	0.42	0.09	4.44
Deseada	PASB	5017.78	5115.13	4396.01	0.70	39	0.09	0.03	1.89
Deseada	PASB	5020.16	5079.46	4440.11	1.13	343	1.07	0.15	5.34
Deseada	PASB	5024.28	5078.06	4440.07	1.30	99	0.24	0.09	1.84
Deseada	PASB	5027.62	5076.76	4440.12	0.90	25	0.08	0.06	2.11
Deseada	PASB	5028.61	5112.00	4396.07	0.98	331	0.51	0.09	1.52
Deseada	PASB	5031.78	5075.04	4440.24	0.80	7	0.03	0.04	0.84
Deseada	PASB	5032.65	5111.33	4396.08	0.75	29	0.10	0.06	0.72
Deseada	PASB	5035.08	5073.60	4440.33	1.33	228	0.50	0.06	4.80
Deseada	PASB	5036.38	5109.48	4396.09	1.26	2	0.00	0.04	0.40
Deseada	PASB	5039.31	5071.46	4440.47	0.95	84	0.21	0.07	1.82
Deseada	PASB	5039.97	5107.04	4396.10	0.70	35	0.06	0.11	1.05
Deseada	PASB	5043.38	5069.63	4440.46	1.40	159	0.39	0.08	8.19
Deseada	PASB	5043.68	5105.11	4396.13	0.70	84	0.22	0.11	0.91

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	PASB	5047.30	5102.76	4396.25	0.97	275	0.59	0.08	3.69
Deseada	PASB	5048.62	5067.95	4440.10	1.25	205	0.53	0.11	9.36
Deseada	PASB	5051.45	5102.60	4396.39	1.43	114	0.27	0.06	1.81
Deseada	PASB	5051.54	5065.75	4439.99	1.35	82	0.24	0.11	1.92
Deseada	PASB	5054.48	5063.97	4440.07	1.30	73	0.24	0.18	2.71
Deseada	PASB	5054.95	5099.79	4396.43	1.00	91	0.17	0.07	1.91
Deseada	PASB	5058.50	5062.46	4440.25	1.00	120	0.51	0.18	1.55
Deseada	PASB	5060.93	5097.39	4395.93	0.70	329	0.96	0.29	12.60
Deseada	PASB	5062.24	5061.26	4440.13	0.85	45	0.12	0.05	1.14
Deseada	PASB	5065.32	5096.07	4396.11	0.74	464	1.20	0.12	9.50
Deseada	PASB	5065.73	5059.81	4440.19	0.95	14	0.09	0.06	0.80
Deseada	PASB	5067.67	5095.46	4396.18	1.20	418	1.50	0.36	13.20
Deseada	PASB	5068.74	5058.56	4440.24	1.05	79	0.19	0.07	6.90
Deseada	PASB	5069.66	5094.88	4396.25	1.77	251	0.40	0.09	4.90
Deseada	PASB	5072.03	5094.40	4396.33	1.67	120	0.21	0.10	1.84
Deseada	PASB	5073.06	5056.77	4440.31	1.00	61	0.28	0.06	3.36
Deseada	PASB	5074.24	5093.79	4396.28	0.70	37	0.32	0.01	1.75
Deseada	PASB	5076.52	5093.16	4396.22	0.70	4	0.04	0.01	0.07
Deseada	PASB	5077.20	5054.93	4440.38	0.70	96	0.20	0.07	0.79
Deseada	PASB	5078.72	5092.62	4396.16	0.70	4	0.07	0.01	0.03
Deseada	PASB	5080.92	5091.91	4396.12	0.70	2	0.06	0.01	0.04

20

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	PASB	5081.19	5053.13	4440.44	0.70	198	0.43	0.09	5.23
Deseada	PASB	5082.96	5091.16	4396.13	0.70	74	0.19	0.13	1.45
Deseada	PASB	5085.25	5050.77	4440.50	1.30	117	0.16	0.07	2.00
Deseada	PASB	5085.44	5090.54	4396.12	0.70	29	0.11	0.02	1.27
Deseada	PASB	5087.52	5049.67	4440.52	0.92	227	0.21	0.17	2.82
Deseada	PASB	5087.59	5090.16	4396.11	0.70	5	0.15	0.01	0.27
Deseada	PASB	5089.78	5089.58	4396.10	0.75	106	0.21	0.14	5.50
Deseada	PASB	5092.02	5089.04	4396.09	1.04	72	0.25	0.04	1.76
Deseada	PASB	5092.29	5047.57	4440.55	0.82	238	0.35	0.11	7.22
Deseada	PASB	5094.29	5088.45	4396.09	1.61	36	0.09	0.04	1.44
Deseada	PASB	5096.41	5087.80	4396.08	1.46	95	0.24	0.04	2.00
Deseada	PASB	5096.97	5045.92	4440.69	1.37	26	0.11	0.04	0.98
Deseada	PASB	5098.68	5087.01	4396.04	0.70	113	0.39	0.12	1.32
Deseada	PASB	5100.53	5044.84	4440.77	1.30	131	0.29	0.05	1.12
Deseada	PASB	5100.77	5086.14	4396.00	0.92	54	0.22	0.03	0.94
Deseada	PASB	5102.82	5085.25	4395.96	0.70	6	0.03	0.01	0.94
Deseada	PASB	5105.26	5044.76	4440.72	1.60	64	0.12	0.04	2.53
Deseada	PASB	5108.36	5044.71	4440.69	1.60	337	0.68	0.12	0.03
Deseada	PASB	5109.81	5082.53	4395.95	1.55	91	0.19	0.11	2.32
Deseada	PASB	5112.17	5044.42	4440.67	1.45	1,496	1.85	0.13	12.37
Deseada	PASB	5113.86	5081.73	4395.97	0.90	262	0.74	0.48	6.39
Deseada	PASB	5116.45	5043.31	4440.71	0.85	500	0.67	0.08	5.75
Deseada	PASB	5117.91	5080.94	4396.00	0.75	0	0.01	0.05	0.03
Deseada	PASB	5120.39	5042.30	4440.75	1.15	353	0.49	0.05	4.96
Deseada	PASB	5121.85	5079.73	4396.09	0.70	554	1.12	0.11	6.18
Deseada	PASB	5124.41	5040.87	4440.89	0.90	858	1.35	0.25	9.12
Deseada	PASB	5125.76	5078.40	4396.25	0.70	318	0.67	0.09	2.80
Deseada	PASB	5128.70	5039.25	4441.05	1.35	596	0.58	0.11	3.34
Deseada	PASB	5129.78	5077.48	4396.43	1.15	27	0.15	0.03	1.22
Deseada	PASB	5132.60	5038.76	4440.90	1.20	426	0.59	0.08	2.85
Deseada	PASB	5135.43	5038.41	4440.78	0.85	385	0.42	0.14	3.94
Deseada	PASB	5137.82	5075.67	4396.58	0.75	2	0.04	0.04	0.18
Deseada	PASB	5139.71	5037.86	4440.61	1.07	924	0.93	0.08	3.88
Deseada	PASB	5142.92	5074.18	4396.58	0.70	3	0.04	0.02	0.27
Deseada	PASB	5144.28	5036.07	4440.65	1.50	137	0.21	0.07	4.60
Deseada	PASB	5147.18	5073.69	4396.79	1.00	376	0.76	1.00	5.80
Deseada	PASB	5147.39	5034.59	4440.77	1.15	161	0.18	0.06	1.67
Deseada	PASB	5149.10	5072.96	4396.89	1.75	420	0.92	0.60	8.10
Deseada	PASB	5151.10	5072.43	4396.87	0.70	362	1.29	0.13	9.14
Deseada	PASB	5152.24	5033.16	4440.86	1.17	2	0.01	0.04	0.38
Deseada	PASB	5153.02	5071.65	4396.77	0.90	400	1.16	0.14	5.80
Deseada	PASB	5154.37	5032.66	4440.89	0.95	61	0.18	0.06	1.33
Deseada	PASB	5154.98	5071.04	4396.66	0.80	180	0.64	0.06	2.80
Deseada	PASB	5157.59	5071.99	4396.52	0.70	264	0.50	0.14	5.81
Deseada	PASB	5159.50	5031.34	4440.93	1.14	606	1.68	0.05	2.48

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	PASB	5160.10	5072.71	4396.44	0.70	126	0.45	0.03	1.42
Deseada	PASB	5162.44	5073.00	4396.38	1.10	296	0.72	0.08	0.96
Deseada	PASB	5163.46	5030.00	4440.80	0.79	1,418	3.55	0.11	6.31
Deseada	PASB	5165.03	5073.88	4396.20	1.10	196	0.48	0.03	0.60
Deseada	PASB	5166.95	5028.82	4440.69	1.11	530	0.88	0.09	4.40
Deseada	PASB	5167.57	5074.68	4396.38	0.98	150	0.56	0.04	1.56
Deseada	PASB	5170.05	5075.34	4396.55	0.80	148	0.44	0.09	4.60
Deseada	PASB	5171.31	5027.40	4440.74	0.77	314	0.48	0.07	3.70
Deseada	PASB	5172.59	5076.09	4396.68	1.20	468	0.84	0.14	4.60
Deseada	PASB	5174.80	5026.28	4440.83	0.71	644	1.29	0.11	7.03
Deseada	PASB	5175.07	5076.74	4396.79	1.84	450	1.56	0.64	7.00
Deseada	PASB	5177.53	5076.43	4396.89	1.07	352	0.84	0.14	11.90
Deseada	PASB	5179.05	5027.49	4440.93	1.00	739	2.08	0.12	3.67
Deseada	PASB	5180.23	5078.72	4396.86	1.20	162	0.48	0.10	3.60
Deseada	PASB	5185.20	5085.32	4396.53	2.20	488	0.64	0.18	10.50
Deseada	PASB	5186.05	5029.99	4441.09	1.70	222	0.27	0.05	1.83
Deseada	PASB	5188.86	5032.55	4441.01	1.63	84	0.16	0.06	8.16
Deseada	PASB	5190.69	5085.18	4396.56	1.70	641	1.18	0.24	8.75
Deseada	PASB	5192.68	5084.61	4396.59	1.58	315	0.56	0.17	5.50
Deseada	PASB	5193.00	5038.19	4440.77	1.95	393	0.44	0.04	0.02
Deseada	PASB	5194.70	5084.11	4396.62	1.68	160	0.30	0.10	3.20

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	PASB	5195.29	5041.26	4440.66	1.76	709	1.37	0.07	6.02
Deseada	PASB	5196.69	5083.51	4396.65	1.60	432	0.64	0.18	13.20
Deseada	PASB	5197.68	5044.41	4440.68	1.24	90	0.16	0.03	2.04
Deseada	PASB	5198.68	5082.93	4396.68	1.97	402	0.76	0.24	13.30
Deseada	PASB	5200.11	5047.31	4440.73	0.84	27	0.05	0.05	1.11
Deseada	PASB	5200.65	5082.34	4396.71	1.55	350	1.08	0.12	9.25
Deseada	PASB	5202.64	5081.77	4396.74	0.80	54	0.19	0.05	1.76
Deseada	PASB	5202.98	5049.72	4440.69	0.70	2	0.00	0.04	0.19
Deseada	PASB	5204.67	5081.28	4396.74	1.14	100	0.33	0.09	1.96
Deseada	PASB	5206.42	5050.50	4440.77	0.73	3	0.00	0.03	0.29
Deseada	PASB	5206.72	5080.84	4396.74	0.95	440	0.72	0.12	6.50
Deseada	PASB	5208.78	5080.45	4396.73	1.32	500	1.00	0.11	9.50
Deseada	PASB	5210.79	5079.91	4396.73	0.85	570	1.70	0.33	5.00
Deseada	PASB	5211.51	5049.58	4440.91	1.50	24	0.04	0.04	1.52
Deseada	PASB	5212.78	5079.34	4396.72	1.80	450	0.92	0.08	5.50
Deseada	PASB	5214.01	5048.69	4440.94	1.20	305	0.33	0.05	3.29
Deseada	PASB	5214.76	5078.76	4396.66	0.85	472	1.00	0.10	10.90
Deseada	PASB	5216.67	5077.99	4396.62	1.00	269	0.92	0.16	3.40
Deseada	PASB	5216.90	5047.65	4440.97	1.11	33	0.05	0.04	1.11
Deseada	PASB	5218.59	5077.22	4396.62	1.30	762	1.52	0.23	17.20
Deseada	PASB	5220.59	5076.70	4396.64	1.10	1,310	2.95	0.23	6.50
Deseada	PASB	5220.63	5046.31	4441.01	1.52	157	0.20	0.05	1.42
Deseada	PASB	5222.52	5075.96	4396.66	1.15	1,118	1.60	0.12	6.00
Deseada	PASB	5224.52	5044.90	4441.05	1.70	77	0.07	0.05	0.02
Deseada	PASB	5224.52	5075.41	4396.68	1.30	455	1.60	0.20	10.30
Deseada	PASB	5226.57	5074.98	4396.71	1.25	157	0.52	0.08	3.60
Deseada	PASB	5228.37	5043.51	4441.09	0.79	222	0.39	0.06	2.56
Deseada	PASB	5228.61	5074.53	4396.73	1.25	424	1.04	0.22	9.00
Deseada	PASB	5230.39	5073.45	4396.75	0.80	231	0.44	0.15	6.50
Deseada	PASB	5232.21	5042.13	4441.13	0.85	285	0.25	0.06	6.94
Deseada	PASB	5236.09	5040.73	4441.17	0.75	85	0.15	0.05	3.63
Deseada	PASB	5240.04	5039.30	4441.22	0.80	86	0.12	0.06	4.64
Deseada	PASB	5244.07	5037.85	4441.26	1.25	114	0.14	0.09	0.07
Deseada	COMIBOL	4153.98	5272.35	4474.25	0.70	70			
Deseada	COMIBOL	4155.95	5271.69	4474.25	0.70	17			1.36
Deseada	COMIBOL	4157.60	5271.14	4474.25	0.70	43			
Deseada	COMIBOL	4159.50	5270.50	4474.25	0.70	23			1.53
Deseada	COMIBOL	4161.27	5269.93	4474.25	0.70	40			1.90
Deseada	COMIBOL	4163.27	5269.34	4474.25	0.70	129			
Deseada	COMIBOL	4165.10	5268.80	4474.25	0.70	34			2.22
Deseada	COMIBOL	4166.99	5268.25	4474.25	0.70	40			2.29
Deseada	COMIBOL	4168.95	5267.67	4474.25	1.00	40			
Deseada	COMIBOL	4170.67	5267.17	4474.25	1.00	60			2.79
Deseada	COMIBOL	4172.18	5266.73	4474.25	0.90	140			2.19
Deseada	COMIBOL	4174.60	5266.09	4474.25	1.20	100			1.65

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4176.10	5265.69	4474.25	1.20	60	
Deseada	COMIBOL	4178.22	5265.13	4474.25	1.20	210	2.67
Deseada	COMIBOL	4180.10	5264.64	4474.25	0.80	100	
Deseada	COMIBOL	4181.92	5264.16	4474.25	0.90	70	2.14
Deseada	COMIBOL	4183.88	5263.65	4474.25	0.80	130	
Deseada	COMIBOL	4185.73	5263.16	4474.25	0.80	50	2.53
Deseada	COMIBOL	4187.52	5262.70	4474.25	1.00	970	
Deseada	COMIBOL	4189.40	5262.07	4474.25	0.80	400	3.11
Deseada	COMIBOL	4191.12	5261.29	4474.25	0.70	17	1.59
Deseada	COMIBOL	4192.96	5260.66	4474.25	0.70	7	
Deseada	COMIBOL	4194.95	5260.22	4474.25	0.70	60	3.10
Deseada	COMIBOL	4196.99	5259.76	4474.25	0.80	10	
Deseada	COMIBOL	4198.90	5259.33	4474.25	1.00	490	37.10
Deseada	COMIBOL	4201.01	5258.79	4474.25	0.70	10	
Deseada	COMIBOL	4202.99	5258.22	4474.25	0.80	40	1.80
Deseada	COMIBOL	4204.45	5257.80	4474.25	1.60	10	
Deseada	COMIBOL	4206.49	5257.21	4474.25	1.70	20	2.40
Deseada	COMIBOL	4208.23	5256.70	4474.25	1.80	130	
Deseada	COMIBOL	4210.39	5256.16	4474.25	0.70	17	2.40
Deseada	COMIBOL	4212.69	5255.58	4474.25	0.70	51	
Deseada	COMIBOL	4214.32	5255.16	4474.25	0.80	60	5.18

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4216.40	5254.64	4474.25	0.80	740			
Deseada	COMIBOL	4218.35	5254.14	4474.25	2.50	90			6.25
Deseada	COMIBOL	4220.36	5253.57	4474.25	0.80	180			
Deseada	COMIBOL	4222.47	5252.98	4474.25	1.00	210			7.82
Deseada	COMIBOL	4224.11	5252.51	4474.25	1.10	210			
Deseada	COMIBOL	4225.87	5252.02	4474.25	0.80	130			9.39
Deseada	COMIBOL	4228.21	5251.32	4474.25	1.20	90			
Deseada	COMIBOL	4230.30	5250.67	4474.25	0.70	26			0.59
Deseada	COMIBOL	4231.59	5250.31	4474.25	1.00	100			
Deseada	COMIBOL	4233.66	5249.81	4474.25	0.80	80			
Deseada	COMIBOL	4235.33	5249.41	4474.25	0.80	150			2.84
Deseada	COMIBOL	4237.28	5248.94	4474.25	1.80	170			
Deseada	COMIBOL	4239.29	5248.45	4474.25	1.10	80			4.40
Deseada	COMIBOL	4240.88	5248.02	4474.25	1.00	90			
Deseada	COMIBOL	4242.78	5247.50	4474.25	1.10	180			6.94
Deseada	COMIBOL	4244.73	5246.97	4474.25	0.80	110			
Deseada	COMIBOL	4246.35	5246.53	4474.25	2.40	360			21.03
Deseada	COMIBOL	4248.05	5245.92	4474.25	2.20	160			7.82
Deseada	COMIBOL	4249.93	5245.00	4474.25	2.60	160			
Deseada	COMIBOL	4251.58	5244.19	4474.25	1.40	150			5.97
Deseada	COMIBOL	4253.41	5243.32	4474.25	0.80	150			
Deseada	COMIBOL	4255.17	5242.62	4474.25	1.60	400			
Deseada	COMIBOL	4256.95	5241.92	4474.25	1.60	60			7.53
Deseada	COMIBOL	4258.77	5241.19	4474.25	0.70	6			
Deseada	COMIBOL	4260.39	5240.88	4474.25	0.80	400			
Deseada	COMIBOL	4262.31	5240.70	4474.25	0.70	154			
Deseada	COMIBOL	4264.14	5240.54	4474.25	0.70	188			
Deseada	COMIBOL	4266.11	5240.44	4474.25	1.00	340			
Deseada	COMIBOL	4268.14	5240.43	4474.25	1.20	600			
Deseada	COMIBOL	4270.20	5240.74	4474.25	0.80	220			
Deseada	COMIBOL	4272.63	5241.37	4474.25	0.70	11			
Deseada	COMIBOL	4274.86	5241.96	4474.25	0.70	31			
Deseada	COMIBOL	4277.50	5242.24	4474.25	0.70	28			
Deseada	COMIBOL	4279.70	5242.38	4474.25	0.70	43			
Deseada	COMIBOL	4281.79	5242.13	4474.25	0.70	38			
Deseada	COMIBOL	4284.38	5241.83	4474.25	0.70	11			
Deseada	COMIBOL	4286.45	5241.20	4474.25	0.70	19			
Deseada	COMIBOL	4287.66	5261.73	4435.75	0.90	1			1.20
Deseada	COMIBOL	4288.82	5240.45	4474.25	0.70	0			
Deseada	COMIBOL	4289.90	5261.12	4435.75	1.00	40			
Deseada	COMIBOL	4290.86	5239.80	4474.25	0.70	0			
Deseada	COMIBOL	4291.72	5260.62	4435.75	1.20	10			1.10
Deseada	COMIBOL	4293.25	5239.07	4474.25	0.70	17			
Deseada	COMIBOL	4293.64	5260.10	4435.75	1.00	40			
Deseada	COMIBOL	4295.45	5259.62	4435.75	0.70	43			1.99

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4296.02	5238.24	4474.25	0.70	8	
Deseada	COMIBOL	4297.24	5259.15	4435.75	0.70	50	
Deseada	COMIBOL	4298.24	5237.57	4474.25	0.70	14	
Deseada	COMIBOL	4299.02	5258.68	4435.75	1.20	70	2.98
Deseada	COMIBOL	4300.12	5237.03	4474.25	0.70	26	
Deseada	COMIBOL	4301.30	5258.08	4435.75	1.30	60	
Deseada	COMIBOL	4302.39	5236.43	4474.25	0.70	57	
Deseada	COMIBOL	4302.99	5257.64	4435.75	1.40	70	3.97
Deseada	COMIBOL	4304.68	5257.21	4435.75	1.60	100	23.74
Deseada	COMIBOL	4304.70	5236.03	4474.25	0.70	28	
Deseada	COMIBOL	4306.48	5256.76	4435.75	1.50	160	
Deseada	COMIBOL	4308.08	5256.36	4435.75	1.70	120	24.44
Deseada	COMIBOL	4310.61	5255.73	4435.75	1.60	110	
Deseada	COMIBOL	4312.25	5255.32	4435.75	2.40	90	20.65
Deseada	COMIBOL	4314.18	5254.80	4435.75	1.40	120	
Deseada	COMIBOL	4316.14	5254.22	4435.75	1.90	110	23.14
Deseada	COMIBOL	4317.81	5253.73	4435.75	1.40	63	
Deseada	COMIBOL	4319.88	5253.12	4435.75	1.40	236	30.85
Deseada	COMIBOL	4321.58	5252.62	4435.75	0.70	300	
Deseada	COMIBOL	4323.53	5252.09	4435.75	1.20	160	24.00
Deseada	COMIBOL	4325.33	5251.62	4435.75	0.70	110	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4327.30	5251.11	4435.75	1.30	130			22.70
Deseada	COMIBOL	4329.03	5250.66	4435.75	1.50	130			
Deseada	COMIBOL	4330.81	5250.19	4435.75	1.50	120			18.66
Deseada	COMIBOL	4333.10	5249.50	4435.75	0.90	90			
Deseada	COMIBOL	4333.78	5228.06	4474.25	0.70	107			
Deseada	COMIBOL	4334.84	5248.89	4435.75	1.00	180			12.26
Deseada	COMIBOL	4335.73	5227.02	4474.25	0.70	95			
Deseada	COMIBOL	4336.34	5248.36	4435.75	0.70	136			
Deseada	COMIBOL	4337.51	5226.08	4474.25	0.70	280			
Deseada	COMIBOL	4338.34	5247.65	4435.75	0.70	120			3.59
Deseada	COMIBOL	4339.37	5225.11	4474.25	1.20	220			
Deseada	COMIBOL	4340.16	5247.01	4435.75	0.70	114			
Deseada	COMIBOL	4341.35	5224.40	4474.25	1.40	60			
Deseada	COMIBOL	4341.74	5246.45	4435.75	0.70	79			13.41
Deseada	COMIBOL	4343.09	5223.77	4474.25	1.60	60			
Deseada	COMIBOL	4343.74	5245.74	4435.75	0.70	120			
Deseada	COMIBOL	4345.20	5223.01	4474.25	1.60	120			
Deseada	COMIBOL	4345.54	5245.11	4435.75	0.70	160			
Deseada	COMIBOL	4347.05	5222.34	4474.25	1.30	60			
Deseada	COMIBOL	4347.46	5244.32	4435.75	0.90	240			16.32
Deseada	COMIBOL	4348.99	5221.65	4474.25	0.70	34			
Deseada	COMIBOL	4349.30	5243.51	4435.75	0.90	140			
Deseada	COMIBOL	4351.06	5242.80	4435.75	1.00	160			18.10
Deseada	COMIBOL	4351.11	5220.98	4474.25	1.00	140			
Deseada	COMIBOL	4353.11	5220.41	4474.25	0.70	25			
Deseada	COMIBOL	4353.19	5242.04	4435.75	0.80	120			
Deseada	COMIBOL	4354.71	5219.95	4474.25	0.70	43			
Deseada	COMIBOL	4354.92	5241.42	4435.75	1.00	120			18.30
Deseada	COMIBOL	4356.76	5240.76	4435.75	1.10	110			
Deseada	COMIBOL	4356.97	5219.30	4474.25	0.70	46			
Deseada	COMIBOL	4358.73	5240.05	4435.75	0.80	110			17.52
Deseada	COMIBOL	4358.81	5218.77	4474.25	0.70	38			
Deseada	COMIBOL	4360.58	5239.41	4435.75	0.70	103			
Deseada	COMIBOL	4360.80	5218.20	4474.25	0.70	84			
Deseada	COMIBOL	4362.40	5238.80	4435.75	0.80	130			17.32
Deseada	COMIBOL	4362.70	5217.57	4474.25	0.70	64			
Deseada	COMIBOL	4364.42	5238.13	4435.75	1.20	170			
Deseada	COMIBOL	4364.77	5216.88	4474.25	0.70	86			
Deseada	COMIBOL	4366.75	5216.22	4474.25	0.70	57			
Deseada	COMIBOL	4366.80	5237.34	4435.75	1.50	150			18.69
Deseada	COMIBOL	4368.47	5236.78	4435.75	1.40	130			
Deseada	COMIBOL	4368.50	5215.64	4474.25	0.70	60			
Deseada	COMIBOL	4370.49	5236.11	4435.75	1.40	270			20.40
Deseada	COMIBOL	4370.61	5214.94	4474.25	0.70	17			
Deseada	COMIBOL	4372.31	5235.50	4435.75	1.20	240			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4372.44	5214.33	4474.25	0.70	11	
Deseada	COMIBOL	4374.10	5234.91	4435.75	0.90	210	16.70
Deseada	COMIBOL	4374.50	5213.69	4474.25	0.70	26	
Deseada	COMIBOL	4376.28	5234.12	4435.75	1.40	220	
Deseada	COMIBOL	4376.58	5213.10	4474.25	0.70	34	
Deseada	COMIBOL	4378.36	5233.35	4435.75	1.40	200	16.30
Deseada	COMIBOL	4378.71	5212.50	4474.25	0.80	90	
Deseada	COMIBOL	4380.10	5232.71	4435.75	1.30	200	
Deseada	COMIBOL	4380.51	5211.99	4474.25	1.10	80	
Deseada	COMIBOL	4382.02	5232.00	4435.75	1.20	180	15.40
Deseada	COMIBOL	4382.39	5211.29	4474.25	0.80	200	
Deseada	COMIBOL	4384.09	5231.24	4435.75	1.90	170	
Deseada	COMIBOL	4384.34	5210.52	4474.25	0.80	130	
Deseada	COMIBOL	4385.69	5230.65	4435.75	1.10	220	18.10
Deseada	COMIBOL	4386.17	5209.82	4474.25	0.70	120	9.87
Deseada	COMIBOL	4387.81	5229.87	4435.75	0.90	204	
Deseada	COMIBOL	4388.41	5209.03	4474.25	0.90	100	
Deseada	COMIBOL	4389.43	5229.26	4435.75	0.70	1,136	14.67
Deseada	COMIBOL	4390.49	5208.29	4474.25	1.00	610	24.71
Deseada	COMIBOL	4391.57	5228.45	4435.75	0.80	110	2.00
Deseada	COMIBOL	4392.36	5207.63	4474.25	0.70	510	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4393.35	5227.77	4435.75	0.70	110			5.38
Deseada	COMIBOL	4394.25	5206.96	4474.25	1.20	530			8.14
Deseada	COMIBOL	4395.41	5226.99	4435.75	0.70	197			
Deseada	COMIBOL	4396.29	5206.23	4474.25	0.70	420			16.29
Deseada	COMIBOL	4397.26	5226.28	4435.75	0.80	1,440			12.09
Deseada	COMIBOL	4398.59	5205.41	4474.25	0.70	390			
Deseada	COMIBOL	4398.87	5225.67	4435.75	0.70	2,660			
Deseada	COMIBOL	4400.48	5204.73	4474.25	0.90	380			15.44
Deseada	COMIBOL	4400.81	5224.94	4435.75	1.10	1,320			5.42
Deseada	COMIBOL	4402.20	5204.12	4474.25	0.90	1,000			
Deseada	COMIBOL	4402.68	5224.31	4435.75	1.20	380			
Deseada	COMIBOL	4404.23	5203.39	4474.25	1.00	340			17.92
Deseada	COMIBOL	4404.65	5223.65	4435.75	1.00	180			15.06
Deseada	COMIBOL	4406.44	5202.64	4474.25	0.70	371			
Deseada	COMIBOL	4406.49	5223.03	4435.75	1.40	110			
Deseada	COMIBOL	4408.39	5222.39	4435.75	1.10	590			10.96
Deseada	COMIBOL	4408.46	5202.00	4474.25	0.80	490			12.10
Deseada	COMIBOL	4410.23	5201.44	4474.25	0.70	340			
Deseada	COMIBOL	4410.31	5221.74	4435.75	0.90	480			
Deseada	COMIBOL	4412.21	5221.10	4435.75	1.00	390			7.92
Deseada	COMIBOL	4412.33	5200.78	4474.25	1.10	400			15.64
Deseada	COMIBOL	4413.90	5220.53	4435.75	1.80	200			0.68
Deseada	COMIBOL	4414.20	5200.18	4474.25	0.90	420			
Deseada	COMIBOL	4415.71	5219.93	4435.75	0.70	6			
Deseada	COMIBOL	4416.43	5199.43	4474.25	0.90	400			16.60
Deseada	COMIBOL	4417.63	5219.30	4435.75	0.70	60			
Deseada	COMIBOL	4418.27	5198.81	4474.25	1.20	1,240			
Deseada	COMIBOL	4419.82	5218.58	4435.75	0.70	857			3.19
Deseada	COMIBOL	4420.14	5198.18	4474.25	0.70	423			4.97
Deseada	COMIBOL	4421.63	5217.99	4435.75	0.70	857			
Deseada	COMIBOL	4421.93	5197.56	4474.25	0.70	371			
Deseada	COMIBOL	4423.18	5197.12	4474.25	0.70	126			3.92
Deseada	COMIBOL	4423.61	5217.34	4435.75	0.70	51			
Deseada	COMIBOL	4424.37	5196.70	4474.25	0.70	339			
Deseada	COMIBOL	4425.38	5216.87	4435.75	0.80	100			5.87
Deseada	COMIBOL	4425.60	5196.26	4474.25	0.70	417			15.13
Deseada	COMIBOL	4426.90	5195.80	4474.25	0.90	200			
Deseada	COMIBOL	4427.16	5216.38	4435.75	2.20	380			14.59
Deseada	COMIBOL	4428.80	5195.13	4474.25	2.00	340			14.56
Deseada	COMIBOL	4429.08	5215.66	4435.75	0.70	260			
Deseada	COMIBOL	4430.68	5194.47	4474.25	1.70	260			
Deseada	COMIBOL	4430.91	5214.97	4435.75	0.90	670			15.29
Deseada	COMIBOL	4432.81	5193.71	4474.25	1.80	620			13.63
Deseada	COMIBOL	4433.17	5214.12	4435.75	0.70	243			
Deseada	COMIBOL	4434.57	5193.24	4474.25	1.00	410			22.00

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4435.19	5213.36	4435.75	0.70	189	9.53
Deseada	COMIBOL	4436.68	5212.82	4435.75	1.10	1,260	
Deseada	COMIBOL	4436.73	5192.73	4474.25	1.20	400	
Deseada	COMIBOL	4438.42	5192.33	4474.25	1.10	440	12.05
Deseada	COMIBOL	4438.48	5212.17	4435.75	0.70	77	12.76
Deseada	COMIBOL	4440.54	5211.44	4435.75	0.80	650	
Deseada	COMIBOL	4440.62	5191.81	4474.25	1.30	430	
Deseada	COMIBOL	4442.66	5210.68	4435.75	0.70	340	19.60
Deseada	COMIBOL	4442.80	5191.30	4474.25	1.00	400	13.04
Deseada	COMIBOL	4444.32	5190.94	4474.25	0.90	560	
Deseada	COMIBOL	4444.87	5209.89	4435.75	0.70	249	
Deseada	COMIBOL	4446.42	5190.31	4474.25	0.70	630	
Deseada	COMIBOL	4446.76	5209.23	4435.75	0.90		
Deseada	COMIBOL	4448.23	5208.72	4435.75	1.80		
Deseada	COMIBOL	4448.38	5189.61	4474.25	0.70	680	
Deseada	COMIBOL	4449.94	5189.06	4474.25	0.70	640	
Deseada	COMIBOL	4450.15	5208.05	4435.75	1.90		
Deseada	COMIBOL	4452.27	5207.31	4435.75	1.20		
Deseada	COMIBOL	4452.30	5188.23	4474.25	0.70	680	
Deseada	COMIBOL	4453.96	5187.64	4474.25	0.80	590	
Deseada	COMIBOL	4454.49	5206.53	4435.75	0.90		

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4455.70	5186.92	4474.25	1.00	560			
Deseada	COMIBOL	4456.32	5205.89	4435.75	1.30				
Deseada	COMIBOL	4457.73	5186.06	4474.25	0.90	390			
Deseada	COMIBOL	4458.26	5205.34	4435.75	0.80	240			15.58
Deseada	COMIBOL	4459.34	5185.44	4474.25	1.80	660			
Deseada	COMIBOL	4460.11	5204.84	4435.75	1.50	220			
Deseada	COMIBOL	4461.32	5184.76	4474.25	1.40	1,680			8.20
Deseada	COMIBOL	4461.90	5204.37	4435.75	0.70	190			31.56
Deseada	COMIBOL	4463.04	5184.17	4474.25	0.70	464			
Deseada	COMIBOL	4464.06	5203.79	4435.75	0.70	840			
Deseada	COMIBOL	4465.40	5183.37	4474.25	0.70	343			5.81
Deseada	COMIBOL	4466.00	5203.20	4435.75	0.70	230			31.86
Deseada	COMIBOL	4467.10	5182.79	4474.25	0.70	263			
Deseada	COMIBOL	4467.64	5202.63	4435.75	1.20	210			
Deseada	COMIBOL	4469.02	5182.14	4474.25	0.70	414			7.76
Deseada	COMIBOL	4469.75	5201.89	4435.75	0.70	150			13.10
Deseada	COMIBOL	4470.89	5181.66	4474.25	0.70	450			
Deseada	COMIBOL	4471.57	5201.26	4435.75	0.80	170			
Deseada	COMIBOL	4473.05	5181.15	4474.25	0.70	309			9.14
Deseada	COMIBOL	4473.38	5200.62	4435.75	0.80	140			13.90
Deseada	COMIBOL	4474.92	5180.71	4474.25	0.70	580			
Deseada	COMIBOL	4475.67	5199.82	4435.75	1.00	150			
Deseada	COMIBOL	4476.61	5180.20	4474.25	0.70	711			10.33
Deseada	COMIBOL	4477.22	5199.28	4435.75	1.00	150			17.37
Deseada	COMIBOL	4478.66	5179.34	4474.25	0.70	1,030			
Deseada	COMIBOL	4478.99	5198.66	4435.75	1.10	590			
Deseada	COMIBOL	4480.31	5178.65	4474.25	0.70	650			10.96
Deseada	COMIBOL	4481.04	5197.95	4435.75	1.00	590			22.63
Deseada	COMIBOL	4482.29	5177.81	4474.25	1.30				
Deseada	COMIBOL	4482.80	5197.33	4435.75	1.40	510			
Deseada	COMIBOL	4484.38	5176.90	4474.25	1.10				
Deseada	COMIBOL	4484.50	5196.74	4435.75	1.40	620			19.97
Deseada	COMIBOL	4486.25	5175.97	4474.25	1.50				
Deseada	COMIBOL	4486.58	5196.01	4435.75	1.70	430			
Deseada	COMIBOL	4488.13	5175.03	4474.25	1.60				
Deseada	COMIBOL	4488.46	5195.36	4435.75	1.40	590			10.77
Deseada	COMIBOL	4490.17	5174.02	4474.25	1.10	393			
Deseada	COMIBOL	4490.56	5194.70	4435.75	1.60	200			9.80
Deseada	COMIBOL	4491.59	5173.43	4474.25	1.00	235			
Deseada	COMIBOL	4492.24	5194.17	4435.75	1.50	190			
Deseada	COMIBOL	4493.41	5172.87	4474.25	0.70	92			
Deseada	COMIBOL	4494.56	5193.43	4435.75	1.80	260			9.31
Deseada	COMIBOL	4495.03	5172.38	4474.25	0.90	380			
Deseada	COMIBOL	4496.37	5192.86	4435.75	1.90	160			
Deseada	COMIBOL	4496.76	5171.70	4474.25	1.10	300			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4498.26	5192.35	4435.75	1.40	220	10.99
Deseada	COMIBOL	4498.73	5170.77	4474.25	1.40	163	
Deseada	COMIBOL	4499.82	5191.98	4435.75	1.30	200	
Deseada	COMIBOL	4500.58	5169.90	4474.25	1.10	69	
Deseada	COMIBOL	4501.80	5191.51	4435.75	1.00	330	
Deseada	COMIBOL	4502.52	5168.99	4474.25	0.80	107	
Deseada	COMIBOL	4503.89	5190.98	4435.75	1.90	160	
Deseada	COMIBOL	4504.31	5168.24	4474.25	1.00	44	
Deseada	COMIBOL	4505.84	5190.45	4435.75	2.00	200	8.32
Deseada	COMIBOL	4506.33	5167.61	4474.25	1.10	113	
Deseada	COMIBOL	4507.65	5189.95	4435.75	0.90	170	
Deseada	COMIBOL	4507.80	5167.15	4474.25	0.90	103	
Deseada	COMIBOL	4509.75	5189.37	4435.75	0.70	240	11.89
Deseada	COMIBOL	4510.10	5166.43	4474.25	1.40	25	
Deseada	COMIBOL	4511.63	5188.84	4435.75	0.70	570	
Deseada	COMIBOL	4511.85	5165.57	4474.25	1.20	165	
Deseada	COMIBOL	4513.86	5188.18	4435.75	0.70	154	6.70
Deseada	COMIBOL	4513.98	5164.68	4474.25	1.10	24	
Deseada	COMIBOL	4515.81	5187.61	4435.75	0.70	617	
Deseada	COMIBOL	4516.17	5164.08	4474.25	1.10	32	
Deseada	COMIBOL	4518.13	5186.93	4435.75	2.00	440	11.09

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4518.21	5163.52	4474.25	1.00	122			
Deseada	COMIBOL	4519.89	5186.41	4435.75	1.00	770			
Deseada	COMIBOL	4520.14	5163.00	4474.25	0.90	79			
Deseada	COMIBOL	4522.04	5185.50	4435.75	1.10	1,080			19.24
Deseada	COMIBOL	4522.08	5162.44	4474.25	0.90	188			
Deseada	COMIBOL	4523.70	5184.79	4435.75	0.70	193			
Deseada	COMIBOL	4524.20	5161.64	4474.25	1.00	117			
Deseada	COMIBOL	4525.56	5183.99	4435.75	0.70	521			9.97
Deseada	COMIBOL	4526.48	5160.79	4474.25	1.00	18			
Deseada	COMIBOL	4527.89	5182.99	4435.75	1.20	600			
Deseada	COMIBOL	4528.41	5160.06	4474.25	1.20	78			
Deseada	COMIBOL	4529.78	5182.28	4435.75	1.50	470			13.66
Deseada	COMIBOL	4530.13	5159.42	4474.25	0.70	309			
Deseada	COMIBOL	4531.54	5181.67	4435.75	2.00	720			
Deseada	COMIBOL	4532.15	5158.88	4474.25	1.60	17			
Deseada	COMIBOL	4533.59	5180.96	4435.75	1.50	710			13.47
Deseada	COMIBOL	4534.10	5158.44	4474.25	1.20	22			
Deseada	COMIBOL	4535.73	5180.22	4435.75	1.40	290			
Deseada	COMIBOL	4535.92	5158.01	4474.25	1.40	18			
Deseada	COMIBOL	4537.38	5157.60	4474.25	0.70	70			
Deseada	COMIBOL	4537.78	5179.51	4435.75	1.00	670			17.43
Deseada	COMIBOL	4538.72	5157.23	4474.25	0.70	46			
Deseada	COMIBOL	4539.90	5178.78	4435.75	1.10	760			
Deseada	COMIBOL	4540.43	5156.75	4474.25	0.70	46			
Deseada	COMIBOL	4541.68	5178.22	4435.75	0.90	650			16.93
Deseada	COMIBOL	4541.75	5178.20	4437.22	0.70	500			
Deseada	COMIBOL	4541.75	5178.20	4439.39	0.70	570			
Deseada	COMIBOL	4541.75	5178.20	4442.57	0.70	522			
Deseada	COMIBOL	4541.75	5178.20	4445.24	0.70	550			
Deseada	COMIBOL	4541.75	5178.20	4448.16	0.70	1,807			
Deseada	COMIBOL	4541.75	5178.20	4450.83	0.70	360			
Deseada	COMIBOL	4541.75	5178.20	4453.08	0.70	154			
Deseada	COMIBOL	4541.75	5178.20	4456.34	0.70	30			
Deseada	COMIBOL	4541.75	5178.20	4459.18	0.70	111			
Deseada	COMIBOL	4541.75	5178.20	4461.60	0.70	42			
Deseada	COMIBOL	4541.75	5178.20	4464.43	0.70	30			
Deseada	COMIBOL	4541.86	5156.44	4474.25	0.70	105			
Deseada	COMIBOL	4543.55	5177.60	4435.75	0.80	540			
Deseada	COMIBOL	4543.80	5156.08	4474.25	0.70	197			
Deseada	COMIBOL	4545.17	5177.01	4435.75	0.70	1,174			
Deseada	COMIBOL	4545.97	5155.69	4474.25	0.70	144			
Deseada	COMIBOL	4546.69	5176.47	4435.75	1.40	920			
Deseada	COMIBOL	4547.81	5155.35	4474.25	0.70	654			
Deseada	COMIBOL	4548.66	5175.76	4435.75	0.70	122			
Deseada	COMIBOL	4549.94	5175.33	4435.75	1.00	539			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4550.05	5154.84	4474.25	0.70	50
Deseada	COMIBOL	4551.61	5154.46	4474.25	0.70	24
Deseada	COMIBOL	4551.62	5174.79	4435.75	1.00	1,080
Deseada	COMIBOL	4553.37	5154.04	4474.25	0.70	84
Deseada	COMIBOL	4553.45	5174.20	4435.75	1.20	770
Deseada	COMIBOL	4555.10	5173.66	4435.75	1.30	720
Deseada	COMIBOL	4555.45	5153.54	4474.25	0.70	18
Deseada	COMIBOL	4556.95	5173.06	4435.75	1.10	580
Deseada	COMIBOL	4557.24	5153.11	4474.25	0.70	357
Deseada	COMIBOL	4558.51	5172.56	4435.75	0.90	10
Deseada	COMIBOL	4559.12	5152.65	4474.25	0.70	211
Deseada	COMIBOL	4560.18	5172.02	4435.75	0.80	180
Deseada	COMIBOL	4561.29	5152.41	4474.25	0.70	646
Deseada	COMIBOL	4561.74	5171.70	4435.75	0.80	350
Deseada	COMIBOL	4563.61	5152.30	4474.25	0.70	83
Deseada	COMIBOL	4563.66	5171.32	4435.75	0.70	454
Deseada	COMIBOL	4565.03	5171.04	4435.75	0.70	343
Deseada	COMIBOL	4565.40	5152.21	4474.25	0.70	23
Deseada	COMIBOL	4567.33	5170.57	4435.75	0.70	
Deseada	COMIBOL	4567.39	5152.12	4474.25	0.70	1,126
Deseada	COMIBOL	4568.87	5170.24	4435.75	0.70	514

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4569.38	5151.97	4474.25	0.70	451			
Deseada	COMIBOL	4570.51	5169.82	4435.75	1.30	400			
Deseada	COMIBOL	4571.08	5151.77	4474.25	0.70	7			
Deseada	COMIBOL	4572.33	5169.35	4435.75	1.40	400			
Deseada	COMIBOL	4573.17	5151.52	4474.25	0.70	8			
Deseada	COMIBOL	4573.92	5168.95	4435.75	1.30	410			
Deseada	COMIBOL	4575.07	5151.34	4474.25	0.70	43			
Deseada	COMIBOL	4575.66	5168.50	4435.75	1.00	370			
Deseada	COMIBOL	4577.58	5151.17	4474.25	0.70	86			
Deseada	COMIBOL	4577.59	5168.01	4435.75	1.00	1,220			
Deseada	COMIBOL	4579.27	5167.36	4435.75	0.90	2,150			
Deseada	COMIBOL	4579.34	5151.05	4474.25	0.70	511			
Deseada	COMIBOL	4580.87	5166.88	4435.75	1.30	260			
Deseada	COMIBOL	4581.17	5150.87	4474.25	0.70	11			
Deseada	COMIBOL	4583.27	5166.39	4435.75	1.10	1,330			
Deseada	COMIBOL	4583.55	5150.57	4474.25	0.70	34			
Deseada	COMIBOL	4584.95	5166.05	4435.75	1.00	450			
Deseada	COMIBOL	4585.50	5150.32	4474.25	0.70	188			
Deseada	COMIBOL	4587.06	5165.62	4435.75	1.30	510			
Deseada	COMIBOL	4587.86	5150.02	4474.25	0.70	150			
Deseada	COMIBOL	4589.22	5165.18	4435.75	2.20	750			
Deseada	COMIBOL	4589.73	5149.78	4474.25	0.70	41			
Deseada	COMIBOL	4591.56	5164.90	4435.75	2.10	940			
Deseada	COMIBOL	4591.76	5149.53	4474.25	0.70	21			
Deseada	COMIBOL	4593.35	5164.73	4435.75	2.20	1,510			
Deseada	COMIBOL	4593.98	5149.10	4474.25	0.70	63			
Deseada	COMIBOL	4595.91	5164.48	4435.75	1.70	570			
Deseada	COMIBOL	4595.96	5148.69	4474.25	0.70	88			
Deseada	COMIBOL	4597.77	5164.30	4435.75	1.60	530			
Deseada	COMIBOL	4597.97	5148.28	4474.25	0.70	40			
Deseada	COMIBOL	4599.57	5164.13	4435.75	2.40	1,060			
Deseada	COMIBOL	4600.00	5148.09	4474.25	0.70	20			
Deseada	COMIBOL	4601.78	5163.91	4435.75	0.80	280			
Deseada	COMIBOL	4602.60	5147.23	4474.25	0.70	8			
Deseada	COMIBOL	4603.82	5163.71	4435.75	1.10	660			
Deseada	COMIBOL	4604.25	5146.82	4474.25	0.70	110			
Deseada	COMIBOL	4606.20	5146.34	4474.25	0.70	687			
Deseada	COMIBOL	4606.25	5163.43	4435.75	1.90	640			
Deseada	COMIBOL	4608.04	5145.84	4474.25	0.70	114			
Deseada	COMIBOL	4608.66	5163.16	4435.75	2.10	650			
Deseada	COMIBOL	4610.27	5162.97	4435.75	2.60	370			
Deseada	COMIBOL	4610.30	5145.14	4474.25	0.70	89			
Deseada	COMIBOL	4612.08	5162.77	4435.75	2.50	360			
Deseada	COMIBOL	4612.19	5144.56	4474.25	0.70	80			
Deseada	COMIBOL	4614.24	5143.94	4474.25	0.70	147			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4614.51	5162.49	4435.75	1.60	630	
Deseada	COMIBOL	4616.36	5143.43	4474.25	0.70	90	
Deseada	COMIBOL	4616.70	5162.22	4435.75	1.20	640	
Deseada	COMIBOL	4618.18	5142.95	4474.25	0.70	156	
Deseada	COMIBOL	4618.91	5161.95	4435.75	1.40	500	
Deseada	COMIBOL	4620.49	5142.29	4474.25	0.70	5	
Deseada	COMIBOL	4620.87	5161.70	4435.75	1.10	620	
Deseada	COMIBOL	4622.50	5141.71	4474.25	0.70	20	
Deseada	COMIBOL	4622.87	5161.45	4435.75	1.30	620	
Deseada	COMIBOL	4623.19	5161.41	4437.39	0.70	146	7.74
Deseada	COMIBOL	4623.19	5161.41	4440.48	1.10	710	
Deseada	COMIBOL	4623.19	5161.41	4443.32	0.70	77	
Deseada	COMIBOL	4623.19	5161.41	4446.82	1.00	490	17.67
Deseada	COMIBOL	4623.19	5161.41	4450.41	0.70	339	
Deseada	COMIBOL	4623.19	5161.41	4453.58	1.70	850	
Deseada	COMIBOL	4623.19	5161.41	4456.67	0.80	120	11.75
Deseada	COMIBOL	4623.19	5161.41	4459.76	0.90	756	
Deseada	COMIBOL	4623.19	5161.41	4463.18	0.90	153	2.14
Deseada	COMIBOL	4623.19	5161.41	4466.35	0.70	216	
Deseada	COMIBOL	4623.19	5161.41	4469.44	0.70	32	0.82
Deseada	COMIBOL	4623.19	5161.41	4472.53	1.00	40	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4624.38	5141.17	4474.25	0.70	680			
Deseada	COMIBOL	4625.13	5161.10	4435.75	0.70	674			
Deseada	COMIBOL	4626.57	5140.55	4474.25	1.90	137			
Deseada	COMIBOL	4627.04	5160.75	4435.75	1.30	1,150			
Deseada	COMIBOL	4628.61	5139.87	4474.25	0.70	130			
Deseada	COMIBOL	4629.04	5160.39	4435.75	1.90	1,160			
Deseada	COMIBOL	4630.88	5139.11	4474.25	0.70	140			
Deseada	COMIBOL	4631.10	5160.02	4435.75	0.90	630			
Deseada	COMIBOL	4632.39	5138.61	4474.25	0.70	214			
Deseada	COMIBOL	4632.69	5159.73	4435.75	1.80	800			
Deseada	COMIBOL	4634.57	5137.88	4474.25	0.70	534			
Deseada	COMIBOL	4634.87	5159.26	4435.75	1.60	1,080			
Deseada	COMIBOL	4636.70	5158.85	4435.75	1.20	810			
Deseada	COMIBOL	4636.79	5137.14	4474.25	0.70	4			
Deseada	COMIBOL	4639.01	5136.31	4474.25	0.70	11			
Deseada	COMIBOL	4639.10	5158.30	4435.75	1.90	210			20.40
Deseada	COMIBOL	4640.96	5135.50	4474.25	0.70	116			
Deseada	COMIBOL	4641.23	5157.82	4435.75	1.50	210			
Deseada	COMIBOL	4642.62	5134.80	4474.25	0.70	183			
Deseada	COMIBOL	4642.84	5157.45	4435.75	1.30	300			21.90
Deseada	COMIBOL	4644.72	5133.92	4474.25	0.70	114			
Deseada	COMIBOL	4644.85	5157.00	4435.75	0.70	216			
Deseada	COMIBOL	4646.58	5133.14	4474.25	1.00	340			17.17
Deseada	COMIBOL	4647.21	5156.52	4435.75	0.70	66			3.71
Deseada	COMIBOL	4648.75	5132.25	4474.25	0.70	66			1.07
Deseada	COMIBOL	4648.95	5156.16	4435.75	0.70	375			
Deseada	COMIBOL	4650.66	5131.53	4474.25	0.70	6			0.18
Deseada	COMIBOL	4650.96	5155.75	4435.75	0.70	83			
Deseada	COMIBOL	4652.73	5130.74	4474.25	0.70	1			0.21
Deseada	COMIBOL	4653.16	5155.30	4435.75	0.70	87			2.21
Deseada	COMIBOL	4655.04	5129.86	4474.25	0.70	8			0.79
Deseada	COMIBOL	4655.27	5154.87	4435.75	0.80	64			
Deseada	COMIBOL	4656.32	5129.36	4474.25	0.70	0			0.20
Deseada	COMIBOL	4657.06	5154.51	4435.75	1.20	120			
Deseada	COMIBOL	4658.46	5128.49	4474.25	0.70	0			0.24
Deseada	COMIBOL	4658.94	5154.02	4435.75	0.99	198			3.82
Deseada	COMIBOL	4660.38	5127.71	4474.25	0.70	43			0.27
Deseada	COMIBOL	4661.04	5153.47	4435.75	0.70	36			
Deseada	COMIBOL	4662.32	5126.97	4474.25	0.70	14			1.64
Deseada	COMIBOL	4662.87	5152.99	4435.75	0.70	46			
Deseada	COMIBOL	4664.68	5126.25	4474.25	1.60	80			8.44
Deseada	COMIBOL	4665.09	5152.42	4435.75	0.70	37			1.01
Deseada	COMIBOL	4666.74	5125.63	4474.25	0.80	190			12.36
Deseada	COMIBOL	4666.89	5151.97	4435.75	1.60	170			
Deseada	COMIBOL	4668.58	5125.07	4474.25	0.70	60			3.12

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4668.76	5151.50	4435.75	1.50	160	13.10
Deseada	COMIBOL	4670.74	5124.39	4474.25	0.70	43	3.26
Deseada	COMIBOL	4670.94	5150.96	4435.75	1.30	960	
Deseada	COMIBOL	4673.00	5123.65	4474.25	0.80	360	13.87
Deseada	COMIBOL	4673.26	5150.38	4435.75	1.10	180	15.48
Deseada	COMIBOL	4675.03	5122.98	4474.25	0.70	200	15.68
Deseada	COMIBOL	4675.42	5149.84	4435.75	1.80	400	
Deseada	COMIBOL	4676.82	5122.39	4474.25	1.20	130	16.94
Deseada	COMIBOL	4677.62	5149.18	4435.75	1.20	500	18.04
Deseada	COMIBOL	4678.93	5121.70	4474.25	0.70	34	3.01
Deseada	COMIBOL	4679.59	5148.59	4435.75	1.20	780	
Deseada	COMIBOL	4680.96	5121.07	4474.25	0.70	11	0.91
Deseada	COMIBOL	4681.31	5148.07	4435.75	1.10	770	13.57
Deseada	COMIBOL	4683.07	5120.54	4474.25	0.70	30	4.21
Deseada	COMIBOL	4683.60	5147.38	4435.75	0.80	810	
Deseada	COMIBOL	4685.10	5120.02	4474.25	0.70	30	5.13
Deseada	COMIBOL	4685.78	5146.72	4435.75	1.10	3,320	10.42
Deseada	COMIBOL	4685.81	5101.62	4505.25	0.70	23	0.89
Deseada	COMIBOL	4687.28	5119.47	4474.25	1.00	100	4.32
Deseada	COMIBOL	4687.93	5146.07	4435.75	0.90	465	
Deseada	COMIBOL	4687.97	5100.81	4505.25	0.70	60	1.05

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4689.30	5118.98	4474.25	1.20	24			1.69
Deseada	COMIBOL	4689.78	5145.52	4435.75	0.80	168			7.86
Deseada	COMIBOL	4689.87	5100.00	4505.25	0.70	23			1.37
Deseada	COMIBOL	4691.21	5118.77	4474.25	0.70	28			2.36
Deseada	COMIBOL	4691.71	5144.94	4435.75	1.10	300			
Deseada	COMIBOL	4692.01	5099.47	4505.25	0.70	17			0.41
Deseada	COMIBOL	4693.38	5118.65	4474.25	0.70	34			2.07
Deseada	COMIBOL	4693.98	5098.83	4505.25	0.70	69			0.99
Deseada	COMIBOL	4694.08	5144.18	4435.75	1.40	370			5.46
Deseada	COMIBOL	4695.65	5118.27	4474.25	0.70	497			11.28
Deseada	COMIBOL	4695.82	5143.62	4435.75	0.90	144			
Deseada	COMIBOL	4696.01	5098.17	4505.25	0.70	17			0.61
Deseada	COMIBOL	4697.52	5117.78	4474.25	0.70	197			6.37
Deseada	COMIBOL	4697.61	5143.05	4435.75	1.50	510			38.91
Deseada	COMIBOL	4698.16	5097.51	4505.25	0.70	40			2.62
Deseada	COMIBOL	4699.46	5142.46	4435.75	1.40	550			
Deseada	COMIBOL	4699.65	5117.21	4474.25	0.70	678			5.27
Deseada	COMIBOL	4700.20	5096.89	4505.25	0.70	86			5.70
Deseada	COMIBOL	4701.26	5116.79	4474.25	0.70	77			2.90
Deseada	COMIBOL	4701.94	5141.76	4435.75	1.60	420			38.91
Deseada	COMIBOL	4702.24	5096.29	4505.25	1.00	140			12.65
Deseada	COMIBOL	4703.46	5116.21	4474.25	0.70	181			3.66
Deseada	COMIBOL	4703.84	5141.28	4435.75	1.30	152			3.80
Deseada	COMIBOL	4704.44	5095.68	4505.25	1.00	40			6.80
Deseada	COMIBOL	4705.53	5115.63	4474.25	0.70	314			1.76
Deseada	COMIBOL	4705.71	5140.86	4435.75	2.40	278			13.70
Deseada	COMIBOL	4706.10	5095.21	4505.25	0.80	10			2.01
Deseada	COMIBOL	4707.21	5115.13	4474.25	0.70	218			7.11
Deseada	COMIBOL	4707.93	5140.37	4435.75	0.70	218			9.69
Deseada	COMIBOL	4708.61	5094.40	4505.25	0.70	9			1.15
Deseada	COMIBOL	4709.36	5114.49	4474.25	0.70	95			1.26
Deseada	COMIBOL	4710.63	5093.73	4505.25	0.70	3			0.43
Deseada	COMIBOL	4711.25	5113.93	4474.25	0.70	31			1.17
Deseada	COMIBOL	4712.82	5093.00	4505.25	0.70	463			3.51
Deseada	COMIBOL	4713.24	5113.34	4474.25	0.70	14			3.40
Deseada	COMIBOL	4714.65	5092.40	4505.25	0.70	143			6.37
Deseada	COMIBOL	4715.00	5112.81	4474.25	0.70	186			6.30
Deseada	COMIBOL	4716.51	5091.79	4505.25	0.70	283			26.23
Deseada	COMIBOL	4717.23	5112.06	4474.25	0.70	111			4.34
Deseada	COMIBOL	4718.53	5091.13	4505.25	0.70	74			2.71
Deseada	COMIBOL	4718.96	5111.47	4474.25	0.70	110			1.11
Deseada	COMIBOL	4720.83	5090.40	4505.25	0.70	951			7.73
Deseada	COMIBOL	4721.08	5110.76	4474.25	0.70	28			0.63
Deseada	COMIBOL	4722.79	5137.87	4441.90	1.00	590			17.62
Deseada	COMIBOL	4722.79	5137.87	4444.24	0.90	480			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4722.79	5137.87	4446.49	0.70	500	19.41
Deseada	COMIBOL	4722.79	5137.87	4448.74	0.70	309	
Deseada	COMIBOL	4722.79	5137.87	4451.08	0.70	360	14.17
Deseada	COMIBOL	4722.79	5137.87	4453.92	0.70	257	
Deseada	COMIBOL	4722.79	5137.87	4455.92	0.70	77	2.20
Deseada	COMIBOL	4722.79	5137.87	4458.42	1.10	490	15.35
Deseada	COMIBOL	4722.79	5137.87	4460.93	1.00	310	
Deseada	COMIBOL	4722.79	5137.87	4463.43	1.10	170	2.20
Deseada	COMIBOL	4722.79	5137.87	4465.77	0.90	200	
Deseada	COMIBOL	4722.79	5137.87	4467.69	0.80	120	
Deseada	COMIBOL	4722.79	5137.87	4470.36	0.70	80	
Deseada	COMIBOL	4722.79	5137.87	4473.20	0.70	63	
Deseada	COMIBOL	4722.93	5110.13	4474.25	0.70	16	0.67
Deseada	COMIBOL	4723.13	5089.70	4505.25	1.30	1,230	27.91
Deseada	COMIBOL	4724.78	5109.52	4474.25	0.70	60	0.44
Deseada	COMIBOL	4725.05	5089.34	4505.25	1.40	1,070	30.12
Deseada	COMIBOL	4726.73	5088.95	4505.25	1.50	980	35.20
Deseada	COMIBOL	4727.01	5108.86	4474.25	0.70	85	0.94
Deseada	COMIBOL	4728.67	5108.36	4474.25	0.70	74	4.77
Deseada	COMIBOL	4728.77	5088.20	4505.25	1.40	250	27.72
Deseada	COMIBOL	4730.65	5087.52	4505.25	1.50	170	15.06

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4730.70	5107.76	4474.25	0.80	370			14.50
Deseada	COMIBOL	4732.54	5107.22	4474.25	0.70	2,020			36.69
Deseada	COMIBOL	4732.60	5086.80	4505.25	1.10	200			11.61
Deseada	COMIBOL	4734.71	5086.01	4505.25	0.70	34			1.73
Deseada	COMIBOL	4736.75	5085.23	4505.25	0.70	86			3.29
Deseada	COMIBOL	4738.49	5084.57	4505.25	0.70	114			21.19
Deseada	COMIBOL	4740.42	5083.76	4505.25	0.70	11			3.90
Deseada	COMIBOL	4742.31	5082.96	4505.25	0.70	171			11.56
Deseada	COMIBOL	4744.27	5082.26	4505.25	0.70	126			16.04
Deseada	COMIBOL	4746.08	5081.77	4505.25	0.70	163			18.61
Deseada	COMIBOL	4747.94	5080.91	4505.25	0.70	57			5.86
Deseada	COMIBOL	4749.73	5079.82	4505.25	0.80	130			19.65
Deseada	COMIBOL	4751.26	5079.17	4505.25	0.80	170			11.87
Deseada	COMIBOL	4753.15	5078.37	4505.25	0.70	194			16.14
Deseada	COMIBOL	4754.02	5129.29	4435.75	0.70	72			4.22
Deseada	COMIBOL	4754.88	5077.64	4505.25	0.70	91			6.88
Deseada	COMIBOL	4755.88	5128.71	4435.75	0.70	161			1.22
Deseada	COMIBOL	4756.47	5076.99	4505.25	0.70	88			12.00
Deseada	COMIBOL	4757.32	5100.66	4474.25	0.70	55			0.85
Deseada	COMIBOL	4757.68	5128.21	4435.75	0.70	82			
Deseada	COMIBOL	4758.36	5076.22	4505.25	0.70	64			4.21
Deseada	COMIBOL	4759.73	5100.34	4474.25	0.70	50			0.77
Deseada	COMIBOL	4759.88	5127.69	4435.75	0.70	71			3.03
Deseada	COMIBOL	4760.14	5075.54	4505.25	0.70	14			0.26
Deseada	COMIBOL	4761.69	5100.00	4474.25	0.70	28			0.84
Deseada	COMIBOL	4761.83	5075.04	4505.25	0.70	9			0.50
Deseada	COMIBOL	4762.07	5127.16	4435.75	0.70	175			
Deseada	COMIBOL	4763.44	5074.56	4505.25	0.70	14			0.68
Deseada	COMIBOL	4763.78	5126.76	4435.75	1.00	220			7.84
Deseada	COMIBOL	4764.05	5099.16	4474.25	0.70	35			1.56
Deseada	COMIBOL	4765.17	5073.83	4505.25	0.70	26			2.07
Deseada	COMIBOL	4765.48	5126.35	4435.75	1.40	960			
Deseada	COMIBOL	4766.17	5098.51	4474.25	0.70	11			0.19
Deseada	COMIBOL	4766.95	5073.60	4505.25	0.70	40			2.63
Deseada	COMIBOL	4767.43	5073.48	4506.33	0.70	10			0.74
Deseada	COMIBOL	4767.43	5073.48	4508.94	0.70	7			2.75
Deseada	COMIBOL	4767.43	5073.48	4511.02	0.70	0			0.89
Deseada	COMIBOL	4767.43	5073.48	4513.25	0.70	21			0.91
Deseada	COMIBOL	4767.43	5073.48	4515.54	0.70	103			8.97
Deseada	COMIBOL	4767.43	5073.48	4518.11	0.70	9			1.75
Deseada	COMIBOL	4767.43	5073.48	4520.29	0.70	3			0.87
Deseada	COMIBOL	4767.43	5073.48	4522.58	0.70	3			0.25
Deseada	COMIBOL	4767.43	5073.48	4524.76	0.70	33			
Deseada	COMIBOL	4767.43	5073.48	4527.38	0.70	9			
Deseada	COMIBOL	4767.43	5073.48	4529.62	0.70	30			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4767.43	5073.48	4532.07	0.70	40	
Deseada	COMIBOL	4767.43	5073.48	4534.36	0.70	46	
Deseada	COMIBOL	4767.43	5073.48	4536.60	0.70	30	
Deseada	COMIBOL	4767.43	5073.48	4539.17	0.70	11	
Deseada	COMIBOL	4767.98	5125.75	4435.75	2.00	1,020	23.72
Deseada	COMIBOL	4768.35	5097.83	4474.25	0.70	148	
Deseada	COMIBOL	4768.84	5073.11	4505.25	0.70	211	8.54
Deseada	COMIBOL	4770.08	5125.25	4435.75	1.80	70	
Deseada	COMIBOL	4770.38	5072.71	4505.25	0.70	1,650	3.62
Deseada	COMIBOL	4770.52	5097.17	4474.25	0.70	64	4.92
Deseada	COMIBOL	4771.90	5124.81	4435.75	1.60	60	5.96
Deseada	COMIBOL	4772.44	5072.29	4505.25	0.70	40	3.45
Deseada	COMIBOL	4772.46	5096.58	4474.25	0.70	5	0.17
Deseada	COMIBOL	4773.87	5124.29	4435.75	1.60	150	
Deseada	COMIBOL	4773.93	5096.09	4474.25	0.70	30	0.67
Deseada	COMIBOL	4774.18	5072.04	4505.25	0.70	372	1.45
Deseada	COMIBOL	4775.59	5095.48	4475.13	0.70	211	9.40
Deseada	COMIBOL	4775.59	5095.48	4477.59	0.70	214	18.27
Deseada	COMIBOL	4775.59	5095.48	4479.77	0.70	117	2.86
Deseada	COMIBOL	4775.59	5095.48	4481.84	0.70	171	4.84
Deseada	COMIBOL	4775.59	5095.48	4484.13	0.70	81	13.14

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4775.59	5095.48	4486.59	0.70	46			1.50
Deseada	COMIBOL	4775.59	5095.48	4488.66	0.70	129			18.27
Deseada	COMIBOL	4775.59	5095.48	4490.90	0.70	180			
Deseada	COMIBOL	4775.59	5095.48	4493.35	0.70	83			0.34
Deseada	COMIBOL	4775.59	5095.48	4495.21	0.70	54			1.36
Deseada	COMIBOL	4775.59	5095.48	4497.66	0.70	29			
Deseada	COMIBOL	4775.59	5095.48	4499.68	0.70	59			3.05
Deseada	COMIBOL	4775.59	5095.48	4502.08	0.70	40			1.78
Deseada	COMIBOL	4775.59	5095.48	4504.26	0.70	47			1.43
Deseada	COMIBOL	4775.81	5095.40	4474.25	0.70	27			1.56
Deseada	COMIBOL	4775.99	5123.70	4435.75	0.70	23			2.99
Deseada	COMIBOL	4777.11	5094.91	4474.25	0.70	3			0.92
Deseada	COMIBOL	4777.69	5123.23	4435.75	0.70	99			
Deseada	COMIBOL	4779.05	5094.21	4474.25	0.70	5			0.07
Deseada	COMIBOL	4779.81	5122.79	4435.75	0.70	42			1.04
Deseada	COMIBOL	4780.62	5093.69	4474.25	0.70	12			0.27
Deseada	COMIBOL	4781.94	5122.50	4435.75	0.70	51			
Deseada	COMIBOL	4782.36	5093.12	4474.25	0.70	22			0.99
Deseada	COMIBOL	4783.56	5092.73	4474.25	0.70	54			1.10
Deseada	COMIBOL	4783.64	5122.12	4435.75	0.80	420			5.26
Deseada	COMIBOL	4785.14	5121.56	4435.75	0.70	390			
Deseada	COMIBOL	4785.70	5092.03	4474.25	0.70	1			0.12
Deseada	COMIBOL	4786.66	5121.00	4435.75	1.10	272			24.62
Deseada	COMIBOL	4786.76	5091.59	4474.25	0.70	2			0.95
Deseada	COMIBOL	4788.31	5120.38	4435.75	1.10	450			
Deseada	COMIBOL	4789.58	5119.94	4435.75	1.20	1,152			23.94
Deseada	COMIBOL	4790.07	5069.91	4505.25	0.70	2,180			15.33
Deseada	COMIBOL	4791.03	5119.50	4435.75	0.90	280			
Deseada	COMIBOL	4792.24	5119.13	4435.75	0.80	420			19.95
Deseada	COMIBOL	4792.58	5069.68	4505.25	0.70	476			9.82
Deseada	COMIBOL	4793.86	5118.64	4435.75	0.70	72			
Deseada	COMIBOL	4795.39	5118.18	4435.75	0.70	236			7.19
Deseada	COMIBOL	4795.72	5069.19	4505.25	0.80	1,080			18.56
Deseada	COMIBOL	4796.85	5117.74	4435.75	0.70	67			
Deseada	COMIBOL	4797.48	5068.69	4505.25	0.90	1,640			18.71
Deseada	COMIBOL	4798.41	5117.28	4435.75	0.70	101			4.42
Deseada	COMIBOL	4798.56	5117.24	4436.97	1.10	705			2.64
Deseada	COMIBOL	4798.56	5117.24	4438.98	0.90	420			
Deseada	COMIBOL	4798.56	5117.24	4441.82	1.50	510			11.51
Deseada	COMIBOL	4798.56	5117.24	4443.82	1.90				
Deseada	COMIBOL	4798.56	5117.24	4446.66	1.00				10.42
Deseada	COMIBOL	4798.56	5117.24	4448.99	0.80				
Deseada	COMIBOL	4798.56	5117.24	4451.41	1.00				11.65
Deseada	COMIBOL	4798.56	5117.24	4453.75	1.00	430			
Deseada	COMIBOL	4798.56	5117.24	4456.17	0.70	4,071			7.30

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4798.56	5117.24	4458.51	0.70		
Deseada	COMIBOL	4798.56	5117.24	4460.93	2.00	1,190	
Deseada	COMIBOL	4798.56	5117.24	4463.10	2.00	640	
Deseada	COMIBOL	4798.56	5117.24	4466.10	1.00	1,258	
Deseada	COMIBOL	4798.56	5117.24	4468.19	0.70	230	
Deseada	COMIBOL	4798.56	5117.24	4470.53	0.70	571	
Deseada	COMIBOL	4798.56	5117.24	4473.11	0.80	1,320	
Deseada	COMIBOL	4800.27	5086.39	4474.25	0.70	51	1.11
Deseada	COMIBOL	4800.64	5068.16	4505.25	0.70	185	4.90
Deseada	COMIBOL	4801.05	5116.52	4435.75	0.70	157	
Deseada	COMIBOL	4802.17	5085.64	4474.25	0.70	128	4.68
Deseada	COMIBOL	4802.47	5067.80	4505.25	0.70	76	2.20
Deseada	COMIBOL	4803.04	5115.93	4435.75	0.70	1,614	7.43
Deseada	COMIBOL	4803.87	5067.48	4505.25	0.70	102	4.33
Deseada	COMIBOL	4803.98	5085.01	4474.25	0.70	103	3.27
Deseada	COMIBOL	4805.60	5067.10	4505.25	0.70	216	4.93
Deseada	COMIBOL	4805.85	5115.05	4435.75	1.10	935	
Deseada	COMIBOL	4805.94	5084.41	4474.25	0.70	265	4.11
Deseada	COMIBOL	4807.45	5066.69	4505.25	0.70	110	1.02
Deseada	COMIBOL	4807.52	5083.93	4474.25	0.70	193	1.58
Deseada	COMIBOL	4807.86	5114.35	4435.75	0.70	165	7.65

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4809.13	5066.32	4505.25	0.70	89			4.15
Deseada	COMIBOL	4809.40	5083.44	4474.25	0.70	103			2.09
Deseada	COMIBOL	4810.26	5113.52	4435.75	0.80	1,640			
Deseada	COMIBOL	4810.49	5066.01	4505.25	0.70	44			1.38
Deseada	COMIBOL	4811.95	5065.69	4505.25	0.70	11			0.22
Deseada	COMIBOL	4812.25	5112.83	4435.75	1.20	2,652			18.11
Deseada	COMIBOL	4813.64	5065.31	4505.25	0.70	30			2.91
Deseada	COMIBOL	4814.75	5111.83	4435.75	1.20	2,184			
Deseada	COMIBOL	4815.58	5064.86	4505.25	0.70	107			2.63
Deseada	COMIBOL	4817.00	5110.88	4435.75	0.90	1,008			35.98
Deseada	COMIBOL	4817.09	5064.52	4505.25	0.70	392			13.65
Deseada	COMIBOL	4818.66	5064.16	4505.25	0.70	350			15.97
Deseada	COMIBOL	4819.18	5110.25	4435.75	0.70	178			
Deseada	COMIBOL	4819.96	5063.86	4505.25	1.10	710			10.00
Deseada	COMIBOL	4821.28	5109.76	4435.75	0.90	347			11.97
Deseada	COMIBOL	4821.79	5063.37	4505.25	0.80	256			8.00
Deseada	COMIBOL	4823.15	5109.14	4435.75	0.80	336			
Deseada	COMIBOL	4823.46	5062.92	4505.25	0.70	280			3.51
Deseada	COMIBOL	4825.06	5108.50	4435.75	1.20	204			10.13
Deseada	COMIBOL	4825.12	5062.47	4505.25	0.70	122			7.52
Deseada	COMIBOL	4826.69	5107.96	4435.75	0.70	434			
Deseada	COMIBOL	4826.71	5062.03	4505.25	0.70	1,497			10.00
Deseada	COMIBOL	4828.59	5107.36	4435.75	0.70	393			19.87
Deseada	COMIBOL	4828.97	5061.40	4505.25	0.70	360			18.07
Deseada	COMIBOL	4830.58	5106.78	4435.75	1.30	890			9.43
Deseada	COMIBOL	4830.92	5060.85	4505.25	0.70	1,080			5.55
Deseada	COMIBOL	4832.14	5106.32	4435.75	1.28	760			
Deseada	COMIBOL	4833.09	5060.23	4505.25	0.70	525			20.26
Deseada	COMIBOL	4834.21	5105.72	4435.75	1.20	790			8.24
Deseada	COMIBOL	4834.80	5059.75	4505.25	0.70	171			3.90
Deseada	COMIBOL	4836.00	5105.19	4435.75	1.10	740			
Deseada	COMIBOL	4837.06	5059.10	4505.25	0.70	250			6.49
Deseada	COMIBOL	4837.97	5104.62	4435.75	1.00	680			8.34
Deseada	COMIBOL	4839.31	5058.47	4505.25	0.70	250			7.38
Deseada	COMIBOL	4839.73	5104.15	4435.75	1.10	610			
Deseada	COMIBOL	4840.77	5058.05	4505.25	0.70	574			4.01
Deseada	COMIBOL	4841.64	5103.68	4435.75	1.20	130			19.95
Deseada	COMIBOL	4842.81	5057.47	4505.25	0.90	586			16.53
Deseada	COMIBOL	4843.62	5103.18	4435.75	1.10	760			
Deseada	COMIBOL	4844.94	5057.02	4505.25	1.30	253			11.81
Deseada	COMIBOL	4845.34	5102.75	4435.75	1.00	640			6.75
Deseada	COMIBOL	4847.12	5056.54	4505.25	1.10	940			22.31
Deseada	COMIBOL	4847.20	5102.29	4435.75	1.10	650			
Deseada	COMIBOL	4848.86	5055.96	4505.25	0.70	215			4.09
Deseada	COMIBOL	4849.31	5101.74	4435.75	1.20	710			9.03

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4850.40	5055.40	4505.25	0.70	109	2.32
Deseada	COMIBOL	4851.21	5101.22	4435.75	1.20	630	
Deseada	COMIBOL	4852.19	5054.74	4505.25	0.70	72	1.16
Deseada	COMIBOL	4852.74	5100.81	4435.75	1.30	700	12.90
Deseada	COMIBOL	4853.91	5054.12	4505.25	0.70	125	2.17
Deseada	COMIBOL	4854.57	5100.32	4435.75	1.40	620	
Deseada	COMIBOL	4855.59	5053.47	4505.25	0.70	145	2.25
Deseada	COMIBOL	4856.63	5099.81	4435.75	2.60	1,000	14.87
Deseada	COMIBOL	4856.91	5052.97	4505.25	0.70	171	2.38
Deseada	COMIBOL	4858.55	5099.65	4435.75	2.40	910	
Deseada	COMIBOL	4858.65	5052.30	4505.25	0.70	60	2.07
Deseada	COMIBOL	4860.28	5099.51	4435.75	3.90	920	17.77
Deseada	COMIBOL	4860.36	5051.63	4505.25	0.90	1,206	23.44
Deseada	COMIBOL	4862.02	5050.95	4505.25	0.70	46	1.51
Deseada	COMIBOL	4862.27	5099.35	4435.75	2.00	740	
Deseada	COMIBOL	4863.34	5050.40	4505.25	0.70	113	1.65
Deseada	COMIBOL	4863.99	5099.27	4435.75	1.80	670	15.48
Deseada	COMIBOL	4865.12	5049.66	4505.25	0.70	111	1.67
Deseada	COMIBOL	4866.00	5099.22	4435.75	1.80	770	
Deseada	COMIBOL	4866.55	5049.04	4505.25	0.70	62	0.89
Deseada	COMIBOL	4868.11	5048.20	4505.25	0.70	300	4.93

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4868.34	5099.29	4435.75	1.90	730			12.01
Deseada	COMIBOL	4869.60	5047.41	4505.25	0.70	85			1.05
Deseada	COMIBOL	4870.16	5099.34	4435.75	2.00	340			7.10
Deseada	COMIBOL	4871.29	5046.58	4505.25	0.70	111			2.33
Deseada	COMIBOL	4872.22	5099.40	4435.75	2.20	590			
Deseada	COMIBOL	4872.67	5046.05	4505.25	0.70	42			0.55
Deseada	COMIBOL	4873.90	5099.46	4435.75	1.80	650			10.30
Deseada	COMIBOL	4874.82	5045.48	4505.25	0.70	51			0.66
Deseada	COMIBOL	4875.94	5099.58	4435.75	2.00	660			
Deseada	COMIBOL	4876.94	5044.92	4505.25	0.70	151			6.25
Deseada	COMIBOL	4877.85	5099.70	4435.75	2.10	750			12.90
Deseada	COMIBOL	4878.91	5044.39	4505.25	0.70	174			4.01
Deseada	COMIBOL	4879.82	5099.83	4435.75	1.40	470			
Deseada	COMIBOL	4880.99	5043.84	4505.25	0.70	80			1.36
Deseada	COMIBOL	4881.79	5099.95	4435.75	1.50	410			11.00
Deseada	COMIBOL	4883.08	5043.29	4505.25	0.70	288			4.47
Deseada	COMIBOL	4883.79	5099.79	4435.75	1.00	250			
Deseada	COMIBOL	4885.42	5042.63	4505.25	0.70	287			8.93
Deseada	COMIBOL	4885.83	5099.58	4435.75	1.40	360			8.80
Deseada	COMIBOL	4887.02	5042.05	4505.25	0.70	46			2.41
Deseada	COMIBOL	4887.74	5099.38	4435.75	1.20	450			
Deseada	COMIBOL	4889.03	5041.33	4505.25	0.70	59			0.97
Deseada	COMIBOL	4889.62	5099.19	4435.75	2.10	450			8.10
Deseada	COMIBOL	4890.82	5040.68	4505.25	0.70	60			2.47
Deseada	COMIBOL	4891.30	5098.64	4435.75	1.50	560			
Deseada	COMIBOL	4892.68	5040.01	4505.25	0.70	23			1.30
Deseada	COMIBOL	4893.42	5098.24	4435.75	1.40	220			9.40
Deseada	COMIBOL	4894.89	5039.22	4505.25	0.70	18			1.10
Deseada	COMIBOL	4895.33	5097.76	4435.75	1.10	350			
Deseada	COMIBOL	4896.71	5038.54	4505.25	0.70	37			1.14
Deseada	COMIBOL	4896.97	5097.32	4435.75	1.10	70			1.00
Deseada	COMIBOL	4898.64	5037.70	4505.25	0.70	67			2.92
Deseada	COMIBOL	4898.83	5096.76	4435.75	1.40	620			
Deseada	COMIBOL	4900.78	5036.77	4505.25	0.70	39			1.74
Deseada	COMIBOL	4901.16	5096.07	4435.75	0.70	564			5.91
Deseada	COMIBOL	4902.82	5035.89	4505.25	0.80	104			8.85
Deseada	COMIBOL	4903.12	5095.49	4435.75	0.80	960			
Deseada	COMIBOL	4904.87	5035.00	4505.25	0.70	105			3.67
Deseada	COMIBOL	4905.20	5095.11	4435.75	0.70	890			9.60
Deseada	COMIBOL	4906.51	5034.29	4505.25	0.70	60			2.39
Deseada	COMIBOL	4907.46	5094.80	4435.75	1.80	210			
Deseada	COMIBOL	4908.28	5033.53	4505.25	0.70	42			3.63
Deseada	COMIBOL	4909.29	5094.55	4435.75	1.60	740			9.80
Deseada	COMIBOL	4910.36	5032.63	4505.25	0.70	42			0.85
Deseada	COMIBOL	4911.33	5094.27	4435.75	1.50	1,060			18.32

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4912.09	5031.81	4505.25	0.70	79	2.40
Deseada	COMIBOL	4913.54	5093.93	4435.75	1.60	890	16.93
Deseada	COMIBOL	4913.68	5031.00	4505.25	0.70	121	11.64
Deseada	COMIBOL	4915.03	5093.48	4435.75	1.40	1,040	
Deseada	COMIBOL	4915.78	5029.93	4505.25	0.70	94	8.31
Deseada	COMIBOL	4917.31	5092.79	4435.75	1.10	880	15.74
Deseada	COMIBOL	4917.40	5029.10	4505.25	0.70	63	4.70
Deseada	COMIBOL	4919.09	5092.22	4435.75	0.80	850	
Deseada	COMIBOL	4919.34	5028.11	4505.25	0.70	24	0.99
Deseada	COMIBOL	4920.97	5091.17	4435.75	1.50	1,200	18.91
Deseada	COMIBOL	4921.15	5027.21	4505.25	0.70	23	0.59
Deseada	COMIBOL	4922.67	5026.52	4505.25	0.70	4	0.14
Deseada	COMIBOL	4922.89	5090.10	4435.75	1.50	780	
Deseada	COMIBOL	4924.43	5025.72	4505.25	0.70	38	1.02
Deseada	COMIBOL	4924.57	5089.16	4435.75	1.50	1,140	16.34
Deseada	COMIBOL	4926.40	5088.26	4435.75	0.90	890	
Deseada	COMIBOL	4926.42	5024.93	4505.25	0.70	19	0.25
Deseada	COMIBOL	4928.14	5024.45	4505.25	0.70	30	3.72
Deseada	COMIBOL	4928.65	5087.47	4435.75	0.70	394	6.96
Deseada	COMIBOL	4929.90	5023.96	4505.25	0.70	93	11.80
Deseada	COMIBOL	4930.55	5086.80	4435.75	0.70	300	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4931.85	5023.41	4505.25	0.70	18			1.71
Deseada	COMIBOL	4932.19	5086.23	4435.75	1.20	1,260			18.02
Deseada	COMIBOL	4933.99	5022.81	4505.25	0.70	110			7.47
Deseada	COMIBOL	4934.34	5085.62	4435.75	0.90	870			
Deseada	COMIBOL	4935.85	5022.30	4505.25	0.70	221			6.66
Deseada	COMIBOL	4936.22	5085.17	4435.75	1.30	940			11.89
Deseada	COMIBOL	4937.73	5022.07	4505.25	0.70	182			20.53
Deseada	COMIBOL	4938.25	5084.63	4435.75	0.80	910			
Deseada	COMIBOL	4939.67	5021.83	4505.25	0.82	168			41.68
Deseada	COMIBOL	4939.83	5084.18	4435.75	0.70	857			8.21
Deseada	COMIBOL	4941.61	5021.58	4505.25	1.10	360			45.24
Deseada	COMIBOL	4942.02	5083.56	4435.75	0.70	714			
Deseada	COMIBOL	4943.57	5021.34	4505.25	0.70	320			16.67
Deseada	COMIBOL	4943.81	5083.05	4435.75	1.30	730			10.10
Deseada	COMIBOL	4945.48	5021.10	4505.25	1.10	270			24.38
Deseada	COMIBOL	4947.62	5020.86	4505.25	1.30	230			41.91
Deseada	COMIBOL	4949.54	5020.72	4505.25	1.00	240			39.72
Deseada	COMIBOL	4951.13	5020.60	4505.25	1.10	220			41.52
Deseada	COMIBOL	4952.87	5107.57	4393.75	2.80	238			7.00
Deseada	COMIBOL	4953.35	5020.40	4505.25	1.00	160			33.81
Deseada	COMIBOL	4954.85	5107.36	4393.75	0.80	77			1.64
Deseada	COMIBOL	4955.15	5020.22	4505.25	0.70	113			19.35
Deseada	COMIBOL	4956.66	5107.17	4393.75	2.80	98			4.25
Deseada	COMIBOL	4956.68	5048.00	4474.25	0.70	20			1.60
Deseada	COMIBOL	4957.29	5020.01	4505.25	0.80	320			29.54
Deseada	COMIBOL	4958.58	5047.77	4474.25	0.70	204			3.03
Deseada	COMIBOL	4958.72	5106.96	4393.75	0.80	373			7.50
Deseada	COMIBOL	4959.27	5019.81	4505.25	0.70	46			7.23
Deseada	COMIBOL	4960.48	5106.77	4393.75	0.90	200			6.00
Deseada	COMIBOL	4960.92	5047.55	4474.25	0.70	103			1.49
Deseada	COMIBOL	4961.20	5019.51	4505.25	0.70	245			15.00
Deseada	COMIBOL	4962.43	5106.45	4393.75	0.80	178			7.50
Deseada	COMIBOL	4962.95	5019.18	4505.25	1.00	470			34.48
Deseada	COMIBOL	4963.21	5047.37	4474.25	0.70	29			0.66
Deseada	COMIBOL	4964.09	5106.17	4393.75	0.98	127			3.20
Deseada	COMIBOL	4964.84	5018.82	4505.25	1.20	240			20.00
Deseada	COMIBOL	4965.56	5047.17	4474.25	0.70	43			0.75
Deseada	COMIBOL	4965.83	5105.87	4393.75	0.80	45			1.46
Deseada	COMIBOL	4966.91	5018.43	4505.25	0.80	328			8.61
Deseada	COMIBOL	4967.55	5046.70	4474.25	1.00	340			11.78
Deseada	COMIBOL	4967.95	5105.51	4393.75	0.80	26			1.00
Deseada	COMIBOL	4968.64	5018.13	4505.25	0.70	261			15.83
Deseada	COMIBOL	4969.84	5105.19	4393.75	0.80	67			1.24
Deseada	COMIBOL	4969.93	5046.03	4474.25	0.90	324			9.25
Deseada	COMIBOL	4970.54	5017.82	4505.25	0.70	42			1.83

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	4971.81	5045.51	4474.25	0.70	648	3.87
Deseada	COMIBOL	4972.47	5017.52	4505.25	0.70	64	4.14
Deseada	COMIBOL	4973.87	5044.54	4474.25	0.70	303	4.57
Deseada	COMIBOL	4974.31	5017.23	4505.25	0.70	96	4.81
Deseada	COMIBOL	4976.00	5043.43	4474.25	0.70	143	3.14
Deseada	COMIBOL	4976.31	5016.71	4505.25	0.70	14	1.44
Deseada	COMIBOL	4977.81	5042.49	4474.25	0.70	94	1.45
Deseada	COMIBOL	4978.33	5015.98	4505.25	0.70	38	1.58
Deseada	COMIBOL	4979.96	5041.41	4474.25	0.70	235	2.07
Deseada	COMIBOL	4980.19	5015.30	4505.25	0.70	66	2.62
Deseada	COMIBOL	4981.81	5014.72	4505.25	0.70	14	0.49
Deseada	COMIBOL	4982.08	5040.34	4474.25	0.70	71	1.55
Deseada	COMIBOL	4983.54	5014.08	4505.25	0.70	93	4.85
Deseada	COMIBOL	4983.71	5039.53	4474.25	0.70	1	1.04
Deseada	COMIBOL	4985.47	5013.22	4505.25	0.70	119	9.98
Deseada	COMIBOL	4985.71	5038.53	4474.25	0.70	8	0.02
Deseada	COMIBOL	4988.03	5037.30	4474.25	0.70	8	0.29
Deseada	COMIBOL	4988.99	5011.20	4505.25	0.70	129	6.05
Deseada	COMIBOL	4990.25	5036.13	4474.25	0.70	159	2.50
Deseada	COMIBOL	4991.03	5010.18	4505.25	0.70	23	1.41
Deseada	COMIBOL	4992.15	5035.25	4474.25	1.30	340	18.57

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	4992.81	5009.30	4505.25	0.70	11			2.50
Deseada	COMIBOL	4993.87	5034.46	4474.25	1.45	320			19.47
Deseada	COMIBOL	4994.55	5008.45	4505.25	0.70	31			3.01
Deseada	COMIBOL	4994.86	5034.00	4477.64	1.00	184			13.13
Deseada	COMIBOL	4994.86	5034.00	4479.01	1.00	69			3.90
Deseada	COMIBOL	4994.86	5034.00	4480.37	1.00	63			1.44
Deseada	COMIBOL	4994.86	5034.00	4481.68	1.00	26			2.07
Deseada	COMIBOL	4994.86	5034.00	4483.10	1.00	38			4.02
Deseada	COMIBOL	4994.86	5034.00	4484.41	1.00	90			14.70
Deseada	COMIBOL	4994.86	5034.00	4485.83	1.00	238			17.49
Deseada	COMIBOL	4994.86	5034.00	4487.19	1.00	312			16.38
Deseada	COMIBOL	4994.86	5034.00	4488.55	1.00	91			8.34
Deseada	COMIBOL	4994.86	5034.00	4489.86	1.00	54			6.11
Deseada	COMIBOL	4994.86	5034.00	4491.23	1.00	116			1.88
Deseada	COMIBOL	4994.86	5034.00	4492.54	1.00	174			7.29
Deseada	COMIBOL	4994.86	5034.00	4493.90	1.00	200			11.57
Deseada	COMIBOL	4994.86	5034.00	4495.26	1.00	120			9.71
Deseada	COMIBOL	4994.86	5034.00	4496.57	1.00	126			10.48
Deseada	COMIBOL	4994.86	5034.00	4497.88	1.00	54			7.61
Deseada	COMIBOL	4994.86	5034.00	4499.19	1.00	106			7.55
Deseada	COMIBOL	4994.86	5034.00	4500.55	1.00	16			1.47
Deseada	COMIBOL	4994.86	5034.00	4501.92	1.00	80			3.80
Deseada	COMIBOL	4995.96	5033.61	4474.25	1.00	300			14.48
Deseada	COMIBOL	4996.18	5007.69	4505.25	0.70	59			6.45
Deseada	COMIBOL	4998.03	5032.95	4474.25	0.70	39			2.41
Deseada	COMIBOL	4998.18	5006.84	4505.25	0.70	43			4.76
Deseada	COMIBOL	5000.00	5006.02	4505.25	0.70	105			5.69
Deseada	COMIBOL	5000.33	5032.21	4474.25	0.70	30			1.17
Deseada	COMIBOL	5002.25	5005.09	4505.25	0.70	26			0.77
Deseada	COMIBOL	5002.36	5031.54	4474.25	0.70	1			0.05
Deseada	COMIBOL	5003.98	5004.22	4505.25	0.70	89			7.85
Deseada	COMIBOL	5004.25	5030.87	4474.25	0.70	10			0.04
Deseada	COMIBOL	5005.19	5003.61	4505.25	0.70	140			27.52
Deseada	COMIBOL	5006.15	5030.20	4474.25	0.70	642			1.67
Deseada	COMIBOL	5007.16	5002.61	4505.25	0.70	114			16.62
Deseada	COMIBOL	5008.02	5029.54	4474.25	0.70	93			0.37
Deseada	COMIBOL	5009.28	5001.49	4505.25	0.70	87			15.58
Deseada	COMIBOL	5009.90	5028.88	4474.25	0.70	1,434			5.85
Deseada	COMIBOL	5010.98	5000.58	4505.25	0.70	165			12.09
Deseada	COMIBOL	5011.94	5028.03	4474.25	0.70	377			0.57
Deseada	COMIBOL	5012.71	4999.72	4505.25	0.70	48			6.05
Deseada	COMIBOL	5013.90	5027.15	4474.25	0.70	134			0.19
Deseada	COMIBOL	5014.51	4998.87	4505.25	0.70	40			6.00
Deseada	COMIBOL	5015.84	5026.33	4474.25	0.70	1			0.34
Deseada	COMIBOL	5016.23	4998.07	4505.25	0.70	31			5.33

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	5017.83	5025.60	4474.25	0.70	769	3.07
Deseada	COMIBOL	5018.11	4997.18	4505.25	0.70	35	4.13
Deseada	COMIBOL	5019.68	4996.36	4505.25	0.70	46	3.61
Deseada	COMIBOL	5019.82	5024.87	4474.25	0.70	694	2.08
Deseada	COMIBOL	5021.58	5058.47	4443.07	0.80	170	
Deseada	COMIBOL	5021.58	5058.47	4445.07	0.70	40	5.32
Deseada	COMIBOL	5021.58	5058.47	4447.41	0.70	446	
Deseada	COMIBOL	5021.58	5058.47	4449.24	0.70	183	2.24
Deseada	COMIBOL	5021.58	5058.47	4451.50	0.70	157	
Deseada	COMIBOL	5021.58	5058.47	4454.00	0.70	527	8.53
Deseada	COMIBOL	5021.58	5058.47	4456.00	0.80	110	
Deseada	COMIBOL	5021.58	5058.47	4458.09	0.70	74	3.91
Deseada	COMIBOL	5021.58	5058.47	4460.26	0.70	1,180	
Deseada	COMIBOL	5021.58	5058.47	4462.10	0.70	194	5.94
Deseada	COMIBOL	5021.58	5058.47	4464.43	0.70	369	
Deseada	COMIBOL	5021.58	5058.47	4466.69	0.70	43	2.83
Deseada	COMIBOL	5021.74	4995.21	4505.25	0.70	15	2.03
Deseada	COMIBOL	5022.00	5024.17	4474.25	0.70	287	
Deseada	COMIBOL	5023.32	4994.32	4505.25	0.70	17	1.57
Deseada	COMIBOL	5023.84	5023.64	4474.25	1.10	540	
Deseada	COMIBOL	5024.93	4993.49	4505.25	0.70	48	8.85

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	5026.04	5022.98	4474.25	0.80	422			
Deseada	COMIBOL	5026.73	4992.58	4505.25	0.70	32			4.90
Deseada	COMIBOL	5027.83	5022.26	4474.25	0.70	96			
Deseada	COMIBOL	5028.21	5022.02	4478.19	1.00	65			4.15
Deseada	COMIBOL	5028.21	5022.02	4479.99	1.00	224			6.64
Deseada	COMIBOL	5028.21	5022.02	4481.52	1.00	240			7.64
Deseada	COMIBOL	5028.21	5022.02	4483.26	1.00	560			13.38
Deseada	COMIBOL	5028.21	5022.02	4484.84	1.00	272			8.64
Deseada	COMIBOL	5028.21	5022.02	4486.64	1.00	329			7.13
Deseada	COMIBOL	5028.21	5022.02	4488.12	1.00	96			8.48
Deseada	COMIBOL	5028.21	5022.02	4489.81	1.00	175			6.78
Deseada	COMIBOL	5028.21	5022.02	4491.39	1.00	120			10.31
Deseada	COMIBOL	5028.21	5022.02	4493.03	1.00	112			8.72
Deseada	COMIBOL	5028.21	5022.02	4494.61	1.00	78			11.39
Deseada	COMIBOL	5028.21	5022.02	4496.30	1.00	86			4.16
Deseada	COMIBOL	5028.21	5022.02	4497.88	1.00	96			9.26
Deseada	COMIBOL	5028.21	5022.02	4499.63	1.00	84			12.82
Deseada	COMIBOL	5028.21	5022.02	4501.21	1.00	78			9.12
Deseada	COMIBOL	5028.56	4991.69	4505.25	0.70	85			6.82
Deseada	COMIBOL	5029.95	5021.42	4474.25	0.70	99			
Deseada	COMIBOL	5030.50	4991.14	4505.25	0.70	26			4.53
Deseada	COMIBOL	5031.76	5020.72	4474.25	0.70	96			
Deseada	COMIBOL	5032.35	4990.63	4505.25	0.70	5			0.45
Deseada	COMIBOL	5033.69	5019.99	4474.25	0.70	60			
Deseada	COMIBOL	5033.90	4990.19	4505.25	0.70	30			5.82
Deseada	COMIBOL	5035.44	5019.40	4474.25	0.70	19			
Deseada	COMIBOL	5035.63	4989.77	4505.25	0.70	79			14.66
Deseada	COMIBOL	5037.34	5018.72	4474.25	0.70	26			
Deseada	COMIBOL	5037.75	4989.27	4505.25	0.70	154			10.09
Deseada	COMIBOL	5038.80	5018.00	4474.25	0.70	3			
Deseada	COMIBOL	5039.68	4988.81	4505.25	0.70	1			0.14
Deseada	COMIBOL	5040.57	5017.12	4474.25	0.70	69			
Deseada	COMIBOL	5041.52	4988.29	4505.25	0.70	3			0.29
Deseada	COMIBOL	5042.23	5016.30	4474.25	0.70	113			
Deseada	COMIBOL	5043.14	4987.79	4505.25	0.70	5			0.27
Deseada	COMIBOL	5044.10	5015.46	4474.25	0.70	247			
Deseada	COMIBOL	5045.18	4987.02	4505.25	0.70	14			1.10
Deseada	COMIBOL	5045.46	5014.88	4474.25	0.70	14			
Deseada	COMIBOL	5046.92	4986.36	4505.25	0.70	21			1.65
Deseada	COMIBOL	5047.59	5013.97	4474.25	0.70	18			
Deseada	COMIBOL	5049.04	5013.36	4474.25	0.70	11			
Deseada	COMIBOL	5050.79	5012.59	4474.25	0.70	14			
Deseada	COMIBOL	5052.51	5011.84	4474.25	0.70				
Deseada	COMIBOL	5054.28	5011.15	4474.25	0.70	14			
Deseada	COMIBOL	5056.06	5010.39	4474.25	0.70	12			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	5094.43	4967.64	4505.25	0.70	165	12.48
Deseada	COMIBOL	5096.60	4968.17	4505.25	0.70	238	16.51
Deseada	COMIBOL	5098.81	4968.71	4505.25	0.70	196	10.74
Deseada	COMIBOL	5100.78	4969.21	4505.25	0.70	214	10.14
Deseada	COMIBOL	5103.09	4969.85	4505.25	0.70	192	6.54
Deseada	COMIBOL	5104.68	4970.30	4505.25	0.70	278	17.49
Deseada	COMIBOL	5106.84	4970.58	4505.25	0.70	232	13.96
Deseada	COMIBOL	5109.14	4970.70	4505.25	0.70	237	16.27
Deseada	COMIBOL	5111.68	4970.83	4505.25	0.70	94	2.67
Deseada	COMIBOL	5113.33	4970.92	4505.78	0.70	2	0.04
Deseada	COMIBOL	5113.33	4970.92	4508.29	0.70	3	0.06
Deseada	COMIBOL	5113.33	4970.92	4510.47	0.70	5	0.06
Deseada	COMIBOL	5113.33	4970.92	4512.43	0.70	11	0.57
Deseada	COMIBOL	5113.33	4970.92	4514.56	0.70	25	1.15
Deseada	COMIBOL	5113.33	4970.92	4516.64	0.70	11	0.91
Deseada	COMIBOL	5113.33	4970.92	4518.71	0.70	87	3.31
Deseada	COMIBOL	5113.33	4970.92	4520.78	0.70	11	1.32
Deseada	COMIBOL	5113.33	4970.92	4522.64	0.70	16	1.45
Deseada	COMIBOL	5113.33	4970.92	4524.87	0.70	46	2.37
Deseada	COMIBOL	5113.33	4970.92	4527.16	0.70	50	2.51
Deseada	COMIBOL	5113.33	4970.92	4528.96	0.70	161	5.61

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	5113.33	4970.92	4531.04	0.70	38			1.63
Deseada	COMIBOL	5113.33	4970.92	4533.00	0.70	329			9.64
Deseada	COMIBOL	5113.33	4970.92	4534.91	0.70	7			0.05
Deseada	COMIBOL	5113.33	4970.92	4537.31	0.70	39			0.66
Deseada	COMIBOL	5113.33	4970.92	4539.44	0.70	93			0.42
Deseada	COMIBOL	5113.87	4970.95	4505.25	0.70	31			6.01
Deseada	COMIBOL	5115.83	4970.97	4505.25	0.70	6			0.68
Deseada	COMIBOL	5117.88	4970.97	4505.25	0.70	21			0.53
Deseada	COMIBOL	5119.79	4970.97	4505.25	0.70	34			0.45
Deseada	COMIBOL	5122.08	4970.69	4505.25	0.70	43			1.21
Deseada	COMIBOL	5124.15	4970.19	4505.25	1.40	210			6.18
Deseada	COMIBOL	5126.53	4969.92	4505.25	0.70	146			16.91
Deseada	COMIBOL	5128.19	4969.55	4505.25	0.70	96			11.72
Deseada	COMIBOL	5130.10	4968.87	4505.25	0.70	82			13.11
Deseada	COMIBOL	5131.95	4968.20	4505.25	0.70	216			15.38
Deseada	COMIBOL	5133.91	4967.89	4505.25	0.70	280			23.77
Deseada	COMIBOL	5135.73	4967.69	4505.25	0.70	226			27.45
Deseada	COMIBOL	5137.67	4967.47	4505.25	0.70	114			17.82
Deseada	COMIBOL	5139.69	4967.25	4505.25	0.70	63			6.79
Deseada	COMIBOL	5141.68	4967.03	4505.25	0.70	336			6.38
Deseada	COMIBOL	5143.53	4966.94	4505.25	0.70	27			4.10
Deseada	COMIBOL	5145.36	4966.86	4505.25	0.70	50			1.06
Deseada	COMIBOL	5147.27	4966.78	4505.25	0.70	96			1.53
Deseada	COMIBOL	5149.46	4966.69	4505.25	0.80	14			3.10
Deseada	COMIBOL	5151.36	4966.82	4505.25	0.70	27			5.61
Deseada	COMIBOL	5153.43	4967.07	4505.25	0.70	32			2.99
Deseada	COMIBOL	5155.23	4967.29	4505.25	0.70	1			0.05
Deseada	COMIBOL	5157.17	4967.57	4505.25	0.70	12			1.97
Deseada	COMIBOL	5159.23	4968.02	4505.25	0.70	16			0.99
Deseada	COMIBOL	5160.83	4968.37	4505.25	0.70	0			0.36
Deseada	COMIBOL	5162.73	4968.78	4505.25	0.70	0			0.08
Deseada	COMIBOL	5164.94	4969.07	4505.25	0.70	27			5.87
Deseada	COMIBOL	5166.58	4969.51	4505.25	0.70	148			3.62
Deseada	COMIBOL	5168.36	4970.17	4505.25	0.70	0			0.05
Deseada	COMIBOL	5170.71	4971.04	4505.25	0.70	27			5.59
Deseada	COMIBOL	5172.49	4972.38	4505.25	0.70	25			6.47
Deseada	COMIBOL	5174.23	4973.85	4505.25	0.70	146			15.05
Deseada	COMIBOL	5175.61	4974.99	4505.25	0.90	288			22.39
Deseada	COMIBOL	5177.39	4976.10	4505.25	0.70	1,288			22.19
Deseada	COMIBOL	5178.96	4977.08	4505.25	0.70	9			14.53
Deseada	COMIBOL	5180.71	4978.15	4505.25	0.70	41			6.78
Deseada	COMIBOL	5182.98	4979.32	4505.25	0.70	22			2.34
Deseada	COMIBOL	5184.85	4980.29	4505.25	0.70	444			5.46
Deseada	COMIBOL	5186.45	4981.12	4505.25	0.70	444			5.46
Deseada	COMIBOL	5188.77	4982.45	4505.25	0.70	471			22.69

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	5189.77	4983.06	4505.25	1.00	930	32.61
Deseada	COMIBOL	5191.80	4984.30	4505.25	0.70	132	32.61
Deseada	COMIBOL	5194.12	4984.66	4505.25	0.70	85	13.23
Deseada	COMIBOL	5195.83	4984.70	4505.25	0.70	36	8.86
Deseada	COMIBOL	5198.08	4984.74	4505.25	0.70	33	5.28
Deseada	COMIBOL	5200.19	4984.69	4505.25	0.70	7	3.66
Deseada	COMIBOL	5202.10	4984.62	4505.25	0.70	3	0.26
Deseada	COMIBOL	5204.21	4984.54	4505.25	0.70	4	0.14
Deseada	COMIBOL	5206.35	4984.30	4505.25	0.70	6	0.23
Deseada	COMIBOL	5208.62	4983.95	4505.25	0.70	94	0.55
Deseada	COMIBOL	5210.53	4983.68	4505.25	0.70	96	5.07
Deseada	COMIBOL	5212.31	4983.38	4505.25	0.70	53	7.82
Deseada	COMIBOL	5214.90	4982.67	4505.25	0.70	33	3.75
Deseada	COMIBOL	5216.40	4982.26	4505.25	0.70	59	5.59
Deseada	COMIBOL	5218.44	4981.70	4505.25	0.70	21	3.08
Deseada	COMIBOL	5220.41	4981.16	4505.25	0.70	94	2.35
Deseada	COMIBOL	5222.23	4980.57	4505.25	0.70	82	7.14
Deseada	COMIBOL	5224.21	4979.87	4505.25	0.70	55	5.62
Deseada	COMIBOL	5225.93	4979.26	4505.25	0.70	214	5.04
Deseada	COMIBOL	5227.93	4978.71	4505.25	0.70	60	6.57
Deseada	COMIBOL	5230.26	5060.41	4393.75	0.80	360	6.45

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	5230.38	4978.26	4505.25	0.70	11			2.48
Deseada	COMIBOL	5231.79	5059.90	4393.75	0.80	312			4.44
Deseada	COMIBOL	5231.82	4977.99	4505.25	0.70	25			1.49
Deseada	COMIBOL	5233.72	5059.25	4393.75	0.80	112			2.14
Deseada	COMIBOL	5233.75	4977.61	4505.25	0.70	41			0.75
Deseada	COMIBOL	5235.75	5058.62	4393.75	0.80	90			0.97
Deseada	COMIBOL	5235.98	4977.12	4505.25	0.70	14			0.92
Deseada	COMIBOL	5237.61	5058.10	4393.75	0.80	81			4.64
Deseada	COMIBOL	5237.96	4976.68	4505.25	0.70	15			1.94
Deseada	COMIBOL	5239.53	5057.57	4393.75	0.80	35			2.56
Deseada	COMIBOL	5239.90	4976.25	4505.25	0.70	9			0.68
Deseada	COMIBOL	5241.41	5057.04	4393.75	0.80				
Deseada	COMIBOL	5241.82	4975.97	4505.25	1.00	350			3.25
Deseada	COMIBOL	5243.81	5021.28	4435.75	0.70	43			7.40
Deseada	COMIBOL	5243.88	4975.79	4505.25	1.50	400			29.24
Deseada	COMIBOL	5245.85	4975.62	4505.25	1.10	260			14.57
Deseada	COMIBOL	5246.01	5020.88	4435.75	0.70	66			
Deseada	COMIBOL	5247.82	4975.57	4505.25	1.60	500			14.96
Deseada	COMIBOL	5248.10	5020.51	4435.75	0.70	126			8.91
Deseada	COMIBOL	5250.05	4975.44	4505.25	0.90	306			18.76
Deseada	COMIBOL	5250.36	5020.12	4435.75	0.70	129			
Deseada	COMIBOL	5251.87	4974.99	4505.25	0.70	51			10.84
Deseada	COMIBOL	5252.06	5019.88	4435.75	0.90	190			29.03
Deseada	COMIBOL	5253.94	5019.61	4435.75	0.80	180			20.25
Deseada	COMIBOL	5254.13	4974.70	4505.25	0.70	89			10.20
Deseada	COMIBOL	5255.91	4974.66	4505.25	0.70	41			1.96
Deseada	COMIBOL	5256.44	5019.26	4435.75	0.80	210			
Deseada	COMIBOL	5258.02	4974.61	4505.25	0.70	23			2.13
Deseada	COMIBOL	5258.71	5019.11	4435.75	0.85	200			29.03
Deseada	COMIBOL	5259.52	4974.65	4506.27	1.00	22			0.59
Deseada	COMIBOL	5259.52	4974.65	4508.34	1.00	70			4.62
Deseada	COMIBOL	5259.52	4974.65	4510.74	1.00	62			3.35
Deseada	COMIBOL	5259.52	4974.65	4512.93	1.00	128			6.21
Deseada	COMIBOL	5259.52	4974.65	4515.16	1.00	80			4.47
Deseada	COMIBOL	5259.52	4974.65	4517.07	1.00	78			3.77
Deseada	COMIBOL	5259.52	4974.65	4519.47	1.00	34			0.98
Deseada	COMIBOL	5259.52	4974.65	4521.65	1.00	69			5.31
Deseada	COMIBOL	5259.52	4974.65	4523.95	1.00	87			4.57
Deseada	COMIBOL	5259.52	4974.65	4525.91	1.00	114			2.15
Deseada	COMIBOL	5259.52	4974.65	4528.09	1.00	66			1.04
Deseada	COMIBOL	5259.52	4974.65	4530.11	1.00	62			0.77
Deseada	COMIBOL	5259.52	4974.65	4532.29	1.00	51			0.38
Deseada	COMIBOL	5259.52	4974.65	4534.53	1.00	57			0.34
Deseada	COMIBOL	5259.52	4974.65	4537.04	1.00	57			0.36
Deseada	COMIBOL	5259.52	4974.65	4539.27	1.00	50			0.22

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	5259.99	4974.70	4505.25	0.70	66	2.49
Deseada	COMIBOL	5260.89	5019.02	4435.75	1.00	140	
Deseada	COMIBOL	5261.96	4974.90	4505.25	0.70	27	0.64
Deseada	COMIBOL	5262.77	5018.93	4435.75	1.45	230	14.66
Deseada	COMIBOL	5264.20	4975.13	4505.25	0.70	7	0.46
Deseada	COMIBOL	5264.88	5018.88	4435.75	0.70	3,807	12.37
Deseada	COMIBOL	5266.17	4974.83	4505.25	0.70	19	0.67
Deseada	COMIBOL	5266.84	5018.84	4435.75	0.70	454	
Deseada	COMIBOL	5268.10	4974.26	4505.25	0.70	102	0.49
Deseada	COMIBOL	5268.53	5018.80	4435.75	0.70	184	10.83
Deseada	COMIBOL	5270.15	4973.66	4505.25	0.70	40	0.78
Deseada	COMIBOL	5270.98	5018.60	4435.75	0.70	707	
Deseada	COMIBOL	5271.93	4973.14	4505.25	0.70	379	3.06
Deseada	COMIBOL	5272.87	5018.25	4435.75	0.70	223	12.15
Deseada	COMIBOL	5273.91	4972.57	4505.25	0.70	770	9.40
Deseada	COMIBOL	5275.25	5017.81	4435.75	0.70	107	
Deseada	COMIBOL	5275.89	4971.99	4505.25	0.70	221	11.06
Deseada	COMIBOL	5277.13	5017.42	4435.75	0.70	77	2.43
Deseada	COMIBOL	5277.87	4971.69	4505.25	0.70	114	15.54
Deseada	COMIBOL	5278.93	5016.99	4435.75	1.20	1,480	
Deseada	COMIBOL	5279.58	4971.58	4505.25	0.70	49	12.39

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	5280.91	5016.52	4435.75	0.70	24			1.82
Deseada	COMIBOL	5282.10	4971.41	4505.25	0.70	69			3.47
Deseada	COMIBOL	5282.88	5016.06	4435.75	0.70	177			
Deseada	COMIBOL	5284.13	4971.28	4505.25	0.70	199			3.97
Deseada	COMIBOL	5284.60	5015.64	4435.75	0.70	79			5.58
Deseada	COMIBOL	5285.62	4970.97	4505.25	0.70	213			7.32
Deseada	COMIBOL	5286.83	5015.10	4435.75	0.70	206			0.99
Deseada	COMIBOL	5288.05	4970.45	4505.25	0.70	23			2.31
Deseada	COMIBOL	5288.76	5014.63	4435.75	0.70	90			
Deseada	COMIBOL	5289.85	4969.94	4505.25	0.80	640			2.90
Deseada	COMIBOL	5290.69	5014.16	4435.75	0.70	159			6.30
Deseada	COMIBOL	5291.87	4969.25	4505.25	1.10	930			15.46
Deseada	COMIBOL	5292.91	5013.62	4435.75	0.70	46			
Deseada	COMIBOL	5293.79	4968.61	4505.25	1.00	1,230			18.29
Deseada	COMIBOL	5294.85	5013.18	4435.75	0.70	126			17.51
Deseada	COMIBOL	5295.56	4968.12	4505.25	0.70	525			35.10
Deseada	COMIBOL	5296.82	5012.88	4435.75	0.70	257			
Deseada	COMIBOL	5298.06	4967.70	4505.25	0.70	162			3.18
Deseada	COMIBOL	5298.80	5012.58	4435.75	0.70	293			19.31
Deseada	COMIBOL	5299.48	4967.59	4505.25	0.70	240			2.71
Deseada	COMIBOL	5300.89	5012.26	4435.75	0.70	283			
Deseada	COMIBOL	5301.79	4967.47	4505.25	0.70	125			5.83
Deseada	COMIBOL	5302.99	5011.93	4435.75	0.70	403			33.25
Deseada	COMIBOL	5304.04	4967.35	4505.25	0.70	298			8.86
Deseada	COMIBOL	5304.80	5011.79	4435.75	0.70	286			
Deseada	COMIBOL	5306.22	4967.23	4505.25	0.70	200			7.14
Deseada	COMIBOL	5306.99	5011.69	4435.75	0.70	598			25.78
Deseada	COMIBOL	5308.76	4967.07	4505.25	0.70	100			4.12
Deseada	COMIBOL	5309.44	5011.68	4435.75	0.70	251			
Deseada	COMIBOL	5310.51	4966.95	4505.25	0.80	880			15.62
Deseada	COMIBOL	5311.68	5011.67	4435.75	0.70	200			28.57
Deseada	COMIBOL	5312.64	4966.81	4505.25	0.70	213			9.38
Deseada	COMIBOL	5313.99	5011.67	4435.75	0.70	343			
Deseada	COMIBOL	5314.97	4966.66	4505.25	0.70	61			2.62
Deseada	COMIBOL	5316.38	5011.67	4435.75	0.70	100			8.71
Deseada	COMIBOL	5317.33	4966.51	4505.25	0.70	45			2.83
Deseada	COMIBOL	5318.34	5011.67	4435.75	0.70	60			
Deseada	COMIBOL	5319.59	4966.51	4505.25	0.70	47			2.31
Deseada	COMIBOL	5320.58	5011.71	4435.75	0.70	150			13.26
Deseada	COMIBOL	5321.16	4966.53	4505.25	0.70	193			3.49
Deseada	COMIBOL	5323.27	4966.56	4505.25	0.70	55			0.31
Deseada	COMIBOL	5323.44	5011.80	4435.75	0.70	97			
Deseada	COMIBOL	5325.77	5011.87	4435.75	0.70	124			19.55
Deseada	COMIBOL	5325.79	4966.59	4505.25	0.70	43			2.38
Deseada	COMIBOL	5327.95	5011.93	4435.75	0.70	286			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	5328.01	4966.53	4505.25	0.70	130	5.70
Deseada	COMIBOL	5329.85	5012.29	4435.75	0.70	150	10.13
Deseada	COMIBOL	5329.86	4966.37	4505.25	0.70	103	2.02
Deseada	COMIBOL	5331.68	4965.95	4505.25	0.70	229	11.25
Deseada	COMIBOL	5332.14	5012.75	4435.75	0.70	559	26.75
Deseada	COMIBOL	5334.46	4966.00	4505.25	0.70	246	10.78
Deseada	COMIBOL	5334.48	5013.22	4435.75	0.70	93	
Deseada	COMIBOL	5336.43	4965.86	4505.25	0.70	406	27.98
Deseada	COMIBOL	5336.51	5013.75	4435.75	0.70	280	24.75
Deseada	COMIBOL	5338.55	4965.80	4505.25	0.70	566	21.88
Deseada	COMIBOL	5338.84	5014.73	4435.75	0.70	193	
Deseada	COMIBOL	5341.04	5015.66	4435.75	0.70	238	27.85
Deseada	COMIBOL	5341.14	4965.72	4505.25	0.70	180	9.59
Deseada	COMIBOL	5342.79	4965.63	4505.25	0.70	395	21.15
Deseada	COMIBOL	5343.04	5016.23	4435.75	0.70	369	
Deseada	COMIBOL	5345.06	4965.43	4505.25	0.70	459	5.38
Deseada	COMIBOL	5345.16	5016.63	4435.75	0.70	210	12.92
Deseada	COMIBOL	5347.17	4965.25	4505.25	0.70	348	13.13
Deseada	COMIBOL	5347.53	5017.07	4435.75	0.70	210	14.06
Deseada	COMIBOL	5349.30	4965.06	4505.25	0.70	155	6.62
Deseada	COMIBOL	5349.93	5017.52	4435.75	0.70	229	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Deseada	COMIBOL	5351.38	4964.87	4505.25	0.70	100			2.09
Deseada	COMIBOL	5351.54	5017.73	4435.75	0.70	75			9.37
Deseada	COMIBOL	5353.66	4964.46	4505.25	0.70	112			1.86
Deseada	COMIBOL	5353.95	5017.91	4435.75	0.70	347			
Deseada	COMIBOL	5355.72	4964.10	4505.25	0.70	143			1.49
Deseada	COMIBOL	5356.03	5018.07	4435.75	0.70	179			17.29
Deseada	COMIBOL	5357.70	4963.74	4505.25	0.70	8			0.63
Deseada	COMIBOL	5358.21	5018.23	4435.75	0.70	257			
Deseada	COMIBOL	5359.80	4963.37	4505.25	0.70	75			2.95
Deseada	COMIBOL	5360.39	5018.39	4435.75	0.70	271			18.74
Deseada	COMIBOL	5361.90	4962.99	4505.25	0.70	166			5.60
Deseada	COMIBOL	5362.14	5018.52	4435.75	0.70	480			
Deseada	COMIBOL	5363.81	4962.62	4505.25	0.70	78			4.53
Deseada	COMIBOL	5364.49	5018.70	4435.75	0.70	583			25.44
Deseada	COMIBOL	5366.30	4962.09	4505.25	0.70	28			0.83
Deseada	COMIBOL	5366.68	5018.86	4435.75	0.70	243			
Deseada	COMIBOL	5368.17	4961.70	4505.25	0.70	115			1.58
Deseada	COMIBOL	5368.59	5019.02	4435.75	0.70	887			15.21
Deseada	COMIBOL	5369.84	4961.34	4505.25	0.70	38			2.29
Deseada	COMIBOL	5370.89	5019.22	4435.75	0.70	206			
Deseada	COMIBOL	5372.16	4960.85	4505.25	0.70	283			6.88
Deseada	COMIBOL	5372.90	5019.40	4435.75	0.70	871			28.36
Deseada	COMIBOL	5374.19	4960.47	4505.25	0.70	86			4.90
Deseada	COMIBOL	5374.93	5019.58	4435.75	0.70	434			
Deseada	COMIBOL	5376.31	4960.13	4505.25	0.70	159			6.76
Deseada	COMIBOL	5377.06	5019.77	4435.75	0.70	251			
Deseada	COMIBOL	5378.30	4959.81	4505.25	0.70	315			5.03
Deseada	COMIBOL	5379.23	5019.96	4435.75	0.70	79			16.86
Deseada	COMIBOL	5381.68	5020.04	4435.75	0.70	270			26.29
Deseada	COMIBOL	5383.43	5020.09	4435.75	0.70	283			16.70
Deseada	COMIBOL	5385.53	5020.15	4435.75	0.70	129			21.66
Deseada	COMIBOL	5387.56	5020.21	4435.75	0.70	270			15.47
Deseada	COMIBOL	5389.96	5020.04	4435.75	0.70	261			8.29
Deseada	COMIBOL	5391.92	5019.84	4435.75	0.70	234			18.57
Deseada	COMIBOL	5393.82	5019.65	4435.75	0.70	1,894			25.89
Deseada	COMIBOL	5395.95	5019.09	4435.75	0.70	386			28.36
Deseada	COMIBOL	5397.69	5018.30	4435.75	0.70	429			8.61
Deseada	COMIBOL	5399.70	5017.29	4435.75	0.70	141			17.01
Deseada	COMIBOL	5401.72	5016.20	4435.75	0.70	2,526			0.68
Deseada	COMIBOL	5403.81	5015.06	4435.75	0.70	1,644			19.40
Deseada	COMIBOL	5405.60	5014.10	4435.75	0.70	377			7.59
Deseada	COMIBOL	5407.64	5012.77	4435.75	0.70	771			2.47
Deseada	COMIBOL	5409.16	5011.67	4435.75	0.70	141			4.22
Deseada	COMIBOL	5411.20	5010.19	4435.75	0.70	594			14.23
Deseada	COMIBOL	5413.00	5009.13	4435.75	0.80	1,080			17.80

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Deseada	COMIBOL	5414.88	5008.13	4435.75	0.70	700			12.15
Deseada	COMIBOL	5417.21	5006.90	4435.75	0.90	1,910			19.10
Guernica2	PASB	5325.47	5578.30	4395.38	2.17	345	0.42	0.99	0.44
Guernica2	PASB	5329.34	5576.89	4395.31	1.27	53	0.10	0.48	0.21
Guernica2	PASB	5333.25	5575.30	4395.23	1.48	165	0.29	0.31	0.29
Guernica2	PASB	5337.15	5573.69	4395.20	2.33	53	0.10	0.48	0.21
Guernica2	PASB	5341.14	5572.00	4395.24	1.73	69	0.14	0.22	0.19
Guernica2	PASB	5344.81	5570.39	4395.30	2.00	116	0.36	0.16	0.17
Guernica2	PASB	5348.66	5568.62	4395.39	1.73	68	0.09	0.08	0.10
Guernica2	PASB	5352.25	5566.87	4395.39	1.11	102	0.16	0.09	0.17
Guernica2	PASB	5355.51	5564.70	4395.35	1.39	11	0.11	0.06	0.06
Guernica2	PASB	5358.78	5562.71	4395.32	1.50	40	0.15	0.13	0.14
Guernica2	PASB	5362.68	5560.51	4395.43	1.39	124	0.58	0.46	0.22
Guernica2	PASB	5366.22	5558.69	4395.52	2.12	17	0.20	0.09	0.11
Guernica2	PASB	5369.78	5557.06	4395.59	2.21	75	0.20	0.20	0.17
Guernica2	PASB	5373.54	5555.64	4395.59	1.75	53	0.12	0.17	0.17
Guernica2	PASB	5377.78	5554.54	4395.59	2.03	11	0.10	0.18	0.10
Guernica2	PASB	5382.10	5553.29	4395.59	1.68	89	0.07	0.27	0.07
Guernica2	PASB	5386.23	5552.44	4395.59	1.90	66	0.17	0.32	0.10
Guernica2	PASB	5390.04	5551.46	4395.66	1.95	88	0.12	0.16	0.16
Guernica2	PASB	5394.10	5550.26	4395.73	1.46	5	0.02	0.10	0.06

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	PASB	5398.16	5548.98	4395.77	1.54	14	0.12	0.14	0.14
Guernica2	PASB	5401.37	5547.98	4395.79	2.15	17	0.31	0.13	0.14
Guernica2	PASB	5405.04	5547.06	4395.79	1.94	29	0.06	0.24	0.19
Guernica2	PASB	5408.34	5546.97	4395.76	1.77	43	0.11	0.25	0.24
Guernica2	PASB	5412.75	5546.56	4395.74	1.87	94	0.16	0.16	0.21
Guernica2	PASB	5417.15	5546.04	4395.71	2.51	49	0.09	0.21	0.21
Guernica2	PASB	5421.36	5545.77	4395.67	2.09	72	0.09	0.17	0.16
Guernica2	PASB	5425.79	5545.58	4395.60	2.21	27	0.07	0.21	0.21
Guernica2	PASB	5429.67	5545.12	4395.68	1.77	84	0.05	0.17	0.22
Guernica2	PASB	5432.47	5545.06	4395.75	2.38	15	0.06	0.07	0.10
Guernica2	PASB	5435.72	5544.57	4395.83	1.66	19	0.03	0.08	0.10
Guernica2	PASB	5492.70	5540.53	4358.13	0.70	267	1.24	0.04	0.16
Guernica2	PASB	5497.34	5541.56	4358.13	1.60	568	0.54	0.07	0.09
Guernica2	PASB	5500.34	5542.28	4396.07	1.14	1,226	0.39	0.10	0.12
Guernica2	PASB	5501.46	5540.53	4358.13	0.70	355	0.67	0.04	0.19
Guernica2	PASB	5505.58	5540.02	4358.13	1.00	491	0.72	0.05	0.30
Guernica2	PASB	5508.04	5541.42	4396.24	1.12	87	0.10	0.05	0.12
Guernica2	PASB	5510.00	5538.47	4358.13	1.20	534	0.86	0.14	0.18
Guernica2	PASB	5512.05	5540.54	4396.24	1.40	824	0.73	0.10	0.11
Guernica2	PASB	5514.12	5537.96	4358.13	1.55	1,404	0.10	1.54	0.45
Guernica2	PASB	5516.20	5539.64	4396.25	1.79	161	0.24	0.06	0.08
Guernica2	PASB	5518.24	5537.96	4358.13	2.80	637	0.06	0.36	0.14
Guernica2	PASB	5520.96	5537.96	4396.36	1.20	362	0.41	0.08	0.13
Guernica2	PASB	5522.57	5537.44	4358.13	2.10	803	0.07	0.65	0.19
Guernica2	PASB	5525.35	5535.97	4396.53	1.88	759	0.40	0.10	0.10
Guernica2	PASB	5527.00	5536.93	4358.13	1.10	177	0.03	0.19	0.08
Guernica2	PASB	5530.32	5534.20	4396.49	0.98	23	0.11	0.06	0.09
Guernica2	PASB	5531.12	5535.90	4358.13	1.40	18	0.02	0.06	0.04
Guernica2	PASB	5535.24	5534.87	4358.13	1.35	16	0.01	0.01	0.05
Guernica2	PASB	5535.69	5532.32	4396.42	1.42	86	0.53	0.04	0.20
Guernica2	PASB	5539.26	5533.84	4358.13	1.05	65	0.02	0.13	0.07
Guernica2	PASB	5539.33	5531.05	4396.37	1.50	45	0.19	0.05	0.07
Guernica2	PASB	5543.05	5529.61	4396.34	1.39	163	0.27	0.06	0.09
Guernica2	PASB	5543.17	5532.29	4358.13	0.80	776	0.52	0.11	0.34
Guernica2	PASB	5546.70	5528.14	4396.30	0.85	14	0.13	0.04	0.11
Guernica2	PASB	5547.08	5530.75	4358.13	0.97	1,640	0.28	1.24	0.33
Guernica2	PASB	5550.51	5526.73	4396.36	1.16	67	0.17	0.05	0.05
Guernica2	PASB	5550.90	5529.72	4358.13	0.70	429	0.06	0.29	0.19
Guernica2	PASB	5554.18	5525.47	4396.50	1.12	66	0.11	0.05	0.08
Guernica2	PASB	5555.02	5528.69	4358.13	0.70	521	0.04	0.82	0.07
Guernica2	PASB	5558.33	5524.05	4396.65	1.35	75	0.27	0.06	0.10
Guernica2	PASB	5559.14	5527.14	4358.13	0.70	127	0.03	0.19	0.09
Guernica2	PASB	5561.73	5522.84	4396.68	1.28	431	1.04	0.07	0.27
Guernica2	PASB	5562.95	5525.60	4358.13	0.70	136	0.03	0.66	0.06
Guernica2	PASB	5565.53	5521.42	4396.59	1.38	928	0.73	0.10	0.20

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	PASB	5566.86	5524.05	4358.13	0.70	148	0.03	0.64	0.03
Guernica2	PASB	5567.99	5520.50	4396.54	1.54	131	0.27	0.06	0.19
Guernica2	PASB	5570.57	5522.51	4358.13	0.70	435	0.03	0.78	0.00
Guernica2	PASB	5574.59	5520.96	4358.13	0.70	552	0.14	0.70	0.21
Guernica2	PASB	5578.19	5519.42	4358.13	0.70	569	0.32	0.53	0.24
Guernica2	PASB	5581.90	5517.56	4358.13	0.70	874	0.23	0.72	0.44
Guernica2	PASB	5585.92	5516.33	4358.13	1.30	508	0.56	0.23	0.40
Guernica2	PASB	5590.04	5514.78	4358.13	1.30	386	0.32	0.33	0.22
Guernica2	PASB	5593.64	5513.75	4358.13	1.10	872	0.52	0.52	0.26
Guernica2	PASB	5597.76	5512.21	4358.13	1.30	432	0.48	0.25	0.21
Guernica2	PASB	5601.37	5511.18	4358.13	1.15	218	0.64	0.10	0.14
Guernica2	PASB	5605.49	5510.15	4358.13	1.10	752	2.06	1.28	0.88
Guernica2	PASB	5609.61	5508.81	4358.13	1.10	894	0.48	0.38	0.20
Guernica2	PASB	5613.21	5507.36	4358.13	0.70	36	0.31	0.09	0.09
Guernica2	PASB	5617.33	5505.51	4358.13	0.75	1,633	1.64	0.44	3.00
Guernica2	PASB	5621.04	5504.17	4358.13	1.20	1,152	1.44	0.72	1.28
Guernica2	PASB	5625.06	5502.94	4358.13	1.20	366	0.92	0.36	0.44
Guernica2	PASB	5629.18	5501.39	4358.13	0.90	1,770	1.16	0.30	0.30
Guernica2	PASB	5632.78	5500.36	4358.13	1.10	287	0.56	0.24	0.40
Guernica2	PASB	5636.90	5499.33	4358.13	1.30	230	0.34	0.20	0.19
Guernica2	PASB	5641.02	5497.79	4358.13	1.85	342	0.57	0.47	0.44

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	PASB	5645.14	5497.06	4358.13	1.75	220	1.11	0.38	0.43
Guernica2	PASB	5649.26	5496.24	4358.13	0.75	370	0.86	0.25	0.50
Guernica2	PASB	5653.38	5494.70	4358.13	0.70	94	1.40	0.06	0.30
Guernica2	PASB	5657.03	5493.58	4358.13	0.70	121	0.76	0.09	0.35
Guernica2	PASB	5660.78	5492.51	4358.13	0.85	353	1.57	0.29	0.79
Guernica2	PASB	5664.35	5491.28	4358.13	0.95	202	0.93	0.10	0.32
Guernica2	PASB	5666.13	5490.02	4396.96	1.00	384			0.08
Guernica2	PASB	5668.06	5489.28	4397.00	0.85	604			0.24
Guernica2	PASB	5668.13	5490.45	4358.13	1.39	546	2.50	0.19	0.72
Guernica2	PASB	5670.00	5488.63	4397.04	1.10	470			0.16
Guernica2	PASB	5671.98	5487.97	4397.08	1.22	3,044			0.24
Guernica2	PASB	5672.01	5489.26	4358.13	1.10	1,010	2.50	0.40	1.30
Guernica2	PASB	5673.99	5487.47	4397.12	0.90	424			0.11
Guernica2	PASB	5675.82	5486.49	4397.15	0.70	382			0.08
Guernica2	PASB	5675.82	5488.11	4358.13	1.10	2,060	2.50	0.28	0.73
Guernica2	PASB	5677.75	5485.74	4397.19	1.00	1,056			0.10
Guernica2	PASB	5679.63	5484.97	4397.22	0.70	1,037			0.24
Guernica2	PASB	5679.65	5487.13	4358.13	1.10	4,865	2.50	0.85	0.83
Guernica2	PASB	5681.46	5484.02	4397.19	0.70	410			0.10
Guernica2	PASB	5683.38	5483.28	4397.16	0.70	384			0.19
Guernica2	PASB	5683.63	5486.08	4358.13	0.80	4,865	2.43	0.57	1.07
Guernica2	PASB	5685.30	5482.49	4397.13	1.10	925			0.30
Guernica2	PASB	5686.83	5485.19	4358.13	0.70	4,865	1.51	0.59	0.27
Guernica2	PASB	5687.29	5481.91	4397.10	1.20	3,042			0.88
Guernica2	PASB	5689.25	5481.26	4397.07	0.85	933			0.20
Guernica2	PASB	5690.56	5484.04	4358.13	1.10	1,160	0.87	0.23	0.51
Guernica2	PASB	5691.16	5480.52	4397.06	0.70	765			0.15
Guernica2	PASB	5693.06	5479.76	4397.06	0.70	500			0.06
Guernica2	PASB	5693.89	5483.06	4358.13	0.85	1,115	1.22	0.21	0.82
Guernica2	PASB	5695.13	5479.35	4397.06	0.70	2,377			0.28
Guernica2	PASB	5697.04	5478.61	4397.06	1.10	1,020			0.12
Guernica2	PASB	5697.16	5481.53	4358.13	1.00	509	1.99	0.06	0.17
Guernica2	PASB	5700.61	5480.48	4358.13	0.80	232	1.70	0.11	0.34
Guernica2	PASB	5704.64	5478.97	4358.13	0.70	170	0.84	0.03	0.18
Guernica2	PASB	5708.08	5477.52	4358.13	0.70	17	0.04	0.01	0.02
Guernica2	PASB	5709.47	5473.12	4397.11	0.99	385	0.49	0.07	0.20
Guernica2	PASB	5711.27	5475.72	4358.13	0.70	148	0.62	0.04	0.11
Guernica2	PASB	5713.68	5471.62	4397.19	1.52	812	2.02	0.21	0.87
Guernica2	PASB	5715.08	5473.85	4358.13	0.70	1,260	1.54	0.30	0.93
Guernica2	PASB	5716.75	5470.43	4397.25	0.86	645	0.71	0.09	0.37
Guernica2	PASB	5718.07	5472.61	4358.13	0.70	162	0.15	0.02	0.07
Guernica2	PASB	5720.72	5468.93	4397.23	1.06	587	2.00	0.09	0.26
Guernica2	PASB	5720.88	5453.11	4438.09	0.70	8	0.05	0.02	0.20
Guernica2	PASB	5722.18	5471.42	4358.13	0.70	1,768	1.85	0.08	0.52
Guernica2	PASB	5723.82	5452.11	4437.89	0.70	1,226	0.82	0.13	2.46

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	PASB	5724.74	5467.66	4397.21	0.75	7	0.05	0.03	0.02
Guernica2	PASB	5726.35	5470.36	4358.13	0.70	235	0.40	0.03	0.50
Guernica2	PASB	5728.47	5450.79	4437.78	0.79	917	1.36	0.15	0.60
Guernica2	PASB	5728.59	5466.50	4397.19	0.82	512	0.25	0.07	0.67
Guernica2	PASB	5730.43	5468.96	4358.13	0.70	602	0.30	0.04	0.13
Guernica2	PASB	5732.37	5465.47	4397.20	0.74	345	0.70	0.07	0.40
Guernica2	PASB	5733.90	5449.61	4438.14	0.76	1,308	1.02	0.09	7.85
Guernica2	PASB	5733.90	5468.25	4358.13	0.88	4,840	1.18	0.16	0.87
Guernica2	PASB	5737.94	5467.27	4358.13	0.70	1,343	0.82	0.05	2.73
Guernica2	PASB	5738.09	5464.15	4397.34	1.38	210	0.60	0.06	0.09
Guernica2	PASB	5738.55	5448.27	4438.34	0.80	222	0.19	0.05	1.33
Guernica2	PASB	5739.98	5463.66	4397.38	1.05	1,752	0.63	0.07	0.65
Guernica2	PASB	5741.14	5463.04	4397.41	0.70	1,968			0.49
Guernica2	PASB	5741.88	5466.45	4358.13	0.70	338	0.40	0.03	0.15
Guernica2	PASB	5742.77	5447.15	4438.23	1.08	157	0.71	0.06	2.33
Guernica2	PASB	5743.05	5462.29	4397.46	0.70	844			0.15
Guernica2	PASB	5744.97	5461.54	4397.49	0.70	343			0.08
Guernica2	PASB	5745.40	5465.41	4358.13	0.70	713	0.65	0.06	1.25
Guernica2	PASB	5746.88	5460.79	4397.50	0.70	1,128			1.37
Guernica2	PASB	5747.16	5445.99	4438.12	1.04	3,342	2.50	0.43	10.81
Guernica2	PASB	5748.80	5459.95	4397.51	0.70	1,079			0.75

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	PASB	5748.83	5464.06	4358.13	0.70	4,865	1.17	0.13	6.58
Guernica2	PASB	5750.79	5459.40	4397.52	0.70	490			0.98
Guernica2	PASB	5751.88	5445.33	4437.91	1.13	242	0.31	0.07	0.50
Guernica2	PASB	5752.37	5462.70	4358.13	0.70	4,865	2.30	0.30	9.25
Guernica2	PASB	5752.78	5458.85	4397.53	0.70	513			0.21
Guernica2	PASB	5754.79	5458.36	4397.54	1.05	2,444			1.12
Guernica2	PASB	5756.07	5444.78	4437.73	1.13	840	1.61	0.13	2.22
Guernica2	PASB	5756.15	5461.70	4358.13	0.70	4,865	1.99	0.09	4.26
Guernica2	PASB	5756.91	5458.12	4397.55	0.70	2,027			3.57
Guernica2	PASB	5758.98	5457.73	4397.56	1.50	2,119			1.68
Guernica2	PASB	5760.06	5460.39	4358.13	0.70	3,231	1.37	0.08	2.73
Guernica2	PASB	5760.89	5456.98	4397.55	1.40	1,341			2.40
Guernica2	PASB	5760.95	5443.82	4437.95	1.24	29	0.05	0.05	2.16
Guernica2	PASB	5762.92	5456.47	4397.51	0.90	304			0.18
Guernica2	PASB	5763.84	5459.24	4358.13	0.70	113	0.74	0.01	0.06
Guernica2	PASB	5764.76	5443.00	4438.23	1.81	1,950	1.81	0.31	8.39
Guernica2	PASB	5764.91	5455.92	4397.47	0.80	2,369			4.50
Guernica2	PASB	5766.88	5455.28	4397.43	0.70	442			0.26
Guernica2	PASB	5767.74	5458.07	4358.13	0.70	283	0.63	0.03	0.40
Guernica2	PASB	5768.78	5442.04	4438.27	1.32	2,914	1.64	0.42	8.25
Guernica2	PASB	5768.92	5454.89	4397.39	0.70	2,686			2.29
Guernica2	PASB	5770.90	5454.28	4397.38	0.80	4,865			3.60
Guernica2	PASB	5771.47	5456.92	4358.13	0.90	538	0.35	0.04	1.01
Guernica2	PASB	5772.93	5453.79	4397.39	0.70	2,430			0.69
Guernica2	PASB	5773.82	5440.63	4438.11	0.91	924	2.50	1.14	1.84
Guernica2	PASB	5774.92	5453.23	4397.40	0.70	4,865			0.63
Guernica2	PASB	5775.29	5455.88	4358.13	0.70	1,509	0.78	0.02	0.91
Guernica2	PASB	5777.88	5439.10	4438.16	0.85	1,714	2.50	1.88	11.09
Guernica2	PASB	5779.47	5454.61	4358.13	0.70	137	0.70	0.02	0.38
Guernica2	PASB	5783.15	5437.44	4438.27	1.56	3,898	2.50	0.24	8.76
Guernica2	PASB	5783.39	5453.47	4358.13	1.00	3,050	1.23	0.04	4.72
Guernica2	PASB	5785.63	5449.12	4397.66	0.76	552	0.50	0.07	0.50
Guernica2	PASB	5787.39	5436.49	4438.22	1.41	539	0.82	0.10	3.04
Guernica2	PASB	5788.17	5451.41	4358.13	0.70	373			2.17
Guernica2	PASB	5788.72	5448.17	4397.73	1.08	2,627	2.50	0.06	0.83
Guernica2	PASB	5791.39	5435.72	4438.02	3.31	102	0.47	0.09	1.92
Guernica2	PASB	5791.47	5451.24	4358.13	1.00	2,410			6.01
Guernica2	PASB	5792.83	5447.03	4397.70	1.11	513	0.26	0.08	0.94
Guernica2	PASB	5795.18	5450.92	4358.13	0.70	139			0.19
Guernica2	PASB	5796.15	5434.82	4438.00	1.13	1,527	2.14	0.56	3.38
Guernica2	PASB	5796.64	5446.36	4397.68	1.43	365	0.28	0.14	3.58
Guernica2	PASB	5798.86	5448.18	4358.13	0.70	2,845			2.40
Guernica2	PASB	5799.67	5445.59	4397.66	1.10	747	1.13	0.18	1.39
Guernica2	PASB	5800.97	5447.12	4358.13	0.70	48			0.06
Guernica2	PASB	5803.50	5444.48	4397.69	1.11	494	0.70	0.18	1.66

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	PASB	5803.80	5433.28	4438.21	1.19	89	0.43	0.07	1.15
Guernica2	PASB	5803.82	5446.06	4358.13	1.30	158			0.51
Guernica2	PASB	5805.93	5445.60	4358.13	0.95	717			3.28
Guernica2	PASB	5806.71	5432.37	4438.18	1.03	607	0.58	0.18	7.56
Guernica2	PASB	5807.37	5443.20	4397.80	1.14	278	0.53	0.06	0.13
Guernica2	PASB	5808.11	5444.80	4358.13	1.25	524			2.22
Guernica2	PASB	5809.90	5444.07	4358.13	0.70	254			0.86
Guernica2	PASB	5811.27	5441.81	4397.90	0.70	813	0.46	0.10	2.19
Guernica2	PASB	5811.60	5430.84	4438.14	1.77	150	1.12	0.07	0.43
Guernica2	PASB	5812.08	5443.21	4358.13	1.00	399			5.50
Guernica2	PASB	5814.40	5442.34	4358.13	0.80	202			2.06
Guernica2	PASB	5814.87	5440.56	4397.89	1.02	386	0.61	0.09	0.66
Guernica2	PASB	5815.44	5429.63	4438.19	1.22	533	2.50	0.11	0.45
Guernica2	PASB	5817.04	5441.15	4358.13	0.70	1,760			1.71
Guernica2	PASB	5817.97	5439.38	4397.89	1.12	37	2.50	0.03	1.03
Guernica2	PASB	5818.49	5428.66	4438.32	1.52	741	1.56	0.44	3.60
Guernica2	PASB	5819.09	5440.49	4358.13	0.95	3,101			3.18
Guernica2	PASB	5821.47	5439.76	4358.13	0.80	4,243			8.23
Guernica2	PASB	5821.91	5437.80	4397.77	0.98	250	0.22	0.07	0.15
Guernica2	PASB	5823.37	5427.00	4438.50	1.09	1,420	1.58	0.33	3.02
Guernica2	PASB	5823.96	5437.72	4397.37	0.90	457			1.47

44

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	PASB	5824.55	5438.75	4358.13	1.20	653			1.13
Guernica2	PASB	5825.91	5437.07	4397.37	1.00	882			3.17
Guernica2	PASB	5826.48	5438.34	4358.13	0.70	103			0.31
Guernica2	PASB	5827.24	5425.38	4438.57	1.39	44	0.06	0.04	0.26
Guernica2	PASB	5827.86	5436.42	4397.37	1.00	650			0.72
Guernica2	PASB	5828.22	5437.72	4358.13	0.80	757			4.46
Guernica2	PASB	5829.77	5435.34	4397.37	1.00	1,468	0.03	0.08	11.25
Guernica2	PASB	5830.32	5437.35	4358.13	0.70	335			0.82
Guernica2	PASB	5831.47	5423.69	4438.64	1.26	282	0.84	0.19	0.66
Guernica2	PASB	5831.78	5435.34	4397.37	2.00	448	0.03	0.08	0.91
Guernica2	PASB	5832.17	5436.73	4358.13	0.85	165			0.35
Guernica2	PASB	5833.79	5434.89	4397.37	0.95	2,496			6.96
Guernica2	PASB	5833.82	5436.19	4358.13	0.70	19			0.21
Guernica2	PASB	5835.70	5435.62	4358.13	0.70	86			0.17
Guernica2	PASB	5835.80	5434.45	4397.37	1.00	314			1.00
Guernica2	PASB	5837.81	5434.01	4397.37	0.90	609			4.57
Guernica2	PASB	5837.86	5434.81	4358.13	0.90	794			1.49
Guernica2	PASB	5839.47	5434.41	4358.13	1.20	537			4.17
Guernica2	PASB	5839.77	5433.58	4397.37	0.80	113			1.96
Guernica2	PASB	5841.56	5434.11	4358.13	2.00	303			1.90
Guernica2	PASB	5841.82	5433.31	4397.38	0.75	332			5.79
Guernica2	PASB	5843.31	5433.49	4358.13	1.85	451			0.55
Guernica2	PASB	5843.79	5420.72	4438.51	1.55	203	1.41	0.25	1.52
Guernica2	PASB	5843.95	5433.04	4397.38	0.80	189			2.49
Guernica2	PASB	5845.11	5432.90	4358.13	1.00	398			0.63
Guernica2	PASB	5845.93	5432.47	4397.41	0.80	305			3.48
Guernica2	PASB	5846.90	5432.28	4358.13	1.65	263			0.28
Guernica2	PASB	5847.76	5420.09	4438.39	1.47	42	1.07	0.06	0.90
Guernica2	PASB	5848.18	5431.84	4397.44	0.90	240			1.64
Guernica2	PASB	5849.02	5431.80	4358.13	1.30	429			0.53
Guernica2	PASB	5850.16	5431.28	4397.46	0.90	343	0.06	0.07	2.56
Guernica2	PASB	5851.07	5431.25	4358.13	1.20	105			0.19
Guernica2	PASB	5851.10	5431.19	4358.16	1.20	4,865			4.76
Guernica2	PASB	5851.96	5419.10	4438.33	1.90	13	0.07	0.04	0.12
Guernica2	PASB	5852.14	5430.71	4397.48	0.85	343	0.06	0.07	1.60
Guernica2	PASB	5852.94	5430.58	4358.19	1.00	127	0.07	0.21	0.98
Guernica2	PASB	5854.13	5430.27	4397.50	1.00	345			4.44
Guernica2	PASB	5854.93	5430.02	4358.22	1.05	29			0.30
Guernica2	PASB	5855.96	5417.90	4438.34	0.70	1,160	0.38	0.10	0.14
Guernica2	PASB	5856.10	5429.82	4397.53	1.00	153			0.24
Guernica2	PASB	5856.91	5429.46	4358.26	1.00	426	0.09	0.17	0.40
Guernica2	PASB	5858.13	5429.48	4397.55	1.05	256			1.16
Guernica2	PASB	5858.96	5428.88	4358.26	1.00	707			0.38
Guernica2	PASB	5859.94	5416.69	4438.36	0.70	649	0.21	0.05	0.07
Guernica2	PASB	5860.16	5429.13	4397.57	1.00	414			0.04

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	PASB	5861.19	5427.34	4358.40	1.00	216	0.09	0.21	1.25
Guernica2	PASB	5862.19	5428.79	4397.59	1.00	161	0.05	0.17	1.71
Guernica2	PASB	5863.03	5426.40	4358.47	1.00	372			0.95
Guernica2	PASB	5863.95	5415.37	4438.36	0.70	528	0.22	0.07	0.12
Guernica2	PASB	5864.29	5428.64	4397.61	1.05	758	0.05	0.17	3.67
Guernica2	PASB	5864.85	5425.45	4358.62	1.00	814			10.18
Guernica2	PASB	5866.32	5428.30	4397.64	0.95	602			5.14
Guernica2	PASB	5866.61	5424.53	4358.64	0.80	333			5.56
Guernica2	PASB	5868.35	5427.95	4397.66	1.00	393			1.18
Guernica2	PASB	5868.56	5423.86	4358.76	1.00	25	0.16	0.16	0.81
Guernica2	PASB	5870.39	5427.61	4397.67	1.10	255			1.33
Guernica2	PASB	5870.47	5423.19	4358.83	1.00	163	0.16	0.16	0.73
Guernica2	PASB	5872.41	5427.26	4397.68	1.00	327	0.07	0.21	2.49
Guernica2	PASB	5872.45	5422.63	4358.91	1.35	1,820			0.66
Guernica2	PASB	5874.45	5426.92	4397.70	1.05	654			2.68
Guernica2	PASB	5874.48	5422.05	4358.98	2.30	3,173			0.56
Guernica2	PASB	5876.47	5421.28	4358.92	1.60	1,872			0.61
Guernica2	PASB	5876.53	5426.57	4397.72	0.80	500			8.42
Guernica2	PASB	5878.52	5426.04	4397.74	1.05	4,483			7.13
Guernica2	PASB	5879.09	5419.94	4358.88	1.90	1,400			3.73
Guernica2	PASB	5880.51	5425.50	4397.76	1.40	680	0.09	0.17	0.68

45

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	PASB	5881.11	5419.63	4358.88	1.95	529	0.11	0.25	1.12
Guernica2	PASB	5882.49	5424.88	4397.77	0.80	375			0.58
Guernica2	PASB	5883.07	5419.35	4358.83	1.65	4,357	0.11	0.25	1.36
Guernica2	PASB	5884.48	5424.35	4397.78	0.80	1,547			5.61
Guernica2	PASB	5885.12	5419.01	4358.79	1.40	1,685			3.80
Guernica2	PASB	5886.47	5424.07	4397.80	0.80	1,444	0.09	0.21	5.38
Guernica2	PASB	5887.17	5418.63	4358.74	1.45	4,865			7.42
Guernica2	PASB	5888.51	5424.18	4397.82	1.00	268			1.03
Guernica2	PASB	5889.24	5418.23	4358.70	1.50	794	0.06	0.24	1.55
Guernica2	PASB	5890.72	5423.37	4397.91	0.80	713			4.36
Guernica2	PASB	5891.23	5417.73	4358.65	1.00	112	0.06	0.24	0.11
Guernica2	PASB	5893.19	5417.07	4358.61	1.00	1,145			5.85
Guernica2	PASB	5893.56	5423.23	4397.97	1.05	89			1.71
Guernica2	PASB	5895.06	5416.21	4358.56	1.00	818			2.29
Guernica2	PASB	5896.65	5421.81	4397.60	0.80	52	0.16	0.09	0.57
Guernica2	PASB	5896.97	5415.45	4358.58	1.00	409			1.37
Guernica2	PASB	5898.02	5422.75	4398.04	1.00	1,219			9.15
Guernica2	PASB	5898.64	5421.46	4397.60	0.80	123	0.09	0.08	3.81
Guernica2	PASB	5898.87	5414.66	4358.60	1.00	458			1.09
Guernica2	PASB	5900.68	5421.09	4397.60	0.80	212	0.14	0.22	2.34
Guernica2	PASB	5900.81	5413.96	4358.63	1.65	3,170			1.73
Guernica2	PASB	5902.73	5420.72	4397.60	0.80	91	0.10	0.48	4.49
Guernica2	PASB	5902.75	5413.24	4358.67	0.80	173			0.44
Guernica2	PASB	5904.68	5412.54	4358.71	0.85	380	0.31	0.13	0.44
Guernica2	PASB	5904.77	5420.36	4397.60	0.80	141	0.42	0.99	2.85
Guernica2	PASB	5906.62	5411.84	4358.73	0.95	2,263	0.31	0.13	0.22
Guernica2	PASB	5908.55	5411.13	4358.75	1.00	275			0.70
Guernica2	PASB	5910.49	5410.43	4358.76	1.00	676			0.62
Guernica2	PASB	5912.43	5409.72	4358.85	1.05	349	0.12	0.14	0.71
Guernica2	PASB	5914.36	5409.02	4358.88	1.10	1,437	0.12	0.14	0.90
Guernica2	PASB	5916.47	5408.82	4358.92	0.80	235			0.63
Guernica2	PASB	5918.41	5408.10	4358.95	1.00	418			0.46
Guernica2	PASB	5920.17	5407.47	4358.95	0.90	1,062			1.83
Guernica2	PASB	5922.15	5407.04	4358.95	1.00	77			1.45
Guernica2	PASB	5924.09	5406.34	4358.95	1.00	17			0.01
Guernica2	PASB	5925.95	5405.65	4358.95	1.00	1,399			0.07
Guernica2	PASB	5927.97	5405.21	4358.95	0.80	75	0.02	0.10	0.04
Guernica2	PASB	5929.95	5404.78	4358.95	0.90	221	0.02	0.10	0.26
Guernica2	PASB	5932.00	5404.33	4358.95	1.15	1,214			0.57
Guernica2	PASB	5934.01	5403.90	4358.95	0.90	708			0.21
Guernica2	PASB	5937.87	5402.98	4358.95	0.95	55			0.06
Guernica2	PASB	5939.82	5402.42	4358.95	0.80	145			0.12
Guernica2	PASB	5941.80	5401.86	4358.95	0.80	534	0.12	0.16	0.08
Guernica2	PASB	5943.77	5401.25	4358.98	0.80	41	0.12	0.16	0.09
Guernica2	PASB	5945.79	5400.67	4359.03	0.95	1,754			1.71

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	PASB	5947.85	5399.94	4359.05	0.80	181			0.82
Guernica2	PASB	5949.71	5399.19	4359.09	0.80	262			0.16
Guernica2	PASB	5951.76	5398.87	4359.12	0.80	242			0.30
Guernica2	PASB	5953.83	5398.70	4359.16	0.80	25	0.17	0.32	0.03
Guernica2	PASB	5955.83	5398.20	4359.19	0.85	297	0.17	0.32	0.10
Guernica2	PASB	5957.83	5397.69	4359.23	0.80	122			0.06
Guernica2	PASB	5959.83	5396.91	4359.26	0.80	487			0.14
Guernica2	PASB	5961.75	5396.25	4359.29	0.80	13			0.05
Guernica2	PASB	5963.73	5395.69	4359.29	0.80	4,004			2.70
Guernica2	PASB	5965.72	5395.14	4359.29	0.80	1,244	0.07	0.27	0.80
Guernica2	PASB	5968.01	5394.52	4359.30	0.90	187	0.07	0.27	0.98
Guernica2	PASB	5969.93	5393.98	4359.31	0.80	191			0.37
Guernica2	PASB	5971.96	5393.65	4359.31	0.80	241			2.42
Guernica2	PASB	5973.99	5393.31	4359.32	0.70	1,057			1.93
Guernica2	PASB	5976.03	5392.98	4359.33	1.20	375			6.81
Guernica2	PASB	5978.06	5392.65	4359.33	1.00	275			4.35
Guernica2	PASB	5980.15	5392.31	4359.34	1.20	81			0.47
Guernica2	PASB	5982.14	5391.78	4359.34	1.10	123	0.10	0.18	2.70
Guernica2	PASB	5984.12	5391.24	4359.34	3.25	41	0.10	0.18	0.24
Guernica2	COMIBOL	5374.44	5519.75	4470.70	0.70	25			
Guernica2	COMIBOL	5376.49	5519.86	4470.70	0.70	36			

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	COMIBOL	5378.28	5519.95	4470.70	0.70	43			
Guernica2	COMIBOL	5380.09	5520.04	4470.70	0.70	19			
Guernica2	COMIBOL	5381.77	5520.12	4470.70	0.70	177			
Guernica2	COMIBOL	5383.57	5519.97	4470.70	0.70	9			
Guernica2	COMIBOL	5385.55	5519.73	4470.70	0.70	12			
Guernica2	COMIBOL	5387.49	5519.40	4470.70	1.10	1,130			
Guernica2	COMIBOL	5388.98	5518.72	4470.70	1.30	3,090			
Guernica2	COMIBOL	5390.63	5518.11	4470.70	0.70	1,450			
Guernica2	COMIBOL	5392.41	5518.11	4470.70	0.70	491			
Guernica2	COMIBOL	5394.28	5518.11	4470.70	0.70	1,310			
Guernica2	COMIBOL	5396.01	5518.11	4470.70	0.70	4,865			
Guernica2	COMIBOL	5397.79	5518.11	4470.70	0.70	1,334			
Guernica2	COMIBOL	5399.54	5518.11	4470.70	0.70	246			
Guernica2	COMIBOL	5401.51	5518.10	4470.70	0.70	934			
Guernica2	COMIBOL	5403.29	5518.05	4470.70	0.70	1,912			
Guernica2	COMIBOL	5404.86	5518.01	4470.70	0.70	805			
Guernica2	COMIBOL	5407.04	5517.99	4470.70	0.70	1,057			
Guernica2	COMIBOL	5408.58	5517.89	4470.70	0.70	1,140			
Guernica2	COMIBOL	5410.90	5517.64	4470.70	0.70	1,284			
Guernica2	COMIBOL	5412.92	5517.42	4470.70	0.85	280			
Guernica2	COMIBOL	5414.90	5517.46	4470.70	0.70	2,765			
Guernica2	COMIBOL	5416.99	5517.55	4470.70	0.70	1,379			
Guernica2	COMIBOL	5419.09	5517.61	4470.70	0.70	3,283			
Guernica2	COMIBOL	5421.07	5517.64	4470.70	0.80	4,865			
Guernica2	COMIBOL	5423.25	5517.67	4470.70	0.70	479			
Guernica2	COMIBOL	5425.30	5517.69	4470.70	0.70	1,182			
Guernica2	COMIBOL	5427.28	5517.59	4470.70	0.70	164			
Guernica2	COMIBOL	5429.46	5517.43	4470.70	0.70	73			
Guernica2	COMIBOL	5431.14	5523.92	4398.50	0.80	55			0.04
Guernica2	COMIBOL	5431.35	5517.29	4470.70	0.70	196			
Guernica2	COMIBOL	5432.74	5523.96	4398.50	1.50	420			0.30
Guernica2	COMIBOL	5433.31	5517.04	4470.70	0.70	4,865			
Guernica2	COMIBOL	5434.94	5523.93	4398.50	1.65	500			2.27
Guernica2	COMIBOL	5435.55	5516.74	4470.70	0.70	2,652			
Guernica2	COMIBOL	5436.89	5523.72	4398.50	0.80	263			
Guernica2	COMIBOL	5437.50	5516.35	4470.70	0.70	313			
Guernica2	COMIBOL	5438.84	5523.50	4398.50	0.80	630			
Guernica2	COMIBOL	5439.36	5515.76	4470.70	0.70	3,522			
Guernica2	COMIBOL	5440.77	5523.29	4398.50	0.80	413			
Guernica2	COMIBOL	5441.21	5515.18	4470.70	0.70	60			
Guernica2	COMIBOL	5442.70	5523.20	4398.50	0.80	3,427			
Guernica2	COMIBOL	5443.37	5514.49	4470.70	0.70	64			
Guernica2	COMIBOL	5444.77	5523.11	4398.50	0.80	592			
Guernica2	COMIBOL	5445.14	5513.92	4470.70	0.70	420			
Guernica2	COMIBOL	5447.04	5513.32	4470.70	0.70	24			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	COMIBOL	5449.20	5512.43	4470.70	0.70	5	
Guernica2	COMIBOL	5451.31	5511.41	4470.70	0.70	84	
Guernica2	COMIBOL	5452.58	5523.46	4358.13	1.60	568	0.09
Guernica2	COMIBOL	5452.67	5522.54	4398.50	0.85	2,290	
Guernica2	COMIBOL	5452.82	5511.03	4470.70	0.80	160	
Guernica2	COMIBOL	5454.81	5522.20	4398.50	0.80	3,860	
Guernica2	COMIBOL	5454.84	5510.86	4470.70	1.00	860	
Guernica2	COMIBOL	5456.23	5523.37	4358.13	0.70	355	0.19
Guernica2	COMIBOL	5456.75	5521.89	4398.50	0.80	830	
Guernica2	COMIBOL	5456.84	5510.69	4470.70	0.70	23	
Guernica2	COMIBOL	5456.84	5523.33	4359.66	1.20	132	
Guernica2	COMIBOL	5456.84	5523.33	4361.90	1.20	289	
Guernica2	COMIBOL	5456.84	5523.33	4364.13	1.20	527	
Guernica2	COMIBOL	5456.84	5523.33	4366.06	1.20	532	
Guernica2	COMIBOL	5456.84	5523.33	4368.60	1.20	114	
Guernica2	COMIBOL	5456.84	5523.33	4370.60	1.20	166	
Guernica2	COMIBOL	5456.84	5523.33	4373.07	1.20	309	
Guernica2	COMIBOL	5456.84	5523.33	4375.15	1.20	186	
Guernica2	COMIBOL	5456.84	5523.33	4376.85	1.20	374	
Guernica2	COMIBOL	5456.84	5523.33	4379.62	1.20	165	
Guernica2	COMIBOL	5456.84	5523.33	4381.62	1.20	125	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	COMIBOL	5456.84	5523.33	4383.55	1.20	120			
Guernica2	COMIBOL	5456.84	5523.33	4386.17	1.20	138			
Guernica2	COMIBOL	5456.84	5523.33	4388.33	1.20	201			
Guernica2	COMIBOL	5456.84	5523.33	4390.87	1.20	148			
Guernica2	COMIBOL	5456.84	5523.33	4392.80	1.20	112			
Guernica2	COMIBOL	5456.84	5523.33	4395.03	1.20	86			
Guernica2	COMIBOL	5456.84	5523.33	4397.58	1.20	71			
Guernica2	COMIBOL	5458.68	5521.57	4398.50	0.80	120			
Guernica2	COMIBOL	5458.79	5510.47	4470.70	0.70	378			
Guernica2	COMIBOL	5460.54	5510.19	4470.70	0.70	185			
Guernica2	COMIBOL	5460.68	5521.13	4398.50	1.55	2,100			
Guernica2	COMIBOL	5460.69	5523.12	4358.13	1.00	491			0.30
Guernica2	COMIBOL	5462.57	5509.87	4470.70	0.70	338			
Guernica2	COMIBOL	5462.73	5520.67	4398.50	0.80	160			
Guernica2	COMIBOL	5464.53	5509.55	4470.70	0.70	239			
Guernica2	COMIBOL	5464.65	5520.25	4398.50	0.80	260			
Guernica2	COMIBOL	5464.91	5521.87	4358.13	1.20	534			0.18
Guernica2	COMIBOL	5466.41	5509.25	4470.70	0.70	97			
Guernica2	COMIBOL	5466.43	5519.85	4398.50	1.10	920			0.42
Guernica2	COMIBOL	5468.37	5521.36	4358.13	1.55	1,404			0.45
Guernica2	COMIBOL	5468.43	5508.97	4470.70	0.70	146			
Guernica2	COMIBOL	5468.47	5519.31	4398.50	1.40	420			2.06
Guernica2	COMIBOL	5470.11	5518.84	4398.50	0.80	810			1.23
Guernica2	COMIBOL	5470.18	5508.75	4470.70	0.70	189			
Guernica2	COMIBOL	5472.12	5518.26	4398.50	0.80	427			0.63
Guernica2	COMIBOL	5472.24	5508.30	4470.70	0.70	318			
Guernica2	COMIBOL	5472.38	5521.31	4358.13	2.80	637			0.14
Guernica2	COMIBOL	5473.89	5507.40	4470.70	0.70	175			
Guernica2	COMIBOL	5473.97	5517.73	4398.50	1.80	950			0.04
Guernica2	COMIBOL	5475.53	5506.52	4470.70	0.70	690			
Guernica2	COMIBOL	5475.92	5517.07	4398.50	0.80	50			0.11
Guernica2	COMIBOL	5476.98	5521.15	4358.13	2.10	803			0.19
Guernica2	COMIBOL	5477.19	5505.62	4470.70	0.70	43			
Guernica2	COMIBOL	5477.82	5516.35	4398.50	0.80	1,137			0.48
Guernica2	COMIBOL	5478.94	5504.69	4470.70	0.70	769			
Guernica2	COMIBOL	5479.87	5515.58	4398.50	0.80	338			0.18
Guernica2	COMIBOL	5480.76	5503.73	4470.70	0.70	432			
Guernica2	COMIBOL	5480.99	5520.65	4358.13	1.10	177			0.08
Guernica2	COMIBOL	5481.69	5514.90	4398.50	0.80	28			0.82
Guernica2	COMIBOL	5482.67	5502.72	4470.70	0.70	555			
Guernica2	COMIBOL	5483.48	5514.23	4398.50	0.80	218			0.16
Guernica2	COMIBOL	5484.12	5501.96	4470.70	0.70	157			
Guernica2	COMIBOL	5485.26	5513.66	4398.50	0.80	54			0.05
Guernica2	COMIBOL	5485.98	5501.03	4470.70	0.70	297			
Guernica2	COMIBOL	5487.49	5500.37	4470.70	0.70	522			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	COMIBOL	5489.51	5499.48	4470.70	0.70	302	
Guernica2	COMIBOL	5496.02	5496.91	4470.70	0.70	75	
Guernica2	COMIBOL	5498.40	5496.22	4470.70	0.70	183	
Guernica2	COMIBOL	5500.65	5495.57	4470.70	1.00	4,400	
Guernica2	COMIBOL	5502.78	5494.97	4470.70	1.00	760	
Guernica2	COMIBOL	5505.06	5494.32	4470.70	0.90	1,026	
Guernica2	COMIBOL	5507.44	5493.75	4470.70	1.05	870	
Guernica2	COMIBOL	5510.07	5493.20	4470.70	1.95	1,444	
Guernica2	COMIBOL	5588.51	5481.59	4398.50	0.80	4,394	1.51
Guernica2	COMIBOL	5590.31	5481.51	4398.50	0.80	4,865	2.75
Guernica2	COMIBOL	5592.32	5481.11	4398.50	0.80	3,180	3.68
Guernica2	COMIBOL	5594.29	5480.71	4398.50	1.00	3,070	2.10
Guernica2	COMIBOL	5594.79	5468.50	4435.85	0.82	2,122	0.90
Guernica2	COMIBOL	5596.27	5480.31	4398.50	0.80	660	0.19
Guernica2	COMIBOL	5598.03	5479.80	4398.50	0.80	328	0.08
Guernica2	COMIBOL	5599.62	5479.26	4398.50	0.80	653	0.23
Guernica2	COMIBOL	5601.78	5478.54	4398.50	0.80	100	0.16
Guernica2	COMIBOL	5614.78	5475.16	4398.50	0.80	660	0.29
Guernica2	COMIBOL	5615.13	5459.74	4435.85	0.80	408	0.10
Guernica2	COMIBOL	5616.65	5474.69	4398.50	0.80	1,415	1.45
Guernica2	COMIBOL	5617.08	5459.15	4435.85	0.80	832	0.28

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	COMIBOL	5618.45	5474.24	4398.50	0.80	1,616			1.88
Guernica2	COMIBOL	5618.97	5458.58	4435.85	0.80	478			0.17
Guernica2	COMIBOL	5620.35	5473.77	4398.50	0.80	1,630			0.17
Guernica2	COMIBOL	5620.80	5458.02	4435.85	0.80	2,465			0.18
Guernica2	COMIBOL	5622.12	5473.16	4398.50	0.80	1,952			0.77
Guernica2	COMIBOL	5622.61	5457.20	4435.85	0.80	280			0.11
Guernica2	COMIBOL	5623.78	5472.51	4398.50	0.80	321			0.29
Guernica2	COMIBOL	5624.34	5456.41	4435.85	0.80	432			0.10
Guernica2	COMIBOL	5625.67	5471.77	4398.50	0.80	550			0.64
Guernica2	COMIBOL	5626.14	5455.59	4435.85	0.80	2,771			0.12
Guernica2	COMIBOL	5627.30	5471.14	4398.50	0.80	110			0.12
Guernica2	COMIBOL	5628.05	5454.81	4435.85	0.80	1,403			0.34
Guernica2	COMIBOL	5629.14	5470.42	4398.50	0.80	86			0.22
Guernica2	COMIBOL	5630.01	5454.05	4435.85	0.80	400			0.17
Guernica2	COMIBOL	5630.78	5469.76	4398.50	0.80	2,985			0.36
Guernica2	COMIBOL	5631.77	5453.38	4435.85	0.80	488			0.20
Guernica2	COMIBOL	5632.58	5469.04	4398.50	0.80	1,500			0.25
Guernica2	COMIBOL	5633.58	5452.71	4435.85	1.00	554			0.30
Guernica2	COMIBOL	5634.39	5468.32	4398.50	0.80	1,330			0.27
Guernica2	COMIBOL	5635.30	5452.08	4435.85	1.20	2,657			0.88
Guernica2	COMIBOL	5636.24	5467.58	4398.50	0.80	503			0.19
Guernica2	COMIBOL	5637.28	5451.37	4435.85	1.10	578			0.18
Guernica2	COMIBOL	5637.66	5467.01	4398.50	1.00	750			0.85
Guernica2	COMIBOL	5639.51	5450.77	4435.85	0.80	1,138			0.20
Guernica2	COMIBOL	5639.72	5466.25	4398.50	1.00	940			6.15
Guernica2	COMIBOL	5641.32	5450.28	4435.85	0.80	530			0.14
Guernica2	COMIBOL	5641.38	5465.70	4398.50	1.10	904			2.17
Guernica2	COMIBOL	5643.21	5449.66	4435.85	0.80	1,557			0.15
Guernica2	COMIBOL	5643.34	5465.07	4398.50	0.80	930			0.25
Guernica2	COMIBOL	5644.96	5448.97	4435.85	0.80	452			0.10
Guernica2	COMIBOL	5645.07	5464.50	4398.50	0.80	500			0.20
Guernica2	COMIBOL	5646.50	5448.37	4435.85	0.90	4,865			7.68
Guernica2	COMIBOL	5646.82	5463.93	4398.50	0.80	500			0.20
Guernica2	COMIBOL	5648.30	5447.66	4435.85	0.70	4,865			
Guernica2	COMIBOL	5648.60	5463.40	4398.50	0.80	602			0.18
Guernica2	COMIBOL	5649.74	5447.10	4435.85	0.70	330			2.66
Guernica2	COMIBOL	5650.69	5462.81	4398.50	0.80	678			0.22
Guernica2	COMIBOL	5651.44	5446.44	4435.85	0.70	651			
Guernica2	COMIBOL	5652.18	5462.28	4398.50	0.80	420			0.48
Guernica2	COMIBOL	5653.01	5445.82	4435.85	0.90	1,200			6.50
Guernica2	COMIBOL	5654.54	5434.84	4506.00	0.70	73			
Guernica2	COMIBOL	5654.60	5445.36	4435.85	0.70	621			
Guernica2	COMIBOL	5656.27	5444.90	4435.85	0.70	1,836			3.80
Guernica2	COMIBOL	5656.82	5434.24	4506.00	0.70	20			
Guernica2	COMIBOL	5657.81	5444.48	4435.85	0.70	189			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	COMIBOL	5658.83	5433.47	4506.00	0.70	19	
Guernica2	COMIBOL	5659.45	5443.94	4435.85	0.70	86	1.63
Guernica2	COMIBOL	5660.60	5432.67	4506.00	0.70	12	
Guernica2	COMIBOL	5660.97	5443.31	4435.85	0.70	47	
Guernica2	COMIBOL	5662.45	5442.68	4435.85	0.70	64	1.98
Guernica2	COMIBOL	5662.58	5431.81	4506.00	0.70	30	
Guernica2	COMIBOL	5663.89	5442.09	4435.85	0.70	560	
Guernica2	COMIBOL	5664.29	5431.25	4506.00	0.70	1	
Guernica2	COMIBOL	5665.63	5441.37	4435.85	0.80	3,610	12.13
Guernica2	COMIBOL	5666.45	5430.55	4506.00	0.70	36	
Guernica2	COMIBOL	5667.21	5440.85	4435.85	0.70	309	
Guernica2	COMIBOL	5668.15	5430.00	4506.00	0.80	72	
Guernica2	COMIBOL	5668.70	5440.37	4435.85	0.70	180	1.56
Guernica2	COMIBOL	5670.22	5439.87	4435.85	0.70	167	1.36
Guernica2	COMIBOL	5670.61	5429.29	4506.00	0.70	2	
Guernica2	COMIBOL	5671.96	5439.32	4435.85	0.70	77	
Guernica2	COMIBOL	5672.31	5428.81	4506.00	0.70	30	
Guernica2	COMIBOL	5673.68	5438.92	4435.85	0.70	386	1.44
Guernica2	COMIBOL	5674.46	5428.24	4506.00	0.70	2	
Guernica2	COMIBOL	5675.23	5438.55	4435.85	0.70	300	
Guernica2	COMIBOL	5675.51	5453.36	4401.55	0.80	710	0.28

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	COMIBOL	5675.51	5453.36	4403.71	0.80	667			0.47
Guernica2	COMIBOL	5675.51	5453.36	4405.79	0.80	1,477			1.88
Guernica2	COMIBOL	5675.51	5453.36	4407.64	0.80	3,144			5.47
Guernica2	COMIBOL	5675.51	5453.36	4410.03	0.80	2,020			3.75
Guernica2	COMIBOL	5675.51	5453.36	4412.03	0.80	380			1.55
Guernica2	COMIBOL	5675.51	5453.36	4414.11	0.80	281			1.12
Guernica2	COMIBOL	5675.51	5453.36	4416.27	0.80	417			0.56
Guernica2	COMIBOL	5675.51	5453.36	4418.12	0.80	2,750			0.69
Guernica2	COMIBOL	5675.51	5453.36	4420.20	0.80	947			0.34
Guernica2	COMIBOL	5675.51	5453.36	4422.21	0.80	1,380			0.52
Guernica2	COMIBOL	5675.51	5453.36	4424.59	0.80	75			0.27
Guernica2	COMIBOL	5675.51	5453.36	4426.60	0.80	37			0.18
Guernica2	COMIBOL	5675.51	5453.36	4428.68	0.80	67			0.10
Guernica2	COMIBOL	5675.51	5453.36	4430.45	0.80	37			0.40
Guernica2	COMIBOL	5675.51	5453.36	4432.84	0.80	80			0.11
Guernica2	COMIBOL	5675.51	5453.36	4434.92	0.80	35			0.06
Guernica2	COMIBOL	5676.28	5427.88	4506.00	0.70	18			
Guernica2	COMIBOL	5676.80	5438.18	4435.85	0.70	371			2.90
Guernica2	COMIBOL	5678.12	5427.53	4506.00	0.70	2			
Guernica2	COMIBOL	5678.65	5437.74	4435.85	0.70	157			
Guernica2	COMIBOL	5680.11	5437.38	4435.85	0.70	209			1.87
Guernica2	COMIBOL	5680.26	5427.11	4506.00	0.70	7			
Guernica2	COMIBOL	5681.90	5436.94	4435.85	0.70	657			
Guernica2	COMIBOL	5682.38	5426.62	4506.00	0.70	5			
Guernica2	COMIBOL	5683.58	5436.67	4435.85	0.70	697			3.79
Guernica2	COMIBOL	5684.45	5426.14	4506.00	0.70	5			
Guernica2	COMIBOL	5685.08	5436.23	4435.85	0.80	2,843			0.60
Guernica2	COMIBOL	5686.35	5425.70	4506.00	0.70	2			
Guernica2	COMIBOL	5687.44	5435.20	4435.85	0.80	1,109			0.28
Guernica2	COMIBOL	5688.15	5425.37	4506.00	0.70	12			
Guernica2	COMIBOL	5689.35	5434.41	4435.85	0.80	590			0.11
Guernica2	COMIBOL	5690.36	5425.06	4506.00	0.70	6			
Guernica2	COMIBOL	5691.47	5434.29	4435.85	0.80	1,476			1.72
Guernica2	COMIBOL	5692.42	5449.02	4398.50	0.80	491			0.44
Guernica2	COMIBOL	5693.87	5434.15	4435.85	0.80	564			0.40
Guernica2	COMIBOL	5694.39	5448.31	4398.50	0.80	2,790			2.20
Guernica2	COMIBOL	5695.73	5434.04	4435.85	0.80	747			1.72
Guernica2	COMIBOL	5696.08	5447.74	4398.50	0.80	2,553			0.75
Guernica2	COMIBOL	5697.96	5433.61	4435.85	0.80	429			0.16
Guernica2	COMIBOL	5700.26	5433.13	4435.85	0.80	1,857			1.12
Guernica2	COMIBOL	5702.36	5432.70	4435.85	0.80	3,490			3.00
Guernica2	COMIBOL	5704.41	5432.33	4435.85	0.80	2,737			2.40
Guernica2	COMIBOL	5706.59	5431.98	4435.85	0.80	1,042			1.96
Guernica2	COMIBOL	5708.75	5431.63	4435.85	0.80	240			0.14
Guernica2	COMIBOL	5760.29	5418.02	4470.70	0.70	25			

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Guernica2	COMIBOL	5762.65	5417.99	4470.70	0.70	31	
Guernica2	COMIBOL	5765.04	5417.92	4470.70	0.70	66	
Guernica2	COMIBOL	5766.70	5417.68	4470.70	0.70	70	
Guernica2	COMIBOL	5768.72	5417.39	4470.70	0.70	192	
Guernica2	COMIBOL	5769.26	5428.90	4398.50	0.80	632	1.97
Guernica2	COMIBOL	5770.81	5417.08	4470.70	0.70	10	
Guernica2	COMIBOL	5770.99	5428.40	4398.50	0.80	444	5.13
Guernica2	COMIBOL	5772.80	5416.74	4470.70	0.70	17	
Guernica2	COMIBOL	5772.98	5427.83	4398.50	0.80	125	1.70
Guernica2	COMIBOL	5774.58	5416.29	4470.70	0.70	75	
Guernica2	COMIBOL	5776.58	5415.79	4470.70	0.70	79	
Guernica2	COMIBOL	5778.60	5415.29	4470.70	0.70		
Guernica2	COMIBOL	5780.50	5414.99	4470.70	0.70	19	0.14
Guernica2	COMIBOL	5782.45	5414.68	4470.70	0.70		
Guernica2	COMIBOL	5784.56	5414.34	4470.70	0.70	311	2.36
Guernica2	COMIBOL	5786.50	5414.43	4470.70	0.70		
Guernica2	COMIBOL	5788.35	5414.63	4470.70	0.70	14	0.12
Guernica2	COMIBOL	5790.51	5414.85	4470.70	0.70	2	
Guernica2	COMIBOL	5792.83	5414.90	4470.70	0.70	86	0.41
Guernica2	COMIBOL	5794.74	5414.88	4470.70	0.70	93	
Guernica2	COMIBOL	5796.71	5414.86	4470.70	0.70	2	0.06

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Guernica2	COMIBOL	5798.49	5414.84	4470.70	0.70				
Guernica2	COMIBOL	5800.57	5414.44	4470.70	0.70	2			
Litoral	PASB	5624.96	5049.93	4437.61	4.45	573	0.76	0.02	3.60
Litoral	PASB	5635.11	5045.90	4397.61	4.45	483	0.40	0.06	3.71
Litoral	PASB	5667.41	5057.09	4357.50	1.70	106			3.15
Litoral	PASB	5669.53	5057.52	4357.50	1.90	59			2.16
Litoral	PASB	5669.86	5077.86	4467.61	3.97	239	0.23	0.10	14.42
Litoral	PASB	5670.79	5058.69	4357.57	2.00	385			1.89
Litoral	PASB	5673.02	5060.05	4357.57	2.10	530			0.99
Litoral	PASB	5674.83	5061.65	4357.57	2.85	1,683			0.61
Litoral	PASB	5677.39	5063.10	4357.68	2.80	905			1.69
Litoral	PASB	5679.15	5063.94	4357.68	3.30	670			0.85
Litoral	PASB	5681.08	5064.66	4357.75	1.95	452			0.79
Litoral	PASB	5682.92	5065.70	4357.78	1.50	188			2.64
Litoral	PASB	5684.60	5066.74	4357.78	1.60	292			11.79
Litoral	PASB	5686.53	5067.58	4357.84	2.00	271			8.21
Litoral	PASB	5688.81	5068.50	4357.84	1.75	266			8.31
Litoral	PASB	5690.72	5069.36	4357.86	2.00	207			4.96
Litoral	PASB	5692.58	5069.81	4357.86	1.55	179			9.25
Litoral	PASB	5694.94	5069.86	4357.86	1.30	1,355			13.15
Litoral	PASB	5697.35	5070.28	4357.86	0.80	73			0.41
Litoral	PASB	5699.63	5071.17	4357.86	2.45	582			2.34
Litoral	PASB	5701.67	5071.89	4357.86	2.20	516			0.56
Litoral	PASB	5702.86	5083.28	4397.61	4.42	1,784	0.54	0.05	2.46
Litoral	PASB	5703.01	5084.72	4437.61	3.22	1,068	0.76	0.10	6.55
Litoral	PASB	5703.67	5072.64	4357.86	2.50	92			0.54
Litoral	PASB	5705.60	5073.40	4357.86	1.90	387			0.57
Litoral	PASB	5709.12	5074.32	4357.86	1.55	125			2.25
Litoral	PASB	5711.08	5074.90	4357.86	2.80	388			1.51
Litoral	PASB	5712.94	5075.81	4357.86	1.85	230			4.16
Litoral	PASB	5714.84	5076.72	4357.86	1.75	639			5.48
Litoral	PASB	5716.78	5077.34	4357.86	1.90	1,099			2.69
Litoral	PASB	5718.71	5078.01	4357.86	1.50	311			3.64
Litoral	PASB	5721.27	5078.26	4357.86	1.10	276			0.64
Litoral	PASB	5727.22	5081.76	4357.86	1.00	97			2.41
Litoral	PASB	5729.04	5082.79	4357.86	1.30	188			7.21
Litoral	PASB	5730.88	5083.68	4357.86	1.90	131			3.63
Litoral	PASB	5733.77	5084.65	4357.86	2.65	213			5.85
Litoral	PASB	5735.62	5085.84	4357.86	1.60	252			2.50
Litoral	PASB	5737.43	5086.51	4357.97	2.30	206			2.38
Litoral	PASB	5738.73	5095.05	4397.61	1.50	204	0.33	0.02	1.16
Litoral	PASB	5739.41	5087.15	4357.97	2.00	245			0.90
Litoral	PASB	5741.72	5087.85	4358.05	1.10	155			5.72
Litoral	PASB	5743.31	5088.62	4358.05	1.70	582			1.58
Litoral	PASB	5745.22	5089.65	4358.11	3.50	668			0.69

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Litoral	PASB	5747.10	5090.57	4358.11	1.50	310	3.64
Litoral	PASB	5748.92	5091.42	4358.22	1.50	356	1.40
Litoral	PASB	5750.82	5092.14	4358.26	1.40	212	0.64
Litoral	PASB	5752.84	5092.90	4358.29	1.00	63	0.40
Litoral	PASB	5754.71	5093.61	4358.33	0.80	202	0.18
Litoral	PASB	5758.02	5094.78	4358.33	1.50	72	0.30
Litoral	PASB	5759.99	5095.48	4358.37	1.20	149	0.38
Litoral	PASB	5763.91	5096.65	4358.37	1.90	53	0.51
Litoral	PASB	5765.84	5097.51	4358.37	1.40	23	0.46
Litoral	PASB	5767.71	5098.32	4358.37	1.50	54	0.42
Litoral	PASB	5769.66	5099.03	4358.37	1.10	7	0.14
Litoral	PASB	5771.63	5099.90	4358.37	0.80	10	0.12
Litoral	PASB	5773.59	5100.71	4358.37	0.90	4	0.08
Litoral	PASB	5775.44	5101.55	4358.37	1.00	2	0.08
Litoral	PASB	5777.38	5102.40	4358.37	1.40	33	0.24
Litoral	PASB	5779.27	5103.49	4358.37	1.10	195	2.78
Litoral	PASB	5781.12	5104.60	4358.37	0.85	162	0.91
Litoral	PASB	5782.78	5105.78	4358.39	1.00	1	0.14
Litoral	PASB	5784.51	5106.89	4358.39	1.25	3	0.49
Litoral	PASB	5786.38	5107.82	4358.39	0.80	5	0.25
Litoral	COMIBOL	5435.70	4995.62	4473.75	1.50	65	1.52

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Litoral	COMIBOL	5437.51	4996.37	4473.75	1.50	532			4.28
Litoral	COMIBOL	5439.42	4997.32	4473.75	1.50	120			4.70
Litoral	COMIBOL	5441.27	4998.45	4473.75	1.50	208			4.91
Litoral	COMIBOL	5442.99	4999.50	4473.75	1.50	352			8.14
Litoral	COMIBOL	5444.87	5000.23	4473.75	1.50	427			6.46
Litoral	COMIBOL	5446.73	5000.92	4473.75	1.50	222			3.34
Litoral	COMIBOL	5448.72	5001.66	4473.75	1.50	582			3.57
Litoral	COMIBOL	5450.62	5002.45	4473.75	1.50	987			16.50
Litoral	COMIBOL	5452.64	5003.30	4473.75	1.50	35			2.57
Litoral	COMIBOL	5454.46	5004.08	4473.75	1.50	528			12.82
Litoral	COMIBOL	5456.38	5004.88	4473.75	1.50	70			2.50
Litoral	COMIBOL	5458.16	5005.70	4473.75	1.50	32			13.83
Litoral	COMIBOL	5460.09	5006.64	4473.75	1.50	27			2.93
Litoral	COMIBOL	5461.82	5007.58	4473.75	1.50	4			0.97
Litoral	COMIBOL	5498.37	5028.68	4439.00	1.50	308			13.97
Litoral	COMIBOL	5499.94	5029.80	4439.00	1.50	240			
Litoral	COMIBOL	5501.66	5030.87	4439.00	1.50	342			23.78
Litoral	COMIBOL	5503.59	5031.66	4439.00	1.50	128			
Litoral	COMIBOL	5505.34	5032.38	4439.00	1.50	114			8.02
Litoral	COMIBOL	5507.33	5033.21	4439.00	1.50	195			
Litoral	COMIBOL	5509.12	5034.01	4439.00	1.50	312			16.40
Litoral	COMIBOL	5511.02	5034.86	4439.00	1.50	400			
Litoral	COMIBOL	5512.80	5035.71	4439.00	1.50	289			14.01
Litoral	COMIBOL	5514.58	5036.60	4439.00	1.50	440			17.82
Litoral	COMIBOL	5516.53	5037.58	4439.00	1.50	147			
Litoral	COMIBOL	5518.32	5038.50	4439.00	1.50	821			35.64
Litoral	COMIBOL	5520.00	5039.36	4439.00	1.60	360			
Litoral	COMIBOL	5521.75	5040.27	4439.00	1.50	504			5.91
Litoral	COMIBOL	5523.30	5031.84	4473.75	1.50	331			
Litoral	COMIBOL	5523.56	5041.23	4439.00	1.50	107			
Litoral	COMIBOL	5523.82	5031.12	4508.00	1.50	5			
Litoral	COMIBOL	5525.48	5042.06	4439.00	1.50	136			1.93
Litoral	COMIBOL	5525.50	5032.07	4473.75	1.50	91			
Litoral	COMIBOL	5525.56	5032.44	4508.00	1.50	35			3.55
Litoral	COMIBOL	5527.32	5033.76	4508.00	1.50	10			
Litoral	COMIBOL	5527.45	5032.16	4473.75	1.50	92			
Litoral	COMIBOL	5528.99	5034.96	4508.00	1.50	21			3.59
Litoral	COMIBOL	5529.53	5032.29	4473.75	2.30	370			30.41
Litoral	COMIBOL	5530.85	5036.34	4508.00	1.50	33			
Litoral	COMIBOL	5531.40	5033.08	4473.75	1.50	104			
Litoral	COMIBOL	5532.33	5037.82	4508.00	1.50	72			7.19
Litoral	COMIBOL	5533.25	5039.71	4508.00	1.50	51			
Litoral	COMIBOL	5533.28	5034.17	4473.75	1.50	64			3.27
Litoral	COMIBOL	5534.03	5041.97	4508.00	1.50	104			6.18
Litoral	COMIBOL	5534.46	5043.96	4508.00	1.50				

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Litoral	COMIBOL	5534.95	5035.33	4473.75	2.00	180	
Litoral	COMIBOL	5535.49	5045.75	4508.00	1.50	50	
Litoral	COMIBOL	5536.09	5022.07	4396.25	1.50	274	0.51
Litoral	COMIBOL	5536.40	5036.48	4473.75	1.80	370	21.33
Litoral	COMIBOL	5536.67	5047.54	4508.00	1.50	187	15.94
Litoral	COMIBOL	5537.96	5038.26	4473.75	2.20	50	
Litoral	COMIBOL	5538.22	5022.83	4396.25	1.50	820	2.58
Litoral	COMIBOL	5538.28	5048.75	4508.00	1.50	85	
Litoral	COMIBOL	5538.58	5040.06	4473.75	1.50	485	5.27
Litoral	COMIBOL	5539.26	5041.93	4473.75	1.50	104	
Litoral	COMIBOL	5540.05	5023.49	4396.25	1.50	99	5.31
Litoral	COMIBOL	5540.26	5049.96	4508.00	1.50		
Litoral	COMIBOL	5540.92	5043.08	4473.75	1.50	99	3.42
Litoral	COMIBOL	5542.08	5024.27	4396.25	1.50	45	0.14
Litoral	COMIBOL	5542.40	5050.61	4508.00	1.50		
Litoral	COMIBOL	5542.77	5044.06	4473.75	1.50	28	
Litoral	COMIBOL	5544.16	5025.07	4396.25	1.50	108	15.52
Litoral	COMIBOL	5544.60	5045.14	4473.75	1.50	1	0.15
Litoral	COMIBOL	5545.93	5025.75	4396.25	1.50	350	1.94
Litoral	COMIBOL	5546.51	5051.86	4508.00	1.50		
Litoral	COMIBOL	5546.52	5046.28	4473.75	1.50	25	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Litoral	COMIBOL	5548.08	5026.48	4396.25	1.50	980			9.47
Litoral	COMIBOL	5548.19	5047.05	4473.75	1.50	65			2.32
Litoral	COMIBOL	5548.55	5052.51	4508.00	1.50				
Litoral	COMIBOL	5550.15	5027.19	4396.25	1.60	720			5.66
Litoral	COMIBOL	5550.15	5047.96	4473.75	1.50	200			
Litoral	COMIBOL	5552.08	5048.76	4473.75	1.50	144			4.26
Litoral	COMIBOL	5552.12	5027.83	4396.25	1.80	1,170			5.85
Litoral	COMIBOL	5553.93	5049.43	4473.75	1.50	2			0.30
Litoral	COMIBOL	5554.20	5028.24	4396.25	1.50	470			21.12
Litoral	COMIBOL	5555.89	5050.22	4473.75	1.50	2			0.08
Litoral	COMIBOL	5556.14	5028.48	4396.25	1.60	780			7.78
Litoral	COMIBOL	5557.72	5050.85	4473.75	1.56	10			3.85
Litoral	COMIBOL	5558.34	5028.85	4396.25	1.70	880			1.70
Litoral	COMIBOL	5558.57	5055.11	4470.20	1.50	60			3.29
Litoral	COMIBOL	5558.57	5055.11	4473.19	1.50	120			12.42
Litoral	COMIBOL	5558.57	5055.11	4476.19	1.50	293			15.41
Litoral	COMIBOL	5558.57	5055.11	4479.19	1.50	565			7.15
Litoral	COMIBOL	5558.57	5055.11	4482.50	1.50	28			3.86
Litoral	COMIBOL	5558.57	5055.11	4485.34	1.50				
Litoral	COMIBOL	5558.57	5055.11	4488.50	1.50				
Litoral	COMIBOL	5558.57	5055.11	4491.65	1.50				
Litoral	COMIBOL	5558.57	5055.11	4494.39	1.50				
Litoral	COMIBOL	5558.57	5055.11	4497.54	1.50	76			8.06
Litoral	COMIBOL	5558.57	5055.11	4500.54	1.50	91			11.34
Litoral	COMIBOL	5558.57	5055.11	4503.64	1.50	180			11.60
Litoral	COMIBOL	5558.57	5055.11	4506.53	1.50	123			8.16
Litoral	COMIBOL	5559.79	5051.45	4473.75	1.50	5			3.84
Litoral	COMIBOL	5560.35	5029.54	4396.25	1.50	75			1.06
Litoral	COMIBOL	5561.81	5052.21	4473.75	1.50	5			0.96
Litoral	COMIBOL	5562.35	5030.26	4396.25	1.50	153			0.77
Litoral	COMIBOL	5563.78	5052.64	4473.75	1.50	13			2.61
Litoral	COMIBOL	5564.44	5031.01	4396.25	1.50	144			1.06
Litoral	COMIBOL	5566.35	5031.93	4396.25	1.50	406			4.78
Litoral	COMIBOL	5568.32	5032.98	4396.25	1.50	117			4.13
Litoral	COMIBOL	5570.20	5033.98	4396.25	1.50	207			1.37
Litoral	COMIBOL	5572.07	5034.61	4396.25	1.50	184			0.18
Litoral	COMIBOL	5574.36	5035.15	4396.25	1.50	160			0.36
Litoral	COMIBOL	5576.20	5035.36	4396.25	1.50	329			0.71
Litoral	COMIBOL	5578.44	5035.60	4396.25	1.50	373			1.70
Litoral	COMIBOL	5580.41	5035.78	4396.25	1.50	53			0.36
Litoral	COMIBOL	5582.56	5035.81	4396.25	1.50	576			2.36
Litoral	COMIBOL	5584.70	5035.46	4396.25	1.50	480			2.02
Litoral	COMIBOL	5586.79	5035.16	4396.25	1.50	350			1.23
Litoral	COMIBOL	5588.97	5035.32	4396.25	1.50	116			8.82
Litoral	COMIBOL	5591.03	5035.78	4396.25	1.50	1,745			14.34

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Litoral	COMIBOL	5592.91	5036.39	4396.25	1.50	205	0.39
Litoral	COMIBOL	5594.84	5037.15	4396.25	1.60	1,120	18.85
Litoral	COMIBOL	5596.72	5038.17	4396.25	1.50	495	9.99
Litoral	COMIBOL	5598.28	5039.14	4396.25	2.00	440	2.68
Litoral	COMIBOL	5600.15	5040.29	4396.25	1.50	320	13.04
Litoral	COMIBOL	5601.79	5041.22	4396.25	1.50	228	10.80
Litoral	COMIBOL	5603.50	5042.19	4396.25	1.50	576	13.16
Litoral	COMIBOL	5604.99	5043.03	4396.25	1.50	910	6.48
Litoral	COMIBOL	5606.71	5044.02	4396.25	1.50	110	0.67
Litoral	COMIBOL	5608.32	5045.08	4396.25	1.50	128	1.20
Litoral	COMIBOL	5609.83	5046.07	4396.25	1.50	267	11.21
Litoral	COMIBOL	5611.49	5047.17	4396.25	1.50	750	0.70
Litoral	COMIBOL	5613.26	5048.20	4396.25	1.60	400	27.50
Litoral	COMIBOL	5614.76	5049.06	4396.25	1.50	1,785	7.23
Litoral	COMIBOL	5616.52	5050.07	4396.25	1.50	320	2.23
Litoral	COMIBOL	5618.18	5050.98	4396.25	1.50	69	5.78
Litoral	COMIBOL	5619.98	5051.88	4396.25	1.50	192	3.25
Litoral	COMIBOL	5621.60	5052.69	4396.25	1.50	102	2.38
Litoral	COMIBOL	5623.33	5053.56	4396.25	1.50	207	4.04
Litoral	COMIBOL	5625.15	5054.26	4396.25	1.50	677	5.64
Litoral	COMIBOL	5626.89	5054.76	4396.25	1.60	930	2.75

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Litoral	COMIBOL	5628.78	5055.30	4396.25	1.50	373			2.20
Litoral	COMIBOL	5630.57	5055.85	4396.25	1.50	1,785			3.66
Litoral	COMIBOL	5632.44	5056.70	4396.25	1.50	1,440			5.70
Litoral	COMIBOL	5634.28	5057.57	4396.25	1.50	370			16.35
Litoral	COMIBOL	5636.06	5058.34	4396.25	1.50	823			3.68
Litoral	COMIBOL	5638.08	5059.16	4396.25	1.50	180			22.50
Litoral	COMIBOL	5639.84	5059.88	4396.25	1.50	420			7.23
Litoral	COMIBOL	5641.60	5060.68	4396.25	1.80	1,050			41.75
Litoral	COMIBOL	5643.47	5061.67	4396.25	1.60	900			41.75
Litoral	COMIBOL	5645.20	5062.59	4396.25	1.50	485			17.64
Litoral	COMIBOL	5647.00	5063.56	4396.25	1.80	570			30.50
Litoral	COMIBOL	5648.75	5064.52	4396.25	1.50	416			16.56
Litoral	COMIBOL	5650.57	5065.52	4396.25	1.90	560			7.96
Litoral	COMIBOL	5652.26	5066.45	4396.25	1.80	670			27.60
Litoral	COMIBOL	5654.02	5067.43	4396.25	1.60	160			9.57
Litoral	COMIBOL	5655.65	5068.47	4396.25	1.50	616			8.87
Litoral	COMIBOL	5657.47	5069.43	4396.25	2.40	820			28.10
Litoral	COMIBOL	5659.27	5070.38	4396.25	2.00	800			32.70
Litoral	COMIBOL	5661.16	5071.34	4396.25	2.20	1,680			21.30
Litoral	COMIBOL	5662.84	5072.21	4396.25	1.60	1,610			17.90
Litoral	COMIBOL	5664.71	5073.32	4396.25	1.60	1,610			30.60
Litoral	COMIBOL	5666.06	5074.32	4396.25	1.50	1,027			8.14
Litoral	COMIBOL	5667.97	5075.67	4396.25	1.50	28			12.88
Litoral	COMIBOL	5669.65	5076.79	4396.25	1.50	696			22.32
Litoral	COMIBOL	5671.27	5077.77	4396.25	1.50	402			13.63
Litoral	COMIBOL	5673.04	5078.83	4396.25	1.50				
Litoral	COMIBOL	5674.91	5079.94	4396.25	1.50				
Litoral	COMIBOL	5676.56	5080.92	4396.25	1.50				
Litoral	COMIBOL	5678.31	5081.84	4396.25	1.50	392			20.32
Litoral	COMIBOL	5680.11	5082.70	4396.25	1.50	112			13.84
Litoral	COMIBOL	5681.99	5083.46	4396.25	1.50	307			11.93
Litoral	COMIBOL	5683.95	5084.09	4396.25	1.50				
Litoral	COMIBOL	5685.52	5085.14	4396.25	2.50	510			3.26
Litoral	COMIBOL	5687.33	5086.34	4396.25	1.50	360			21.00
Litoral	COMIBOL	5689.04	5087.21	4396.25	2.40	420			23.50
Litoral	COMIBOL	5690.94	5088.17	4396.25	2.40	260			21.10
Litoral	COMIBOL	5692.62	5088.92	4396.25	2.10	160			27.40
Litoral	COMIBOL	5694.63	5089.73	4396.25	2.00	290			17.00
Litoral	COMIBOL	5696.61	5090.54	4396.25	2.40	250			18.00
Litoral	COMIBOL	5698.54	5091.16	4396.25	2.20	600			22.20
Litoral	COMIBOL	5700.41	5091.75	4396.25	2.80	330			14.00
Litoral	COMIBOL	5702.29	5092.32	4396.25	2.60	420			19.41
Litoral	COMIBOL	5704.33	5092.97	4396.25	2.60	370			13.60
Litoral	COMIBOL	5706.07	5093.56	4396.25	2.40	220			23.20
Litoral	COMIBOL	5708.01	5094.43	4396.25	2.40	310			24.30

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Litoral	COMIBOL	5709.69	5095.24	4396.25	2.10	770	28.50
Litoral	COMIBOL	5711.46	5096.26	4396.25	1.50	261	9.43
Litoral	COMIBOL	5715.96	5120.49	4439.00	2.90	1,640	
Litoral	COMIBOL	5716.98	5098.96	4396.25	1.50	315	12.91
Litoral	COMIBOL	5717.30	5121.33	4439.00	2.10	1,460	39.18
Litoral	COMIBOL	5718.50	5122.53	4439.00	3.00	1,540	
Litoral	COMIBOL	5718.82	5099.94	4396.25	1.50	152	9.12
Litoral	COMIBOL	5719.46	5123.90	4439.00	2.50	1,480	39.00
Litoral	COMIBOL	5720.46	5125.34	4439.00	2.40	1,550	
Litoral	COMIBOL	5720.62	5100.79	4396.25	1.50	90	1.11
Litoral	COMIBOL	5721.52	5126.63	4439.00	2.80	450	20.00
Litoral	COMIBOL	5722.42	5101.45	4396.25	1.50	64	1.80
Litoral	COMIBOL	5722.56	5127.78	4439.00	2.00	730	
Litoral	COMIBOL	5723.70	5128.91	4439.00	1.80	430	11.12
Litoral	COMIBOL	5724.35	5102.13	4396.25	1.50	66	2.61
Litoral	COMIBOL	5724.82	5130.07	4439.00	1.80	1,370	
Litoral	COMIBOL	5725.99	5131.24	4439.00	2.00	920	18.11
Litoral	COMIBOL	5726.35	5102.68	4396.25	1.50	325	12.85
Litoral	COMIBOL	5727.36	5132.22	4439.00	1.50	348	5.90
Litoral	COMIBOL	5728.51	5103.27	4396.25	1.50	33	0.27
Litoral	COMIBOL	5728.59	5133.14	4439.00	1.50	273	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Litoral	COMIBOL	5730.13	5134.43	4439.00	1.50	138			1.82
Litoral	COMIBOL	5730.23	5103.68	4396.25	1.50	56			0.26
Litoral	COMIBOL	5731.91	5135.80	4439.00	1.50	243			
Litoral	COMIBOL	5732.24	5104.15	4396.25	1.50	53			0.52
Litoral	COMIBOL	5733.34	5136.73	4439.00	1.50	232			2.92
Litoral	COMIBOL	5734.15	5104.52	4396.25	1.50	8			0.17
Litoral	COMIBOL	5735.20	5137.85	4439.00	1.50	288			
Litoral	COMIBOL	5736.23	5104.84	4396.25	1.50	19			2.61
Litoral	COMIBOL	5737.02	5138.95	4439.00	1.50	892			1.46
Litoral	COMIBOL	5738.18	5105.09	4396.25	1.50	17			0.24
Litoral	COMIBOL	5738.83	5140.04	4439.00	1.50	768			
Litoral	COMIBOL	5740.31	5105.15	4396.25	1.50	221			0.18
Litoral	COMIBOL	5740.75	5141.18	4439.00	1.50	490			3.88
Litoral	COMIBOL	5742.17	5142.33	4439.00	1.50	191			2.18
Litoral	COMIBOL	5742.44	5105.35	4396.25	1.50	16			0.83
Litoral	COMIBOL	5743.81	5143.75	4439.00	1.60	510			
Litoral	COMIBOL	5744.21	5161.68	4473.75	1.50	8			
Litoral	COMIBOL	5744.38	5105.64	4396.25	1.50	248			1.68
Litoral	COMIBOL	5745.33	5145.06	4439.00	1.50	260			3.98
Litoral	COMIBOL	5746.05	5162.75	4473.75	1.50	43			0.69
Litoral	COMIBOL	5746.45	5105.86	4396.25	1.50	1,785			2.71
Litoral	COMIBOL	5746.83	5146.34	4439.00	2.20	1,540			
Litoral	COMIBOL	5748.14	5163.89	4473.75	1.50	12			0.32
Litoral	COMIBOL	5748.54	5147.54	4439.00	1.50	776			5.32
Litoral	COMIBOL	5748.81	5106.05	4396.25	1.50	1,027			1.14
Litoral	COMIBOL	5750.16	5164.68	4473.75	1.50	16			
Litoral	COMIBOL	5750.36	5148.73	4439.00	2.30	860			
Litoral	COMIBOL	5750.85	5106.05	4396.25	1.50	653			5.19
Litoral	COMIBOL	5752.06	5149.76	4439.00	2.10	410			3.37
Litoral	COMIBOL	5752.18	5165.41	4473.75	1.80	30			0.69
Litoral	COMIBOL	5752.96	5106.08	4396.25	1.50	579			1.00
Litoral	COMIBOL	5753.90	5150.79	4439.00	2.30	530			
Litoral	COMIBOL	5754.04	5166.00	4473.75	1.50	16			
Litoral	COMIBOL	5755.15	5106.23	4396.25	1.50	800			3.03
Litoral	COMIBOL	5755.73	5151.69	4439.00	1.50	360			2.12
Litoral	COMIBOL	5756.29	5166.51	4473.75	1.80	40			0.80
Litoral	COMIBOL	5757.33	5106.38	4396.25	1.50	650			0.81
Litoral	COMIBOL	5757.61	5152.61	4439.00	1.50	536			
Litoral	COMIBOL	5757.67	5166.72	4440.08	1.50	6			
Litoral	COMIBOL	5757.67	5166.72	4442.01	1.50	0			0.22
Litoral	COMIBOL	5757.67	5166.72	4444.09	1.50	80			
Litoral	COMIBOL	5757.67	5166.72	4446.18	1.50	10			1.84
Litoral	COMIBOL	5757.67	5166.72	4448.21	1.50	11			
Litoral	COMIBOL	5757.67	5166.72	4450.25	1.50	3			
Litoral	COMIBOL	5757.67	5166.72	4454.31	1.50	3			0.36

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Litoral	COMIBOL	5757.67	5166.72	4456.40	1.50	3	0.40
Litoral	COMIBOL	5757.67	5166.72	4458.48	1.50	2	
Litoral	COMIBOL	5757.67	5166.72	4460.47	1.50	1	0.07
Litoral	COMIBOL	5757.67	5166.72	4462.55	1.50	1	
Litoral	COMIBOL	5757.67	5166.72	4464.48	1.50	21	1.08
Litoral	COMIBOL	5757.67	5166.72	4466.62	1.50	152	
Litoral	COMIBOL	5757.67	5166.72	4468.65	1.50	59	3.78
Litoral	COMIBOL	5758.50	5166.84	4473.75	1.60	80	
Litoral	COMIBOL	5759.25	5106.52	4396.25	1.50	597	0.29
Litoral	COMIBOL	5759.50	5153.48	4439.00	2.10	480	14.79
Litoral	COMIBOL	5760.52	5167.14	4473.75	1.50	12	0.14
Litoral	COMIBOL	5761.33	5154.33	4439.00	1.50	887	
Litoral	COMIBOL	5761.58	5106.68	4396.25	1.50	173	1.38
Litoral	COMIBOL	5762.78	5167.52	4473.75	1.50	16	
Litoral	COMIBOL	5763.29	5155.18	4439.00	1.50	656	11.99
Litoral	COMIBOL	5763.71	5106.83	4396.25	1.50	725	3.17
Litoral	COMIBOL	5764.71	5167.86	4473.75	1.50	7	0.27
Litoral	COMIBOL	5764.94	5155.94	4439.00	1.60	80	
Litoral	COMIBOL	5765.70	5106.96	4396.25	1.50	1,227	6.53
Litoral	COMIBOL	5766.69	5156.78	4439.00	1.50	32	5.59
Litoral	COMIBOL	5767.00	5168.26	4473.75	1.50	0	

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Litoral	COMIBOL	5768.44	5157.45	4439.00	2.30	60			
Litoral	COMIBOL	5769.04	5168.64	4473.75	1.50	13			0.13
Litoral	COMIBOL	5770.04	5157.97	4439.00	2.10	480			17.42
Litoral	COMIBOL	5770.12	5107.27	4396.25	2.00	590			2.43
Litoral	COMIBOL	5771.12	5169.04	4473.75	1.50	10			
Litoral	COMIBOL	5771.60	5158.48	4439.00	1.50	121			
Litoral	COMIBOL	5772.19	5107.42	4396.25	2.10	1,785			3.91
Litoral	COMIBOL	5773.43	5169.48	4473.75	1.50	5			0.16
Litoral	COMIBOL	5773.56	5159.00	4439.00	1.60	290			11.24
Litoral	COMIBOL	5774.47	5107.57	4396.25	2.00	210			0.53
Litoral	COMIBOL	5775.29	5159.40	4439.00	1.50	467			5.48
Litoral	COMIBOL	5775.46	5170.12	4473.75	1.50	7			
Litoral	COMIBOL	5776.66	5107.73	4396.25	1.50	1,013			5.69
Litoral	COMIBOL	5777.17	5159.78	4439.00	2.80	1,080			
Litoral	COMIBOL	5777.63	5170.80	4473.75	1.50	3			1.12
Litoral	COMIBOL	5778.75	5160.46	4439.00	2.60	550			15.49
Litoral	COMIBOL	5779.72	5171.24	4473.75	1.50	0			
Litoral	COMIBOL	5780.32	5161.32	4439.00	2.50	490			
Litoral	COMIBOL	5781.69	5171.65	4473.75	1.50	0			0.17
Litoral	COMIBOL	5781.92	5162.27	4439.00	4.45	670			12.30
Litoral	COMIBOL	5783.35	5163.19	4439.00	2.50	530			
Litoral	COMIBOL	5784.94	5163.92	4439.00	1.70	480			
Litoral	COMIBOL	5786.93	5164.88	4439.00	1.50	546			
Litoral	COMIBOL	5788.86	5166.08	4439.00	1.50	1,232			29.99
Litoral	COMIBOL	5790.50	5167.17	4439.00	1.50	227			
Litoral	COMIBOL	5792.20	5168.37	4439.00	1.50	176			19.29
Litoral	COMIBOL	5793.92	5169.57	4439.00	1.50	272			
Litoral	COMIBOL	5795.79	5170.79	4439.00	1.50	697			35.51
Litoral	COMIBOL	5797.52	5171.91	4439.00	1.50	1,120			
Litoral	COMIBOL	5799.33	5173.04	4439.00	1.50	364			8.95
Litoral	COMIBOL	5800.98	5173.89	4439.00	1.50	309			
Litoral	COMIBOL	5803.12	5174.64	4439.00	1.50	171			5.73
Litoral	COMIBOL	5805.17	5175.35	4439.00	1.50	475			
Litoral	COMIBOL	5807.13	5175.83	4439.00	1.50	13			0.98
Litoral	COMIBOL	5809.26	5176.40	4439.00	1.50	44			
Litoral	COMIBOL	5811.17	5177.03	4439.00	1.50	173			26.07
Litoral	COMIBOL	5813.15	5178.07	4439.00	1.50	96			
Litoral	COMIBOL	5814.90	5179.17	4439.00	1.50	27			2.33
Litoral	COMIBOL	5816.82	5180.20	4439.00	1.50	65			
Litoral	COMIBOL	5818.55	5181.12	4439.00	1.50	236			15.80
Litoral	COMIBOL	5820.38	5182.07	4439.00	1.50	440			
Litoral	COMIBOL	5822.33	5183.04	4439.00	1.50	491			21.23
Litoral	COMIBOL	5824.17	5183.99	4439.00	1.50	512			10.82
Litoral	COMIBOL	5826.10	5185.10	4439.00	1.50	336			
Litoral	COMIBOL	5827.78	5186.06	4439.00	1.50	499			12.31

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Lit_Ramo2	PASB	5635.73	5043.60	4397.61	5.38	406	0.71	0.06	4.94
Lit_Ramo2	PASB	5781.10	5113.00	4397.61	1.63	860	0.71	0.02	1.06
Lit_Ramo2	PASB	5840.16	5155.35	4356.85	2.00	129			
Lit_Ramo2	PASB	5843.57	5156.61	4356.85	3.00	205			
Lit_Ramo2	PASB	5846.70	5158.51	4356.85	3.00	290			
Lit_Ramo2	PASB	5852.83	5159.42	4356.85	3.00	290			
Lit_Ramo2	PASB	5856.35	5158.76	4356.85	3.00	160			
Lit_Ramo2	PASB	5865.28	5156.74	4356.85	2.50	225			
Lit_Ramo2	PASB	5866.89	5156.47	4356.85	2.40	136			
Lit_Ramo2	PASB	5868.77	5156.34	4356.85	2.40	647			
Lit_Ramo2	PASB	5871.05	5156.34	4356.85	2.20	883			
Lit_Ramo2	PASB	5872.90	5156.47	4356.85	2.20	439			
Lit_Ramo2	PASB	5874.82	5156.61	4356.85	3.00	744			
Lit_Ramo2	PASB	5876.97	5156.48	4356.85	2.40	186			
Lit_Ramo2	PASB	5878.86	5156.06	4356.85	2.30	181			
Lit_Ramo2	PASB	5881.41	5155.79	4356.85	2.30	181			
Lit_Ramo2	PASB	5883.70	5155.79	4356.85	2.10	1,002			
Lit_Ramo2	PASB	5885.13	5180.37	4397.61	3.08	361	0.55	0.14	3.26
Lit_Ramo2	PASB	5887.20	5157.37	4356.85	1.50	26			1.34
Lit_Ramo2	PASB	5887.93	5157.76	4359.63	1.50	30			3.06
Lit_Ramo2	PASB	5888.54	5156.14	4356.85	2.40	436			5.87

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Lit_Ramo2	PASB	5888.65	5158.14	4362.41	1.50	20			3.30
Lit_Ramo2	PASB	5889.31	5158.68	4365.19	1.50	16			2.02
Lit_Ramo2	PASB	5889.87	5159.29	4367.97	1.50	28			0.37
Lit_Ramo2	PASB	5890.42	5159.92	4370.75	1.50	19			0.24
Lit_Ramo2	PASB	5890.95	5160.56	4373.53	1.50	109			3.31
Lit_Ramo2	PASB	5891.18	5156.16	4356.85	1.90	134			3.61
Lit_Ramo2	PASB	5891.44	5161.18	4376.31	1.50	227			5.55
Lit_Ramo2	PASB	5891.95	5161.89	4379.09	1.50	54			0.59
Lit_Ramo2	PASB	5892.42	5162.55	4381.87	1.50	101			1.52
Lit_Ramo2	PASB	5892.90	5163.23	4384.65	1.50	12			1.74
Lit_Ramo2	PASB	5893.13	5156.16	4356.85	1.55	479			3.01
Lit_Ramo2	PASB	5893.43	5163.86	4387.43	1.50	37			0.11
Lit_Ramo2	PASB	5893.96	5164.50	4390.21	1.50	15			0.11
Lit_Ramo2	PASB	5894.44	5165.19	4392.99	1.50	61			1.04
Lit_Ramo2	PASB	5894.86	5165.88	4395.77	1.50	1			0.80
Lit_Ramo2	PASB	5895.29	5166.59	4398.55	1.50	287			3.82
Lit_Ramo2	PASB	5897.28	5156.33	4356.85	1.70	787			2.03
Lit_Ramo2	PASB	5900.28	5157.57	4356.85	2.35	282			1.38
Lit_Ramo2	PASB	5902.10	5158.71	4356.85	1.80	66			1.65
Lit_Ramo2	PASB	5904.99	5160.65	4356.85	1.50	76			1.85
Lit_Ramo2	PASB	5907.38	5161.82	4356.85	1.50	60			0.91
Lit_Ramo2	PASB	5909.36	5162.61	4356.85	1.95	34			3.21
Lit_Ramo2	PASB	5911.28	5163.19	4356.85	1.50	42			1.61
Lit_Ramo2	PASB	5913.50	5163.39	4356.85	1.90	89			0.84
Lit_Ramo2	PASB	5915.53	5163.74	4356.85	1.90	48			0.54
Lit_Ramo2	PASB	5915.91	5205.13	4437.61	2.66	119	0.34	0.09	4.03
Lit_Ramo2	PASB	5917.51	5164.07	4356.85	1.50	358			5.79
Lit_Ramo2	PASB	5919.69	5163.96	4356.85	2.20	490			2.62
Lit_Ramo2	PASB	5921.76	5163.80	4356.85	1.50	203			0.72
Lit_Ramo2	PASB	5924.75	5163.60	4356.85	1.66	78			1.20
Lit_Ramo2	PASB	5926.26	5163.52	4356.85	1.75	264			5.48
Lit_Ramo2	PASB	5927.65	5163.49	4356.85	1.70	159			2.67
Lit_Ramo2	PASB	5928.88	5163.48	4356.85	2.00	359			0.63
Lit_Ramo2	PASB	5930.93	5163.59	4356.85	1.50	325			0.66
Lit_Ramo2	PASB	5933.01	5164.07	4356.85	1.75	982			2.31
Lit_Ramo2	PASB	5935.06	5164.31	4356.85	2.35	202			0.93
Lit_Ramo2	PASB	5937.12	5164.34	4356.85	1.75	211			1.61
Lit_Ramo2	PASB	5939.27	5164.72	4356.85	2.00	96			0.67
Lit_Ramo2	PASB	5941.25	5164.81	4356.85	2.05	52			1.24
Lit_Ramo2	PASB	5943.24	5165.08	4356.85	1.90	56			0.62
Lit_Ramo2	PASB	5945.31	5165.27	4356.85	1.90	61			0.82
Lit_Ramo2	PASB	5947.31	5165.46	4356.85	2.05	91			0.40
Lit_Ramo2	PASB	5947.61	5190.23	4397.61	4.04	591	0.64	0.18	1.47
Lit_Ramo2	PASB	5949.30	5165.56	4356.85	1.50	408			0.74
Lit_Ramo2	PASB	5951.88	5165.52	4356.85	1.95	510			0.63

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Lit_Ramo2	PASB	5951.90	5169.29	4356.85	1.50	60	0.67
Lit_Ramo2	PASB	5952.53	5170.14	4362.45	1.50	67	0.59
Lit_Ramo2	PASB	5953.40	5170.85	4368.05	1.50	420	0.54
Lit_Ramo2	PASB	5953.51	5166.08	4356.85	1.50	541	0.49
Lit_Ramo2	PASB	5954.14	5171.67	4373.65	1.50	25	0.15
Lit_Ramo2	PASB	5954.87	5172.34	4379.25	1.50	60	0.71
Lit_Ramo2	PASB	5955.70	5172.97	4384.85	1.50	73	0.71
Lit_Ramo2	PASB	5956.52	5173.66	4390.45	1.50	20	0.11
Lit_Ramo2	PASB	5957.25	5174.33	4396.05	1.50	33	0.15
Lit_Ramo2	PASB	5957.55	5166.33	4356.85	2.15	367	1.14
Lit_Ramo2	PASB	5957.55	5166.33	4356.85	1.70	144	0.11
Lit_Ramo2	PASB	5959.61	5166.26	4356.85	1.90	1,787	1.26
Lit_Ramo2	PASB	5961.67	5166.22	4356.85	1.75	1,518	0.48
Lit_Ramo2	PASB	5963.73	5166.32	4357.20	1.90	3,000	1.91
Lit_Ramo2	PASB	5965.78	5166.42	4357.20	2.10	1,440	0.43
Lit_Ramo2	PASB	5967.85	5166.25	4357.20	1.95	1,794	0.93
Lit_Ramo2	PASB	5969.92	5166.06	4357.20	1.90	795	0.86
Lit_Ramo2	PASB	5971.97	5166.15	4357.20	2.20	3,000	1.06
Lit_Ramo2	PASB	5974.03	5166.33	4357.37	2.00	2,546	0.92
Lit_Ramo2	PASB	5976.19	5166.25	4357.37	2.20	374	0.92
Lit_Ramo2	PASB	5978.24	5166.31	4357.37	2.20	249	0.10

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Lit_Ramo2	PASB	5980.29	5166.35	4357.37	1.85	873			0.13
Lit_Ramo2	PASB	5982.39	5166.35	4357.37	2.20	74			0.14
Lit_Ramo2	PASB	5984.42	5166.41	4357.48	1.85	9			0.13
Lit_Ramo2	PASB	5986.47	5166.33	4357.48	1.90	13			0.35
Lit_Ramo2	PASB	5988.94	5166.33	4357.48	2.10	9			0.52
Lit_Ramo2	PASB	5990.97	5166.29	4357.48	1.85	44			0.80
Lit_Ramo2	PASB	5992.65	5166.19	4357.48	2.00	53			1.75
Lit_Ramo2	PASB	5994.72	5166.10	4357.62	2.10	69			0.82
Lit_Ramo2	PASB	5996.41	5165.83	4357.62	2.10	15			1.66
Lit_Ramo2	PASB	5998.37	5165.17	4357.62	2.00	13			1.14
Lit_Ramo2	PASB	6000.98	5164.16	4357.62	2.05	97			0.79
Lit_Ramo2	PASB	6002.89	5163.29	4357.62	2.25	3,000			12.82
Lit_Ramo2	PASB	6004.91	5162.49	4357.62	2.45	1,850			9.65
Lit_Ramo2	PASB	6007.12	5161.94	4357.62	2.30	261			1.84
Lit_Ramo2	PASB	6009.24	5161.81	4357.62	2.00	1,644			8.11
Lit_Ramo2	PASB	6012.71	5162.05	4357.62	1.45	596			3.20
Lit_Ramo2	PASB	6014.75	5162.30	4357.62	1.00	347			4.46
Lit_Ramo2	PASB	6016.31	5162.57	4357.62	1.10	946			3.65
Lit_Ramo2	PASB	6018.36	5162.83	4357.62	1.40	519			1.98
Lit_Ramo2	PASB	6020.38	5162.75	4357.62	2.55	1,006			6.03
Lit_Ramo2	PASB	6022.45	5162.68	4357.79	3.65	381			4.84
Lit_Ramo2	PASB	6024.50	5163.19	4357.79	2.60	840			1.42
Lit_Ramo2	PASB	6026.55	5163.19	4357.79	1.70	599			1.77
Lit_Ramo2	PASB	6028.63	5163.25	4357.79	2.85	514			1.33
Lit_Ramo2	PASB	6030.66	5162.87	4358.02	2.60	868			4.54
Lit_Ramo2	PASB	6032.71	5162.68	4358.02	3.05	1,080			5.08
Lit_Ramo2	PASB	6036.60	5162.39	4358.18	3.40	647			3.26
Lit_Ramo2	PASB	6042.48	5162.47	4358.34	3.15	806			4.28
Lit_Ramo2	PASB	6045.20	5162.68	4358.39	2.70	2,672			17.86
Lit_Ramo2	PASB	6047.29	5162.68	4358.39	2.95	1,212			16.40
Lit_Ramo2	PASB	6049.36	5162.63	4358.41	2.90	654			7.91
Lit_Ramo2	PASB	6051.39	5162.17	4358.41	3.00	1,953			12.15
Lit_Ramo2	PASB	6053.46	5161.88	4358.43	2.90	1,976			18.96
Lit_Ramo2	PASB	6055.55	5162.19	4358.43	2.70	1,543			19.13
Lit_Ramo2	PASB	6057.14	5196.66	4397.61	1.50	169	0.48	0.10	5.08
Lit_Ramo2	PASB	6057.57	5162.34	4358.44	2.50	1,366			12.68
Lit_Ramo2	PASB	6059.64	5162.28	4358.44	2.80	852			6.84
Lit_Ramo2	PASB	6061.59	5162.15	4358.48	2.80	1,217			5.06
Lit_Ramo2	PASB	6063.64	5162.09	4358.48	3.00	743			2.97
Lit_Ramo2	PASB	6066.63	5161.71	4358.48	2.85	765			4.16
Lit_Ramo2	PASB	6070.71	5161.64	4358.49	2.70	790			5.49
Lit_Ramo2	PASB	6072.94	5161.40	4358.49	2.80	1,435			10.41
Lit_Ramo2	PASB	6075.88	5161.31	4358.61	2.60	735			5.15
Lit_Ramo2	PASB	6077.90	5161.04	4358.61	2.20	833			7.94
Lit_Ramo2	PASB	6079.94	5160.86	4358.66	2.20	1,222			15.93

Edgar Filing: PAN AMERICAN SILVER CORP - Form 6-K

Lit_Ramo2	PASB	6081.97	5160.74	4358.66	2.40	741	8.75
Lit_Ramo2	PASB	6087.75	5160.53	4358.77	3.00	821	6.07
Lit_Ramo2	PASB	6090.40	5160.73	4358.77	2.95	826	3.44
Lit_Ramo2	PASB	6092.44	5160.96	4358.86	2.70	1,331	15.78
Lit_Ramo2	PASB	6097.03	5160.68	4359.02	3.05	997	19.13
Lit_Ramo2	PASB	6099.13	5160.78	4359.07	3.30	580	7.57
Lit_Ramo2	PASB	6103.16	5160.01	4359.07	2.95	940	11.30
Lit_Ramo2	PASB	6105.26	5159.72	4359.07	2.85	817	10.52
Lit_Ramo2	PASB	6107.31	5159.63	4359.07	2.75	685	9.70
Lit_Ramo2	PASB	6109.37	5159.96	4359.33	2.80	910	5.15
Lit_Ramo2	PASB	6111.47	5160.15	4359.33	2.30	517	7.96
Lit_Ramo2	PASB	6113.33	5160.39	4359.33	2.80	445	1.44
Lit_Ramo2	PASB	6115.40	5160.15	4359.34	2.85	301	2.38
Lit_Ramo2	PASB	6117.43	5160.15	4359.34	3.30	507	6.25
Lit_Ramo2	PASB	6119.49	5160.18	4359.34	3.00	3,000	5.48
Lit_Ramo2	PASB	6121.56	5159.87	4359.35	2.95	332	3.10
Lit_Ramo2	PASB	6123.59	5159.74	4359.35	3.05	590	6.69
Lit_Ramo2	PASB	6125.61	5159.67	4359.35	3.00	374	1.61
Lit_Ramo2	PASB	6127.65	5159.52	4359.35	2.80	295	5.37
Lit_Ramo2	PASB	6129.75	5159.54	4359.35	2.40	413	3.84
Lit_Ramo2	PASB	6131.77	5159.49	4359.35	2.70	1,037	5.93

Appendix C Channel Sampling Results

Vein	Sampling	X Co-ord.	Y Co-ord.	Z Co-ord.	Width (m)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)
Lit_Ramo2	PASB	6133.84	5159.37	4359.35	3.10	858			5.42
Lit_Ramo2	PASB	6135.87	5158.87	4359.30	2.35	473			8.46
Lit_Ramo2	PASB	6139.79	5158.42	4359.20	2.50	1,600			7.06
Lit_Ramo2	PASB	6142.13	5158.04	4359.14	2.55	1,346			